



Designation: **D5326–94a (Reapproved 2013) D5326 – 22**

Standard Test Method for Color Development in Tinted Latex Paints¹

This standard is issued under the fixed designation D5326; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a procedure for measuring color development in tinted latex paints, for the purpose of determining the efficiency of colorants, the tintability of base paints and the potential for poor color uniformity of applied paint films.

1.2 The values stated in ~~inch-pound~~SI units are to be regarded as standard. The values given in parentheses ~~are after SI units are provided for information only and are not considered standard.~~ The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to ~~S~~inch-pound units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and ~~health~~ environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D16 Terminology for Paint, Related Coatings, Materials, and Applications
- D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates
- D3924 Specification for Standard Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials
- D3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings
- E284 Terminology of Appearance
- E1164 Practice for Obtaining Spectrometric Data for Object-Color Evaluation
- E1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry
- E1345 Practice for Reducing the Effect of Variability of Color Measurement by Use of Multiple Measurements
- E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry
- E1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry

3. Terminology

3.1 Definitions:

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.42 on Architectural Coatings.

Current edition approved July 1, 2013; Jan. 1, 2022. Published July 2013; January 2022. Originally approved in 1992. Last previous edition approved in 2009 as D5326 – 94a (2009); (2013). DOI: 10.1520/D5326-94AR13.10.1520/D5326-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 *color development, n*—the extent to which the colorant has achieved its full tinting potential, as evidenced by the color change or lack thereof, when the tinted paint is subjected to very strong shear stress.

3.1.2 *tintability, n*—the capability of a white or tint base paint to accept various colorants, as evidenced by the color development in the mixture.

3.1.2.1 *Discussion*—
Sometimes called “color acceptance.”

3.2 See Terminology **D16**, **E284**, and the *Paint/Coatings Dictionary*³ for definitions of other terms used in this test method.

4. Summary of Test Method

4.1 The test paint is applied by drawing it down on a striped black and white sealed chart, at a film thickness sufficient to obtain full hiding.

4.2 A portion of the drawdown is subjected to strong shearing forces in a prescribed brushing procedure.

4.3 The CIELAB color difference between the drawdown and sheared areas after drying, is reported as a measure of deficiency in the color development of the test paint.

5. Significance and Use

5.1 A colorant sometimes fails to disperse completely in a base paint due to poor compatibility, which can be the fault of the colorant, the paint, or both. This will result in poor color development, which is readily manifested by the common procedure of applying the paint with a doctor blade and subjecting the drawdown to high shear stress by finger-rubbing a small area of the partially dry film. This tends to disperse undeveloped colorant, if any, and produces a color variation between the unsheared and sheared areas of the paint film. The variation can be measured colorimetrically to give a numerical color difference value that is a measure of the color development of the original paint, the smaller the difference the better the color development and vice versa. Color difference values obtained by finger-rubbing were found to vary widely for the same as well as among different operators. This test method establishes a controlled shear-stress procedure analogous to the finger rub-up test, but with far better reproducibility.

5.2 Poor color development can be a problem in the production of paints, and in their performance in the field. In production it causes a loss of colorant monetary value, and unpredictable tinting results. In field performance it results in color variations in the applied paint film due to the varying shear forces to which the paint is subjected at different stages or by different modes of application.

5.3 Although poor color development is primarily and most often related to the colorant portion of a tinted paint, the white pigment in the base paint can also be poorly developed due to flocculation or other causes. In the latter case, shear dispersion can make the paint film lighter and less colorful, rather than the reverse. Then too, the colorant and the white might both be poorly developed, and the color change due to shear stress would then be the combined effect of both.

5.4 In any case, color development is an important paint property, for the measurement of which this test method is intended to provide a generally accepted and reproducible test method.

6. Apparatus

6.1 *Film Applicator*, ~~6-in. (150-mm)~~ 150 mm (6-in.) wide with a clearance of ~~10 mils (250 μm)~~ 250 μm (10 mils).⁴

6.2 *Drawdown Plate*—A vacuum plate or thick plate glass are both satisfactory.

³ Available from Federation of Societies for Coatings Technology (FSCT), 492 Norristown Rd., Blue Bell, PA 19422-2350, <http://www.coatingstech.org>.

⁴ A Bird type film applicator, obtainable from most suppliers of paint test equipment, has been found satisfactory for this purpose. Other suitable applicators may be used.

6.3 *Test Charts*, black and white striped, with a sealed surface, and overall size approximately 8245 by 280 mm (8½ by 11 in. (245 by 280 mm)in.) having a test area of 0.538 ft²500 cm² (500 cm(0.538 ft²).⁵

6.4 *Paint Brush*, 2-in. (50-mm)50 mm (2-in.) polyester filaments, 270 mm¾-in. (70-mm) (2¾-in.) length out, ¼-in. (15-mm)15 mm (¼-in.) thick, with chisel tip.⁶

6.5 *Syringe*, 20 mL, plastic disposable type.

6.6 *Force-Draft Oven*, maintained at ±2050 ± 2°F (501 °C (120 ± 1°C):2 °F).

6.7 *Reflectometer*, using CIE Illuminant C, specular reflection excluded, and capable of measuring CIELAB color coordinates as defined in Practice [D2244](#) and Terminology [E284](#).⁷

7. Sampling and Conditioning

7.1 Take a pint (500 mL)500 mL (pint) sample of the material in accordance with Practice [D3925](#).

7.2 Adjust or allow the sample to come to room temperature as defined in Specification [D3924](#) (18 to 29.5 °C (65 to 85°F, 18 to 29.5°C):85 °F).

8. Procedure

8.1 Stir the test paint thoroughly by hand, making sure that it is completely uniform with no trace of sediment or otherwise undispersed material. If necessary filter to remove persistent large ~~agregates~~aggregates.

8.2 Clean the drawdown plate thoroughly and place the test chart on it with the applicator close to the top edge of the chart.

8.3 Fill the syringe to the 17-mL mark and from it distribute 10 mL of test coating evenly onto the chart in front of and close to the applicator, then draw down with a uniform motion.

8.4 Without delay cut an approximately 3-in. (75-mm)75 mm (3-in.) wide paint strip from the bottom end of the chart and set it aside.

8.5 Tape one edge of the remaining portion of the chart onto a flat support surface and distribute an additional 7 mL of test paint from the syringe evenly over the test area.

8.6 Dampen a clean paint brush, shake out the moisture vigorously, then dip the brush to $\frac{2}{3}$ of its filament length into the test paint in a $\frac{3}{4}$ -filled pint container. Remove the brush, wipe the tip against the edge of the container to remove the surplus, then spread the paint evenly over the test area of the chart and allow to dry for 15 ± 1 min under room temperature conditions.

8.7 During this drying period keep the wet paint brush wrapped in plastic film to prevent it from drying out.

8.8 After the specified drying period, brush over the painted area repeatedly for $2 \text{ min} \pm 10 \text{ s}$. Make sure that each brush stroke fully traverses the painted area and is at a uniform speed such that there will be 150 ± 5 strokes during the stated brushing period. Cover the entire area with six successive parallel strokes in alternate opposite directions followed by the same in the direction perpendicular to the preceding six, alternating in this way until the specified brushing time is completed. During each stroke press

⁵ Leneta Form 8K-BW; obtainable from The Leneta Company; 15 Whitney Road; Mahwah, NJ 07430, was used in the round robins for this standard and found satisfactory. An equivalent may be used.

⁶ The E-Z Paints "ONE-V20-90 ONE COATER BRISTLENE" brush has been found satisfactory. Available from E-Z Paints, 4051 S. Iowa Ave., Milwaukee, WI 53207.

⁷ Any reflectometer that measures the CIE tristimulus values of opaque surfaces will be found suitable. Types that provide a direct read-out of color difference ΔE^*_{ab} are available, and are particularly desirable for this test method. The following standards are applicable to this measurement, depending on instrumentation and other factors: Practice [E1164](#), Test Method [E1331](#), Practice [E1345](#), Test Methods [E1347](#) and [E1349](#).