



Designation: C76M—20 C76M – 22

Standard Specification for Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe (Metric)¹

This standard is issued under the fixed designation C76M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers reinforced concrete pipe intended to be used for the conveyance of sewage, industrial wastes, and storm water, and for the construction of culverts.

1.2 This specification is the SI companion to Specification C76; therefore, no inch-pound equivalents are presented in this specification. Reinforced concrete pipe that conform to the requirements of C76 are acceptable under this Specification C76M unless prohibited by the Owner.

NOTE 1—This specification is a manufacturing and purchase specification only, and does not include requirements for bedding, backfill, or the relationship between field load condition and the strength classification of pipe. However, experience has shown that the successful performance of this product depends upon the proper selection of the class of pipe, type of bedding and backfill, controlled manufacture in the plant, and care and installation conforms to the construction specifications. The owner of the reinforced concrete pipe specified herein is cautioned that he must correlate the field requirements with the class of pipe specified and provide inspection at the construction site.

NOTE 2—Attention is called to the specification for reinforced concrete D-load culvert, storm drain, and sewer pipe (ASTM Designation C655M).

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

A36/A36M Specification for Carbon Structural Steel
A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement
A1064/A1064M Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete
C33/C33M Specification for Concrete Aggregates
C150/C150M Specification for Portland Cement
C260/C260M Specification for Air-Entraining Admixtures for Concrete
C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.02 on Reinforced Sewer and Culvert Pipe.

Current edition approved Sept. 1, 2020 March 1, 2022. Published September 2020 March 2022. Originally approved in 1980. Last previous edition approved in 2019 2020 as C76M – 19b C76M – 20. DOI: 10.1520/C0076M-20.10.1520/C0076M-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**

[C443M](#) Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets (Metric)
[C494/C494M](#) Specification for Chemical Admixtures for Concrete
[C497M](#) Test Methods for Concrete Pipe, Concrete Box Sections, Manhole Sections, or Tile (Metric)
[C595/C595M](#) Specification for Blended Hydraulic Cements
[C618](#) Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
[C655M](#) Specification for Reinforced Concrete D-Load Culvert, Storm Drain, and Sewer Pipe (Metric)
[C822](#) Terminology Relating to Concrete Pipe and Related Products
[C989/C989M](#) Specification for Slag Cement for Use in Concrete and Mortars
[C990M](#) Specification for Joints for Concrete Pipe, Manholes, and Precast Box Sections Using Preformed Flexible Joint Sealants (Metric)
[C1017/C1017M](#) Specification for Chemical Admixtures for Use in Producing Flowing Concrete (Withdrawn 2022)³
[C1116/C1116M](#) Specification for Fiber-Reinforced Concrete
[C1602/C1602M](#) Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete
[C1628](#) Specification for Joints for Concrete Gravity Flow Sewer Pipe, Using Rubber Gaskets

3. Terminology


3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology [C822](#).

4. Classification

4.1 Pipe manufactured in accordance with this specification shall be of five classes identified as Class I, Class II, Class III, Class IV, and Class V. The corresponding strength requirements are prescribed in [Tables 1-5](#).

5. Basis of Acceptance

5.1 Unless otherwise designated by the owner at the time of, or before placing an order, there are two separate and alternative bases of acceptance. Independent of the method of acceptance, the pipe shall be designed to meet both the 0.01-in. crack and ultimate strength requirements specified in [Tables 1-5](#).



NOTE 1—The total reinforcement area of the inner circular cage and the elliptical cage shall not be less than that specified for the inner cage in [Tables 1-5](#).

NOTE 2—The total reinforcement area of the outer circular cage and the elliptical cage shall not be less than that specified for the outer cage in [Tables 1-5](#).

FIG. 1 Triple Cage Reinforcement

³ The last approved version of this historical standard is referenced on www.astm.org.