



Designation: ~~A705/A705M—20^{ε1}~~ A705/A705M – 22

Standard Specification for Age-Hardening Stainless Steel Forgings¹

This standard is issued under the fixed designation A705/A705M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

~~^{ε1} NOTE—The minimum allowable yield strength of Type 630, Condition HH150D found in Table 3 was corrected editorially in May 2021.~~

1. Scope*

1.1 This specification² covers age-hardening stainless steel forgings for general use.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3 Unless the order specifies an “M” designation, the material shall be furnished to inch-pound units.

NOTE 1—Bar products are covered by Specification [A564/A564M](#).

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:³

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A484/A484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings](#)

[A564/A564M Specification for Hot-Rolled and Cold-Finished Age-Hardening Stainless Steel Bars and Shapes](#)

[A751 Test Methods and Practices for Chemical Analysis of Steel Products](#)

[A788/A788M Specification for Steel Forgings, General Requirements](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

2.2 *Other Document*:⁴

[SAE J 1086 Recommended Practice for Numbering Metals and Alloys \(UNS\)](#)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved March 1, 2020/April 1, 2022. Published March 2020/April 2022. Originally approved in 1974. Last previous edition approved in 2017/2020 as [A705/A705M—17/A705/A705M – 20^{ε1}](#). DOI: [10.1520/A0705_A0705M-20E01](#). [10.1520/A0705_A0705M-22](#).

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-705/SA-705M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, [http://www.sae.org](#).

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements^A

		Composition, %											
UNS Designation ^B	Type	C	Mn	P	S	Si	Cr	Ni	Al	Mo	Ti	Cu	Other Elements ^C
S17400	630	0.07	1.00	0.040	0.030	1.00	15.00–17.50	3.00–5.00	3.00–5.00	^D
S17700	631	0.09	1.00	0.040	0.030	1.00	16.00–18.00	6.50–7.75	0.75–1.50
S15700	632	0.09	1.00	0.040	0.030	1.00	14.00–16.00	6.50–7.75	0.75–1.50	2.00–3.00
S35500	634	0.10–0.15	0.50–1.25	0.040	0.030	0.50	15.00–16.00	4.00–5.00	...	2.50–3.25	^E
S17600	635	0.08	1.00	0.040	0.030	1.00	16.00–17.50	6.00–7.50	0.40	...	0.40–1.20
S15500	XM-12	0.07	1.00	0.040	0.030	1.00	14.00–15.50	3.50–5.50	2.50–4.50	^D
S13800	XM-13	0.05	0.20	0.010	0.008	0.10	12.25–13.25	7.50–8.50	0.90–1.35	2.00–2.50	^F
S45500	XM-16	0.03	0.50	0.015	0.015	0.50	11.00–12.50	7.50–9.50	...	0.50	0.90–1.40	1.50–2.50	^G
S45503	...	0.010	0.50	0.010	0.010	0.20	11.00–12.50	7.50–9.50	...	0.50	1.00–1.35	1.50–2.50	^G
S45000	XM-25	0.05	1.00	0.030	0.030	1.00	14.00–16.00	5.00–7.00	...	0.50–1.00	...	1.25–1.75	^H
S10120		0.02	0.25	0.015	0.010	0.25	11.00–12.50	9.00–10.50	0.80–1.10	1.75–2.25	0.20–0.50	...	^F
S11100		0.02	0.25	0.015	0.010	0.25	11.00–12.50	10.25–11.25	1.35–1.75	1.75–2.25	0.20–0.50	...	^F

^A Limits are in percent maximum unless shown as a range or stated otherwise.

^B New designation—Designation established in accordance with Practice E527 and SAEJ1086, Recommended Practice for Numbering Metals and Alloys (UNS).

^C Columbium (Cb) and niobium (Nb) are considered interchangeable names for element 41 in the periodic table and both names are acceptable for use.

^D Niobium (columbium) plus tantalum 0.15–0.45.

^E Nitrogen 0.07–0.13.

^F Nitrogen 0.01.

^G Niobium (columbium) plus tantalum 0.10–0.50.

^H Niobium (columbium) 8× carbon minimum.

3. Ordering Information

3.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include but are not limited to the following:

3.1.1 Quantity (weight or number of pieces),

3.1.2 Name of material (age-hardening stainless steel forgings),

3.1.3 Dimensions, including prints or sketches,

3.1.4 Type or UNS designation (Table 1),

3.1.5 Heat-treated condition (Section 5),

3.1.6 Transverse properties when required (7.4),

3.1.7 ASTM designation and date of issue, and

3.1.8 Special requirements (5.3 and 5.4).

3.2 If possible, the intended end use of the item should be given on the purchase order, especially when the item is ordered for a specific end use or uses.

NOTE 2—A typical ordering description is as follows: five age-hardening stainless steel forgings, Type 630, solution-annealed, Specification A705 dated _____. End use: pump blocks for oil well equipment.

4. General Requirements

4.1 In addition to the requirements of this specification, all requirements of the current edition of Specification A484/A484M shall apply. Forgings shall comply with the Terminology and Forging sections of Specification A788/A788M, which further clarify the forging definitions in the Terminology section of Specification A484/A484M. Failure to comply with the general requirements of Specification A484/A484M, constitutes nonconformance with this specification.



TABLE 2 Solution Heat Treatment

Type	Condition	Solution Treatment	Mechanical Test Requirements in Solution Treated Condition ^A					Hardness ^B	
			Tensile Strength, min ksi [MPa]	Yield Strength, min ksi [MPa]	Elongation in 2 in. [50 mm] or 4D, min. %	Reduction of Area, minute %	Rockwell C, max	Brinell, max	
630	A	1900 ± 25 °F [1040 ± 15 °C] (cool as required to below 90 °F [32 °C])	38	363	
631	A	1900 ± 25 °F [1040 ± 15 °C] (water quench)	Rb89	229	
632	A	1900 ± 25 °F [1040 ± 15 °C] (water quench)	Rb100	269 ^C	
634 ^D	A	1900 ± 25 °F [1040 ± 15 °C] quench, hold not less than 3 h at -100 °F or lower	363 ^D	
635	A	1900 ± 25 °F [1040 ± 15 °C] (air cool)	120 [825]	75 [515]	10	45	32	302	
XM-12	A	1900 ± 25 °F [1040 ± 15 °C] (cool as required to below 90 °F [32 °C])	38	363	
XM-13	A	1700 ± 25 °F [925 ± 15 °C] (cool as required to below 60 °F [16 °C])	38	363	
XM-16	A	1525 ± 25 °F [830 ± 15 °C] (cool rapidly)	36	331	
S45503	A	1525 ± 25 °F [830 ± 15 °C] (cool rapidly)	36	331	
XM-25	A	1900 ± 25 °F [1040 ± 15 °C] (cool rapidly)	125 [860] ^E	95 [655]	10	40	33	311	
S10120	A	1545 ± 25 °F [840 ± 14 °C] (cool rapidly below 90 °F [32 °C])	36	331	
S11100	A	1545 ± 25 °F [840 ± 14 °C] (oil or water quench), hold for min. 8 h at minus 100 °F [-73 °C], ^F air warm	36	331	

^A See 6.1.

^B Either Rockwell C hardness or Brinell is permissible. On sizes of ½ in. [12.70 mm] and smaller, Rockwell C is preferred.

^C 321 BHN for rounds cold drawn after solution treating.

^D Equalization and over-tempering treatment 1425 ± 50 °F [775 ± 30 °C] for not less than 3 h, cool to room temperature, heat to 1075 ± 25 °F [580 ± 15 °C] for not less than 3 h.

^E 125 to 165 ksi [860 to 1140 MPa] for sizes up to ½ in. [13 mm].

^F Required hold time at minus 100 °F [-73 °C] is not mandatory if product is under 2 in. [51 mm] thickness.

iTeh Standards

(<https://standards.itih.ai>)

Document Preview

5. Materials and Manufacture

5.1 Material for forgings shall consist of billets or bars, either forged, rolled, or cast, or a section cut from an ingot. The cuts shall be made to the required length by a suitable process. This material may be specified to Specification **A564/A564M**.

ASTM A705/A705M-22

5.2 The material shall be forged by hammering, pressing, rolling, extruding, or upsetting to produce a wrought structure throughout and shall be brought as nearly as possible to the finished shape and size by hot working.

5.3 When specified on the order, sample forging may be sectioned and etched to show flow lines and the condition in regard to internal imperfections. When so specified, the question of acceptable and unacceptable metal flow shall be subject to agreement between the manufacturer and the purchaser prior to order entry.

5.4 When specified on the order, the manufacturer shall submit for approval of the purchaser a sketch showing the shape of the rough forging before machining, or before heat treating for mechanical properties.

5.5 The grain size shall be as fine as practicable and precautions shall be taken to minimize grain growth.

5.6 Material of types other than XM-9 shall be furnished in the solution-annealed condition, or in the equalized and over-tempered condition, as noted in **Table 2**, unless otherwise specified by the purchaser.

5.6.1 Types 630, XM-16, and XM-25 may be furnished in the solution-annealed or age-hardened condition.

6. Chemical Composition

6.1 The steel shall conform to the chemical composition limits specified in **Table 1**.

6.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology **A751**.



7. Mechanical Properties

7.1 The material, as represented by mechanical test specimens, shall conform to the mechanical property requirements specified in [Table 2](#) and shall be capable of developing the properties in [Table 3](#) when heat treated as specified in [Table 3](#).

7.2 The yield strength shall be determined by the offset method as described in the current edition of Test Methods and Definitions [A370](#). The limiting permanent offset shall be 0.2 % of the gage length of the specimen.

7.3 The impact strength shall be determined at 70 to 80 °F [20 to 25 °C], by Charpy V-notch specimen Type A as described in Test Methods and Definitions [A370](#).

7.4 Material tensile tested and, when specified, impact tested in the transverse direction (perpendicular to the forging flow lines) and meeting the requirements shown in [Table 3](#) need not be tested in the longitudinal direction.

7.5 Samples cut from forging shall conform to the mechanical properties of [Table 3](#) when heat treated as specified in [Tables 2 and 3](#) and tested in accordance with Test Methods and Definitions [A370](#).

8. Prolongations for Tests

8.1 Subject to [Section 7](#), the forgings shall be produced with prolongations for testing, unless otherwise specified. The producer may elect to submit an extra forging to represent each test lot instead of prolongations, or the test specimens can be taken from the forgings themselves.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM A705/A705M-22](#)

<https://standards.iteh.ai/catalog/standards/sist/a5bbaf6f-a34a-4872-908f-b32074d004d7/astm-a705-a705m-22>



TABLE 3 Mechanical Test Requirements After Age Hardening Heat Treatment^A

Type	Condition	Suggested Hardening or Aging Treatment, or Both ^{B,C,D}		Applicable Thickness, in., and Test Direction ^E	Tensile Strength, min		Yield Strength, min ^F		Elongation in 2 in. [50 mm] or 4D, min. %		Hardness ^G		Impact Charpy-V, min	
		Temperature, °F [°C]	Time, h		Quench	ksi	[MPa]	ksi	[MPa]	Reduction of area, min. %	Rockwell C, min	Brinell, min	ft-lbf	J
630	H900	900 [480]	1.0	air cool	Up to 3 in. [75 mm], incl (L)	190	[1310]	170	[1170]	10	40	40	388	...
					Over 3 to 8 in. [75 to 200 mm], incl (L)	35		
H925	4.0	air cool	Up to 3 in. [75 mm], incl (L)	170	[1170]	155	[1070]	10	44	38	375	5	6.8	
			Over 3 to 8 in. [75 to 200 mm], incl (L)	38				
H1025	4.0	air cool	Up to 8 in. [200 mm], incl (L)	155	[1070]	145	[1000]	12	45	35	331	15	20	
			Over 8 to 12 in. [200 mm], incl (L)				
H1075	4.0	air cool	Up to 8 in. [200 mm], incl (L)	145	[1000]	125	[860]	13	45	32	311	20	27	
			Over 8 to 12 in. [200 mm], incl (L)				
H1100	4.0	air cool	Up to 8 in. [200 mm], incl (L)	140	[965]	115	[795]	14	45	31	302	25	34	
			Over 8 to 12 in. [200 mm], incl (L)				
H1150	4.0	air cool	Up to 8 in. [200 mm], incl (L)	135	[930]	105	[725]	16	50	28	277	30	41	
			Over 8 to 12 in. [200 mm], incl (L)				
H1150D	4.0	air cool	Up to 8 in. [200 mm], incl (L)	125	[860]	105	[725]	16	50	24	255	30	41	
			Over 8 to 12 in. [200 mm], incl (L)				
H1150M	4.0	air cool	Up to 8 in. [200 mm], incl (L)	115	[795]	75	[520]	18	55	24	255	55	75	
			Over 8 to 12 in. [200 mm], incl (L)				
631	RH950	1750°F [955°C] for not less than 10 min, but not more than 1 h, cool rapidly to room temperature. Cool within 24 h to minus 100 ± 10°F [75°C], hold not less than 8 h. Warm in air to room temperature. Heat to 950°F [510°C], hold 1 h, air cool.	1.0	air cool	Up to 4 in. [100 mm], incl (L)	185	[1280]	150	[1030]	6	10	41	388	...
					Over 4 to 8 in. [100 mm], incl (L)		
632	RH950	Same as Type 631	1.0	air cool	Up to 4 in. [100 mm], incl (L)	200	[1380]	175	[1210]	7	25	...	415	...
					Over 4 to 8 in. [100 mm], incl (L)		
634 ^H	H1000	1750 [955] for not less than 10 min, but not more than 1 h. Water quench. Cool to not higher than minus 100°F [75°C]. Hold for not less than 3 h. Temper at 1000°F [540°C], holding for not less than 3 h.	1.0	air cool	Up to 4 in. [100 mm], incl (L)	170	[1170]	155	[1070]	12	25	37	341	...
					Over 4 to 8 in. [100 mm], incl (L)		
635	H950	950 [510] for not less than 10 min, but not more than 1 h. Water quench. Cool to not higher than minus 100°F [75°C]. Hold for not less than 3 h. Temper at 1000°F [540°C], holding for not less than 3 h.	0.5	air cool	Up to 4 in. [100 mm], incl (L)	190	[1310]	170	[1170]	8	25	39	363	...
					Over 4 to 8 in. [100 mm], incl (L)		
XM-12	H900	900 [480] for not less than 10 min, but not more than 1 h. Water quench. Cool to not higher than minus 100°F [75°C]. Hold for not less than 3 h. Temper at 1000°F [540°C], holding for not less than 3 h.	0.5	air cool	Up to 4 in. [100 mm], incl (L)	180	[1240]	160	[1100]	8	30	37	352	...
					Over 4 to 8 in. [100 mm], incl (L)		
H925	4.0	air cool	Up to 12 in. [300 mm], incl (L)	190	[1310]	170	[1170]	10	35	40	388	
			Over 12 to 16 in. [300 mm], incl (L)				
H925	4.0	air cool	Up to 12 in. [300 mm], incl (L)	170	[1170]	155	[1070]	10	38	38	375	5	6.8	
			Over 12 to 16 in. [300 mm], incl (L)				