



Designation: **B163—19 B163 – 22**

Standard Specification for Seamless Nickel and Nickel Alloy Condenser and Heat- Exchanger Tubes¹

This standard is issued under the fixed designation B163; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers seamless tubes of nickel and nickel alloys, as shown in **Table 1**, for use in condenser and heat-exchanger service.

1.2 This specification covers outside diameter and average wall, or outside diameter and minimum wall tube.

1.2.1 The sizes covered by this specification are ~~3 in. (76.2 mm)~~ 3 in. (76.2 mm) and under in outside diameter with minimum wall thicknesses of ~~0.148 in. (3.76 mm)~~ 0.148 in. (3.76 mm) and under, and with average wall thicknesses of ~~0.165 in. (4.19 mm)~~ 0.165 in. (4.19 mm) and under.

1.3 Tube shall be furnished in the alloys and conditions as shown in **Table 2**. For small diameter and light wall tube (converter sizes), see **Appendix X2**.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 The following safety hazards caveat pertains only to the test method portion, Section 12, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:³

B829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2019 April 1, 2022. Published November 2019 April 2022. Originally approved in 1941. Last previous edition approved in 2018 2019 as B163 – 18: B163 – 19. DOI: 10.1520/B0163-19.10.1520/B0163-22.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-163 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements^A

Element	Composition, %									
	N02200	N02201	N04400	N06025	N06045	N06600	N06601	N06603	N06686	N06690
Nickel	99.0 min ^B	99.0 min ^B	63.0 min ^B	remainder ^B	45.0 min ^B	72.0 min ^B	58.0-63.0	remainder ^B	remainder ^B	58.0 min ^B
Copper	0.25	0.25	28.0-34.0	0.1	0.3	0.5	1.0	0.5	...	0.5
Copper	0.25	0.25	28.0 - 34.0	0.1	0.3	0.5	1.0	0.5	...	0.5
Molybdenum
Molybdenum
Iron	0.40	0.40	2.5	8.0-11.0	21.0-25.0	6.0-10.0	remainder ^B	8.0-11.0	15.0-17.0	7.0-11.0
Iron	0.40	0.40	2.5	8.0 - 11.0	21.0 - 25.0	6.0 - 10.0	remainder ^B	8.0 - 11.0	15.0 - 17.0	7.0 - 11.0
Manganese	0.35	0.35	2.0	0.15	1.0	1.0	1.0	0.15	0.75	0.5
Carbon	0.15	0.02	0.3	0.15-0.25	0.05-0.12	0.15	0.10	0.20-0.40	0.010	0.05
Carbon	0.15	0.02	0.3	0.15 - 0.25	0.05 - 0.12	0.15	0.10	0.20 - 0.40	0.010	0.05
Silicon	0.35	0.35	0.5	0.5	2.5-9.0	0.5	0.5	0.5	0.08	0.5
Silicon	0.35	0.35	0.5	0.5	2.5 - 3.0	0.5	0.5	0.5	0.08	0.5
Sulfur	0.01	0.01	0.024	0.010	0.010	0.015	0.015	0.010	0.02	0.015
Chromium	24.0-26.0	26.0-29.0	14.0-17.0	21.0-25.0	24.0-26.0	19.0-23.0	27.0-31.0
Chromium	24.0 - 26.0	26.0 - 29.0	14.0 - 17.0	21.0 - 25.0	24.0 - 26.0	19.0 - 23.0	27.0 - 31.0
Aluminum	1.8-2.4	1.0-1.7	2.4-3.0
Aluminum	1.8 - 2.4	1.0 - 1.7	2.4 - 3.0
Titanium	0.1-0.2	0.01-0.25	0.02-0.25	...
Titanium	0.1 - 0.2	0.01 - 0.25	0.02 - 0.25	...
Phosphorus	0.020	0.020	0.02	0.04	...
Phosphorus	0.020	0.020	0.02	0.04	...
Cerium	0.03-0.09
Cerium	0.03 - 0.09
Zirconium	0.01-0.10	0.01-0.10
Zirconium	0.01 - 0.10	0.01 - 0.10
Yttrium	0.05-0.12	0.01-0.15
Yttrium	0.05 - 0.12	0.01 - 0.15
Boron
Boron
Cobalt
Cobalt
Niobium (Nb)
Niobium (Nb)
Niobium
Niobium
Tungsten	3.0-4.4	...
Tungsten	3.0 - 4.4	...
Tungsten	3.0 - 4.4	...
Nitrogen
Nitrogen

^A Maximum unless range or minimum is given. Where ellipses (...) appear in this table, there is no requirement and analysis for the element need not be determined or reported.

^B Element shall be determined arithmetically by difference.

^C Columbium and niobium are interchangeable names for the same element and both names are acceptable for use in B02.07 specifications.

TABLE 1 Chemical Requirements^A (continued)

Element	Composition, %									
	N06696	N06699	N06845	N08120	N08800	N08801	N08810	N08811	N08825	N08935
Nickel	remainder ^B	remainder ^B	44.0-50.0	35.0-39.0	30.0-35.0	30.0-34.0	30.0-35.0	30.0-35.0	36.0-46.0	34.0-36.0
Nickel	remainder ^B	remainder ^B	44.0-50.0	35.0-39.0	30.0-35.0	30.0-34.0	30.0-35.0	30.0-35.0	38.0-46.0	34.0-36.0
Copper	1.5-3.0	0.50	2.0-4.0	0.50	0.75	0.50	0.75	0.75	1.5-3.0	0.4
Copper	1.5-3.0	0.50	2.0-4.0	0.50	0.75	0.50	0.75	0.75	1.5-3.0	0.4
Molybdenum	1.0-3.0	...	5.0-7.0	2.50	2.5-3.5	6.1-7.1
Molybdenum	1.0-3.0	...	5.0-7.0	2.50	2.5-3.5	6.1-7.1
Iron	2.0-6.0	2.5	remainder ^B	remainder ^B	39.5 min ^B	39.5 min ^B	39.5 min ^B	39.5 min ^B	22.0 min ^B	remainder ^B
Iron	2.0-6.0	2.5	remainder ^B	remainder ^B	39.5 min ^B	39.5 min ^B	39.5 min ^B	39.5 min ^B	22.0 min ^B	remainder ^B
Manganese	1.0	0.50	0.5	1.5	1.5	1.50	1.5	1.5	1.0	1.2
Manganese	0.15	0.005-0.10	0.05	0.02-0.10	0.10	0.10	0.05-0.10	0.06-0.10	0.05	0.050
Carbon	0.15	0.005-0.10	0.05	0.02-0.10	0.10	0.10	0.05-0.10	0.06-0.10	0.05	0.030
Silicon	1.0-2.5	0.50	0.5	1.0	1.0	1.00	1.0	1.0	0.5	0.5
Silicon	1.0-2.5	0.50	0.5	1.0	1.0	1.00	1.0	1.0	0.5	0.5
Sulfur	0.010	0.01	0.010	0.03	0.015	0.015	0.015	0.015	0.03	0.020
Chromium	26.0-32.0	26.0-30.0	20.0-25.0	23.0-27.0	19.0-23.0	19.0-22.0	19.0-23.0	19.0-23.0	19.5-23.5	26.0-28.0
Chromium	28.0-32.0	26.0-30.0	20.0-25.0	23.0-27.0	19.0-23.0	19.0-22.0	19.0-23.0	19.0-23.0	19.5-23.5	26.0-28.0
Aluminum	...	1.9-3.0	...	0.40	0.15-0.60	...	0.15-0.60	0.15-0.60 ^C	0.2	...
Aluminum	...	1.9-3.0	...	0.40	0.15-0.60	...	0.15-0.60	0.15-0.60 ^C	0.2	...
Titanium	1.0	0.60	...	0.20	0.15-0.60	0.75-1.5	0.15-0.60	0.15-0.60 ^C	0.6-1.2	...
Titanium	1.0	0.60	...	0.20	0.15-0.60	0.75-1.5	0.15-0.60	0.15-0.60 ^C	0.6-1.2	...
Phosphorus	...	0.02	...	0.04
Phosphorus	...	0.02	...	0.04
Phosphorus	...	0.02	...	0.04
Cerium	...	0.10	0.045	...	0.045	0.045	...	0.030
Zirconium	...	0.10
Yttrium	...	0.008
Boron	...	0.008
Cobalt
Columbium	...	0.50	...	0.4-0.9
(Nb)	...	0.50	...	0.4-0.9
Niobium	...	0.50	...	0.4-0.9
Tungsten	2.0-5.0	2.50
Tungsten	2.0-5.0	2.50
Nitrogen	...	0.05	...	0.13-0.30	0.25-0.36
Nitrogen	...	0.05	...	0.13-0.30	0.25-0.36

^A Maximum unless range or minimum is given. Where ellipses (...) appear in this table, there is no requirement and analysis for the element need not be determined or reported.

^B Element shall be determined arithmetically by difference.

^C Columbium and niobium are interchangeable names for the same element and both names are acceptable for use in B02.07 specifications.

^D Alloy UNS N08811: Al+Ti, 0.95-1.20-Al + Ti = 0.85-1.20.

TABLE 2 Alloy and Conditions

Alloy	Condition
Nickel UNS N02200 and low-carbon nickel UNS N02201	annealed or stress-relieved
Nickel-copper alloy UNS N04400	annealed or stress-relieved
Nickel-chromium-iron-aluminum alloy UNS N06603	annealed
Nickel-chromium-iron-copper alloy UNS N06696	annealed
Nickel-chromium-iron-aluminum alloy UNS N06601	annealed
Nickel-chromium-iron alloy UNS N06600	annealed
Low-carbon nickel-chromium-molybdenum-tungsten alloy UNS N06686	annealed
Nickel-chromium-iron alloy UNS N06690	annealed
Nickel-chromium-iron alloy UNS N06045	annealed
Nickel-iron-chromium alloy UNS N08120 ^A	annealed or cold-worked
Nickel-iron-chromium alloy UNS N08800 ^A	annealed or cold-worked
Nickel-iron-chromium alloy UNS N08810 ^A	annealed
Nickel-iron-chromium alloy UNS N08811 ^A	annealed
Nickel-iron-chromium alloy UNS N08801	annealed
Nickel-iron-chromium-molybdenum alloy UNS N08935	annealed
Nickel-iron-chromium-molybdenum-copper alloy UNS N08825	annealed
Nickel-chromium-iron alloy UNS N06025	annealed
Nickel-iron-chromium-molybdenum-copper alloy UNS N06845	annealed
Nickel-chromium-aluminum alloy UNS N06699	annealed

^A Alloy UNS N08800 is normally employed in service temperatures up to and including 1100 °F (593 °C). Alloys UNS N08810, UNS N08811, and UNS N08120 are normally employed in service temperatures above 1100 °F (539 °C) where resistance to creep and rupture is required, and it is annealed to develop controlled grain size for optimum properties in this temperature range.

[B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys](#)

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E76 Test Methods for Chemical Analysis of Nickel-Copper Alloys \(Withdrawn 2003\)⁴](#)

[E112 Test Methods for Determining Average Grain Size](#)

[E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness](#)

[E1473 Test Methods for Chemical Analysis of Nickel, Cobalt and High-Temperature Alloys](#)

2.2 *Federal Standards:*⁵

[Fed. Std. No. 102 Preservation, Packaging and Packing Levels](#)

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)

[Fed. Std. No. 182 Continuous Identification Marking of Nickel and Nickel-Base Alloys](#)

2.3 *Military Standard:*⁵

[MIL-STD-129 Marking for Shipment and Storage](#)

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.

3. Terminology

3.1 Definitions:

3.1.1 *average diameter, n*—average of the maximum and minimum outside diameters, as determined at any one cross section of the tube.

3.1.2 *tube, n*—hollow product of round or any other cross section having a continuous periphery.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

4.1.1 *Alloy* (Table 1).

4.1.2 *Condition (Temper)* Table 3 and Appendix X1 and Appendix X2.

4.1.2.1 If annealed ends for stress relieved tubing are desired, state length of end to be annealed and whether or not one end or both ends are to be annealed.

4.1.3 *Finish*.

4.1.4 *Dimensions*—Outside diameter, minimum or average wall thickness (in inches, not gage number), and length.

4.1.5 *Fabrication Operations*:

TABLE 3 Mechanical Properties of Tubes

Material and Condition	Tensile Strength, min, ksi (MPa)	Yield Strength (0.2 % Offset), min, ksi (MPa)	Elongation in 2 in. or 50 mm (or 4 D) min, %	Rockwell Hardness (or equivalent) for annealed ends ^A
<i>Nickel UNS N02200:</i>				
Annealed	55 (379)	15 (103)	40	...
Stress-relieved	65 (448)	40 (276)	15	B65 max
<i>Low-carbon nickel UNS N02201:</i>				
Annealed	50 (345)	12 (83)	40	...
Stress-relieved	60 (414)	30 (207)	15	B62 max
<i>Nickel-copper alloy UNS N04400:</i>				
Annealed	70 (483)	28 (193)	35	...
Stress-relieved	85 (586)	55 (379)	15	B75 max
<i>Nickel-chromium-iron alloys:</i>				
Annealed alloy UNS N06600	80 (552)	35 (241)	30	...
Annealed alloy UNS N06601	80 (552)	30 (207)	30	...
Annealed alloy UNS N06690	85 (586)	35 (241)	30	...
Annealed alloy UNS N06045	90 (620)	35 (240)	35	...
Annealed alloy UNS N06025	98 (680)	39 (270)	30	...
Annealed alloy UNS N06603	94 (650)	43 (300)	25	...
Annealed alloy UNS N06696	85 (586)	35 (240)	30	...
<i>Low-carbon nickel-chromium-molybdenum-tungsten alloy:</i>				
Annealed UNS N06686	100 (690)	45 (310)	45	...
<i>Nickel-iron-chromium alloys:</i>				
Annealed alloy UNS N08120	90 (620)	40 (276)	30	...
Annealed alloy UNS N08800	75 (517)	30 (207)	30	...
Annealed alloy UNS N08801	65 (448)	25 (172)	30	...
Cold-worked alloy UNS N08800	83 (572)	47 (324)	30	...
Annealed alloy UNS N08810	65 (448)	25 (172)	30	...
Annealed alloy UNS N08811	65 (448)	25 (172)	30	...
<i>Nickel-iron-chromium-molybdenum alloy:</i>				
Annealed alloy UNS N08935	109 (750)	62 (425)	35	...
<i>Nickel-iron-chromium-molybdenum-copper alloys:</i>				
Annealed UNS N08825	85 (586)	35 (241)	30	...
Annealed UNS N06845	100 (690)	40 (276)	30	...
<i>Nickel-chromium-aluminum alloys:</i>				
Annealed UNS N06699	89 (610)	35 (240)	40	...

^A Rockwell or equivalent hardness values apply only to the annealed ends of stress-relieved tubing. Caution should be observed in using the Rockwell test on thin material, as the results may be affected by the thickness of specimen. For thickness under 0.050 in. (1.27 mm) the use of the Rockwell superficial or the Vickers hardness test is suggested. For hardness conversions for nickel and high-nickel alloys see Hardness Conversion Tables E140.

TABLE 4 Permissible Variations in Outside Diameter and Wall Thickness of Condenser and Heat Exchanger Tubes

NOTE 1—The tolerances in the table apply to individual measurements of outside diameter and include out-of-roundness (ovality), and apply to all materials and all conditions, except that for thin wall tubes having a nominal wall of 3 % or less of the outside diameter, the mean outside diameter shall comply with the permissible variations of the above table and individual measurements (including ovality) shall conform to the plus and minus values of the table with the values increased by ½ % of the nominal outside diameter.

NOTE 2—*Eccentricity*—The variation in wall thickness in any one cross section of any one tube shall not exceed plus or minus 10 % of the actual (measured) average wall of that section. The actual average wall is defined as the average of the thickest and thinnest wall of that section.

NOTE 3—For tolerances of small diameter and light wall tube (converter sizes) see **Appendix X2 (Table X2.2)**.

Material	Nominal Outside Diameter, in. (mm)	Permissible Variations ^A					
		Outside Diameter, in. (mm)		Wall Thickness, %			
		+	–	Average Wall		Minimum Wall	
				+	–	+	–
UNS N02200, UNS N02201, and UNS N04400	½ to ⅝ (12.7 to 15.9), excl	0.005 (0.13)	0	12.5	12.5	25.0	0
	⅝ to 1½ (15.9 to 38.1), incl over 1½ to 3 (38.1 to 76.2), incl	0.005 (0.13) 0.010 (0.25)	0.005 (0.13) 0.010 (0.25)	10.0 10.0	10.0 10.0	20.0 22.0	0 0
UNS N06600, UNS N06601, UNS N06690, UNS N06045, UNS N06025, UNS N06603, UNS N06696, UNS N08800, UNS N06699, UNS N08810, UNS N08811, UNS N08801, UNS N08935 UNS N08825, UNS N06845, and UNS N08120 UNS N06686	½ to ⅝ (12.7 to 15.9), excl	0.005 (0.13)	0.005 (0.13)	12.5	12.5	25.0	0
	⅝ to 1½ (15.9 to 38.1), incl over 1½ to 3 (38.1 to 76.2), incl	0.0075 (0.19) 0.010 (0.25)	0.0075 (0.19) 0.010 (0.25)	10.0 10.0	10.0 10.0	20.0 22.0	0 0

^A Wall variations as indicated above are applicable only to the wall as ordered, for instance, to minimum or to average wall, but not to both.

(https://standards.iteh.ai)
Document Preview

4.1.5.1 *Cold Bending or Coiling*.

4.1.5.2 *Packing*.

4.1.5.3 *Rolling or Expanding into Tube Sheets*.

4.1.5.4 *Welding or Brazing*—Process to be employed.

4.1.5.5 *Hydrostatic Test or Nondestructive Electric Test*—Specify type of test (6.5).

4.1.5.6 *Pressure Requirements*—If other than required by 6.5.

4.1.5.7 *Ends*—Plain ends cut and deburred will be furnished.

4.1.6 *Supplementary Requirements*—State nature and details.

4.1.7 *Certification*—State if certification is required (Section 15).

4.1.8 *Samples for Product (Check) Analysis*—Whether samples for product (check) analysis shall be furnished.

4.1.9 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed (Section 13).

4.1.10 *Small-Diameter and Light-Wall Tube (Converter Sizes)*—See **Appendix X2**.

5. Chemical Composition

5.1 The material shall conform to the composition limits specified in **Table 1**.

5.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis per Specification **B880**.

6. Mechanical Properties and Other Requirements

6.1 *Mechanical Properties*—The material shall conform to the mechanical properties specified in **Table 3**.

6.2 *Hardness*—When annealed ends are specified for tubing in the stress-relieved condition (see **Table 3**), the hardness of the ends after annealing shall not exceed the values specified in **Table 3**.

6.3 *Flare*—A flare test shall be made on one end of 1 % of the number of finished tube lengths from each lot. For less than 100 tubes in a lot, a flare test shall be made on one end of one tube length in the lot. In the case of stress relieved tubing with annealed ends, the test shall be made prior to, or subsequent to, annealing of the ends at the option of the manufacturer.

6.3.1 The flare test shall consist of flaring a test specimen with an expanding tool having an included angle of 60° until the specified outside diameter has been increased by 30 %. The flared specimen shall not exhibit cracking through the wall.

6.4 *Grain Size*—A transverse sample representing full-wall thickness of annealed alloys UNS N08120, UNS N08810 and UNS N08811 shall conform to an average grain size of ASTM No. 5 or coarser.

6.5 *Hydrostatic or Nondestructive Electric Test*—Each tube shall be subjected to either the hydrostatic test or the nondestructive electric test. The type of test to be used shall be at the option of the manufacturer, unless otherwise specified in the purchase order.

6.5.1 Hydrostatic Test:

6.5.1.1 Each tube with an outside diameter $\frac{1}{8}$ in. (3.2 mm) and larger and tubes with wall thickness of 0.015 in. (0.38 mm) and over shall be tested by the manufacturer to an internal hydrostatic pressure of 1000 psi (6.9 MPa) provided that the fiber stress calculated in accordance with the following equation does not exceed the allowable fiber stress, S , indicated below. The tube shall show no evidence of leakage.

$$P = 2St/D$$

where:

P = hydrostatic test pressure, psi (MPa),

S = allowable fiber stress for material in the condition furnished, as follows:

t = minimum wall thickness, in. (mm); equal to the specified average wall minus the permissible “minus” wall tolerance, **Table 4** and **Table X2.2**, or the specified minimum wall thickness, and

D = outside diameter of the tube, in. (mm).

	psi	MPa
Annealed low-carbon nickel UNS N02201	8 000	55.2
Stress-relieved low-carbon nickel UNS N02201	15 000	103.4
Annealed nickel UNS N02200	10 000	68.9
Stress-relieved nickel UNS N02200	16 200	111.7
Annealed nickel-copper alloy UNS N04400	17 500	120.6
Stress-relieved nickel-copper alloy UNS N04400	21 200	146.2
Annealed nickel-chromium-aluminum alloy UNS N06699	22 100	152
Annealed nickel-chromium-iron alloy UNS N06600	20 000	137.9
Annealed nickel-chromium-iron alloy UNS N06601	20 000	137.9
Annealed nickel-chromium-iron alloy UNS N06690	21 200	146
Annealed nickel-chromium-iron alloy UNS N06045	22 500	155
Annealed nickel-chromium-iron alloy UNS N06025	24 500	169
Solution annealed low-carbon nickel-chromium-molybdenum-tungsten alloy UNS N06686	25 000	172
Annealed nickel-chromium-iron-aluminum alloy UNS N06603	24 000	165
Annealed nickel-chromium-iron-copper alloy UNS N06696	21 200	146
Annealed nickel-iron-chromium alloy UNS N08120	22 500	155
Annealed nickel-iron-chromium alloy UNS N08800	18 700	128.9
Annealed nickel-iron-chromium alloy UNS N08810	16 600	114.4