



Designation: ~~E1545 – 11 (Reapproved 2016)~~ E1545 – 22

Standard Test Method for Assignment of the Glass Transition Temperature by Thermomechanical Analysis¹

This standard is issued under the fixed designation E1545; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope ~~Scope~~*

1.1 This test method describes procedures for the assignment of the glass transition temperature of materials on heating using thermomechanical measurements under compression experimental conditions.

1.2 This test method is applicable to amorphous or to partially crystalline materials that are sufficiently rigid below the glass transition to inhibit indentation by the sensing probe.

1.3 The normal operating temperature range is ~~from –100~~ from –100 °C to 600 °C. This temperature range may be extended depending upon the instrumentation used.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

~~1.5 This test method is related to ISO 11359-2. ISO 11359-2 additionally covers the determination of coefficient of linear thermal expansion not covered by this test method. This test method is related to IEC 61006 but uses a slower heating rate.~~

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and ~~health~~ environmental practices and determine the applicability of regulatory limitations prior to use. Specific precautionary statements are given in Section 7.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[E473 Terminology Relating to Thermal Analysis and Rheology](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

[E1142 Terminology Relating to Thermophysical Properties](#)

[E1363 Test Method for Temperature Calibration of Thermomechanical Analyzers](#)

¹ This test method is under the jurisdiction of ASTM Committee E37 on Thermal Measurements and is the direct responsibility of Subcommittee E37.10 on Fundamental, Statistical and Mechanical Properties.

Current edition approved ~~Sept. 1, 2016~~ April 1, 2022. Published ~~September 2016~~ April 2022. Originally approved in 1993. Last previous edition approved in 2014 as ~~E1545 – 11~~ E1545 – 11 (2016). DOI: ~~10.1520/E1545-11R16~~ 10.1520/E1545-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

2.2 Other Standards:

~~ISO 11359-2~~ ~~Plastics—Thermomechanical Analysis (TMA)—Part 2: Determination of Coefficient of Linear Thermal Expansion and Glass Transition Temperature~~³

~~IEC 61006~~ ~~Methods of Test for the Determination of the Glass Transition Temperature of Electrical Insulating Materials~~³

3. Terminology

3.1 *Definitions*—The following terms are applicable to this test method and can be found in Terminologies **E473** and **E1142**: *thermomechanical analysis (TMA)*, *thermomechanical measurement*, *thermodilatometry*, *glass transition*, *glass transition temperature*, and *linear thermal expansion*.

4. Summary of Test Method

4.1 This test method uses thermomechanical analysis equipment (thermomechanical analyzer, dilatometer, or similar device) to assign the change in dimension of a specimen observed when the material is subjected to a constant heating rate through its glass transition. This change in dimension associated with the change from vitreous solid to amorphous liquid is observed as movement of the sensing probe in direct contact with the specimen and is recorded as a function of temperature. The intersection of the extrapolation of the slope of the probe displacement curve before and after the transition is used to determine the glass transition temperature.

5. Significance and Use

5.1 The glass transition is dependent on the thermal history of the material to be tested. For amorphous and semicrystalline materials the assignment of the glass transition temperature may lead to important information about thermal history, processing conditions, stability, progress of chemical reactions, and mechanical and electrical behavior.

5.2 Thermomechanical analysis provides a rapid means of detecting changes in hardness or linear expansion associated with the glass transition.

5.3 This test method is useful for research and development, quality control, and specification acceptance.

6. Apparatus

6.1 *Thermomechanical Analyzer (TMA)*—The essential instrumentation required to provide the minimum thermomechanical analytical capability for this test method includes the following:

6.1.1 A rigid specimen holder, composed of inert low expansivity material $\leq 1 \mu\text{m m}^{-1} \text{ } ^\circ\text{C}^{-1}$, to center the specimen in the furnace and to fix the specimen to mechanical ground.

6.1.2 A rigid circular expansion probe, 2 mm to 6 mm in diameter, composed of inert low expansivity material $\leq 1 \mu\text{m m}^{-1} \text{ } ^\circ\text{C}^{-1}$, that contacts the specimen with an applied compressive force.

6.1.3 A linear sensing element with a nominal range of 2 mm capable of measuring the displacement in length of the specimen readable to within ± 50 nm.

6.1.4 A weight or force transducer to generate a constant force of 0 mN to 50 mN that is applied through the rigid compression probe to the specimen.

6.1.5 A furnace capable of providing uniform controlled heating (cooling) of a specimen to a constant temperature or at a constant rate over the temperature range of -100 to 600 $^\circ\text{C}$.

6.1.6 A temperature controller capable of executing a specific temperature program by operating the furnace between selected temperature limits at a rate of temperature change of 55 $^\circ\text{C}/\text{min} \pm 0.5$ $^\circ\text{C}/\text{min}$.

6.1.7 A temperature sensor that can be attached to, in contact with, or reproducibly placed in close proximity to the specimen to provide an indication of the specimen/furnace temperature readable to ± 0.1 to 0.3 $^\circ\text{C}$.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

³ Available from International Electrotechnical Commission (IEC), 3 rue de Varembe, Case postale 131, CH-1211, Geneva 20, Switzerland, <http://www.iec.ch>.

6.1.8 A means of sustaining an environment around the specimen of a dry inert purge gas of 45 mL/min to 55 mL/minute: mL/min.

NOTE 1—Typically, 99.9+ % pure nitrogen, argon, or helium is used. Unless effects of moisture are to be studied, dry purge gas is recommended and is essential for operation at subambient temperatures.

6.1.9 A data collection device, to provide a means of acquiring, storing, and displaying measured or calculated signals, or both. The minimum output signals required for thermomechanical analysis are change in linear dimension, temperature, and time.

6.2 Micrometer or other measuring device to determine specimen dimensions of up to 8 mm readable to within \pm of $10\ \mu\text{m}$: $\pm 10\ \mu\text{m}$.

7. Hazards

7.1 This test method may be used for amorphous and semicrystalline materials having a glass transition that is at or below room temperature providing care is taken to avoid contacting the specimen with a loaded probe prior to cooling the specimen below its glass transition. Applying a loaded probe to a specimen that is above its glass transition may cause partial penetration by the probe which can lead to probe sticking upon cooling below the glass transition. This condition has been known to yield erroneous results during the heating cycle.

7.2 With some materials a transient may be observed between the pre-transition slope and the final slope (Run 1 of Fig. 1). This may occur due to settling, residual stresses within the specimen, or alteration of the specimen morphology. Refer to Note 5 for directions when this is encountered.

7.3 Specimens of thickness less than 0.2 mm may be very difficult to handle. Thin films (50 μm to 200 μm) on a substrate may be considered for this test method providing the substrate is mechanically stable in the temperature region of the film glass transition.

7.4 For specimens of thickness greater than 5 mm, temperature nonuniformities of sufficient extent can develop within the specimen as to yield erroneously high values of the glass transition temperature using this test method.

8. Sampling

8.1 Analyze samples as received or after pretreatment. If some treatment is applied to a specimen prior to analysis, note this treatment and any resulting change in mass in the report.




FIG. 1 Glass Transition Temperature from Expansion Mode

9. Calibration

9.1 Perform calibration in accordance with Test Method [E1363](#).

10. Procedure

10.1 Calibrate the thermomechanical analyzer in accordance with Test Method [E1363](#).

10.2 Place a preweighed specimen of 0.5 mm to ~~3-mm~~ 3 mm thickness on the specimen holder in line with the probe. BE SURE THE POSITIONING OF THE TEMPERATURE SENSOR IS UNCHANGED FROM THAT USED IN THE CALIBRATION PROCEDURE.

NOTE 2—Refer to Section 7 if thicknesses outside of this range are to be used.

10.3 Move the furnace to enclose the specimen and holder. Start the dry inert gas purge before cooling or heating the specimen.

NOTE 3—If measurements are to be made at or below ambient temperature, cool the specimen and furnace to a temperature equivalent to at least 3 min of heating below the first temperature of interest to ensure stable heater control, for example, $\pm 5^{\circ}\text{C}$ for $5^{\circ}\text{C}/\text{min}$ to $5^{\circ}\text{C}/\text{min}$. The refrigerant used for cooling should not come in direct contact with the specimen.

10.4 *Procedure A—Expansion Mode*—The transition temperature derived from this procedure is considered the glass transition temperature.

10.4.1 Lower the probe (4 mm to ~~6-mm~~ 6 mm diameter) into contact with the specimen and apply a force of ~~10 mN~~ to 5 mN to 5 mN (or as recommended by the instrument manufacturer) to the probe.

10.4.2 Heat the specimen at a constant heating rate of $5^{\circ}\text{C}/\text{min}$ to $5^{\circ}\text{C}/\text{min}$ over the desired temperature range.

NOTE 4—Other forces and heating rates may be used if applied both in the calibration and throughout the testing. The conditions used shall be noted in the report.

10.4.3 Note the occurrence of an abrupt positive change in the slope of the linear thermal expansion that indicates a transition of the material from one state to another (Run 2 of [Fig. 1](#)).

NOTE 5—If a sudden irreversible deflection is observed as in Run 1 of [Fig. 1](#), stop the heating program 20°C to 20°C above this temperature, remove any applied force from the probe, raise the probe from the specimen, and cool the specimen and furnace to the original start temperature. Conduct a second thermal cycle on the specimen beginning with 10.4.1.

10.4.4 Upon reaching the limit temperature of the heating program, remove any applied force from the probe, raise the probe from the specimen, and restore the furnace and specimen holder to room temperature.

10.5 *Procedure B—Penetration Mode*—The transition temperature derived from this procedure is referred to as the softening point, T_s . For most materials $T_{s\bar{s}}$ is close to the $T_{g\bar{g}}$ as measured in the expansion mode or as measured by differential scanning calorimetry. It is a common practice in many polymer laboratories to report $T_{s\bar{s}}$ for T_g . The value of $T_{s\bar{s}}$ may be affected by the applied force and the probe contact area. Hence, those values should also be reported when using this procedure.

10.5.1 Lower the probe (2 mm to ~~4-mm~~ 4 mm diameter) into contact with the specimen and apply a force of 20 to 50 mN to 50 mN to the probe.

10.5.2 Heat the specimen at a constant heating rate of $5^{\circ}\text{C}/\text{min}$ to $5^{\circ}\text{C}/\text{min}$ over the desired temperature range.

NOTE 6—Other forces and heating rates may be used if applied both in the calibration and throughout the testing. The conditions used shall be noted in the report.

10.5.3 Note the occurrence of an abrupt negative change in the slope of the thermal curve which indicates a transition of the material from one state to another (Run 2 of [Fig. 2](#)).