



Designation: A1066/A1066M – 22

Standard Specification for High-Strength Low-Alloy Structural Steel Plate Produced by Thermo-Mechanical Controlled Process (TMCP)¹

This standard is issued under the fixed designation A1066/A1066M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers steel plates produced by the thermo-mechanical controlled process (TMCP). Five grades are defined by the yield strength: 50 [345], 60 [415], 65 [450], 70 [485], and 80 [550]. The plates are intended primarily for use in welded steel structures.

1.2 The TMCP method consists of rolling reductions and cooling rate controls that result in mechanical properties in the finished plate that are equivalent to those attained using conventional rolling and heat treatment processes, which entail reheating after rolling. A description of the TMCP method is given in [Appendix X1](#).

1.3 The maximum thicknesses available in the grades covered by this specification are shown in [Table 1](#).

1.4 Due to the special combination of mechanical and thermal treatment inducing lower rolling temperatures than for conventional hot rolling the plates cannot be formed at elevated temperatures without sustaining significant losses in strength and toughness. The plates may be formed and post-weld heat-treated at temperatures not exceeding 1050°F [560°C]. Higher temperatures may be possible if proven that minimum mechanical characteristics are retained after tests with specimens in the post-weld heat treatment (PWHT) condition. For flame straightening higher temperatures can be used in accordance with the steel manufacturer's recommendations.

1.5 If the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See [Appendix X3](#) of Specification [A6/A6M](#) for information on weldability.

1.6 Supplementary requirements are available but shall apply only if specified in the purchase order.

1.7 *Units*—This specification is expressed in both inch-pound units and SI units; however, unless the purchase order or contract specifies the applicable M specification designation

(SI units), the inch-pound units shall apply. The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system is to be used independently of the other. Combining values from the two systems may result in nonconformances with the standard.

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- [A6/A6M](#) Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
- [A673/A673M](#) Specification for Sampling Procedure for Impact Testing of Structural Steel
- [A770/A770M](#) Specification for Through-Thickness Tension Testing of Steel Plates for Special Applications

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification [A6/A6M](#), including any supplementary requirements indicated in the purchase order or contract. Failure to comply with the general requirements of Specification [A6/A6M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A6/A6M](#), this specification shall prevail.

4. Materials and Manufacture

4.1 The steel shall be killed.

4.2 The plates shall be produced by the thermo-mechanical controlled process.

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.02](#) on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved March 15, 2022. Published May 2022. Originally approved in 2011. Last previous edition approved in 2015 as A1066/A1066M – 11 (2015)^{ε2}. DOI: 10.1520/A1066_A1066M-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements (Heat Analysis)

Element	Content in [%]				
	Grade 50 [345]	Grade 60 [415]	Grade 65 [450]	Grade 70 [485]	Grade 80 [550]
Thickness	Max 6 in. [150 mm]	Max 6 in. [150 mm]	Max 6 in. [150 mm]	Max 3 in. [75 mm]	Max 1 in. [25 mm]
Carbon, max	0.14 ^A	0.16	0.16	0.16	0.16
Manganese	0.70–1.60	0.80–1.70	0.80–1.70	0.80–1.70	1.00–2.00
Phosphorus, max	0.030	0.030	0.030	0.030	0.030
Sulfur, max	0.020	0.020	0.020	0.020	0.020
Silicon	0.15–0.50	0.15–0.50	0.15–0.50	0.15–0.50	0.15–0.50
Copper, max	0.35	0.35	0.35	0.35	0.35
Nickel, max	0.30	0.70	0.70	0.70	0.70
Chromium, max	0.30	0.30	0.30	0.35	0.40
Molybdenum, max	0.10	0.20	0.25	0.30	0.40
Columbium/Niobium, max ^B	0.05	0.05	0.05	0.05	0.10
Vanadium, max	0.08	0.08	0.08	0.09	0.09
Aluminium, min	0.020 total or 0.015 soluble ^C	0.020 total or 0.015 soluble ^C	0.020 total or 0.015 soluble ^C	0.020 total or 0.015 soluble ^C	0.020 total or 0.015 soluble ^C
Boron, max	0.002	0.002	0.002	0.002	0.002

^A When Supplementary Requirement S75 is ordered the carbon content is 0.16 % max.

^B Columbium (Cb) and Niobium (Nb) are considered interchangeable names for the same element and both names are acceptable for use in A01 specifications.

^C By agreement the steel may be produced with titanium, in which case the minimum aluminum content shall not apply. When this option is exercised, the titanium content, by heat analysis, shall be 0.006 % to 0.02 %, and the actual titanium content shall be reported on the test report.

TABLE 2 Maximum Carbon Equivalent (Heat Analysis)

	Maximum Carbon Equivalent in [%]				
	Grade 50 [345]	Grade 60 [415]	Grade 65 [450]	Grade 70 [485]	Grade 80 [550]
CE	0.40	0.43	0.45	0.47	0.50

TABLE 3 Tensile Requirements

Grade		Yield Point, min		Tensile Strength, min		Elongation, min	
		ksi	[MPa]	ksi	[MPa]	8 in. [200 mm], %	2 in. [50 mm], %
50	[345]	50	[345]	65	[450]	18	20
60	[415]	60	[415]	75	[520]	16	18
65	[450]	65	[450]	80	[550]	15	17
70	[485]	70	[485]	85	[585]	14	16
80	[550]	80	[550]	90	[620]	13	15

5. Chemical Composition

5.1 The chemical composition on heat analysis shall conform to the requirements given in **Table 1**.

5.2 The steel shall conform on product analysis to the requirements prescribed in **Table 1** subject to the product analysis tolerances in Specification **A6/A6M**.

5.3 The carbon equivalent on heat analysis shall not exceed the limits listed in **Table 2**. The chemical analysis (heat analysis) of the elements that appear in the carbon equivalent formula and the actual carbon equivalent shall be reported. For the calculation of the carbon equivalent the following formula shall be used:

$$CE = C + \frac{Mn}{6} + \frac{(Cr+Mo+V)}{5} + \frac{(Cu+Ni)}{15}$$

6. Mechanical Properties

6.1 *Tensile Properties*—The material as represented by the test specimens shall conform to the tensile properties given in **Table 3**.

6.2 Charpy V-notch tests shall be made in accordance with Specification **A673/A673M**, Frequency H.

6.2.1 The test results of full-size specimens taken from the longitudinal direction of the product shall meet an average value of 35 ft-lbf [48 J] at –10°F [–23°C]. Subsize specimens are permitted as allowed by Specification **A673/A673M**.

6.2.2 Charpy-V-notch test requirements varying from the value specified in 6.2.1 or other test temperatures are subject to the agreement between the purchaser and the producer.

7. Keywords

7.1 high-strength low-alloy steel; steel plates; structural steel; thermo-mechanical controlled rolling; welded construction

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order or contract. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification **A6/A6M**. Those that are considered suitable for use with this specification are listed by title.

- | | |
|--|--------------------------------------|
| S1. Vacuum Treatment, | S4. Additional Tension Test, |
| S2. Product Analysis, | S5.2 Charpy V-Notch Impact Test, and |
| S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons, | S8. Ultrasonic Examination. |

ADDITIONAL SUPPLEMENTARY REQUIREMENTS

In addition, the following special supplementary requirements are also suitable for use with this specification.

S75. Maximum Yield Point to Tensile Strength Ratio: Grade 50 and Grade 60—The maximum yield to tensile ratio shall be 0.87 for grade 50 and 0.90 for grade 60. In this case the maximum carbon content on the heat analysis can be raised to 0.16 % for grade 50.

S76. Maximum Tensile Strength—The maximum tensile strength shall be 91 ksi [630] for grade 50, 98 ksi [680] for grade 60, 105 ksi [720] for grade 65, 110 ksi [750] for grade 70, and 115 ksi [800] for grade 80.

S77. Through-Thickness Tension Testing of Steel Plates—Through-Thickness Tension Testing of Steel Plates in accordance with Specification **A770/A770M**.

ASTM A1066/A1066M-22

<https://standards.iteh.ai/catalog/standards/sist/ad9ace21-703c-aa7f-b92eff65a573/astm-a1066-a1066m-22>

APPENDIX

(Nonmandatory Information)

X1. THERMO-MECHANICAL CONTROLLED PROCESSING (TMCP)

X1.1 Introduction—The Thermo-Mechanical Controlled Processing, commonly referred to as “TMCP” has evolved from the “controlled rolling” (CR) processes. TMCP produces fine-grain steel by a combination of chemical composition and integrated controls of manufacturing processes from slab reheating to post-rolling cooling, thereby achieving the specified mechanical properties in the required plate thicknesses. TMCP requires accurate control of both the steel temperature and rolling reductions, and does not involve coiling after post-cooling.

X1.2 Outline of TMCP—As shown in **Fig. X1.1**, TMCP may incorporate three processes as follows:

X1.2.1 Thermo-Mechanical Rolling (TMR)—Steels of fine grain size are produced by rolling in the recrystallisation and non-recrystallisation regions of austenite, and sometimes in the dual-phase temperature region of austenite and ferrite. Generally, a high proportion of rolling reduction is performed

close to, or below, the temperature at which austenite begins to transform to ferrite during cooling (Ar₃) and may involve rolling in the lower portion of the temperature range of the intercritical dual-phase region.

X1.2.2 Accelerated Cooling (AC)—Steels meeting the specified requirements are produced by controlled cooling (accelerated cooling by water or air cooling) through the dual-phase temperature region immediately after final CR or TMR operation.

X1.2.3 Direct Quenching and Tempered (DQT)—Steels meeting the specified requirements are produced by promoting grain refinement and increasing hardness through direct quenching immediately after final CR or TMR operation. Subsequent to direct quenching the plates are tempered.

X1.3 The selection, from the above, of the method to be used is made by the steel producer depending upon chemical composition, the plate thickness, and the required properties.