



Designation: **B806—14 B806 – 14 (Reapproved 2022)**

Standard Specification for Copper Alloy Permanent Mold Castings for General Applications¹

This standard is issued under the fixed designation B806; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes requirements for copper alloy² permanent mold castings for general applications. Nominal compositions of the alloys under this specification are shown in **Table 1**.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form part of this specification to the extent referenced herein:

<https://standards.iteh.ai/catalog/standards/sist/91dd32bd-aa5f-4af4-9690-5542829ac63d/astm-b806-142022>

2.2 *ASTM Standards*:³

B208 Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and Continuous Castings

B824 Specification for General Requirements for Copper Alloy Castings

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Ordering Information

3.1 Orders for casting under this specification shall include the following information:

3.1.1 Quantity of castings required,

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved April 1, 2014; May 1, 2022. Published May 2014; May 2022. Originally approved in 1990. Last previous edition approved in 2008; 2014 as B806—08a; B806 – 14. DOI: 10.1520/B0806-14.10.1520/B0806-14R22.

² The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the [standard's Document Summary page](#) on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Nominal Composition

Classification	Copper Alloy UNS No.	Nominal Composition								
		Copper	Aluminum	Iron	Manganese	Nickel (incl Cobalt)	Silicon	Lead	Zinc	Tin
Yellow brass	C85470 ^A	62.5	0.5	34.3	2.5
Silicon brass	C87500	82.0	4.0	...	14.0	...
	C87800	82.0	4.0	...	14.0	...
	C87850 ^B	76.0	3.0	...	20.9	...
Lead-free yellow brass ^C	C89540	61.0	0.40	0.30	...	0.5	36.0	0.8
Aluminum bronze	C95300	89.0	10.0	1.0
	C95400	85.0	11.0	4.0
	C95410	84.0	10.0	4.0	...	2.0
Nickel aluminum bronze	C95500	81.0	11.0	4.0	...	4.0
	C95800	81.3	9.0	4.0	1.2	4.5

^A Phosphorus 0.13.

^B Phosphorus 0.12.

^C Bismuth 0.9; selenium 0.03.

3.1.2 Copper Alloy UNS number (Table 2) and temper (as-cast, heat-treated, and so forth), (4.2),

3.1.3 Specification number, title, and year of issue.

3.1.4 Pattern or drawing number, and condition (cast, machined, and so forth),

3.1.5 Pressure test requirements, if specified in the purchase order (Specification B824),

3.1.6 Soundness requirements, if specified in the purchase order (Specification B824),

3.1.7 Repair of castings (Section 7),

3.1.8 Certification, if specified in the purchase order (Specification B824),

3.1.9 Foundry test report, if specified in the purchase order (Specification B824),

3.1.10 Witness inspection, if specified in the purchase order (Specification B824),

3.1.11 Product marking, if specified in the purchase order (Specification B824), and

3.1.12 Castings for Seawater Service (Section 4).

TABLE 2 Chemical Requirements

Classification	Copper Alloy UNS No.	Composition, % max except as indicated									Copper + Sum of named elements, min
		Copper	Aluminum	Iron	Manganese	Nickel (incl Cobalt)	Silicon	Lead	Zinc	Tin	
Yellow brass	C85470 ^A	60.0–65.0	0.10–1.0	0.20	0.09	Rem	1.0–4.0	99.5
Silicon brass	C87500	79.0 min	0.5	3.0–5.0	0.09	12.0–16.0	...	99.5
	C87800	80.0 min	0.15	0.15	0.15	0.20	3.8–4.2	0.09	12.0–16.0	0.25	99.8 ^B
	C87850 ^C	75.0–78.0	...	0.10	0.10	0.20	2.7–3.4	0.09	Remainder	0.30	99.5
Lead-free yellow brass ^D	C89540	58.0–64.0	0.10–0.60	0.50	...	1.0	...	0.10	32.0–38.0	1.2	99.5
Aluminum bronze	C95300	86.0 min	9.0–11.0	0.75–1.5	99.0
	C95400	83.0 min	10.0–11.5	3.0–5.0	0.25	1.5	99.5
	C95410	83.0 min	10.0–11.5	3.0–5.0	0.25	1.5–2.5	99.5
Nickel aluminum bronze	C95500	78.0 min	10.0–11.5	3.0–5.0	1.0	3.0–5.5	99.5
	C95800	79.0 min	8.5–9.5	3.5–4.5 ^E	0.8–1.5	4.0–5.0 ^E	0.10	0.03	99.5

^A Phosphorus 0.02–0.25; 0.02–0.25.

^B Antimony 0.05 %; arsenic 0.05 %; magnesium 0.01 %; phosphorus 0.01 %; and sulfur 0.05 % max.

^C Antimony 0.10 %; phosphorus is a major element at 0.05–0.20 %.

^D Bismuth 0.6–1.2; selenium 0.10.

^E Iron content shall not exceed the nickel content.