



Designation: **B506—16 B506 – 22**

# Standard Specification for Copper-Clad Stainless Steel Sheet and Strip for Building Construction<sup>1</sup>

This standard is issued under the fixed designation B506; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope\*

1.1 This specification establishes the requirements for rolled copper-clad stainless steel, sheet and strip in flat lengths, coils, or in rolls in thicknesses for roofing, siding, flashing, rain drainage, windows, doors, curtain wall components, and for other architectural gutters, downspouts, and general sheet metal work and fabricated products in building and for outside building construction.

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units which are provided for information only and are not considered standard.

1.2.1 *Exception*—Grain size units are stated in SI units.

1.3 The following safety hazard caveat pertains only to the test method(s) described in this specification.

1.3.1 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4

*1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications](#)

[B152/B152M Specification for Copper Sheet, Strip, Plate, and Rolled Bar](#)

[B846 Terminology for Copper and Copper Alloys](#)

[E3 Guide for Preparation of Metallographic Specimens](#)

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved July 1, 2016; May 1, 2022. Published July 2016; May 2022. Originally approved in 1970. Last previous edition approved in 2009 as B506-09-16. DOI: 10.1520/B0506-16.10.1520/B0506-22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

E18 Test Methods for Rockwell Hardness of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E112 Test Methods for Determining Average Grain Size

### 3. Terminology

3.1 For definitions of terms related to copper and copper alloys, refer to Terminology B846.

### 4. Ordering Information

4.1 Include the following specified choices when placing orders for product under this specification, as applicable:

4.1.1 ASTM designation and year of issue,

4.1.2 UNS No. designations of both the copper and stainless steel specified,

4.1.3 Temper (see 7.1),

4.1.4 *Dimensions*: thickness, width, and length (see 10.2, 10.3, and 10.4),

4.1.5 *How Furnished*: flat lengths or rolls,

4.1.6 *Quantity*: total weight or total length or number of pieces of each size, and

4.1.7 Cladding ratio (see 6.3).

4.2 The following options are available but may not be included unless and, when required, shall be specified at the time of placing of the order when required: order.

4.2.1 Heat identification or traceability details,

4.2.2 Certification, and

4.2.3 Test Report.

### 5. Materials and Manufacture

5.1 *Material*:

5.1.1 The material of manufacture shall be a form of sheet or strip of such purity and soundness as to be suitable for processing into the products prescribed herein.

5.1.2 When specified in the contract or purchase order that heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 1—Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

## 5.2 Manufacture:

5.2.1 The product shall be produced by roll bonding the cladding metals to the specified base metal (core), and subsequently annealed, when required, to meet the temper properties specified.

## 6. Chemical Composition

6.1 The cladding shall be, unless otherwise specified, a copper conforming in chemical composition to any of those established in Specification **B152/B152M**.

6.2 The core shall be a stainless steel conforming in chemical composition to any of those established by Specification **A240/A240M**. Unless otherwise specified, stainless steel UNS Alloy No. S43000 shall be supplied.

6.3 The cladding ratio shall be 10/80/10, copper/stainless steel/copper, unless otherwise specified.

## 7. Temper

7.1 The standard temper for the product described in this specification is given in **Table 1**, ~~unless otherwise specified.~~

7.1.1 Annealed temper O61.

## 8. Grain Size

8.1 Although no minimum grain size is prescribed for annealed material, it shall be fully recrystallized in both cladding and core.

## 9. Mechanical Property Requirements

### 9.1 Tensile Strength Requirements:

9.1.1 Product furnished under this specification shall conform to the tensile requirements prescribed in **Table 1** when tested in accordance with Test Methods **E8/E8M**.

9.1.2 Acceptance or rejection based upon mechanical properties shall depend only on tensile ~~properties and yield strength~~ requirements.

9.1.3 The mechanical properties of material in tempers other than annealed and with cladding ratios other than 10/80/10 shall be as agreed upon between purchaser and supplier.

### 9.2 Rockwell Hardness Requirement:

9.2.1 The approximate Rockwell hardness values given in **Table 1** are for general information and assistance in testing, and shall not be used as a basis for product rejection.

9.2.2 Copper should be etched off with a suitable reagent prior to test.

**TABLE 1 Mechanical Properties for 10/80/10 Ratio Composite Strip Material with Type 430 Stainless Steel Core**

Temper Designation		Tensile Strength		Yield Strength at 0.5 % Extension Under Load		Approximate Rockwell Hardness
Code	Name	ksi <sup>A</sup> (MPa <sup>B</sup> )		ksi <sup>A</sup> (MPa <sup>B</sup> )		(for Information Only)
		Min	Max	Min	Max	15T
O61	annealed	58 (400)	70 (485)	30 (205)	51 (350)	89 max

<sup>A</sup> ksi = 1000 psi

<sup>B</sup> See **Appendix X1**.

NOTE 2—The Rockwell Hardness test offers a quick and convenient method of checking for general conformity to the specification requirements for temper and tensile strength.

## 10. Dimensions and Permissible Variations

10.1 Unless closer tolerances are specified in the contract or purchase order, the product furnished shall conform to the following appropriate tables:

10.2 *Thickness Tolerances*—Table 2.

10.3 *Width Tolerances*—Table 3 for slit metal and Table 4 for square-sheared metal.

10.4 *Length Tolerances*—Table 5 for stock lengths of flat sheet and strip. Table 6 for square-sheared metal.

10.5 *Straightness Tolerances*—Table 7 for slit metal. Table 8 for square-sheared metal.

10.6 *Cladding Ratio*—Cladding ratios shall be within  $\pm 10\%$  of nominal; method of test shall be metallurgical microsection of at least three samples per lot.

## 11. Workmanship, Finish, and Appearance

11.1 The material shall be free of defects, but blemishes of a nature that do not interfere with the intended application are acceptable.

## 12. Sampling

12.1 *Sampling*—The lot size, portion size, and selection of sample pieces shall be as follows:

12.1.1 *Lot Size*—An inspection lot shall be 10 000 lb (4550 kg), or less material of the same mill form, alloy, temper, and thickness, subject to inspection at one time.

12.1.2 *Portion Size*—A portion shall be four or more pieces selected as to be representative of each lot. If the lot consists of less than four pieces, a sample shall be taken from each piece.

12.1.2.1 *Chemical Analysis*—A sample for chemical analysis shall not be taken. The copper sheet or strip that is used as the cladding for this product was sampled and tested as prescribed in Specification B152/B152M. The stainless steel strip that is used as the core in this product was sampled and tested as prescribed in Specification A240/A240M.

**TABLE 2 Thickness Tolerances**

Thickness, in. (mm)	Thickness Tolerances, Plus and Minus			
	For Widths 8 in. and Under (203 mm and Under) in. (mm)	For Widths Over 8 in. to 14 in. (203(203 mm to 356 mm), incl in. (mm)	For Widths Over 14 in. to 20 in. (356(356 mm to 508 mm), incl in. (mm)	For Widths Over 20 in. (508 mm) in. (mm)
0.012 in. (0.305 mm) to 0.018 in. (0.457 mm), incl	0.0010 (0.025)	0.0015 (0.038)	0.0020 (0.051)	0.0025 (0.064)
Over 0.018 in. (0.457 mm) to 0.022 in. (0.559 mm), incl	0.0013 (0.033)	0.0018 (0.046)	0.0020 (0.051)	0.0030 (0.076)
Over 0.022 in. (0.559 mm) to 0.030 in. (0.762 mm), incl	0.0015 (0.038)	0.0020 (0.051)	0.0025 (0.064)	0.0030 (0.076)
Over 0.030 in. (0.762 mm) to 0.065 in. (1.65 mm), incl	0.0020 (0.051)	0.0025 (0.064)	0.0030 (0.076)	0.0035 (0.089)

**TABLE 3 Width Tolerances for Slit Metal**

Width in. (mm)	Width Tolerance, Plus and Minus in. (mm)
Up to 20 (508 incl)	1/64 (0.40)
Over 20 to 48 (508 to 1219 incl)	1/32 (0.79)

**TABLE 4 Width Tolerances for Square-Sheared Metal**

Width in. (mm)	Width Tolerance, Plus and Minus in. (mm)
Up to 20 (508)	1/32 (0.79)
Over 20 to 36 (508 to 814, incl)	3/64 (1.2)
Over 36 (914)	1/16 (1.6)

**TABLE 5 Length Tolerance for Specific and Stock Lengths**

Length	Length Tolerance (Applicable Only to Full-Length Pieces) in. (mm)
Specific lengths 120 in. (3.05 m) and under	1/4 (6.4) (all plus)

**TABLE 6 Length Tolerances for Square-Sheared Metal**

Length	Length Tolerance, Plus and Minus in. (mm)
Over 36 in. (914 mm) to 120 in. (3.05 m), incl	1/16 (1.6)

**TABLE 7 Straightness Tolerances for Slit Metal**

NOTE 1—Maximum edgewise curvature (depth of arc) in any ~~72-in. (1.83 m)~~ 72 in. (1.83 m) portion of the total length.

Width	Straightness Tolerance in. (mm)
Over 4 in. (102 mm) to 48 in. (1219 mm) incl	1/2 (13)

**TABLE 8 Straightness Tolerances for Square Sheared Metal**

NOTE 1—Maximum edgewise curvature (depth of arc) in any ~~72-in. (1.83 m)~~ 72 in. (1.83 m) portion of the total length (not applicable to metal over 120 in. (3.05 m) in length).

	Straightness Tolerance	
	Up to 10 in. (254 mm), incl, in Width in. (mm)	Over 10 in. (254 mm) in Width in (mm)
All Thicknesses	1/16 (1.6)	1/32 (0.79)

12.1.2.2 *Samples for All Other Tests*—Samples for all other tests shall be taken from the sample portion in 12.1.2 and be of a convenient size to accommodate the test and comply with the requirements of the appropriate ASTM Product Standards and Test Methods.