



Designation: D7991 – 22

Standard Test Method for Determining Aerobic Biodegradation of Plastics Buried in Sandy Marine Sediment under Controlled Laboratory Conditions¹

This standard is issued under the fixed designation D7991; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method determines the biodegradation level of plastic materials exposed to laboratory conditions that simulate the environment found in the sandy tidal zone.

1.2 The tidal zone, that is, the part of the coast affected by the tides and movement of the waves, is the borderline between sea and land, frequently a sandy area that is kept constantly damp by the lapping of the waves. Stony and rocky shorelines also exist.

1.3 Plastic marine debris is frequently washed up in this habitat where it must be removed in order to restore the original landscape.

1.4 It is of interest to know the biodegradation behavior of plastics when exposed to conditions simulating this habitat, because this information can help in predicting the time needed for the biodegradation of the litter.

1.5 Biodegradation is determined by measuring the CO₂ evolved by the plastic material when exposed to a sediment kept wet with salt-water in a reactor, to simulate the tidal zone.

1.6 Marine fresh-water habitats (for example, those found in brackish waters and estuaries) are not considered by this standard.

1.7 Reports shall clearly state the percentage of net CO₂ generation for both the test and reference samples at the completion of the test. Furthermore, in the laboratory reports, the results shall not be extrapolated beyond the actual duration of the test.

NOTE 1—There is no known ISO equivalent to this standard.

1.8 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.96 on Environmentally Degradable Plastics and Biobased Products.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 2015. Last previous edition approved in 2015 as D7991 - 15. DOI: 10.1520/D7991-22.

1.9 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.10 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:²

D5988 Test Method for Determining Aerobic Biodegradation of Plastic Materials in Soil

2.2 *ISO Standards*:³

ISO 8245 Water quality Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC)

3. Terminology

3.1 *Definitions*:

3.1.1 *tidal zone, n*—the part of the marine environment that extends from the high tide line, which is rarely inundated with water, to the low tide line, which is typically always covered with water.

3.1.1.1 *Discussion*—Synonyms are: eulittoral zone, midlittoral zone, mediolittoral zone, intertidal zone, foreshore.

4. Summary of Test Method

4.1 This test method consists of the following:

4.1.1 Selection of plastic material for the determination of aerobic biodegradation in a controlled laboratory system.

4.1.2 Obtaining sediment and seawater from the shoreline.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

4.1.3 Exposing the plastic material to the wet sediment under controlled conditions.

4.1.4 Measuring CO₂ evolved as a function of time.

4.1.5 Assessing the degree of biodegradation by determining the percentage of organic carbon in the plastic material that is converted to CO₂ during the duration of the test. This percentage represents the percentage of mineralization and will not include the amount of carbon converted to cell biomass that is not in turn metabolized to CO₂ during the course of the test.

4.1.6 Estimating the qualitative disintegration of the test material by visual inspection at the end of the test.

5. Significance and Use

5.1 Plastic is sometimes carried by rivers or accidentally discharged by ships into the sea; this plastic can then reach different parts of the marine environment. Tides and waves also frequently deliver plastic marine debris into the sandy tidal zones.

5.2 This test method simulates the environmental conditions found in the tidal zone. Plastic debris that reaches the sandy tidal zone can settle there and become partially or totally buried by sand and kept wet by waves or tides. It is of interest to assess the biodegradation behavior of plastic materials under these conditions to predict the removal time of this waste in the environment.

5.3 This test method is applied to determine the extent of biodegradation of a plastic exposed in the laboratory to a sandy sediment kept wet with seawater. Both sediment and seawater are collected from a sandy beach in the tidal zone. If the natural microbial population present in the sediment is able to biodegrade the plastic, there will be an evolution of CO₂ as a consequence of the aerobic microbial respiration. The level of biodegradation at any given time is the ratio between the cumulative amount of the evolved net carbon dioxide and the theoretical amount produced in the case of total conversion of the organic carbon present in the plastic into carbon dioxide.

5.4 This test method does not measure the amount of organic carbon that is converted into biomass, but only the biodegradation that leads to mineralization (that is, the formation of CO₂).

6. Apparatus

6.1 *Reactor*—Glass vessel approximately 2 to 4-L internal volume that can be sealed air-tight, such as 150-mm desiccators, with an airtight opening, large enough to allow the handling of the content. Biometer flasks are also appropriate. A suitable apparatus is shown in Figure 1 in Test Method **D5988**. Reactors with higher volumes can be used, if environmental conditions are not affected.

6.2 *Container for the CO₂ Absorber*—A glass beaker to be located in the headspace of the reactor and filled with 100 mL of Ba(OH)₂ 0.025 N or with 30 mL of KOH 0.5 N.

6.3 *Darkened Chamber or Cabinet*, in which the temperature can be maintained at a constant level within a $\pm 2^\circ\text{C}$ range.

NOTE 2—Incubator with either built in lights that can be programmed or else plug in lights that can be operated with a timer power strip can be used to better simulate the environment. The lighting in that case need to

be 12:12 day/night. Details on the lighting regime, light intensity, wave length, incubator type, etc. shall be provided in the report.

6.4 *Analytical Balance*, to weigh the test specimen.

6.5 *Technical Balance*, to weigh reactors and sediment.

6.6 *pH Meter*.

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁴ It is acceptable to use other grades provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Barium Hydroxide Solution (0.025 N)*, prepared by dissolving 4.0 g anhydrous Ba(OH)₂/L in distilled water. Filter free of solid material and store sealed as a clear solution to prevent absorption of CO₂ from the air. It is recommended that 2 to 4 L be prepared at a time when running a series of tests. Confirm normality by titration with standard acid before use. When using Ba(OH)₂, however, care must be taken that a film of BaCO₃ does not form on the surface of the solution in the beaker, which would inhibit CO₂ diffusion into the absorbing medium. Alternatively, potassium hydroxide solution (KOH, 0.5 N) could be used and is prepared by dissolving 28 g of anhydrous KOH/L in distilled water and proceeding in the same way as for the Ba(OH)₂ solution.

7.3 *Hydrochloric acid*, 0.05 N HCl when using 0.025 N Ba(OH)₂ or 0.3 N HCl when using 0.5 N KOH.

7.4 *Sediment*—Collect seawater and sediment samples from the shoreline of a sandy beach, where the sediment is submerged in the shallow water. Collect top sediment (the layer from surface till about 20 cm depth). It is important to obtain sediment from multiple samples from the same location (at least 3). Collect the seawater with a bucket and then collect sediment samples with a shovel in separate containers overlain with water, then transfer all samples to a watertight container and quickly deliver it to the laboratory. Remove any obvious plant material, shells, pieces of driftwood, petroleum tar, and other large material. Store the sediment and seawater at approximately 4°C until use. Allow air exchange at time to avoid anaerobiosis. Use preferably within four weeks of sampling. Report the storage times. Before use, perform gravity filtration on the sediment in a funnel with a coarse filter paper to remove excess water. Sediment is ready for testing when seawater is no longer recovered from the filtration. Nitrogen sources (such as NH₄Cl or NaNO₃) can be added to the sediment if this is considered as a factor limiting biodegradation. These additions shall be reported in the test report.

NOTE 3—No data are available at this stage indicating that a specific

⁴ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Anal. Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

nitrogen level is beneficial for the biodegradation process.

7.5 Plastic Material—Determine the total organic carbon both of the test material and the reference material using ISO 8245 and report it, preferably, as grams of total organic carbon per gram of total dry solids. Alternatively, provided the materials do not contain inorganic carbon, it is possible to determine the carbon content by elemental analysis. The test material shall have sufficient organic carbon to yield CO₂ in an amount suitable for the determination.

7.6 Reference Material—A cellulose filter paper⁵ for laboratory purposes. Determine the carbon content as described in 7.5.

7.7 Negative Control Material (optional)—A polyethylene film. Determine the carbon content as described in 7.5.

7.8 Test Samples—It is preferable that the plastic material is in the form of film or plate. Cut out square-shaped samples with a dimension of approximately 5 cm. Likewise prepare square-shaped samples of reference material and negative control material. Record the mass of each sample.

NOTE 4—It is acceptable that the test material be introduced as powder. Mix the powder homogeneously with the sediment. Refer to ISO 10210 for preparation of powder from plastic materials. Furthermore, report data showing that milling has not changed the chemical structure of the test material.

NOTE 5—It is acceptable that the test material be introduced as a perforated film or plate in order to facilitate gas exchange.

8. Hazards

8.1 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

9. Procedure

9.1 Test Set-up—Prepare at least the following number of reactors (6.1): a) three reactors for the test material; b) three reactors for the reference material; c) three reactors for negative control (optional); d) three reactor for the technical control (optional); and (e) three reactors for the blank.

NOTE 6—Two replicates are sufficient for screening purposes.

NOTE 7—The technical controls contain only the absorbing solution and no sediment. The ambient air which fills the headspace of all the vessels introduces CO₂ into the system. The technical controls allow accounting for and subtracting this introduced CO₂. Additionally, the technical controls indicate the air-tightness of the vessel system by showing possible infiltration of CO₂ into the sealed vessel.

9.2 Preliminary Phase:

9.2.1 Place an equal volume (between 200 and 600 g) of wet sediment (see 7.4) in the bottom of each reactor. In a typical case, weigh out 400 g of wet sediment and place it into the bottom of the reactor to form a homogenous layer. Do not press or compact the sediment. Introduce a container (6.2) with the CO₂ trapping solution (7.2) to each reactor. Close the reactors and locate them in a room or chamber preferably at a

temperature from 15 to 25°C, but not exceeding 28°C. Monitor the CO₂ production (9.4).

9.2.2 This phase is carried out in order to: (i) verify the vitality of the sediment, as shown by the respiration level; (ii) verify that the different reactors have similar background respiration; and (iii) obtain a preliminary oxidation of excess organic matter, so as to start the test with a lower level of endogenous respiration.

9.2.3 This phase is generally carried out for one week. In the case that the CO₂ evolution of a given reactor is significantly different from its replicates, reject the diverging reactor, or in the case of multiple anomalies, restart using new sediment. Report CO₂ evolution and details of this phase on the test report.

9.3 Start of the Test—Open the vessels and remove about 100 g of sediment from the layer in the bottom of the reactor. Transfer it in a clean container. Smooth the surface of the residual sediment with a spatula but do not apply pressure. Place 100 mg of plastic material (7.5) or of reference material (7.6) onto the surface of the sediment. The blank reactor will not include any sample. Cover the plastic or reference material with the withdrawn sediment, forming a homogenous layer. Close the vessels tightly. Select a temperature preferably between 15 to 25°C, but not exceeding 28°C, and maintain the selected temperature at ±2°C.

NOTE 8—If the test material is introduced as a powder, mix it homogeneously with the sediment

9.4 CO₂ Analysis:

9.4.1 The CO₂ produced in each reactor will react with Ba(OH)₂ and precipitate as barium carbonate (BaCO₃). The amount of CO₂ produced is determined by titrating the remaining Ba(OH)₂ with 0.05 N hydrochloric acid to a phenolphthalein end-point or by using an automatic titrator. Because of the static incubation, the (BaCO₃) builds up on the surface of the liquid and must be broken up periodically by shaking the container gently to ensure continued absorption of the evolved CO₂. This problem can be avoided by using KOH instead of Ba(OH)₂, which does not form a precipitate.

9.4.2 The container for the CO₂ absorber must be removed and titrated before its capacity is exceeded. The period of time will vary with sediments and test materials and increases slowly as the carbon content of the sediment is reduced (a recommended frequency of every 3 to 4 days for the first 2 to 3 weeks and every 1 to 3 weeks thereafter). At the time of removal of the containers, weigh the reactor to monitor moisture loss from the sediment. Allow the reactor to sit open approximately 15 min so that the air in the reactor is refreshed before replacing 100 mL of fresh Ba(OH)₂ and resealing the reactor. Add distilled or deionized water periodically to the sediment to maintain the initial weight of the reactor, if needed.

NOTE 9—Distilled/deionized water can adsorb atmospheric CO₂ and become more acidic. To avoid this, boil water and then allow it to cool before use.

NOTE 10—The minimum water content is what the sediment retains after filtration. The initial mass (wet sediment) shall be kept constant by adding distilled or deionized water.

9.4.3 It is possible that the CO₂ evolution will plateau when all of the accessible carbon has been oxidized.

⁵ Laboratory filter paper Whatman n. 42 has been found satisfactory for this purpose.