



Designation: F373 – 13 (Reapproved 2022)

Standard Test Method for Embossed Depth of Resilient Floor Coverings¹

This standard is issued under the fixed designation F373; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 Two important characteristics involved in the manufacture of resilient flooring relate to the smoothness of the wear surface and the hardness of the layers under the wear surface. The surfaces may vary from completely textured areas to portions that are flat but separated by textured areas. This test method covers flooring with these interrupted wear surfaces which are not supported by soft, cushioned layers.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

F141 Terminology Relating to Resilient Floor Coverings

3. Terminology

3.1 For terminology relating to Resilient Floor Coverings, see Terminology **F141**.

¹ This test method is under the jurisdiction of ASTM Committee **F06** on Resilient Floor Coverings and is the direct responsibility of Subcommittee **F06.20** on Test Methods.

Current edition approved June 1, 2022. Published June 2022. Originally approved in 1973. Last previous edition approved in 2017 as F373–13(2017). DOI: 10.1520/F0373-13R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance

4.1 This test method is designed to measure the vertical distance between any two levels on the face of the flooring, that is, between any two flat areas, between a flat area and any part of a textured area, or between two textured areas. This vertical distance may be of interest in itself or it may be applied to the questions of: (1) how much of the thickness of the flooring is available before the pattern is destroyed; or (2) how deep the depressed areas must be before valley printing ink is not walked on in normal traffic.

5. Apparatus

5.1 The apparatus shall consist of a comparator stand having a flat anvil base at least 6 in. (15 cm) square, equipped with a dial micrometer graduated to 0.001 in. (0.02 mm), and a hemispherical pressure foot $\frac{1}{32}$ in. (0.80 mm) in diameter. The foot shall exert a force of not more than 1 ozf (0.28 N) at any point in its travel. The force shall be obtained by an appropriate weight. The plunger of the gauge shall be perpendicular to the anvil.

6. Test Specimen

6.1 The specimen shall be a piece of flooring at least 9 in. by 9 in. (230 mm by 230 mm).

7. Calibration

7.1 The calibration of the gauge shall be verified by means of gauge blocks or shim stock traceable to national standard of known thickness of the appropriate thickness for the depths being measured.

8. Conditioning

8.1 Condition the specimens at least 24 h at 73.4 °F \pm 3.6 °F (23 °C \pm 2 °C) and 50 \pm 5 % relative humidity. Test at the same conditions.

9. Procedure

9.1 Select the two types of areas on a specimen that are to be examined.

9.2 Zero the gauge at a random point on the higher area.

9.3 Move the gauge to a random spot in the second area and measure the depth.

9.4 When measuring on a nominally flat wearing surface, do not place the tip close to a built-up shoulder area around a depressed spot; such a shoulder reading would give an erroneous result.

9.5 Make five measurements per specimen scattered at random over the specimen face. Record the measurements to the nearest 0.001 in. (0.02 mm).

10. Report

10.1 Report the average of the five measurements calculated to 0.001 in. (0.02 mm) as the depth between the two types of areas of interest.

10.2 Report the minimum and maximum values obtained.

11. Precision and Bias

11.1 The number of laboratories, materials, and determinations in this study *does* meet the minimum requirements for determining precision prescribed in Practice E691.

	This Study	Practice E691 Minimum
Laboratories	6	6
Materials	5	4
Determinations	5	2

11.2 Precision, characterized by repeatability, S_r , r , and reproducibility, SR , R has been determined for the materials to be:

Materials	Average ^A	S_r ^B	SR ^C	r ^D	R ^E
Material A	14.07	2.05	2.51	5.74	7.02
Material B	17.47	2.25	2.48	6.30	6.95
Material C	22.22	1.14	1.42	3.19	3.97
Material D	4.08	0.43	0.50	1.20	1.40
Material E	14.55	0.76	0.97	2.12	2.71

^A Average is the numerical average of test results for all replicates from all laboratories.

^B S_r is the within-laboratory standard deviation of the average.

^C $r = 2.83 S_r$.

^D SR is the between-laboratory standard deviation of the average.

^E $R = 2.83 SR$.

11.3 *Repeatability* (S_r , r)—In comparing two average values for the same material obtained by the same operator using the same equipment on the same day, the means should be judged *not equivalent* if they differ by more than the r value for that material and condition.

11.4 *Reproducibility* (SR , R)—In comparing two average values for the same material obtained by different operators using different equipment on different days, the means should be judged *not equivalent* if they differ by more than the R value for that material and condition. (This applies between different laboratories or between different equipment within the same laboratory.)

11.5 These judgments will have an approximate 0.95 (95%) probability of being correct. Other materials would be expected to give somewhat different results. For further information on the methodology used in this section or for further clarification, please refer to Practice E691.

12. Keywords

12.1 embossing; flooring; micrometer; resilient; texture

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/