



Designation: A923 – 14 A923 – 22

Standard Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels¹

This standard is issued under the fixed designation A923; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 The purpose of these test methods is to allow detection of the presence of intermetallic phases in certain duplex stainless steels as listed in Table 1, Table 2, and Table 3 to the extent that toughness or corrosion resistance is affected significantly. These test methods will not necessarily detect losses of toughness or corrosion resistance attributable to other causes. Similar test methods for other duplex stainless steels are described in Test Method A1084, but the procedures described in this standard differ significantly from Test Methods A, B, and C in A1084.

1.2 Duplex (austenitic-ferritic) stainless steels are susceptible to the formation of intermetallic compounds during exposures in the temperature range from approximately 600 to 1750 °F (320 to 955 °C). The speed of these precipitation reactions is a function of composition and thermal or thermomechanical history of each individual piece. The presence of these phases is detrimental to toughness and corrosion resistance.

1.3 Correct heat treatment of duplex stainless steels can eliminate these detrimental phases. Rapid cooling of the product provides the maximum resistance to formation of detrimental phases by subsequent thermal exposures.

1.4 Compliance with the chemical and mechanical requirements for the applicable product specification does not necessarily indicate the absence of detrimental phases in the product.

1.5 These test methods include the following:

1.5.1 *Test Method A*—Sodium Hydroxide Etch Test for Classification of Etch Structures of Duplex Stainless Steels (Sections 3 – 7).

1.5.2 *Test Method B*—Charpy Impact Test for Classification of Structures of Duplex Stainless Steels (Sections 8 – 13).

1.5.3 *Test Method C*—Ferric Chloride Corrosion Test for Classification of Structures of Duplex Stainless Steels (Sections 14 – 20).

1.6 The presence of detrimental intermetallic phases is readily detected in all three tests, provided that a sample of appropriate location and orientation is selected. Because the occurrence of intermetallic phases is a function of temperature and cooling rate, it is essential that the tests be applied to the region of the material experiencing the conditions most likely to promote the formation

¹ These test methods are under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and are the direct responsibility of Subcommittee A01.14 on Methods of Corrosion Testing.

Current edition approved March 1, 2014; June 1, 2022. Published March 2014; June 2022. Originally approved in 1994. Last previous edition approved in 2008 as A923 – 08; A923 – 14. DOI: 10.1520/A0923-14.10.1520/A0923-22.

***A Summary of Changes section appears at the end of this standard**

of an intermetallic phase. In the case of common heat treatment, this region will be that which cooled most slowly. Except for rapidly cooled material, it may be necessary to sample from a location determined to be the most slowly cooled for the material piece to be characterized.

1.7 The tests do not determine the precise nature of the detrimental phase but rather the presence or absence of an intermetallic phase to the extent that it is detrimental to the toughness and corrosion resistance of the material.

1.8 Examples of the correlation of thermal exposures, the occurrence of intermetallic phases, and the degradation of toughness and corrosion resistance are given in [Appendix X1](#) and [Appendix X2](#).

1.9 The values stated in either inch-pound or SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.10 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and ~~health~~ environmental practices and determine the applicability of regulatory limitations prior to use.*

1.11 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A1084 Test Method for Detecting Detrimental Phases in Lean Duplex Austenitic/Ferritic Stainless Steels](#)

[G48 Test Methods for Pitting and Crevice Corrosion Resistance of Stainless Steels and Related Alloys by Use of Ferric Chloride Solution](#)

(<https://standards.iteh.ai>)

TEST METHOD A—SODIUM HYDROXIDE ETCH TEST FOR CLASSIFICATION OF ETCH STRUCTURES OF DUPLEX STAINLESS STEELS

3. Scope

[ASTM A923-22](#)

</catalog/standards/astm/9686a30e-504c-4572-bea6-c3a4f17b67f9/astm-a923-22>

3.1 The sodium hydroxide etch test may be used for the acceptance of material but not for rejection. This test method may be used with other evaluation tests to provide a rapid method for identifying those specimens that are free of detrimental intermetallic phases as measured in these other tests.

3.2 The sodium hydroxide etch test may be used to screen specimens intended for testing in Test Method B, Charpy Impact Test for Classification of Structures of Duplex Stainless Steels, and in Test Method C, Ferric Chloride Corrosion Test for Classification of Structures of Duplex Stainless Steels.

3.3 Reference photomicrographs are provided to show classifications of etch structures of a particular stainless steel type that are equivalent to acceptable or to possibly unacceptable performance for each practice. When Test Method A is used as a screening test for Test Method B or Test Method C, specimens having acceptable etch structures need not be subjected to Test Method B or Test Method C.

3.4 [Table 1](#) indicates the applicability and acceptance criteria for Test Method A. When Test Method A is specified as an acceptance test, specimens having other than acceptable etch structures may, at the option of the producer, be tested by Test Method B or Test Method C.

3.5 The steel shall be tested in the final solution heat treated condition or such other conditions as are agreed upon between the producer and the user.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.