



Designation: C126 – 22

Standard Specification for Ceramic Glazed Structural Clay Facing Tile, Facing Brick, and Solid Masonry Units¹

This standard is issued under the fixed designation C126; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers structural clay load-bearing facing tile and facing brick and other “solid masonry units” made from clay, shale, fire-clay, or mixtures thereof, with or without the addition of grog or other mixtures, having a finish consisting of a ceramic glaze fused to the body at above 1500°F (655°C) making them inseparable, excluding natural salt-glazed ware.

1.2 The property requirements of this specification apply at the time of purchase. The use of results from testing of brick and tile extracted from masonry structures for determining conformance or nonconformance to the property requirements (Section 6) of this standard is beyond the scope of this specification.

1.3 Brick and tile covered by this specification are manufactured from clay, shale, or similar naturally occurring substances and subjected to a heat treatment at elevated temperatures (firing). The heat treatment must develop sufficient fired bond between the particulate constituents to provide the strength requirements of this specification. (See firing and fired bond in Terminology C1232.)

1.4 Two grades and two types of ceramic glazed units are covered.

1.5 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.6 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.7 The following precautionary caveat pertains only to the test portion of this specification. *This standard does not*

¹ This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.02 on Brick and Structural Clay Tile.

Current edition approved June 1, 2022. Published June 2022. Originally approved in 1936. Last previous edition approved in 2019 as C126 – 19. DOI: 10.1520/C0126-22.

purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C67/C67M Test Methods for Sampling and Testing Brick and Structural Clay Tile

C1232 Terminology for Masonry

E84 Test Method for Surface Burning Characteristics of Building Materials

E2105 Practice for General Techniques of Thermogravimetric Analysis (TGA) Coupled With Infrared Analysis (TGA/IR)

2.2 *National Fire Protection Association Standard:*³

NFPA No. 255 Test for Surface Burning Characteristics of Building Materials

2.3 *Underwriters Laboratories, Inc. Standard:*⁴

UL No. 723 Flammability Studies of Cellular Plastics and other Building Materials used for Interior Finishes

3. Terminology

3.1 *Definitions*—For definitions relating to ceramic glazed structural clay facing tile, facing brick, and solid masonry units, refer to Terminology C1232.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

⁴ Available from Underwriters Laboratories (UL), 333 Pfingsten Rd., Northbrook, IL 60062-2096, <http://www.ul.com>.

*A Summary of Changes section appears at the end of this standard

4. Classification

4.1 *Grades*—Grades classify units according to their permissible tolerances. Two grades of ceramic glazed facing tile, brick, and solid masonry units are covered. The requirements are given in Section 7.

4.1.1 *Grade S (select)*, for use with comparatively narrow mortar joints.

4.1.2 *Grade SS (select sized or ground edge)*, for use where variation of face dimension must be very small.

4.1.3 When the grade is not specified, the requirements for Grade S shall govern.

4.2 *Types*—Two types of ceramic glazed facing tile, brick, and solid masonry units are covered. The requirements are given in Section 7.

4.2.1 *Type I (single-faced units)*, for general use where only one finished face will be exposed.

4.2.2 *Type II (two-faced units)*, for use where two opposite finished faces will be exposed.

4.2.3 When the type is not specified, the requirements for Type I shall govern.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 *Grade*—When the grade is not specified, the requirements for Grade S shall govern.

5.1.2 *Type*—When the type is not specified, the requirements for Type I shall govern.

5.1.3 *Sizes and Shapes*—The sizes and shapes shall be specified in accordance with Section 7.1.

5.1.4 *Color and Texture of Finish*—The color and texture of the finish shall be specified in accordance with Section 8.6.

5.1.5 *Back Surfaces*—Unless otherwise specified, smooth, scored, combed, or roughened unglazed backs and smooth unselected glazed backs or a mixture thereof, are furnished. When plaster is to be applied, the back surface shall be specified in accordance with Section 8.5.

5.1.6 *Coring*—Unless otherwise specified, either standard or special duty units as prescribed in Section 9 are furnished.

5.1.7 *Opacity*—Where ceramic glazed units are not specified as opaque, they need not meet the requirements for opacity prescribed in 8.4.2.

5.1.8 *Exterior Use*—Where ceramic glazed units are required for exterior use, the manufacturers shall be consulted for material suitable for this purpose.

NOTE 1—The requirements included in this specification do not cover minimum criteria for durability of units exposed to exterior environments.

6. Physical Properties

6.1 The compressive strengths (based on gross area) of the units shall be not less than the values prescribed in Table 1.

TABLE 1 Compressive Strengths of Units

Direction of Coring	Minimum Average of Five Tests, psi (MPa)	Individual Minimum, psi (MPa)
Vertical	3 000 (20.7)	2 500 (17.2)
Horizontal	2 000 (13.8)	1 500 (10.3)

NOTE 2—Special duty units may be available from various manufacturers where higher compressive strengths are required.

7. Dimensions and Permissible Variations

7.1 The face sizes of ceramic glazed units and fittings therefore shall be as specified.

NOTE 3—The sizes shown in Table 2 are standard in the industry for single-faced units (Type I).

7.2 *Face Dimension Tolerances*—The total variation in the finished face dimensions of units shall be not more than the values shown in Table 3.

7.3 *Bed-Depth Dimension Tolerances*—The total variation in the bed-depth (through the wall) dimension of units shall be not more than the value shown in Table 4.

7.4 *Warpage Tolerances*—The maximum permissible deviation of the plane and the edges of the face of individual units from a plane surface and from a straight line, respectively, shall not exceed the value shown in Table 5.

NOTE 4—When convex units are laid upon a plane surface, the apparent variation is greater than the actual variation from the plane of the unit.

8. Finish and Appearance

8.1 The body of the units shall be free of cracks or other imperfections which would impair the strength or durability of the masonry.

8.2 Unless otherwise agreed upon between the purchaser and the seller, a delivery of brick or tile shall not contain more than 3 % brick or tile that are chipped, cracked or broken.

8.3 The finished face (one face of stretcher units and the finished faces of shapes) that will be exposed when in place shall be covered with a ceramic glaze of uniform quality. The glaze shall be free of chips, crazes, blisters, crawling, or other imperfections detracting from the appearance of the finished wall when viewed from a distance of 5 ft (1.52 m) under diffused lighting at right angles from the wall.

NOTE 5—The purchaser or his authorized representative shall be accorded opportunity for sampling and inspecting units at the place of manufacture, prior to shipment. At least 10 days from the time of sampling should be allowed for completion of the tests. Unless otherwise specified in the purchase order, the cost of tests is typically borne as follows: If the results of the tests show that the brick does not conform to the requirements of this specification, the cost is typically borne by the seller. If the results of the tests show that the brick does conform to the requirements of this specification, the cost is typically borne by the purchaser.

8.4 Properties of Glaze:

8.4.1 *Imperviousness*—After the imperviousness test, no stain seen from a distance of 5 ft (1.5 m) shall remain on or beneath the surface, except a slight discoloration in the depressions on matt, stippled, or mottled finishes.

8.4.2 *Opacity*—Where opacity of finish is desired and so specified, discoloration of the body shall not be visible through the glaze in the opacity test. Clear ceramic glazes and special decorative glazes shall not be required to meet this requirement.

8.4.3 *Resistance to Fading*—The color of the glaze shall not change in the chemical resistance test. Finishes of metallic or special decorative glazes shall not be required to meet this requirement.

TABLE 2 Size of Single-Faced Units

Series Designation	Specified Face Dimensions		Specified Thickness, in. (mm)
	Height, in. (mm)	Length, in. (mm)	
4S	2¼ (57.2)	7⅝ (193.7)	1¼, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7)
4W	7⅝ (193.7)	7⅝ (193.7)	1¼, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7)
6P	3⅝ (92.1)	11⅝ (295.3)	1¼, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7)
6T	5 (127)	11⅞ (296.9)	1¼, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7)
8W	7⅝ (193.7)	15⅝ (396.9)	1¼, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7)

TABLE 3 Permissible Variations in Face Dimensions

NOTE 1—Permissible variations for units having specified dimensions more than ¼ in. (6.4 mm) greater than shown in this table shall be the same as for the next larger dimension.

Specified Face Dimension, Return or Reveal (Height, Length), in. (mm)	Maximum Difference Between Dimension of Any Unit and the Specified Dimension		Maximum Difference Between Largest and Smallest Unit in One Lot, ^A in. (mm)
	If Larger, in. (mm)	If Smaller, in. (mm)	
Grade S Units			
6 (152.4) and Under	⅛ (1.6)	⅜ (2.4)	⅜ (2.4)
Over 6 to 8 (152.4 to 203.2)	⅛ (1.6)	⅜ (3.2)	⅜ (4.0)
Over 8 to 16 (203.2 to 406.4)	⅛ (1.6)	⅜ (4.0)	⅜ (4.8)
Grade SS—Select Sized or Ground-Edge Units Only			
Any dimension	⅛ (1.6)	⅛ (1.6)	⅛ (3.2)

^ASize of lot shall be determined by agreement between the purchaser and the seller.

TABLE 4 Permissible Variation in Bed Depth Dimensions

NOTE 1—Permissible variations for units having specified dimensions more than ¼ in. (6.4 mm) greater than shown in this table shall be the same as for the next larger dimension.

NOTE 2—Variation in the bed depth of individual units is controlled by the limitations on warpage. The thickness of a unit shall be considered either the maximum or minimum thickness, whichever is the farther from the specified dimension.

Specified Bed Depth Dimension (Wall Thickness), in. (mm)	Maximum Difference Between Dimension of Any Unit and the Specified Dimension		Maximum Difference Between Largest and Smallest Unit in One Lot, in. (mm) ^A
	If Larger, in. (mm)	If Smaller, in. (mm)	
Type I—Single-Faced Units			
2 (50.8) and Under	⅛ (3.2)	⅛ (3.2)	⅛ (3.2)
Over 2 to 4 (50.8 to 101.6)	⅛ (3.2)	⅜ (4.7)	⅜ (4.7)
Over 4 to 6 (101.6 to 152.4)	⅛ (3.2)	¼ (6.4)	¼ (6.4)
Over 6 to 8 (152.4 to 203.2)	⅛ (3.2)	⅜ (7.9)	⅜ (7.9)
Type II—Two-Faced Units			
8 (203.2) and Under	⅛ (3.2)	⅛ (3.2)	⅛ (3.2)

^ASize of lot shall be determined by agreement between the purchaser and the seller.

8.4.4 *Resistance to Crazing*—The glaze shall not craze, spall, or crack when subjected to one cycle of autoclaving in the crazing test.

8.4.5 *Flame Spread Index (FSI) and Smoke Density Index (SDI)*—Body and finish shall withstand temperatures up to 1900°F (1037.8°C) without distortion or melting and rate “non-combustible.” When tested in accordance with the pro-

TABLE 5 Permissible Warpage

NOTE 1—Warpage tolerances for units having specified dimensions more than ¼ in. (6.4 mm) greater than shown in this table shall be the same as for the next larger dimension.

Specified Face Dimensions (Height and Length), in. (mm)	Grade	Maximum Permissible Warpage, in. (mm)
2¼ × 7⅝ (57.2 × 193.7)	S	⅛ (1.6)
3⅝ × 7⅝ (92.1 × 193.7)	S	⅛ (1.6)
7⅝ × 7⅝ (193.7 × 193.7)	S	⅛ (1.6)
5 × 11⅝ (127 × 295.3)	S	⅛ (1.6)
3⅝ × 11⅝ (92.1 × 295.3)	S	⅛ (1.6)
7⅝ × 11⅝ (193.7 × 295.3)	S	⅜ (4.0)
7⅝ × 15⅝ (193.7 × 396.9)	S	⅜ (4.0)
7⅝ × 11⅝ (193.7 × 295.3)	SS	⅜ (2.4)
7⅝ × 15⅝ (193.7 × 396.9)	SS	⅜ (2.4)

visions of Test Method E84, structural facing tile shall measure 0 flame spread index and 0 smoke density index.

NOTE 6—This test method is similar to that specified in NFPA No. 255 and UL No. 723.

8.4.6 *Fumes*—Under thermogravimetric analysis (TGA), in a flowing air atmosphere, weight loss due to release of gases from the body and glaze finish shall not exceed 0.2 % of dry weight at temperatures up to 1800°F (982.2°C).

NOTE 7—See Practice E2105 for TGA only. TGA test results can be a measure of sample combustibility. Very low weight loss under TGA will demonstrate non-combustibility coupled with low flame spread index and smoke density index.

8.4.7 *Scratch Resistance and Hardness*—Glaze must resist scratching by ordinary glass or steel and be rated above five on the Mohs Hardness Scale. Finishes of metallic or special decorative glazes shall not be required to meet this requirement.

8.5 *Plaster Base Finish:*

8.5.1 Unless otherwise specified by the purchaser, smooth, scored, combed or roughened-back units or a mixture thereof are furnished.

8.5.2 When smooth, at least 90 % of the tile area shall be free of glaze and the average absorption shall be not less than 5 %, unless acceptable plaster adhesion bond test data is provided.

8.5.3 When scored, each groove shall be dovetailed and shall be not less than ⅛ in. (1.6 mm) nor more than ¼ in. (6.4 mm) in depth, and not more than 1 in. (25.4 mm) in width. The area covered by the grooves shall not exceed 50 % of the area of the scored faces.

8.5.4 When combed, the tile shall be scarified, prior to burning, by mechanical means which shall make scarifications on the surface of the tile not less than ⅛ in. (1.6 mm) nor more