



Designation: C302 – 13 (Reapproved 2022)

Standard Test Method for Density and Dimensions of Preformed Pipe-Covering-Type Thermal Insulation¹

This standard is issued under the fixed designation C302; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the dimensions and density, after conditioning, of preformed pipe insulation.

1.1.1 Procedure A is applicable to sections of one-piece pipe covering or to sections of segmental pipe covering that can be joined together concentrically and measured as one-piece.

1.1.2 Procedure B is applicable to segmental pipe covering where each section of material is measured.

1.1.3 Procedure C is applicable to sections of one-piece pipe covering, such as soft foam or mineral wool materials, where it is possible to penetrate the material.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations

¹ This test method is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.32 on Mechanical Properties.

Current edition approved May 1, 2022. Published June 2022. Originally approved in 1952. Last previous edition approved in 2017 as C302 – 13 (2017). DOI: 10.1520/C0302-13R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C168 Terminology Relating to Thermal Insulation

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C870 Practice for Conditioning of Thermal Insulating Materials

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 *Definitions*—See Terminology **C168**.

4. Summary of Test Method

4.1 The material to be tested is conditioned to constant weight. The density of the pipe insulation is calculated from the conditioned mass and measured dimensions.

5. Significance and Use

5.1 Density measurements of preformed pipe insulation are useful in determining compliance of a product with specification limits and in providing a relative gage of product weights. For any one kind of insulation some important physical and mechanical properties, such as thermal conductivity, heat capacity, strength, etc., bear a specific relationship with its density; however, on a density basis, these properties are not directly comparable with those for other kinds of material.

5.2 The physical dimensions of preformed pipe insulation are important quantities not only for determining the density of the pipe insulation but also for determining the conformance to specifications. The use of multilayer insulations is common, and the dimensions are necessary to ensure proper nesting of the layers.

6. Apparatus

6.1 *Flexible Steel Rule*, graduated in 1/32-in. or 1.0-mm intervals.

6.2 *Scale*, with sufficient capacity to weigh the specimen to within 0.01 lb or 5 g.

6.3 *Pin Probe*, as defined in Test Methods **C167**.

6.4 *Steel Rule*, graduated in 1/32-in. or 1.0-mm intervals.

6.5 *Stainless Steel Shim Stock*, 2 in. (75 mm) wide, longer than the circumference of the pipe insulation, and 0.010 in. (0.25 mm) thick.

6.6 *Pi Tape*, graduated to read a diameter directly to the nearest 1/32 in. or 1.0 mm.

6.7 *Pieces of Pipe*, on which to install the pipe insulation under test (only required for Procedure 3).

7. Test Specimen

7.1 The test specimen shall be of a commercial size.

7.2 If sectional pipe segments are to be used for Procedures 1 or 3, the sections shall be joined together to form a hollow cylinder.

8. Conditioning

8.1 Remove any jacket on the specimen unless it is of a type that would cause disintegration of the specimen upon removal.

8.2 Condition the specimen to constant mass in accordance with Practice C870.

9. Procedures

Procedure A

9.1 *One-Piece Pipe Section:*

9.1.1 Weigh the conditioned pipe section to the nearest 0.01 lb or 5 g.

9.1.2 Measure the length of the specimen in six locations, uniformly spaced around its circumference, to the nearest 1/32 in. or 1.0 mm.

9.1.3 Measure the circumference of the specimen in six locations, uniformly spaced along its length, to the nearest 1/32 in. or 1.0 mm.

9.1.4 Measure the wall thickness at six locations, uniformly spaced, three on each end of the specimen, to the nearest 1/32 in. or 1.0 mm.

Procedure B

9.2 *Segmental Pipe Sections:*

9.2.1 Weigh the conditioned segmental pipe section to the nearest 0.01 lb or 5 g.

9.2.2 Measure the length of the arc formed by the outer surface of the specimen at six locations, uniformly spaced along its length, to the nearest 1/32 in. or 1.0 mm.

9.2.3 Measure the length of the arc formed by the inner surface of the specimen at six locations, uniformly spaced along its length, to the nearest 1/32 in. or 1.0 mm.

9.2.4 Measure the length of the specimen in six locations, uniformly spaced around the outer surface, to the nearest 1/32 in. or 1.0 mm.

9.2.5 Measure the wall thickness at six locations, uniformly spaced, one on each end and two on each side of the specimen, to the nearest 1/32 in. or 1.0 mm.

Procedure C

9.3 *Non-Rigid Pipe Insulations:*

9.3.1 Weigh the conditioned pipe section to the nearest 0.01 lb or 5 g.

9.3.2 Place the insulation on a pipe of the same outside diameter as the nominal inside diameter of the specimen, and tie in place. Support the ends of the pipe such that the specimen is not resting on a surface.

9.3.3 Measure the length of the specimen in six locations, uniformly spaced around its circumference, to the nearest 1/32 in. or 1.0 mm.

9.3.4 Measure the diameter of the specimen in six locations, uniformly spaced along its length, to the nearest 1/32 in. or 1.0 mm, using the Pi tape. In order to avoid compressing the insulation specimens under the Pi tape, wrap the shim stock around the specimen and use the Pi tape over the shim stock. Subtract twice the thickness of the shim stock from the

diameter measured and convert the diameter to a circumference by multiplying the average diameter by π .

9.3.5 Measure the wall thickness at six locations, uniformly spaced along the length of the specimen and uniformly spaced around its surface, using the pin probe of 6.3, to the nearest 1/32 in. or 1.0 mm.

10. Calculations

10.1 Calculate the volume of the specimen using one of the following equations:

10.1.1 *Procedures A and C:*

$$V = L(C - \pi t)/1728 \quad (1)$$

where:

V = volume of the specimen, ft³,

L = average length of the specimen, in.,