



Designation: ~~D8178—20a~~ D8178 – 22

Standard Terminology Relating to Recovered Carbon Black (rCB)¹

This standard is issued under the fixed designation D8178; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology covers a compilation of definitions of technical terms used in the recovered carbon black industry. Terms that are generally understood or adequately defined in other readily available sources are not included.

1.2 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D3053 Terminology Relating to Carbon Black](#)

3. Terminology

3.1 *Definitions:*

carbon black, *n*—this definition is under the jurisdiction of Committee D24 and maintained in Terminology [D3053](#).

char, *n*—solid carbonaceous residue formed during carbonization of organic compounds.

raw rCB, *n*—solid material resulting from thermal decomposition of rubber goods which contain carbon black; exhibiting poor dispersion so requiring milling to become rCB.

recovered carbon black (rCB), *n*—solid product recovered via thermal decomposition from rubber goods which contain carbon black, which is free of wire and fabric, and when milled typically gives semi-reinforcing properties in rubber.

DISCUSSION—

A type of filler derived from post-consumer rubber goods (feedstock) via a variety of thermal decomposition processes. This semi-reinforcing filler predominantly consisting of carbon, also containing inorganic compounding ingredients originating from the feedstock but is free of wire and fabric. This material, typically pelletized currently marketed under the name recovered carbon black (rCB), should not be confused with “Raw rCB” which exhibits poor dispersion and minimal reinforcing properties when used in rubber compounding.

recovered carbon black pellet, *n*—a relatively large agglomerate mass that has been densified in spheroidal form to facilitate handling and processing.

¹ This terminology is under the jurisdiction of ASTM Committee [D36](#) on Recovered Carbon Black (rCB) and is the direct responsibility of Subcommittee [D36.30](#) on Nomenclature.

Current edition approved ~~Dec. 1, 2020~~ June 1, 2022. Published ~~January 2021~~ July 2022. Originally approved in 2018. Last previous edition approved in 2020 as ~~D8178—20~~ D8178 – 20a. DOI: ~~10.1520/D8178-20A~~ 10.1520/D8178-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

APPENDIX

(Nonmandatory Information)

~~X1. EXISTING STANDARDS RECOGNIZED BY COMMITTEE D36~~

~~X1.1~~ The following is a list of existing standards that are currently available for use in the industry. These standards are maintained by ASTM Committee D24 on Carbon Black; however, they can be applied for use in the rCB industry.³

~~X1.2~~ In 2017, Committee D36 approved to recognize these standards as acceptable for use in the rCB industry until rCB statistical data is available that may suggest otherwise.

~~D1506 Test Methods for Carbon Black—Ash Content
D1508 Test Method for Carbon Black, Pelleted Fines and Attrition
D1509 Test Methods for Carbon Black—Heating Loss
D1511 Test Method for Carbon Black—Pellet Size Distribution
D1512 Test Methods for Carbon Black—pH Value
D1513 Test Method for Carbon Black, Pelleted—Pour Density
D1514 Test Method for Carbon Black—Sieve Residue
D1618 Test Method for Carbon Black Extractables—Transmittance of Toluene Extract
D1619 Test Methods for Carbon Black—Sulfur Content
D1799 Practice for Carbon Black—Sampling Packaged Shipments
D1900 Practice for Carbon Black—Sampling Bulk Shipments
D1937 Test Method for Carbon Black, Pelleted—Mass Strength
D2663 Test Methods for Carbon Black—Dispersion in Rubber
D3053 Terminology Relating to Carbon Black
D3191 Test Methods for Carbon Black in SBR (Styrene-Butadiene Rubber)—Recipe and Evaluation Procedures
D3192 Test Methods for Carbon Black Evaluation in NR (Natural Rubber)
D3849 Test Method for Carbon Black—Morphological Characterization of Carbon Black Using Electron Microscopy
D4122 Practice for Carbon Black—Evaluation of an Industry Reference Black
D4821 Guide for Carbon Black—Validation of Test Method Precision and Bias
D5230 Test Method for Carbon Black—Automated Individual Pellet Hardness
D5817 Practice for Carbon Black, Pelleted—Reduction, Blending, and Drying of Gross Samples for Testing
D6915 Practice for Carbon Black—Evaluation of Standard Reference Blacks
D7771 Test Method for Determination of Benzo- α -Pyrene (BaP) Content in Carbon Black~~

~~X1.3~~ The Committee has concluded that typical Carbon black characterization methods based on structure level and surface area measurements do not seem to correlate to in-rubber performance in an equal matter for Recovered Carbon Black products. Therefore, the committee does not recommend such test methods for predicting the applications performance of recovered carbon black products. The committee is open to new research that can contradict above statement.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/