



Designation: D2524 – 22

# Standard Test Method for Breaking Tenacity of Wool Fibers, Flat Bundle Method— $\frac{1}{8}$ in. (3.2 mm) Gage Length<sup>1</sup>

This standard is issued under the fixed designation D2524; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the breaking tenacity of wool fibers as a flat bundle with a  $\frac{1}{8}$  in. (3.2 mm) clamp separation.

1.2 This test method is especially adapted to the fiber bundle clamps and strength testing instruments specified, but may be used on other tensile testing machines when equipped with appropriate adapters to accommodate the prescribed clamps.

1.3 This test method is applicable to wool in any form which can be hand-combed into small bundles of parallelized fibers.

NOTE 1—Other test methods for measuring breaking tenacity of fiber bundles include Test Methods [D1294](#), [D1445](#), and [D540](#).

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D123 Terminology Relating to Textiles](#)

[D540 Methods of Testing Man-Made Staple Fibers; Replaced by D 3660 \(Withdrawn 1973\)](#)<sup>3</sup>

[D1294 Test Method for Tensile Strength and Breaking Tenacity of Wool Fiber Bundles 1-in. \(25.4 mm\) Gage Length](#)

[D1445 Test Method for Breaking Strength and Elongation of Cotton Fibers \(Flat Bundle Method\)](#)

[D1776 Practice for Conditioning and Testing Textiles](#)

[D4845 Terminology Relating to Wool](#)

[D2525 Practice for Sampling Wool for Moisture \(Withdrawn 2022\)](#)<sup>3</sup>

## 3. Terminology

3.1 For all terminology related to D13.13, Wool and Felt, see Terminology [D4845](#).

3.1.1 The following terms are relevant to this standard: breaking tenacity, constant-rate-of-extension (CRE) type tensile testing machine, constant-rate-of-loading (CRL) type tensile testing machine, constant-rate-of-traverse (CRT) type tensile testing machine, gage length, tenacity, wool.

3.2 For definitions of all other textile terms see Terminology [D123](#).

## 4. Summary of Test Method

4.1 A bundle of fibers is combed until parallel, placed under a uniform tension sufficient to remove as much crimp as possible without stretching the fibers, and secured in special clamps. The fibers are then cut to a known length, broken in the tensile testing machine, removed from the clamps, and weighed. Breaking tenacity is calculated from the ratio of breaking force to bundle linear density. The length measured under the applied tension is the basis for computing linear density from bundle mass.

## 5. Significance and Uses

5.1 Test Method D2524 for testing wool fibers for tenacity is considered satisfactory for acceptance testing when the participating laboratories, using a reference wool, have shown acceptable between-laboratory precision. It is recommended

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D13](#) on Textiles and is the direct responsibility of Subcommittee [D13.13](#) on Wool and Felt.

Current edition approved June 1, 2022. Published July 2022. Originally approved in 1966. Last previous edition approved in 2013 as D2524 – 13 which was withdrawn in January 2022 and reinstated in June 2022. DOI: 10.1520/D2524-22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

that any program of acceptance testing be preceded by an interlaboratory check in the laboratory of the purchaser and the laboratory of the seller on replicate specimens of samples of the material to be evaluated. In cases of dispute, the statistical bias, if any, between the laboratory of the purchaser and the seller should be determined with each comparison being based on testing randomized specimens from one sample of material of the type being evaluated.

5.2 Values obtained from flat bundle tenacity show a good correlation with values obtained from single fiber tests and require much less time.

5.3 The basic differences between the procedures described in Test Method D2524 and those described in Test Method D1294 lie in the manner of clamping the bundles and the shorter gage length employed. The special clamps used in this method allow quicker and easier bundle preparation; however, for Test Method D1294 no special clamps are required. Closer agreement with single fiber tenacity is also obtained with Test Method D2524 than when using the procedure in Test Method D1294.

5.4 As the observed tenacity of fibers depends in part on the type of tensile testing machine used and the time required to break the specimen, results obtained with the different types of machines which may be used in this method will not necessarily agree. The machines specifically designed for bundle testing are CRL testers which operate at a loading rate of 1 kgf/s and therefore reach the breaking force at variable times in the order of 5 s. CRE and CRT type machines would be expected to produce somewhat different results not only because of the inherent difference in operation but because CRE and CRT type machines are to be operated at a rate to achieve the breaking load in 20 s.

## 6. Apparatus and Materials

6.1 *Tensile Testing Machine*, having a capacity of at least 7 kgf (70 N), equipped to accommodate the specified flat bundle clamps. For CRL testing machines,<sup>4</sup> the rate of loading is specified as 1 kgf/s (10 N/s). For CRE and CRT machines, select a rate of operation which will reach the breaking force in an average time of  $20 \pm 3$  s.

6.1.1 In case the CRE or CRT testing machine is not capable of operating as specified in 6.1, select a rate so as to reach the breaking force in an average time as close to 20 s as possible and report the average time to break.

NOTE 2—There may be no overall correlation between the results obtained with the CRE, CRT or CRL type testing machines. Consequently, these three machines cannot be used interchangeably.

6.2 *Balance*, suitable for weighing 2 mg to 6 mg with a sensitivity of 0.02 mg.

6.3 *Flat Bundle Clamps and Accessories*, including the following components:

<sup>4</sup> The sole source of supply for the Stelometer known to the committee at this time is Special Instruments Laboratory, Inc., 312 W. Vine St., Knoxville, TN 37901. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend. The Clemson Tester (no longer available) have been found satisfactory for this purpose.

NOTE 3—Pressley clamps and accessories have been found satisfactory for this purpose.<sup>5</sup> Adapters to fit the clamps to various tensile testing instruments are also available or can be fabricated.

6.3.1 *Clamps*, having a total thickness of 0.465 in.  $\pm$  0.001 in. (11.8 mm  $\pm$  0.03 mm) and a 0.125 in.  $\pm$  0.001 in. (3.2 mm  $\pm$  0.03 mm) spacer.

6.3.2 *Clamp Vise*, with a device to indicate approximately 8 lbf-in. (0.9 N·m) torque.

6.3.3 *Clamp Wrench*.

6.4 *Coarse Comb*, approximately 8 teeth per in. (3 per 10 mm).

6.5 *Fine Comb*, approximately 50 teeth per in. (20 per 10 mm).

6.6 *Black Paper*, to hold bundles.

6.7 *Shearing Knife or Razor Blade*.

6.8 *Tweezers*.

6.9 *Torque Wrench or Friction Disk Wrench*, to indicate approximately 8 lbf-in. (0.9 N·m) torque (optional).

6.10 *Standard Wool Top Sample*<sup>6</sup>, having an assigned breaking tenacity of 11.4 gf/tex (112 mN/tex).

NOTE 4—The standard wool top sample, USDA Lot 58-27, has a breaking tenacity (based on single fiber tests) of 11.4 gf/tex  $\pm$  0.6 gf/tex, at the 95 % probability level.

## 7. Sampling

7.1 *Division into Lots*—Treat a single shipment of a single fiber type as a lot.

7.2 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of shipment containers directed in an applicable material specification or other agreement between the purchaser and the supplier, such as an agreement to use Practice D2525. Consider shipping containers to be the primary sampling units.

7.3 *Laboratory Sample*—For acceptance testing, take a laboratory sample from each shipping container in the lot sample as follows:

7.3.1 For loose fiber, grease, and scoured wool, reduce the mass of clean fiber submitted for testing to approximately 15 g by randomly selecting pieces throughout the mass. Form into a loose sliver by hand.

7.3.2 For card sliver and top, cut a length of sliver about 20 in. (500 mm) long from each ball submitted for testing.

7.3.3 For roving, cut a length about 20 in. (500 mm) long from each spool submitted for testing and include all ends.

<sup>5</sup> The sole source of supply of the apparatus known to the committee at this time is J. M. Doebrich and Co., P. O. Box 2789, Tucson, AZ 85702. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>6</sup> The sole source of supply of the apparatus known to the committee at this time is the Wool and Mohair Laboratory, Livestock and Seed Division, AMS, U.S. Department of Agriculture, 711 "O" Street, Greeley, CO 80631. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

7.4 *Test Specimens*—Scour or solvent-extract the laboratory sample until residual contamination is 1 % or less of the laboratory mass, as established by further cleaning of a part of the laboratory sample. From each unit in the laboratory sample, prepare five test specimens as directed in 10.1.

## 8. Preparation, Calibration, and Verification of Apparatus

8.1 *Tensile Testing Machine*—Check the calibration of the instrument according to the manufacturer’s instruction.

8.2 *Balance*—Check the zero reading and the sensitivity in the range to be used.

## 9. Preconditioning and Conditioning

9.1 Bring the laboratory sample to moisture equilibrium for testing in the standard atmosphere for testing as directed in Practice D1776.

## 10. Preparation of Specimens

10.1 Prepare each specimen by drawing small groups of fibers from at least five locations in a unit of the laboratory sample. Parallelize and combine them in a bundle which may be held conveniently between the thumb and forefinger. Depending on fiber entanglement, take a sufficient number of fibers so that, after combining, an aligned specimen of 2 mg to 6 mg is available for testing.

10.2 Grasp the tuft about one-fourth the distance from the end of the tuft with the thumb and forefinger or a fiber hand vise<sup>7</sup> and comb the protruding end with the coarse comb to remove loose fibers and foreign material and to secure partial parallelization of the fibers. Reverse the tuft and repeat the combing on the other end.

10.3 Grasp the partially parallelized tuft at both ends using the fingers of one hand, thumb and ring finger holding one end and middle and index fingers holding the other end. Complete the parallelization of the fibers in the tuft by combing with the fine comb; with each pass of the comb release the end of the tuft toward which the comb is moving and grasp again immediately after the comb passes the holding position. To avoid moisture transfer from fingers to fibers, do not handle the middle section of the tuft. If the specimen is estimated to be too heavy, remove fibers during the combing operation from either side with the tip of the comb to obtain the correct specimen size. The specimen is now ready to be placed in the clamps.

## 11. Procedure

11.1 Test the conditioned specimens in the standard atmosphere for testing.

11.2 Inspect the leather faces of the clamps frequently to ensure that they are in good condition. Keep the inner edges of

the leathers trimmed flush with the metal surfaces and replace the leathers as soon as grooves become evident to the touch.

11.3 Place the parallelized specimen (10.3) in the clamps in the following manner: Using a Pressley type vise, lock the clamps with a 1/8 in. (3.2 mm) spacer separating the clamps of the vise and open the jaws of the clamps. Hold both ends of the specimen as directed in 10.3, keeping the specimen approximately 1/4 in. (6 mm) wide, and place it in the central part of the open clamps. Maintain sufficient tension on the specimen to hold the fibers straight while the jaws of the clamps are lowered and tightened in place by applying an 8 lbf-in. (0.9 N·m) torque. The torque may be controlled by either a vise-mounted, torque-indicating instrument or by a friction disk wrench.

11.4 Remove the clamps from the vise. Shear off the protruding ends of the specimen with the shearing knife or razor blade, cutting downward and away from the leather face of the clamps and flush with the surface.

11.5 Insert the loaded clamps in the tensile testing machine and break the test specimen in accordance with the manufacturer’s instructions. For other than the special instruments designed specifically for flat bundle testing, operate the test instrument as directed in 6.1.

11.6 After the specimen has been broken, record the breaking force to the nearest scale or chart reading. Remove the clamps from the instrument and place the clamps in the vise. Check to see that all fibers are broken. If all the fibers are not broken, are broken irregularly indicating some slippage of fibers in the clamps, or if the breaking force is less than the required minimum for the instrument used, discard the specimen and make a new test. If the break is acceptable, open the clamps, collect all the broken fibers with tweezers, and weigh to the nearest 0.02 mg (Note 5). To avoid gain in weight from moisture pickup, do not touch the fibers with the fingers while collecting and weighing the specimen.

NOTE 5—If desired, the broken specimens may be stored temporarily in the standard atmosphere for testing in folded black papers and weighed later.

11.7 Make a check test on a standard sample each day before making other tests and repeat the check after every ten samples to check the level of testing results. Calculate and record for each operator a correction factor based on results secured in tests made on the standard sample. Maintain a separate record of each operator’s correction factors and use, as the operator’s norm, the average of the last five factors to correct the next ten tests (Note 6). If a correction factor is observed that differs by more than 5 % from the established norm, reject the factor and examine the instrument and technique carefully. Make any indicated adjustments to either the instrument or the technique and make a new test on the standard sample. If an abnormal factor is observed for the second time, establish a new factor to correct the results observed on specimens of unknown samples by averaging the two factors obtained from tests on the standard sample before and after the tests on the unknowns. Continue to use the two

<sup>7</sup> The sole source of supply of the apparatus known to the committee at this time suitable for this purpose is the hand vise supplied with the Suter Sorter wool fiber stapling apparatus. Available from the Alfred Suter Co., Inc., Prel Plaza, Orangeburg, NY 10962. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.