



Designation: ~~E2664 – 16~~ E2664 – 22

Standard Test Method Practice for Methanol Wall Wash of Marine Vessels Handling Polyester Grade Monoethylene Glycol¹

This standard is issued under the fixed designation E2664; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the methanol wall wash procedure and the chemical and physical analysis of the wall wash sampling for cargo tanks of marine vessels handling polyester grade monoethylene glycol. The key sections for the wall wash procedure and test methods appear in the following order:

Wall Wash Procedure
Appearance
Color
Hydrocarbons
Chloride

Sections
~~7 and 8~~
~~9–11~~
~~12–14~~
~~15–17~~
~~18–21~~

1.2 The values given in SI units are to be considered as the standard. No other units of measurement are included in this standard.

1.3 Review the current Safety Data Sheet (SDS) for detailed information concerning toxicity, first aid procedures and safety precautions.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. For specific hazard statements, see Section 6.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- ~~D1193 Specification for Reagent Water~~
- ~~D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)~~
- ~~D1722 Test Method for Water Miscibility of Water-Soluble Solvents~~
- ~~D4176 Test Method for Free Water and Particulate Contamination in Distillate Fuels (Visual Inspection Procedures)~~
- ~~D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry~~

¹ This test method practice is under the jurisdiction of ASTM Committee D16 on Aromatic, Industrial, Specialty and Related Chemicals and is the direct responsibility of Subcommittee D16.14 on Alcohols & Glycols.

Current edition approved Jan. 1, 2016/July 15, 2022. Published February 2016/July 2022. Originally approved in 2009. Last previous edition approved in 2009/2016 as E2664 – 09a/16. DOI: ~~10.1520/E2664-16~~ 10.1520/E2664-22.

*A Summary of Changes section appears at the end of this standard

~~E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³~~
~~E2469 Test Method for Chloride in Mono-, Di- and Tri-ethylene Glycol by Ion Chromatography~~
~~E2680 Test Method for Appearance of Clear, Transparent Liquids (Visual Inspection Procedure)~~

~~3. Significance and Use~~

~~3.1 The methanol wall wash test is performed to determine the cleanliness and suitability of cargo tanks or compartments on a marine vessel prior to loading polyester grade monoethylene glycol. Polyester grade monoethylene glycol has very high quality requirements and must be handled with care, as it is adversely affected by oxygen, hydrocarbons, water and chloride. It is especially susceptible to aromatic contamination, which degrades UV transmittance. Possible sources of contamination are the prior cargoes and cleaning agents. The methanol wall wash procedure provides a representative sampling of the impurities and contamination present on the sides of the cargo tank.~~

~~3.2 The test methods used for analysis of the methanol wall wash samples are capable of determining low levels of impurities or contamination in methanol. These tests include appearance, color, hydrocarbons and chloride. The producers of polyester grade monoethylene glycol need confirmation of the cleanliness and suitability of the marine vessel's tanks prior to loading with in-specification material. Cargo tanks that do not pass the wall wash test should not be loaded.~~

~~3.3 Alternative test methods and technology for several of the methods can be found in the Appendix. The alternative test methods do not have precision data for the application of these methods in analyzing methanol. Use of these methods is optional and individuals using the alternative methods should assure themselves that the method is sufficiently precise. Precision data is only for the original test methods listed.~~

~~4. Purity of Reagents~~

~~4.1 Purity of Reagents—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society (ACS) where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.~~

~~4.2 High-Purity Water—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type II of Specification [D1193](#). It is recommended that all water be filtered through a 0.2- μ m filter.~~

~~4.3 Methanol, ACS reagent grade with very low concentrations of chloride.~~

~~Note 1—Chloride in high purity methanol used for preparation of the chloride working standards should not exceed 0.01 mg/kg. This information should be provided by the supplier or determined by the analyst before use.~~

~~5. Quality Control~~

~~5.1 It is recommended that a control chart for the concentration of chloride in a methanol wall wash quality control sample be established and maintained according to common guidelines.⁵ Measure the control sample each time a test sample(s) is tested. If the measured value exceeds the action limit of the control chart, take appropriate action before proceeding with sample tests.~~

~~6. Hazards~~

~~6.1 Each analyst must be acquainted with the potential hazards of the equipment, reagents, products, solvents and procedures before beginning laboratory work. Sources of information include: operation manuals, SDS, literature, and other related data. Safety information should be requested from the supplier. Disposal of waste materials, reagents, reactants, and solvents must be in compliance with laws and regulations from all applicable governmental agencies.~~

~~6.2 Methanol is a flammable and toxic substance. Methanol is absorbed through the skin and by breathing the vapors. Be careful when handling a flammable solvent and work in a well-ventilated area away from sources of ignition. Use the proper Personal Protective Equipment (PPE) to minimize exposure.~~

METHANOL WALL WASH

7. Procedure

7.1 All equipment must be clean and rinsed with reagent grade, low chloride methanol to prevent chloride contamination of the sample.

7.2 Pour approximately 1 L of reagent grade, low chloride methanol into a 1-L plastic squeeze bottle.

7.3 Use a plastic funnel that has been cut flat on one side to catch the methanol. The funnel and 1-L sample bottle should be rinsed with reagent grade, low chloride methanol immediately before sampling.

7.4 Clean, chemical resistant gloves and eye protection should be worn for personal protection and to prevent contamination of the samples.

7.5 Do not test wet areas of a cargo tank. The tank must be dry before conducting the wall wash tests. The tank is not acceptable for testing if wet areas are more than a few spots.

7.6 Choose two sites on each tank wall (bulkhead) approximately 15 to 20 cm wide and as high as possible (approximately 2 m high). Start spraying methanol on the wall with the spray bottle approximately 15 cm from the wall. Collect the methanol with the special funnel into a clean 1-L glass bottle with the funnel placed at least 0.3 to 0.6 m below the spray. Continue spraying methanol while moving down the wall until approximately 0.6 m from the bottom. Use approximately 200 mL of methanol on each of the four sides of the tank. Be consistent with the spraying and collecting of the methanol. Do not scrap the tank wall with the funnel when collecting the methanol.

7.7 Include “non-typical” areas, such as discolored patches, lining breaks and exposed metal. If the “non-typical” areas are less than 20 % of the tank surface, include them in the four areas normally tested. If they are more than 20 % of the tank surface, test them separately.

<https://standards.iteh.ai/catalog/standards/sist/006f05e0-e4ea-4a90-aced-5cbc506d3be4/astm-e2664-22>

7.8 Test separately any areas having crystalline deposits.

7.9 Collect the methanol from the four sides of a tank into the same sample bottle. Cap the bottle, label from which cargo tank it was taken and transport to the laboratory for analysis.

7.10 Include a sample of the methanol used in the wall wash procedure. This is the analytical “blank”. This methanol will be analyzed with the tank samples and the results of the “blank” will be subtracted from each tank’s wall wash sample’s results.

8. Analysis

8.1 The methanol wall wash samples shall be analyzed for the following:

1. Appearance	Clear and bright (pass)
2. Color	10 Pt/Co, maximum
3. Hydrocarbons	None by test (pass)
4. Chloride	0.5 mg/kg, maximum

8.2 If the container needs to be cleaned further, a sample of the water used to do the cleaning may be sampled for chlorides. The water should contain less than 0.2 mg/kg chlorides.

APPEARANCE

9. Procedure

9.1 Determine the appearance of the sample in accordance with Test Method ~~E2680~~ for visual clarity and particulate contamination.

9.2 Allow the sample to equilibrate to room temperature (or to the storage temperature or the temperature at which the sample is used) prior to visual inspection. A temperature-controlled water bath can be used to bring the sample to the desired temperature if measurements must be made at a specific temperature according to product specifications.

9.3 When using a water bath, replace the sample container's cap with an airtight closure through which a calibrated temperature-sensing device is immersed in the sample. Periodically agitate the sample in a manner sufficient to homogenize the bulk of the sample. Remove the sample container from the water bath and wipe dry. Remove the temperature-sensing device and replace the original cap before proceeding with the visual inspection.

9.4 Hold the sample up to a bright light source and visually examine the sample at arm's length for clarity, suspended matter (any foreign matter that does not float or settle to the bottom of the bottle) and any free water (or oil) droplets or layers.

9.5 Swirl the sample gently to form a vortex and avoid formation of bubbles. Examine the bottom of the vortex at arm's length for particulate matter (any foreign material that settles to the bottom of the bottle) and free water (or oil).

10. Report

10.1 Report the following information:

10.1.1 Report the appearance as "Pass" if the visual clarity was found to be "Clear and Bright" with no more than the maximum number of particles of suspended matter no greater than 1 mm in diameter and no free water (or oil) were found and the particulate matter had no particulates of sufficient size and quantity to be easily noted at the bottom of the vortex. See ~~Table 1~~.

10.1.2 Report the appearance as "Fail" if the visual clarity as found to be "Not Clear and Bright" with more than the maximum number of particles of suspended matter greater than 1 mm in diameter and/or free water (or oil) were found and/or particulate matter was found with particulates of sufficient size and quantity to be easily noted at the bottom of the vortex. See ~~Table 1~~.

11. Precision and Bias

11.1 No information is presented about either the precision or bias of Test Method ~~E2680~~ since the test result is nonquantitative.

COLOR

12. Procedure

12.1 Determine the color of the sample in accordance with Test Method ~~D5386~~ for near clear liquids using an instrument with color measurements converted to the platinum-cobalt system (Pt-Co).

13. Report

13.1 Report the following information:

13.1.1 Report the color for an instrumental Pt-Co measurement to the nearest whole unit.

14. Precision and Bias

14.1 The following criteria should be used to judge the acceptability of results (see ~~Note 2~~):

~~14.1.1 Repeatability (Single Analyst)—The precision of the procedure for measuring color will be determined.~~

~~14.1.2 Laboratory Precision (Within-Laboratory, Between-Days Variability)—The precision of the procedure for measuring color will be determined.~~

~~14.1.3 Reproducibility (Multi-Laboratory)—The precision of the procedure for measuring color will be determined.~~

~~Note 2—The equations in Practice E180 will be used in developing the precision estimates.~~

~~14.2 Bias—The bias of this test method cannot be determined because no referee method or reference standard is available to determine the true value.~~

HYDROCARBONS

15. Procedure

~~15.1 Determine the presence of water-immiscible materials (hydrocarbons) in the sample in accordance with Test Method D1722. This is a qualitative test.~~

16. Report

~~16.1 Report the following information:~~

~~16.1.1 If the sample water mixture has no hydrocarbon layer and is as free of cloudiness or turbidity as the blank, report the sample as “passes” test. If any cloudiness, turbidity or a hydrocarbon layer is detected after 30 min, report as “fails” test.~~

17. Precision and Bias

~~17.1 No information is presented about either precision or bias of this test method since the test result is non-quantitative and is reported as pass or fail.~~

[ASTM E2664-22](https://standards.iteh.ai/catalog/standards/sist/006f05e0-e4ea-4a90-aced-5cbc506d3be4/astm-e2664-22)

<https://standards.iteh.ai/catalog/standards/sist/006f05e0-e4ea-4a90-aced-5cbc506d3be4/astm-e2664-22>

CHLORIDE

18. Procedure

~~18.1 Determine the concentration of chloride in the sample in accordance with Test Method E2469 by ion chromatography (IC). An IC system with Carbonate-Based Eluent should produce a separation of chloride equivalent to or better than that shown in Fig. 1.~~

~~18.1.1 The chloride working standards should be prepared in methanol. The methanol used to prepare the chloride working standards should not exceed 0.01 mg/kg of chloride (see 4.3).~~

~~18.1.2 The methanol wall wash sample should be analyzed without dilution. It is recommended that each sample be analyzed in duplicate and the average result reported.~~

19. Report

~~19.1 Report the following information:~~

~~19.1.1 Report the concentration of chloride in the methanol wall wash sample to the nearest 0.01 mg/kg.~~

~~19.1.2 A correction should be made to each wall wash sample if chloride is found in the methanol analytical “blank” submitted with the samples.~~

20. Precision and Bias⁶

20.1 The following criteria should be used to judge the acceptability of results (see [Note 3](#)):

20.1.1 *Repeatability (Single Analyst)*—The standard deviation for a single determination has been estimated to be the value given in [Table 2](#) at the indicated degrees of freedom. The 95 % limit of difference between two such runs is also given in [Table 2](#).

20.1.2 *Laboratory Precision (Within-Laboratory, Between-Days Variability)*—The precision of the procedure for measuring chloride will be determined.

20.1.3 *Reproducibility (Multi-Laboratory)*—The precision of the procedure for measuring chloride will be determined.

Note 3—The precision statements are preliminary based on six analyses by one analyst on two days of two samples of methanol containing approximately 0.1 mg/kg and 0.5 mg/kg chloride. An interlaboratory study is planned for 2008/2009. The equations in Practice [E180](#) will be used in developing the precision estimates.⁷

20.2 Bias:

20.2.1 The bias of this test method was determined by spiking two samples of methanol with chloride standard at the 0.1 mg/kg and 0.5 mg/kg levels and analyzing the spiked samples six times on two days. The recovery (accuracy) and standard deviation are estimated to be the values given in [Table 3](#) based on a linear fit of the calibration curve. The bias depends upon the accuracy of the calibration, weighing of the spike and the extent of any interferences.⁷

21. Linearity⁶

21.1 Peak area response for chloride was found to be linear for the Bottled Carbonate Eluent over the range of 0.01 to 1.0 mg/kg.⁷

22. Keywords

22.1 appearance; chloride; color; hydrocarbons; methanol; polyester grade monoethylene glycol; wall wash

<https://standards.iteh.ai/catalog/standards/sist/006f05e0-e4ea-4a90-aced-5cbc506d3be4/astm-e2664-22>

APPENDIX

X1. ALTERNATIVE TEST METHODS

X1.1 *Scope*—Listed in [Table X1.1](#) are alternative test methods and technology for several of the test methods. The alternative test methods do not have precision data for the application of these methods in analyzing methanol. Use of these methods is optional and individuals using the alternative methods should assure themselves that the method is sufficiently precise. Precision data presented is only for the original test methods listed.

SUMMARY OF CHANGES

Subcommittee E15.02 has identified the location of selected changes to this standard since the last issue (E2644-09a) that may impact the use of this standard.

(1) 7.6 and 8.1 were revised.

(2) 8.2 was deleted and subsequent section was renumbered.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

1. Scope*

1.1 This practice covers the methanol wall wash procedure for cargo tanks of marine vessels handling polyester grade monoethylene glycol.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. For specific hazard statements, see Section 7.

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

[E1547 Terminology Relating to Industrial and Specialty Chemicals](#)

2.2 Other Documents:

[OSHA Regulations, 29 CFR, paragraphs 1910.1000 and 1910.1200 Toxic and Hazardous Substances — Air contaminants; Hazard Communication³](#)

<https://standards.iteh.ai/catalog/standards/sist/006f05e0-e4ea-4a90-aced-5cbc506d3be4/astm-e2664-22>

3. Terminology

3.1 See Terminology [E1547](#) for definitions of terms used in this practice.

4. Significance and Use

4.1 The methanol wall wash practice is performed to determine the cleanliness and suitability of cargo tanks or compartments on a marine vessel prior to loading polyester grade monoethylene glycol. Polyester grade monoethylene glycol has very high quality requirements and must be handled with care, as it is adversely affected by oxygen, hydrocarbons, water, and chloride. It is especially susceptible to aromatic contamination, which degrades UV transmittance. Possible sources of contamination are the prior cargoes and cleaning agents. The methanol wall wash procedure provides a representative sampling of the impurities and contamination present on the sides of the cargo tank.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society (ACS) where

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org. Available from Superintendent of Documents, U.S. Government Printing Office, 732 N. Capitol St. NW, Mail Stop: SDE, Washington, DC 20401.