



## Designation: A1007 – 22

# Standard Specification for Carbon Steel Wire for Wire Rope<sup>1</sup>

This standard is issued under the fixed designation A1007; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers uncoated and metallic coated classes of round, cold-drawn, carbon steel wire for wire rope in five strength levels. This specification specifies:

- 1.1.1 Dimensional tolerances,
- 1.1.2 Mechanical characteristics,
- 1.1.3 Chemical composition requirements,
- 1.1.4 Coating requirements (if applicable), and
- 1.1.5 Packaging requirements.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 This specification incorporates provisions from other publications. These normative references are cited at their appropriate place in the text and the publications are listed.

#### 2.2 ASTM Standards:<sup>2</sup>

**A90/A90M Test Method for Weight [Mass] of Coating on Iron and Steel Articles with Zinc or Zinc-Alloy Coatings**

**A510/A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel**

**A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment**

**A902 Terminology Relating to Metallic Coated Steel Products**

**A938 Test Method for Torsion Testing of Wire**

**A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys**

**B6 Specification for Zinc**

**B750 Specification for GALFAN (Zinc-5 % Aluminum-Mischmetal) Alloy in Ingot Form for Hot-Dip Coatings**

**B899 Terminology Relating to Non-ferrous Metals and Alloys**

**B997 Specification for Zinc-Aluminum Alloys in Ingot Form for Hot-Dip Coatings**

**E8/E8M Test Methods for Tension Testing of Metallic Materials**

**IEEE/ASTM-SI-10 American National Standard for Metric Practice**

#### 2.3 Industry Standard:

**API 9A Specification for Wire Rope<sup>3</sup>**

### 3. Terminology

3.1 *Definitions*—For definitions of terms used in this standard, refer to Terminologies **B899**, **A902**, and **A941**.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *actual diameter, n*—the arithmetic mean of the minimum and maximum diameter measurements in one location on the wire.

3.2.2 *breaking strength level (Levels 1,2,3,4 or 5), n*—a wire strength based on the minimum load carrying capability of a designated wire.

3.2.3 *drawn-metallic coated, n*—a pure zinc, Zn-5Al-MM (Type 5), Type 10, or Type 15 coating that is applied to the wire prior to the final cold drawing operation by either an electro-deposition or hot-dipping process.

3.2.4 *final-metallic coated, n*—a pure zinc, Zn-5Al-MM (Type 5), Type 10, or Type 15 coating that is applied to the wire after the final cold drawing operation by either an electro-deposition or hot-dipping process.

3.2.5 *nominal diameter, n*—the diameter of the wire expressed in inches (millimeters) and specified by the user to designate the wire size. It is the basis for the determination of the values of all characteristics of the wire for acceptance purposes.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.03** on Steel Rod and Wire.

Current edition approved Aug. 1, 2022. Published August 2022. Originally approved in 2000. Last previous edition approved in 2015 as A1007 – 15. DOI: 10.1520/A1007-22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American Petroleum Institute (API), 1220 L. St., NW, Washington, DC 20005-4070, <http://api.org>.

3.2.6 *ovality*, *n*—the arithmetic difference between the maximum diameter and the minimum diameter in one location on the wire.

3.2.7 *uncoated wire*, *n*—the surface of a carbon steel wire furnished with a residual lube film as a result of cold-drawing said wire.

#### 4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements shall include, but are not limited to the following:

- 4.1.1 Quantity (mass),
- 4.1.2 Name of material (drawn steel wire for wire rope),
- 4.1.3 Wire type (uncoated, drawn-metallic coated, or final-metallic coated),
- 4.1.4 Wire diameter,
- 4.1.5 Wire strength grade (Level 1 through 5),
- 4.1.6 Packaging (Section 15),
- 4.1.7 Cast or heat analysis; if requested,
- 4.1.8 Certification or test report; if requested, and
- 4.1.9 ASTM designation and date of issue.

#### 5. Materials and Manufacture

5.1 The base metal rod used in the manufacture of rope wire shall be made by any commercially accepted steel making process as specified by A510/A510M.

5.2 A sufficient discard shall be made to ensure freedom from detrimental piping and undue segregation.

5.3 The wire shall be cold-drawn to produce the desired properties.

5.4 The wire shall be furnished in one of the specified types:

- 5.4.1 Uncoated,
- 5.4.2 Drawn-metallic coated, and
- 5.4.3 Final-metallic coated.

5.5 The method utilized in the production of either drawn- or final-galvanized wire types may be by an electro-deposition or hot-dip galvanizing process at the option of the producer.

5.5.1 The slab zinc used in galvanized zinc coatings shall be as specified in Specification B6.

5.6 The method utilized in the production of Zn-5Al-MM (Type 5), Type 10, or Type 15 wire types may be either a continuous hot-dip metallic coating or two step coating where the first coating is zinc followed by a final bath having up to the

allowable aluminum content, as specified in B750 or B997, to prevent the depletion of aluminum within the bath during the coating process.

5.6.1 The bath metal used in continuous hot-dip Zn-5Al-MM (Type 5) metallic coating shall meet the chemical composition limits specified in Specification B750 or B997.

5.6.2 The bath metal used in continuous hot-dip Type 10 or Type 15 metallic coating shall meet the chemical composition limits specified in Specification B997.

#### 6. Chemical Composition

6.1 Upon agreement with the purchaser, the wire manufacturer shall supply a steel of suitable chemical composition that will satisfy the properties of the material ordered.

6.2 A quantitative analysis of each cast or heat shall be made by the steel producer or their representative to determine the percentage of the elements specified. The analysis shall be made from a test sample preferably taken during the pouring of the cast or heat. The chemical composition thus determined shall be reported, if required, to the purchaser or their representative.

6.3 An analysis may be made by the purchaser from the finished wire. The chemical composition thus determined as to the elements required shall conform to the product analysis requirements specified in Table 3 of Specification A510/A510M or as agreed upon between the purchaser and the manufacturer.

#### 7. Wire Diameter

7.1 The wire shall be measured using a micrometer with a minimum accuracy of 0.0001 in. (0.002 mm) for all diameters.

7.2 All diameter values measured in one location along the wire shall be within the tolerance limits given in Table 1 for uncoated and drawn-metallic coated rope wire or Table 2 for final-metallic coated rope wire.

7.3 The measured ovality shall not be greater than half the tolerance limits specified in Table 1 for uncoated and drawn-metallic coated rope wire or Table 2 for final-metallic coated rope wire.

#### 8. Tensile Properties

##### 8.1 Tensile Test Procedure:

8.1.1 *Standard Testing Method*—The tensile test shall be carried out in accordance with Test Methods E8/E8M. The distance between the grips of the testing machine shall not be

TABLE 1 Wire Diameter Tolerances Uncoated and Drawn-Metallic Coated Rope Wire

Diameter Range, in.	Diameter Range, mm	Tolerance, in.		Tolerance, mm	
		Minus	Plus	Minus	Plus
Up to 0.010 incl.	Up to 0.25 incl.	0.0003	0.0005	0.008	0.013
Over 0.010 to 0.025 incl.	Over 0.25 to 0.64 incl.	0.0003	0.0007	0.008	0.018
Over 0.025 to 0.060 incl.	Over 0.64 to 1.52 incl.	0.0005	0.001	0.013	0.025
Over 0.060 to 0.093 incl.	Over 1.52 to 2.36 incl.	0.001	0.001	0.025	0.025
Over 0.093 to 0.142 incl.	Over 2.36 to 3.61 incl.	0.001	0.0015	0.025	0.038
Over 0.142 to 0.200 incl.	Over 3.61 to 5.08 incl.	0.0015	0.002	0.038	0.051
Over 0.200 to 0.250 incl.	Over 5.08 to 6.35 incl.	0.002	0.002	0.051	0.051



TABLE 2 Wire Diameter Tolerances Final-Metallic Coated Rope Wire

Diameter Range, in.	Diameter Range, mm	Tolerance, in.		Tolerance, mm	
		Minus	Plus	Minus	Plus
Up to 0.025 incl.	Up to 0.64 incl.	0.0007	0.0007	0.018	0.018
Over 0.025 to 0.061 incl.	Over 0.64 to 1.55 incl.	0.001	0.001	0.025	0.025
Over 0.061 to 0.079 incl.	Over 1.55 to 2.01 incl.	0.002	0.002	0.051	0.051
Over 0.079 to 0.142 incl.	Over 2.01 to 3.61 incl.	0.003	0.003	0.076	0.076
Over 0.142 to 0.250 incl.	Over 3.61 to 6.35 incl.	0.004	0.004	0.102	0.102

less than 8 in. (203 mm). The speed of the movable head of the testing machine, under no load, shall not exceed 1 in./min (0.4 mm/s). Any specimen breaking within 1 in. (25.4 mm) of the jaws may be disregarded and a retest performed.

8.1.2 *Alternate Testing Method*—The tensile test shall be carried out in accordance with Test Methods E8/E8M. The loading rate may be greater than that specified, depending on the number of tests to be carried out for the batch inspection. However, it shall not exceed the rate corresponding to a 25 % elongation between anchorages in 1 min. The minimum distance between the clamping jaws of the test machine is 4 in. (102 mm). In the event of a dispute, the tensile test shall be carried out strictly in accordance with Test Methods E8/E8M, in particular with regard to the loading rate.

8.1.3 The minimum breaking strengths are specified in Table 3 of this specification, for uncoated and metallic coated

wire grade Levels 1 through 5. The range in breaking strength for a given grade level is based on the calculated minimum tensile strength requirement (psi). While no maximum values are shown for breaking strength, rope wire is produced to a tensile strength range of 30 000 psi unless an alternative is agreed upon between the purchaser and producer. The resultant minimum breaking strength of uncoated and drawn-metallic coated wires of various levels shall meet or exceed the values shown in Table 3. The resultant minimum breaking strength for final-metallic coated wire is obtained by reducing the value stated for its level in Table 3 for uncoated wire by 10 %. Minimum breaking strength and torsional values for wire diameters not specified within Table 3 shall be agreed upon between the purchaser and producer.

TABLE 3 Minimum Rope Wire Breaking Strengths and Torsional Values

Wire Diameter			Minimum Torsional Values (Number of Twists in 8 in.)					Minimum Breaking Strength <sup>A</sup>								
in.	mm	Level 1	Level 2	Level 3	Level 4	Level 5	Level 1 lbf	Level 1 N	Level 2 lbf	Level 2 N	Level 3 lbf	Level 3 N	Level 4 lbf	Level 4 N	Level 5 lbf	Level 5 N
0.010	0.254	274	254	234	218	190	16	70	17	80	20	90	22	100	24	110
0.011	0.279	249	231	213	196	173	18	90	21	100	24	110	27	120	29	130
0.012	0.305	228	212	195	182	158	22	100	25	120	29	130	32	150	31	160
0.013	0.330	211	196	180	168	146	26	120	29	140	34	150	37	170	41	180
0.014	0.356	196	181	167	156	136	31	140	34	160	39	180	43	200	45	210
0.015	0.381	182	169	156	145	126	36	180	39	180	45	200	49	220	53	240
0.016	0.406	171	156	146	136	118	40	180	41	200	51	230	56	250	60	270
0.017	0.432	161	149	137	126	111	48	200	50	230	57	260	63	290	68	300
0.018	0.457	152	141	130	121	105	50	230	53	250	64	290	71	320	76	340
0.019	0.483	144	133	123	114	100	56	250	62	260	72	320	79	360	85	380
0.020	0.508	136	126	116	108	94	60	280	69	310	79	360	87	390	94	420
0.021	0.533	130	120	111	103	90	68	310	73	340	87	390	96	430	100	450
0.022	0.559	124	115	106	96	86	75	340	83	360	96	430	110	490	110	490
0.023	0.584	118	110	101	94	82	80	370	91	410	100	450	120	540	120	540
0.024	0.610	113	105	97	90	78	85	400	100	450	110	490	130	580	130	580
0.025	0.635	109	101	93	86	75	90	430	110	490	120	540	140	630	150	670
0.026	0.660	105	97	89	83	72	100	450	115	540	130	560	150	670	160	720
0.027	0.686	101	93	86	80	70	110	490	125	580	140	630	160	720	170	730
0.028	0.711	97	90	83	77	67	120	540	130	580	150	670	170	760	180	810
0.029	0.737	94	87	80	74	65	130	580	140	630	170	760	180	810	200	890
0.030	0.762	90	84	77	72	62	140	630	150	670	180	810	190	850	210	940
0.031	0.787	86	81	75	69	60	150	670	160	720	190	850	210	940	220	960
0.032	0.813	85	78	72	67	56	160	720	180	810	200	890	220	980	240	1070
0.033	0.838	82	76	70	65	57	170	780	190	850	210	940	240	1070	250	1130
0.034	0.864	80	74	68	63	55	180	810	200	890	230	1030	250	1120	270	1210
0.035	0.889	77	72	66	61	53	190	860	210	940	240	1070	260	1160	280	1250
0.036	0.914	75	70	64	60	52	200	890	220	960	250	1120	280	1250	300	1340
0.037	0.940	73	68	62	58	50	210	940	230	1030	270	1210	300	1340	320	1430
0.038	0.965	71	66	61	56	49	220	960	250	1120	280	1250	310	1360	330	1470
0.039	0.991	69	64	59	55	48	230	1030	260	1160	300	1340	330	1470	350	1560
0.040	1.02	67	62	57	53	46	240	1070	270	1210	310	1360	340	1520	370	1650
0.041	1.04	66	61	56	52	45	250	1160	290	1290	330	1470	360	1610	390	1740
0.042	1.07	64	59	55	51	44	270	1210	300	1340	340	1520	380	1700	410	1830
0.043	1.09	63	58	53	50	43	280	1250	310	1380	360	1610	400	1780	430	1920
0.044	1.12	61	57	52	48	42	300	1340	330	1470	380	1700	420	1870	450	2010
0.045	1.14	60	56	51	47	41	310	1360	340	1520	390	1740	430	1920	470	2100
0.046	1.17	58	54	50	46	40	320	1430	360	1610	410	1830	450	2010	490	2130
0.047	1.19	57	53	49	45	39	340	1530	370	1650	430	1920	470	2100	510	2270

TABLE 3 *Continued*

Wire Diameter			Minimum Torsional Values (Number of Twists in 8 in.)					Minimum Breaking Strength <sup>A</sup>								
in.	mm	Level 1	Level 2	Level 3	Level 4	Level 5	Level 1 lbf	Level 1 N	Level 2 lbf	Level 2 N	Level 3 lbf	Level 3 N	Level 4 lbf	Level 4 N	Level 5 lbf	Level 5 N
0.048	1.22	56	52	48	44	36	350	1560	390	1740	450	2010	490	2180	540	2350
0.049	1.24	55	51	47	43	36	370	1560	410	1830	470	2100	510	2270	550	2450
0.050	1.27	54	50	46	42	37	380	1700	420	1870	490	2180	530	2380	570	2500
0.051	1.30	53	49	45	42	36	400	1760	440	1960	500	2230	560	2500	610	2670
0.052	1.32	52	48	44	41	36	410	1830	480	2050	520	2320	580	2580	620	2730
0.053	1.35	51	47	43	40	36	430	1920	470	2100	540	2410	600	2670	640	2850
0.054	1.37	50	46	42	39	34	440	1960	490	2180	580	2500	620	2780	660	2990
0.055	1.40	49	45	41	38	33	460	2050	510	2270	590	2630	640	2850	690	3070
0.056	1.42	48	44	41	36	33	470	2100	530	2360	610	2720	670	2990	720	3200
0.057	1.45	47	43	40	37	32	490	2180	550	2450	630	2810	690	3070	740	3300
0.058	1.47	46	43	39	36	32	510	2270	570	2540	650	2900	720	3210	770	3430
0.059	1.50	45	42	36	36	31	530	2360	580	2580	670	2990	740	3300	790	3520
0.060	1.52	44	41	38	35	30	540	2410	600	2670	690	3070	760	3390	810	3550
0.061	1.55	44	40	37	35	30	560	2500	620	2760	720	3210	790	3520	850	3790
0.062	1.57	43	40	37	34	29	580	2580	640	2850	740	3300	810	3610	830	3923
0.063	1.60	42	39	36	33	29	600	2670	660	2940	760	3390	840	3740	930	4310
0.064	1.63	42	38	36	33	28	620	2760	690	3070	790	3520	870	3870	930	4140
0.065	1.65	41	38	35	32	28	640	2850	710	3160	810	3610	890	3980	960	4283
0.066	1.68	40	37	34	32	28	660	2940	730	3250	840	3740	920	4100	990	4410
0.067	1.70	40	37	34	31	27	670	2990	750	3340	860	3830	950	4230	1000	4540
0.068	1.73	39	36	33	31	27	690	3070	770	3430	890	3960	980	4360	1060	4630
0.069	1.75	38	36	33	30	26	710	3160	790	3520	910	4050	1000	4450	1080	4810
0.070	1.78	38	35	32	30	26	730	3250	820	3650	940	4190	1030	4590	1110	4940
0.071	1.80	37	35	32	29	26	760	3390	840	3740	970	4320	1080	4720	1140	5080
0.072	1.83	37	34	31	29	25	780	3470	880	3830	990	4410	1090	4850	1170	5200
0.073	1.85	36	34	31	29	25	800	3580	890	3960	1020	4540	1120	4990	1210	5360
0.074	1.88	36	33	30	28	24	820	3650	910	4050	1050	4680	1150	5120	1240	5600
0.075	1.91	35	33	30	28	24	840	3740	930	4140	1070	4760	1180	5250	1270	5680
0.076	1.93	35	32	30	27	24	860	3830	960	4280	1100	4900	1210	5390	1300	5790
0.077	1.96	34	32	29	27	23	890	3960	980	4380	1130	5030	1240	5520	1340	5900
0.078	1.98	34	31	29	27	23	910	4080	1010	4500	1160	5160	1280	5700	1370	6100
0.079	2.01	33	31	28	26	23	930	4140	1030	4590	1190	5300	1310	5830	1410	6300
0.080	2.03	33	30	28	26	22	950	4230	1080	4720	1230	5430	1340	5970	1440	6400
0.081	2.06	33	30	28	26	22	960	4260	1090	4850	1250	5570	1370	6100	1480	6500
0.082	2.08	32	30	27	25	22	1000	4460	1110	4960	1280	5700	1410	6280	1510	0000
0.083	2.11	32	29	27	25	22	1020	4500	1140	5080	1310	5830	1440	6410	1550	0000
0.084	2.13	31	29	27	25	21	1050	4680	1160	5160	1340	5970	1470	6540	1580	7030
0.085	2.16	31	29	26	24	21	1070	4760	1190	5300	1370	6100	1510	6720	1620	7210
0.086	2.18	31	28	26	24	21	1100	4800	1220	5430	1400	6230	1540	6660	1660	7390
0.087	2.21	30	28	26	24	21	1120	4990	1250	5570	1430	6370	1580	7030	1700	7570
0.088	2.24	30	28	25	23	20	1150	5120	1270	5650	1470	6540	1610	7170	1730	7700
0.089	2.26	30	27	25	23	20	1170	5210	1300	5790	1500	6660	1650	7340	1770	7880
0.090	2.29	29	27	25	23	20	1200	5340	1330	5920	1530	6610	1680	7480	1810	8080
0.091	2.31	29	27	24	23	20	1220	5430	1360	6050	1560	6940	1720	7660	1850	8230
0.092	2.34	28	26	24	22	19	1250	5670	1390	6190	1600	7120	1760	7830	1890	8410
0.093	2.36	28	26	24	22	19	1280	5700	1420	6320	1630	7260	1790	7970	1930	8590
0.094	2.39	28	26	24	22	19	1300	5790	1450	6450	1670	7430	1830	8150	1970	8770
0.095	2.41	28	25	23	22	19	1330	5920	1480	6590	1700	7570	1870	8320	2010	8900
0.096	2.44	27	25	23	21	18	1360	6050	1510	6720	1740	7740	1910	8500	2050	9130
0.097	2.46	27	25	23	21	18	1390	6190	1540	6880	1770	7880	1950	8680	2090	9300
0.098	2.49	27	25	23	21	18	1410	6280	1570	6990	1810	8060	1990	8860	2140	9529
0.099	2.51	26	24	22	21	18	1440	6410	1600	7120	1840	8190	2030	9030	2180	9700
0.100	2.54	26	24	22	20	18	1470	6540	1630	7260	1880	8370	2070	9210	2220	9880
0.101	2.57	26	24	22	20	18	1500	6580	1680	7390	1910	8500	2110	9390	2260	10 000
0.102	2.59	26	24	22	20	17	1530	6810	1700	7570	1950	8680	2150	9570	2310	10 210
0.103	2.62	25	23	21	20	17	1560	6940	1730	7700	1990	8860	2190	9750	2360	10 410
0.104	2.64	25	23	21	20	17	1580	7030	1760	7830	2030	9030	2230	9920	2390	10 610
0.105	2.67	25	23	21	19	17	1610	7170	1790	7970	2080	9170	2270	10 100	2440	10 810
0.106	2.69	25	23	21	19	17	1640	7300	1830	8150	2100	9350	2310	10 280	2480	11 010
0.107	2.72	24	22	21	19	16	1670	7430	1860	8280	2140	9520	2350	10 460	2530	11 280
0.108	2.74	24	22	20	19	16	1700	7570	1890	8410	2180	9700	2400	10 680	2580	11 430
0.109	2.77	24	22	20	19	16	1730	7700	1930	8590	2220	9880	2440	10 860	2620	11 630
0.110	2.79	24	22	20	18	16	1770	7880	1960	8720	2260	10 060	2480	11 040	2670	11 830
0.111	2.82	23	22	20	18	16	1800	8010	2000	8900	2300	10 240	2530	11 260	2710	12 050
0.112	2.84	23	21	20	18	16	1830	8150	2030	9030	2340	10 410	2570	11 440	2760	12 230
0.113	2.87	23	21	19	18	15	1880	8280	2070	9210	2380	10 590	2610	11 610	2810	12 500
0.114	2.90	23	21	19	18	15	1890	8410	2100	9350	2420	10 770	2660	11 840	2860	12 730
0.115	2.92	22	21	19	18	15	1920	8550	2140	9620	2480	10 950	2700	12 020	2910	12 950
0.116	2.95	22	21	19	17	15	1960	8720	2170	9660	2500	11 130	2750	12 240	2950	13 130
0.117	2.97	22	20	19	17	15	1990	8860	2210	9840	2540	11 300	2790	12 420	3000	13 350
0.118	3.00	22	20	18	17	15	2020	8960	2240	9970	2580	11 480	2840	12 640	3050	13 670
0.119	3.02	22	20	18	17	15	2050	9120	2290	10 150	2620	11 660	2890	12 880	3100	13 790

TABLE 3 *Continued*

Wire Diameter			Minimum Torsional Values (Number of Twists in 8 in.)					Minimum Breaking Strength <sup>A</sup>									
in.	mm	Level 1	Level 2	Level 3	Level 4	Level 5	Level 1		Level 2		Level 3		Level 4		Level 5		
							Ibf	N	Ibf	N	Ibf	N	Ibf	N	Ibf	N	
0.120	3.05	21	20	18	17	14	2090	9300	2320	10 320	2670	11 880	2930	13 040	3150	14 030	
0.121	3.07	21	20	18	17	14	2120	9440	2360	10 500	2710	12 080	2960	13 260	3200	14 210	
0.122	3.10	21	19	18	17	14	2150	9570	2390	10 640	2750	12 240	3030	13 480	3250	14 160	
0.123	3.12	21	19	18	16	14	2190	9750	2430	10 610	2800	12 460	3070	13 660	3310	14 730	
0.124	3.15	21	19	18	16	14	2220	9660	2470	10 990	2840	12 640	3120	13 880	3360	14 950	
0.125	3.18	21	19	17	16	14	2260	10 080	2510	11 170	2880	12 820	3170	14 110	3410	15 170	
0.126	3.20	20	19	17	16	14	2290	10 190	2550	11 360	2930	13 040	3220	14 330	3460	15 200	
0.127	3.23	20	19	17	16	14	2330	10 370	2580	11 480	2970	13 220	3270	14 550	3510	15 320	
0.128	3.25	20	18	17	16	13	2360	10 500	2620	11 600	3020	13 440	3320	14 770	3570	15 390	
0.129	3.28	20	18	17	16	13	2400	10 660	2680	11 840	3080	13 620	3370	15 000	3620	16 110	
0.130	3.30	20	18	17	15	13	2430	10 610	2700	12 020	3110	13 640	3420	15 220	3670	16 330	
0.131	3.33	20	18	17	15	13	2470	10 990	2740	12 190	3150	14 020	3470	15 440	3730	16 800	
0.132	3.35	19	18	16	15	13	2500	11 130	2780	12 370	3200	14 240	3490	15 660	3780	16 830	
0.133	3.38	19	18	16	15	13	2540	11 300	2820	12 550	3250	14 480	3545	15 890	3840	17 090	
0.134	3.40	19	18	16	15	13	2580	11 460	2860	12 730	3290	14 640	3620	16 110	3890	17 310	
0.135	3.43	19	17	16	15	13	2610	11 610	2900	12 900	3340	14 860	3670	16 330	3950	17 580	
0.136	3.45	19	17	16	15	13	2650	11 790	2940	13 080	3390	15 080	3720	16 550	4000	17 800	
0.137	3.48	19	17	16	15	13	2690	11 970	2990	13 310	3430	15 260	3780	16 820	4080	18 060	
0.138	3.51	18	17	16	14	12	2720	12 100	3030	13 480	3480	15 480	3830	17 040	4120	18 330	
0.139	3.53	18	17	15	14	12	2760	12 260	3070	13 660	3530	15 710	3880	17 260	4170	18 560	
0.140	3.56	18	17	15	14	12	2800	12 460	3110	13 840	3580	15 630	3940	17 530	4230	18 820	
0.141	3.58	18	17	15	14	12	2840	12 640	3150	14 020	3630	16 150	3990	17 750	4290	19 090	
0.142	3.61	18	17	15	14	12	2880	12 820	3200	14 240	3680	16 370	4040	17 980	4350	19 360	
0.143	3.63	18	16	15	14	12	2910	12 950	3240	14 420	3720	16 550	4100	18 240	4400	19 680	
0.144	3.66	18	16	15	14	12	2960	13 130	3260	14 600	3770	16 770	4150	18 470	4460	19 840	
0.145	3.68	18	16	15	14	12	2990	13 310	3330	14 820	3820	17 000	4210	18 730	4620	20 110	
0.146	3.71	17	16	15	14	12	3030	13 480	3370	15 000	3870	17 220	4280	18 950	4680	20 380	
0.147	3.73	17	16	15	13	12	3070	13 880	3410	15 170	3920	17 440	4320	19 220	4640	20 640	
0.148	3.76	17	16	14	13	11	3110	13 840	3480	15 400	3960	17 710	4370	19 440	4700	20 910	
0.149	3.78	17	16	14	13	11	3150	14 020	3500	15 570	4030	17 930	4430	19 710	4760	21 180	
0.150	3.81	17	16	14	13	11	3190	14 190	3550	15 800	4080	18 150	4490	19 980	4820	21 450	
0.151	3.84	17	15	14	13	11	3230	14 370	3590	15 970	4130	18 380	4540	20 200	4880	21 710	
0.152	3.86	17	15	14	13	11	3270	14 550	3640	16 200	4180	18 800	4600	30 470	4940	21 980	
0.153	3.89	17	15	14	13	11	3310	14 730	3680	16 370	4230	18 820	4660	20 730	5010	22 290	
0.154	3.91	16	15	14	13	11	3350	14 910	3730	18 800	4290	19 090	4710	20 980	5070	22 580	
0.155	3.94	16	15	14	13	11	3400	15 130	3770	16 770	4340	19 310	4770	21 220	5130	22 830	
0.156	3.96	16	15	14	13	11	3440	15 310	3820	17 000	4390	19 630	4830	21 490	5190	23 090	
0.157	3.99	16	15	14	13	11	3480	15 480	3880	17 180	4440	19 760	4890	21 750	5260	23 400	
0.158	4.01	16	15	14	13	12	3520	15 880	3910	17 400	4490	20 030	4950	22 020	5320	23 670	
0.159	4.04	16	15	14	13	12	3560	15 840	3980	17 620	4550	20 240	5010	22 290	5380	23 940	
0.160	4.06	16	14	13	12	10	3600	16 020	4010	17 840	4610	20 510	5070	22 560	5450	24 250	
0.161	4.09	16	14	13	12	10	3650	16 240	4050	18 020	4660	20 730	5130	22 820	5510	24 510	
0.162	4.11	16	14	13	12	10	3690	16 420	4100	18 240	4720	21 000	5190	23 090	5580	24 830	
0.163	4.14	15	14	13	12	10	3730	16 600	4150	18 470	4770	21 220	5250	23 360	5840	25 090	
0.164	4.17	15	14	13	12	10	3780	16 820	4200	18 690	4830	21 490	5310	23 630	5710	25 400	
0.165	4.19	15	14	13	12	10	3820	17 000	4240	18 870	4880	21 710	5370	23 890	5770	25 870	
0.166	4.22	15	14	13	12	10	3880	17 180	4290	19 090	4940	21 980	5430	24 160	5840	25 680	
0.167	4.24	15	14	13	12	10	3910	17 400	4340	19 310	4990	22 200	5490	24 430	5900	26 250	
0.168	4.27	15	14	13	12	10	3950	17 580	4390	19 530	5050	22 470	5560	24 690	5970	26 560	
0.169	4.29	15	14	12	12	10	4000	17 800	4440	19 760	5110	22 740	5620	25 000	6040	26 870	
0.170	4.32	15	14	12	11	10	4040	17 980	4490	19 980	5180	22 960	5660	25 270	6100	27 140	
0.171	4.34	15	13	12	11	10	4080	18 150	4540	20 200	5220	23 220	5740	25 540	6170	27 450	
0.172	4.37	15	13	12	11	10	4130	18 380	4590	20 420	5280	23 490	5800	25 800	6240	27 760	
0.173	4.39	14	13	12	11	10	4170	18 550	4640	20 640	5330	23 710	5870	26 120	6310	28 070	
0.174	4.42	14	13	12	11	10	4220	18 780	4690	20 870	5390	23 980	5930	26 380	6380	28 380	
0.175	4.45	14	13	12	11	9	4270	19 000	4740	21 090	5450	24 250	6000	26 690	6450	28 700	
0.176	4.47	14	13	12	11	9	4310	19 180	4790	21 310	5510	24 510	6060	26 960	6510	28 960	
0.177	4.50	14	13	12	11	9	4360	19 400	4840	21 530	5570	24 780	6120	27 230	6580	29 270	
0.178	4.52	14	13	12	11	9	4400	19 580	4890	21 780	5630	25 050	6190	27 540	6650	29 590	
0.179	4.55	14	13	12	11	9	4450	19 800	4940	21 980	5690	25 320	6250	27 810	6720	29 900	
0.180	4.57	14	13	12	11	9	4500	20 020	5000	22 250	5750	25 580	6320	28 120	6790	30 210	
0.181	4.60	14	13	12	11	9	4540	20 200	5050	22 470	5810	25 850	6390	28 430	6860	30 620	
0.182	4.62	14	13	11	11	9	4590	20 420	5100	22 690	5870	26 120	6450	28 700	6940	30 880	
0.183	4.65	14	12	11	11	9	4640	20 640	5150	22 910	5930	26 380	6520	29 010	7010	31 190	
0.184	4.67	13	12	11	10	9	4680	20 820	5210	23 180	5990	26 650	6580	29 270	7060	31 500	
0.185	4.70	13	12	11	10	9	4730	21 050	5260	23 400	6050	26 920	6650	29 590	7150	31 810	
0.186	4.72	13	12	11	10	9	4780	21 270	5310	23 630	6110	27 180	6720	29 900			