



Designation: C616/C616M – 22

Standard Specification for Quartz-Based Dimension Stone¹

This standard is issued under the fixed designation C616/C616M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of quartz-based dimension stone for general building and structural purposes. Refer to Guides [C1242](#) and [C1528](#) for the appropriate selection and use of quartz-based dimension stone.

1.2 Quartz-based dimension stone shall include stone that is sawed, cut, split, or otherwise finished or shaped, and shall specifically exclude molded, cast, or otherwise artificially aggregated units composed of fragments, and also crushed and broken stone.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C97/C97M Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone](#)

[C99/C99M Test Method for Modulus of Rupture of Dimension Stone](#)

[C119 Terminology Relating to Dimension Stone](#)

[C170/C170M Test Method for Compressive Strength of Dimension Stone](#)

[C241/C241M Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic](#)

[C1242 Guide for Selection, Design, and Installation of Dimension Stone Attachment Systems](#)

[C1353 Test Method for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic Using a Rotary Platform Abraser](#)

[C1528 Guide for Selection of Dimension Stone](#)

3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology [C119](#).

4. Classification

4.1 Quartz-based dimension stone sandstone shall be classified according to the free silica content as follows:

4.1.1 *I Sandstone*, with 60 % minimum free silica content.³

4.1.2 *II Quartzitic Sandstone*, with 90 % minimum free silica content.

4.1.3 *III Quartzite*, with 95 % minimum free silica content.

5. Physical Properties

5.1 Quartz-based dimension stone supplied under this specification shall conform to the physical requirements in [Table 1](#).

5.2 Quartz-based dimension stone shall be sound, durable, and free of spalls, cracks, open seams, pits, or other defects that are likely to impair its structural integrity in its intended use.

5.3 The desired color and texture, with their permissible natural variations in material characteristics for all material to be produced for the project, shall be established by control samples. Select representative samples by viewing a sufficient number of physical samples prior to production that show the complete range of variations in color and texture of the quartz-based dimension stone specified.

6. Sampling

6.1 Samples, if required, for testing to determine the characteristics and physical properties shall be representative of the quartz-based dimension stone to be used.

³ Free silica consists of detrital quartz grains plus authigenic silica.

¹ This specification is under the jurisdiction of ASTM Committee [C18](#) on Dimension Stone and is the direct responsibility of Subcommittee [C18.03](#) on Material Specifications.

Current edition approved Aug. 1, 2022. Published September 2022. Originally approved in 1968. Last previous edition approved in 2015 as C616/C616M – 15. DOI: 10.1520/C0616_C0616M-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Physical Requirements

NOTE 1—The values in Table 1 were established using samples prepared according to the individual test methods. Finishes, other than those specified in the individual test methods, may result in a deviation from established values.

Property	Test Requirements	Classifications	Test Method(s)
Absorption by weight, max, %	8	I Sandstone	C97/C97M
	3	II Quartzitic Sandstone	
	1	III Quartzite	
Density, min, lb/ft ³ [kg/m ³]	125 [2000]	I Sandstone	C97/C97M
	150 [2400]	II Quartzitic Sandstone	
	160 [2560]	III Quartzite	
Compressive strength, min, psi (MPa)	4000 [28]	I Sandstone	C170/C170M
	10000 [69]	II Quartzitic Sandstone	
	20000 [140]	III Quartzite	
Modulus of rupture min, psi (MPa)	350 [2.4]	I Sandstone	C99/C99M
	1000 [6.9]	II Quartzitic Sandstone	
	2000 [13.8]	III Quartzite	
Abrasion resistance, min H _a ^A	2 ^B	I Sandstone	C241/C241M/C1353
	8	II Quartzitic Sandstone	
	8	III Quartzite	

^A Pertains only to stone subject to foot traffic.

^B Not recommended for paving in areas subject to heavy foot traffic.

7. Keywords

7.1 ashlar; Bluestone; Quartzite; Sandstone

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

<https://standards.iteh.ai/catalog/standards/sist/a65b5df4-ec5a-43d4-a8ce-5a247f0a5539/astm-c616-c616m-22>