



Designation: **C361M—19** C361M – 22

## Standard Specification for Reinforced Concrete Low-Head Pressure Pipe (Metric)<sup>1</sup>

This standard is issued under the fixed designation C361M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers reinforced concrete pipe intended to be used for the construction of pressure pipelines with low internal hydrostatic heads generally not exceeding 375 kPa.

1.2 This specification is the SI companion to Specification C361. It is compatible in technical content.

NOTE 1—Field tests on completed portions of the pipeline are not covered by this specification for the manufacture of the pipe but should be included in specifications for pipe laying.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- A27/A27M Specification for Steel Castings, Carbon, for General Application
- A36/A36M Specification for Carbon Structural Steel
- A82/A82M Specification for Steel Wire, Plain, for Concrete Reinforcement (Withdrawn 2013)<sup>3</sup>
- A185/A185M Specification for Steel Welded Wire Reinforcement, Plain, for Concrete (Withdrawn 2013)<sup>3</sup>
- A283/A283M Specification for Low and Intermediate Tensile Strength Carbon Steel Plates
- A496/A496M Specification for Steel Wire, Deformed, for Concrete Reinforcement (Withdrawn 2013)<sup>3</sup>
- A497/A497M Specification for Steel Welded Wire Reinforcement, Deformed, for Concrete (Withdrawn 2013)<sup>3</sup>
- A575 Specification for Steel Bars, Carbon, Merchant Quality, M-Grades
- A576 Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality
- A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
- A675/A675M Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality, Mechanical Properties
- A1008/A1008M Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, Required Hardness, Solution Hardened, and Bake Hardenable
- A1011/A1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.04 on Low Head Pressure Pipe.

Current edition approved July 15, 2019/Sept. 1, 2022. Published July 2019/September 2022. Originally approved in 1978. Last previous edition approved in 2016/2019 as C361M – 16/C361M – 19. DOI: 10.1520/C0361M-19.10.1520/C0361M-22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field  
C33/C33M Specification for Concrete Aggregates  
C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens  
C150/C150M Specification for Portland Cement  
C260/C260M Specification for Air-Entraining Admixtures for Concrete  
C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete  
C497M Test Methods for Concrete Pipe, Concrete Box Sections, Manhole Sections, or Tile (Metric)  
C595/C595M Specification for Blended Hydraulic Cements  
C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete  
C822 Terminology Relating to Concrete Pipe and Related Products  
C1602/C1602M Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete  
C1619 Specification for Elastomeric Seals for Joining Concrete Structures  
D698 Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400 ft-lbf/ft<sup>3</sup> (600 kN-m/m<sup>3</sup>))  
D4253 Test Methods for Maximum Index Density and Unit Weight of Soils Using a Vibratory Table  
D4254 Test Methods for Minimum Index Density and Unit Weight of Soils and Calculation of Relative Density

#### 2.2 Other Standard:

ACI Code 318 Standard Building Code Requirements for Reinforced Concrete<sup>4</sup>  
AISI-C1012<sup>5</sup>

### 3. Terminology

3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology C822.

### 4. Classification

4.1 Pipe manufactured according to this specification shall be for hydrostatic heads of 75, 150, 225, 300, and 375 kPa measured to the centerline of the pipe. Designs are provided in Table 1 and Table 2 for the above hydrostatic heads combined with external loadings of 1.5, 3.0, 4.5, and 6.0 m (designated A, B, C, and D in Table 1 and Table 2) of earth cover over the top of the pipe under specific installation conditions. The specific installation conditions are covered in Appendix X1. Where the hydrostatic head, external loadings, and installation conditions vary from those given in Table 1 and Table 2 and Appendix X1, detailed design calculations shall be made. The design criteria for Table 1 and Table 2 are presented in Appendix X2.

### 5. Basis of Acceptance

<https://standards.iteh.ai/catalog/standards/sist/f54e5741-b331-4a6b-963b-1a1b5bfb3f66/astm-c361m-22>  
5.1 Acceptability of the pipe in all diameters and classes shall be determined by the results of such material tests as are required in 6.2 through 6.9 by crushing tests on cured concrete cylinders, by hydrostatic pressure tests on units of the pipe, by joint leakage tests, and by inspection during or after manufacture to determine whether the pipe conforms to this specification as to design and freedom from defects.

5.2 *Age for Acceptance*—Pipe shall be considered ready for acceptance when they conform to the requirements, as indicated by the specified tests.

### 6. Materials

6.1 *Reinforced Concrete*—The reinforced concrete shall consist of portland cement, mineral aggregates, and water, in which steel has been embedded in such a manner that the steel and concrete act together. Fly ash or pozzolan is not prohibited when used as a partial cement replacement; see 9.1.

#### 6.2 Cementitious Materials:

##### 6.2.1 Cement:

6.2.1.1 *Portland Cement*—Portland cement shall conform to the requirements of Specification C150/C150M.

<sup>4</sup> Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

<sup>5</sup> Available from the American Iron and Steel Institute (AISI), 1140 Connecticut Ave. NW, Suite 705, Washington D.C. 20036, <http://www.steel.org>.

**TABLE 1 Design Requirements for Reinforced Concrete Low-Head Pressure Pipe [300 to 3650 mm Diameter], Concrete Design Strength 34.5 MPa (except as noted) Steel Reinforced Yield Strength 276 MPa**

NOTE 1—See Appendix for specific installation conditions and design criteria conditions required in conjunction with the use of Table 1.

NOTE 2—Designations A, B, C, and D, for class of pipe, denote 1.5, 3.0, 4.5, and 6.0 m of earth cover over top of pipe. Figures 150, Figures 225, etc. for class of pipe, denote hydrostatic pressure heads in kilopascals measured to centerline of pipe.

NOTE 3—An “s” in place of a steel area indicates the pipe class is a special design requiring stirrup reinforcement. Stirrups may be eliminated by changing wall thickness, main reinforcement, concrete strength, or a combination thereof.

NOTE 4—The boldfaced value denotes 41.4 MPa concrete strength required.

Internal Designated Dia., mm	Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>															
	300		375		450		525		600		675					
	Type of Reinforcement		Type of Reinforcement		Type of Reinforcement		Type of Reinforcement		Type of Reinforcement		Type of Reinforcement					
Wall Thickness, mm	50	75	50	75	57	75	60	75	63	75	66	79	82	107	66	82
Layers of Reinforcement	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Inner	Outer	Single
Class	140	220	200	280	250	320	320	290	390	350	460	410	290	200	230	370
A-75	170	230	310	380	390	420	480	500	540	540	740	650	440	280	340	460
B-75	220	280	420	500	540	570	690	690	870	870	1060	890	590	350	450	740
C-75	360	270	540	390	700	540	910	730	1150	950	1430	1170	750	440	560	1060
D-75	220	220	280	270	350	320	430	390	510	480	600	550	390	300	330	1430
A-150	270	230	380	320	480	420	600	530	740	660	880	780	540	370	430	780
B-150	340	280	500	390	630	520	800	680	990	860	1190	1030	690	450	540	880
C-150	420	330	620	470	790	640	1020	840	1280	1070	1570	1310	850	530	650	1190
D-150	340	340	430	430	520	520	600	600	690	690	770	770	490	400	430	1570
A-225	340	340	460	430	580	520	710	640	860	780	1020	920	640	470	520	350
B-225	400	340	570	470	720	620	910	790	1110	980	1330	1170	790	550	630	390
C-225	480	390	700	550	880	730	1130	950	1400	1200	1710	1440	940	630	730	440
D-225	490	490	610	610	730	730	860	860	980	980	1100	1100	590	500	590	480
A-300	490	490	610	610	730	730	860	860	980	980	1160	1100	590	500	590	510
B-300	490	490	610	610	730	730	860	860	980	980	1160	1100	590	500	590	510
C-300	490	490	610	610	730	730	860	860	980	980	1160	1100	590	500	590	510
D-300	540	490	770	620	980	820	1240	1050	1530	1320	1850	1580	1040	730	820	570
A-375	650	650	820	820	980	980	1140	1140	1310	1310	1470	1470	790	680	780	690
B-375	650	650	820	820	980	980	1140	1140	1310	1310	1470	1470	790	680	780	690
C-375	650	650	820	820	980	980	1140	1140	1310	1310	1470	1470	790	680	780	690
D-375	650	650	850	820	1070	980	1350	1160	1650	1450	1990	1720	1140	830	910	670

**TABLE 1 Continued**

Internal Designated Dia, mm	Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																	
	750						825											
	Circular						Circular											
Type of Reinforcement	Circular			Elliptical			Circular			Elliptical								
Wall Thickness, mm	82		88		119		82		94		119							
Layers of Reinforcement	Single	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Single	Single					
Class	530	490	340	230	320	220	250	170	530	410	610	72	79	82	94	119	72	94
A-75	530	490	340	230	320	220	250	170	530	410	610	72	79	82	94	119	72	94
B-75	880	790	530	340	490	310	370	220	880	490	1020	1020	950	400	340	440	270	610
C-75	1260	1110	720	440	660	400	490	280	1260	660	1490	1490	1360	530	440	580	440	1020
D-75	1750	1470	920	550	840	490	600	330	1750	840	1940	1940	1850	670	540	720	400	1490
A-150	680	640	450	350	430	330	350	270	870	870	780	740	740	400	360	400	310	950
B-150	1030	940	640	450	600	420	470	320	1030	870	1190	1120	1120	520	460	550	380	1190
C-150	1420	1260	830	550	770	500	580	370	1420	870	1660	1660	1530	650	550	680	440	1660
D-150	1900	1630	1030	650	940	600	700	430	1900	940	2110	2020	2020	780	660	820	510	2110
A-225	860	860	560	460	530	440	470	390	860	870	950	950	950	520	470	520	430	950
B-225	1180	1100	750	560	700	520	570	420	1180	870	1360	1290	1290	640	570	650	480	1360
C-225	1570	1410	940	660	870	610	680	470	1570	940	1830	1700	1700	770	670	790	550	1830
D-225	2060	1780	1130	760	1040	700	800	520	2060	940	2280	2190	2190	900	770	930	610	2280
A-300	1220	1220	670	570	660	560	660	560	1220	1340	1340	1340	1340	640	620	730	620	1340
B-300	1340	1250	860	670	810	630	690	540	1340	1460	1530	1460	1460	760	690	760	590	1530
C-300	1730	1570	1040	760	980	720	780	570	1730	1870	2000	1870	1870	890	780	900	660	2000
D-300	2210	1930	1240	870	1150	810	890	620	2210	2360	2450	2360	2360	1020	880	1030	720	2450
A-375	1630	1630	870	760	870	760	870	760	1630	1800	1800	1800	1800	830	840	960	840	1800
B-375	1630	1630	970	780	920	740	900	730	1630	1800	1800	1800	1800	890	800	990	800	1800
C-375	1880	1720	1150	870	1080	820	930	710	1880	2040	2170	2040	2040	1010	900	1020	780	2170
D-375	2360	2090	1340	980	1250	910	990	720	2360	2530	2620	2530	2530	1140	990	1140	830	2620

**TABLE 1 Continued**

Internal Designated Dia., mm		Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																						
		900						975 <sup>C</sup>						1050										
Type of Reinforcement	Wall Thickness, mm	Circular						Circular						Circular										
		82			100			125			79			100			79			100				
Layers of Reinforcement	Single	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	
		A-75	670	460	320	380	260	330	220	670	490	340	420	290	360	240	530	530	520	360	450	310	390	270
B-75	1130	740	480	600	380	490	300	1130	600	510	650	410	540	330	790	650	850	540	710	450	590	370	850	710
C-75	1650	1030	640	800	480	640	370	1650	800	680	870	530	710	420	1090	870	1160	720	940	570	780	460	1160	940
D-75	<b>2150</b>	1330	800	1010	600	800	450	<b>2150</b>	1010	860	1100	650	880	500	1410	1100	1500	910	1190	710	970	550	1500	1190
A-150	850	590	450	510	390	440	340	1040	1040	480	550	420	480	370	1130	1130	670	510	590	450	530	400	1210	1210
B-150	1320	870	610	720	500	610	420	1320	1040	650	780	540	660	460	1130	1130	990	690	840	580	730	500	1210	1210
C-150	1840	1150	760	920	610	760	490	1840	1040	810	1000	660	830	540	1220	1130	1300	860	1080	710	910	590	1300	1210
D-150	<b>2330</b>	1450	930	1130	720	910	570	<b>2330</b>	1130	990	1230	780	1000	620	1540	1230	1630	1050	1330	840	1100	680	1630	1330
A-225	1040	720	580	630	510	570	460	...	...	620	680	550	620	500	...	...	810	650	730	590	670	540	...	...
B-225	1500	1000	740	840	620	720	530	...	...	780	910	670	790	580	...	...	1130	830	980	720	860	630	...	...
C-225	2030	1280	890	1040	730	870	610	...	...	950	1130	790	950	660	...	...	1440	1000	1210	850	1040	720	...	...
D-225	<b>2520</b>	1580	1060	1250	840	1030	680	...	...	1120	1350	910	1130	750	...	...	1760	1180	1460	980	1230	820	...	...
A-300	1470	860	720	800	670	790	670	...	...	760	860	730	860	730	...	...	960	800	930	780	930	780	...	...
B-300	1690	1130	870	960	740	840	650	...	...	920	1040	800	910	710	...	...	1270	980	1120	860	990	770	...	...
C-300	2210	1400	1020	1160	850	990	720	...	...	1080	1250	920	1080	790	...	...	1580	1150	1350	980	1170	850	...	...
D-300	<b>2700</b>	1700	1180	1370	960	1140	800	...	...	1250	1480	1040	1250	870	...	...	1900	1320	1590	1110	1360	950	...	...
A-375	1960	1050	910	1050	910	1050	910	...	...	980	1140	980	1140	990	...	...	1230	1060	1230	1060	1230	1060	...	...
B-375	1960	1260	1000	1090	870	1090	870	...	...	1060	1180	940	1180	950	...	...	1420	1120	1270	1010	1270	1020	...	...
C-375	2400	1530	1150	1280	970	1110	850	...	...	1220	1380	1050	1210	920	...	...	1720	1290	1480	1120	1300	990	...	...
D-375	<b>2890</b>	1820	1310	1480	1080	1250	910	...	...	1390	1600	1160	1370	990	...	...	2030	1460	1720	1250	1490	1080	...	...

**TABLE 1 Continued**

Internal Designated Dia., mm		Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																		
		1125 <sup>C</sup>						1200						1275 <sup>C</sup>						
Type of Reinforcement	Wall Thickness, mm	Circular			Elliptical			Circular			Elliptical			Circular			Elliptical			
		Inner	Outer	Layers of Reinforcement	Inner	Outer	Single	Inner	Outer	Layers of Reinforcement	Inner	Outer	Single	Inner	Outer	Layers of Reinforcement	Inner	Outer	Single	
	97	97	119	144	97	119	104	125	144	104	125	104	125	107	132	150	107	132	107	132
	1280	1650	1000	1290	770	1060	610	1020	860	1380	1790	620	1380	1790	1080	1410	840	1210	710	1950
	1080	1420	940	1160	990	1190	610	1020	860	1380	1790	620	1380	1790	1080	1410	840	1210	710	1950
	1790	1150	1150	1420	910	1190	610	1020	860	1380	1790	620	1380	1790	1080	1410	840	1210	710	1950
	880	710	780	630	480	570	610	430	290	430	570	610	430	290	430	570	610	430	290	430
	1230	900	1050	770	930	680	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1570	1090	1300	910	1130	780	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1930	1300	1560	1050	1330	880	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1040	860	1000	840	1000	840	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1380	1060	1200	920	1070	830	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1720	1240	1440	1050	1270	920	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	2070	1440	1700	1190	1470	1020	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1320	1130	1320	1130	1310	1140	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1540	1210	1360	1090	1360	1090	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	1860	1400	1590	1200	1410	1060	610	540	400	540	680	930	680	540	400	540	680	930	680	540
	2220	1590	1840	1330	1600	1160	610	540	400	540	680	930	680	540	400	540	680	930	680	540

**TABLE 1 Continued**

Internal Designated Dia., mm	Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																				
	1350						1425 <sup>C</sup>						1500								
	Circular			Elliptical			Circular			Elliptical			Circular			Elliptical					
Type of Reinforcement	Circular			Elliptical			Circular			Elliptical			Circular			Elliptical					
Wall Thickness, mm	113	138		157		113	138		119	144		163		125	150		169		125	150	
Layers of Reinforcement	Inner	Outer	Inner	Outer	Inner	Single	Single	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single
Class	710	480	610	410	560	380	740	740	740	740	510	640	440	600	400	780	780	780	780	820	820
A-75	1140	730	940	590	840	520	1140	940	1190	760	990	630	890	560	1190	990	1240	1240	1240	1040	1040
B-75	1580	980	1270	770	1120	670	1580	1270	1650	1030	1340	820	1200	720	1650	1340	1730	1730	1730	1420	1420
C-75	2030	1240	1590	950	1400	820	2030	1590	2120	1290	1690	1010	1490	880	2120	1690	2210	2210	2210	1790	1790
D-75	890	670	780	590	730	550	1560	1560	930	700	830	620	770	580	1640	1640	980	980	980	730	730
A-150	1320	910	1110	760	1010	690	1560	1560	1370	950	1170	810	1070	730	1640	1640	1430	1430	1430	850	850
B-150	1740	1150	1430	940	1280	840	1740	1560	1820	1210	1520	1000	1370	890	1820	1640	1910	1910	1910	1450	1450
C-150	2190	1410	1760	1120	1560	980	2190	1760	2290	1470	1860	1180	1660	1050	2290	1860	2380	2380	2380	1760	1760
D-150	1070	850	950	760	900	720	...	...	1120	890	1010	800	950	760	...	...	1170	1170	1170	800	800
A-225	1490	1090	1280	940	1170	860	...	...	1550	1140	1340	990	1240	910	...	...	1620	1620	1620	1030	1030
B-225	1910	1330	1600	1110	1450	1000	...	...	2000	1390	1690	1170	1540	1070	...	...	2090	2090	2090	1430	1430
C-225	2350	1580	1920	1280	1720	1150	...	...	2460	1640	2030	1360	1830	1220	...	...	2560	2560	2560	1710	1710
D-225	1250	1030	1200	1000	1200	1000	...	...	1310	1080	1270	1050	1270	1050	...	...	1370	1370	1370	1110	1110
A-300	1670	1270	1450	1110	1340	1030	...	...	1740	1320	1520	1170	1420	1090	...	...	1810	1810	1810	1340	1340
B-300	2080	1500	1760	1280	1610	1170	...	...	2180	1570	1860	1350	1710	1240	...	...	2270	2270	2270	1420	1420
C-300	2520	1750	2080	1450	1880	1310	...	...	2620	1820	2200	1530	2000	1390	...	...	2740	2740	2740	1610	1610
D-300	1590	1350	1580	1360	1580	1360	...	...	1680	1420	1670	1430	1670	1430	...	...	1770	1770	1770	1500	1500
A-375	1850	1450	1640	1300	1640	1300	...	...	1920	1510	1730	1370	1730	1370	...	...	2000	2000	2000	1600	1600
B-375	2260	1680	1930	1450	1780	1340	...	...	2360	1760	2040	1530	1890	1420	...	...	2460	2460	2460	1810	1810
C-375	2680	1920	2250	1620	2040	1480	...	...	2800	2000	2370	1710	2170	1560	...	...	2910	2910	2910	2000	2000
D-375							...	...							...	...				2290	2290

**TABLE 1 Continued**

Internal Designated Dia., mm	Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																						
	1575 <sup>C</sup>						1650						1725 <sup>C</sup>										
	Circular			Elliptical			Circular			Elliptical			Circular			Elliptical							
Type of Reinforcement	Circular			Elliptical			Circular			Elliptical			Circular			Elliptical							
Wall Thickness, mm	132	157		175		132	157		138	182		163		144		169		188		144		169	
Layers of Reinforcement	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single	Single
Class	840	570	740	500	690	460	860	860	880	600	780	530	730	490	900	900	820	550	770	520	940	940	940
A-75	1310	840	1110	700	1010	630	1310	1110	1360	870	1160	740	1060	670	1360	1160	1220	770	1120	700	1410	1410	1220
B-75	1840	1140	1520	930	1370	820	1840	1520	1910	1190	1610	980	1450	870	1910	1610	1690	1030	1530	920	1990	1990	1690
C-75	2350	1430	1920	1150	1700	1000	2350	1920	2450	1490	2020	1210	1800	1060	2450	2020	2120	1270	1900	1120	2540	2540	2120
D-75	1040	780	940	700	880	660	1820	1820	1090	810	990	730	930	690	1900	1900	1040	770	980	730	1990	1990	1990
A-150	1510	1040	1300	900	1200	830	1820	1820	1560	1080	1370	940	1260	870	1900	1900	1430	990	1330	910	1990	1990	1990
B-150	2030	1340	1710	1120	1560	1020	2030	1820	2110	1390	1800	1180	1650	1070	2110	1900	1890	1240	1730	1130	2200	2200	1990
C-150	2530	1620	2100	1340	1890	1190	2530	2100	2630	1690	2210	1400	1990	1260	2630	2210	2310	1470	2100	1330	2740	2740	2310
D-150	1250	990	1140	900	1080	860	...	...	1300	1030	1190	940	1140	900	...	...	1250	990	1200	940	...	...	...
A-225	1710	1250	1500	1100	1390	1020	...	...	1770	1290	1570	1150	1460	1070	...	...	1640	1200	1540	1120	...	...	...
B-225	2220	1540	1900	1320	1750	1210	...	...	2310	1600	2000	1380	1840	1270	...	...	2100	1450	1940	1340	...	...	...
C-225	2720	1820	2280	1530	2070	1380	...	...	2820	1890	2400	1600	2190	1460	...	...	2510	1680	2300	1530	...	...	...
D-225	1460	1200	1410	1160	1400	1160	...	...	1520	1250	1470	1210	1470	1210	...	...	1540	1270	1540	1270	...	...	...
A-300	1910	1450	1700	1300	1590	1220	...	...	1980	1510	1770	1360	1670	1280	...	...	1850	1420	1750	1340	...	...	...
B-300	2410	1740	2100	1520	1940	1400	...	...	2510	1810	2200	1590	2040	1470	...	...	2300	1660	2140	1550	...	...	...
C-300	2900	2010	2470	1720	2260	1570	...	...	3010	2090	2590	1800	2380	1650	...	...	2710	1890	2500	1740	...	...	...
D-300	1860	1570	1860	1580	1850	1580	...	...	1950	1640	1950	1650	1940	1650	...	...	2040	1720	2030	1720	...	...	...
A-375	2110	1660	1920	1510	1910	1520	...	...	2190	1720	2010	1590	2000	1590	...	...	1780	1660	2100	1660	...	...	...
B-375	2610	1940	2290	1710	2130	1600	...	...	2710	2010	2400	1790	2240	1680	...	...	2090	1870	2350	1760	...	...	...
C-375	3090	2210	2660	1910	2450	1760	...	...	3210	2290	2790	2000	2570	1850	...	...	2380	2090	2700	1940	...	...	...
D-375							...	...							...	...					...	...	...



**TABLE 1 Continued**

Internal Designated Dia, mm		Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																		
		1800				1950				2100										
Type of Reinforcement	Wall Thickness, mm	Circular				Circular				Circular										
		150	175	194	194	163	188	207	207	175	200	219								
Layers of Reinforcement	Inner	Outer	Inner	Outer	Single	Single	Outer	Inner	Outer	Inner	Outer	Inner	Outer							
														Inner	Outer	Inner	Outer	Inner	Outer	Inner
Class																				
A-75	1020	690	910	610	850	570	1020	980	1110	750	1000	670	940	630	1210	810	1100	730	1040	690
B-75	1550	1000	1340	850	1230	770	1550	1340	1660	1060	1460	920	1340	840	1780	1140	1580	1000	1460	920
C-75	2210	1370	1860	1140	1690	1020	2210	1860	2370	1470	2020	1240	1840	1110	2500	1550	2170	1330	1990	1200
D-75	2830	1720	2340	1400	2100	1240	2830	2340	3020	1840	2550	1530	2300	1360	3150	1920	2760	1660	2520	1490
A-150	1260	930	1140	850	1080	800	2080	2080	1370	1010	1250	920	1190	870	1480	1080	1360	1000	1300	950
B-150	1790	1230	1570	1080	1450	1000	2080	2080	1910	1320	1700	1170	1580	1090	2040	1400	1830	1260	1720	1180
C-150	2430	1600	2080	1360	1900	1240	2430	2080	2600	1710	2260	1480	2070	1350	2750	1810	2420	1580	2230	1460
D-150	3040	1940	2550	1620	2310	1460	3040	2550	3250	2070	2770	1760	2530	1600	3400	2180	3000	1910	2760	1740
A-225	1500	1180	1370	1080	1310	1030	...	...	1620	1270	1500	1170	1430	1120	1750	1360	1630	1270	1560	1210
B-225	2020	1470	1790	1310	1680	1220	...	...	2160	1570	1940	1410	1820	1330	2300	1670	2090	1520	1980	1440
C-225	2660	1830	2310	1590	2120	1460	...	...	2840	1960	2490	1720	2310	1590	3000	2070	2670	1840	2480	1710
D-225	3250	2160	2770	1840	2520	1680	...	...	3470	2310	3000	2000	2760	1830	3650	2440	3240	2160	3000	1990
A-300	1740	1420	1610	1320	1610	1320	...	...	1880	1530	1750	1430	1750	1430	2020	1630	1890	1530	1890	1530
B-300	2260	1710	2020	1540	1900	1450	...	...	2410	1820	2190	1660	2070	1570	2560	1940	2350	1790	2230	1700
C-300	2880	2070	2530	1820	2350	1690	...	...	3080	2200	2730	1960	2540	1830	3250	2330	2920	2100	2740	1970
D-300	3470	2390	2980	2070	2740	1900	...	...	3700	2550	3230	2240	2990	2070	3890	2690	3490	2410	3240	2240
A-375	2130	1790	2130	1790	2130	1790	...	...	2310	1930	2310	1940	2310	1940	2500	2080	2490	2080	2490	2080
B-375	2490	1950	2260	1780	2190	1730	...	...	2660	2080	2430	1910	2370	1870	2830	2210	2610	2050	2560	2010
C-375	3110	2300	2750	2050	2570	1910	...	...	3320	2450	2970	2210	2780	2070	3510	2590	3170	2360	2990	2230
D-375	3690	2620	3200	2290	2960	2120	...	...	3930	2790	3470	2480	3220	2310	4150	2960	3730	2660	3490	2490

**TABLE 1 Continued**

Internal Designated Dia., mm		2250		2400		2550		2700		3050		3350		3650											
Type of Reinforcement		Circular		Circular		Circular		Circular		Circular		Circular		Circular											
Wall Thickness, mm	Layers of Reinforcement	188		200		213		225		238		254		279		305									
		Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer								
Class																									
A-75		1310	880	1250	1530	1160	1710	1410	940	1360	900	1520	1010	1470	970	1640	1080	1580	1040	1880	1240	2140	1400	2420	1570
B-75		1900	1210	1790	2060	1490	2310	2020	1290	1920	1220	2160	1370	2050	1300	2290	1460	2190	1390	2580	1640	2890	1830	3210	2030
C-75		2640	1630	2460	3190	2780	3580	2780	1720	2610	1610	2930	1820	2770	1710	3090	1910	2930	1810	3420	2120	3770	2330	4140	2560
D-75		<b>3360</b>	<b>2050</b>	3190	1930	<b>3580</b>	<b>2180</b>	<b>3580</b>	<b>2180</b>	3410	2060	<b>3790</b>	<b>2310</b>	<b>3570</b>	<b>2160</b>	<b>3980</b>	<b>2420</b>	<b>3750</b>	<b>2280</b>	S	S	S	S	S	S
A-150		1590	1160	1530	1120	1710	1240	1710	1240	1650	1200	1830	1330	1780	1290	1960	1420	1910	1370	2240	1600	2520	1790	2830	1990
B-150		2170	1490	2060	1420	2310	1590	2310	1590	2210	1510	2460	1680	2360	1610	2610	1780	2510	1710	2920	1990	3260	2210	3610	2440
C-150		2900	1910	2720	1790	3060	2010	2890	1900	2890	1900	3220	2120	3060	2010	3390	2230	3230	2120	3750	2460	4130	2710	4530	2960
D-150		<b>3620</b>	<b>2320</b>	3440	2190	<b>3850</b>	<b>2460</b>	<b>3850</b>	<b>2460</b>	3670	2340	<b>4080</b>	<b>2610</b>	<b>3860</b>	<b>2460</b>	<b>4270</b>	<b>2740</b>	<b>4050</b>	<b>2590</b>	S	S	S	S	S	S
A-225		1860	1450	1810	1400	2010	1550	2010	1550	1950	1500	2150	1650	2090	1600	2290	1750	2230	1710	2600	1960	2910	2190	3250	2420
B-225		2450	1780	2340	1700	2600	1880	2600	1880	2500	1810	2760	2000	2660	1920	2930	2110	2830	2040	3270	2350	3640	2600	4020	2860
C-225		3160	2180	2990	2060	3340	2300	3340	2300	3170	2190	3520	2420	3350	2310	3700	2550	3540	2440	4090	2810	4500	3080	4920	3370
D-225		<b>3880</b>	<b>2590</b>	3690	2450	<b>4120</b>	<b>2750</b>	<b>4120</b>	<b>2750</b>	3940	2620	<b>4370</b>	<b>2910</b>	<b>4140</b>	<b>2760</b>	<b>4570</b>	<b>3050</b>	<b>4350</b>	<b>2900</b>	S	S	S	S	S	S
A-300		2160	1740	2100	1690	2310	1850	2310	1850	2250	1800	2470	1970	2400	1920	2630	2090	2560	2040	2960	2330	3310	2590	3670	2850
B-300		2730	2060	2620	1980	2900	2180	2900	2180	2790	2110	3070	2310	2970	2230	3250	2440	3150	2370	3630	2710	4020	2990	4430	3280
C-300		3430	2460	3260	2340	3620	2590	3620	2590	3450	2480	3810	2730	3650	2620	4010	2870	3850	2760	4430	3160	4860	3470	5320	3780
D-300		<b>4140</b>	<b>2860</b>	3950	2720	<b>4400</b>	<b>3030</b>	<b>4400</b>	<b>3030</b>	4210	2900	<b>4660</b>	<b>3210</b>	<b>4430</b>	<b>3060</b>	<b>4880</b>	<b>3360</b>	<b>4660</b>	<b>3210</b>	S	S	S	S	S	S
A-375		2680	2220	2680	2220	2860	2360	2860	2360	2860	2370	3050	2510	3050	2510	3230	2650	3230	2650	3600	2930	3980	3210	4350	3490
B-375		3010	2350	2900	2260	3190	2490	3190	2490	3080	2410	3380	2630	3280	2550	3580	2770	3470	2700	3980	3070	4410	3380	4850	3700
C-375		3700	2740	3530	2620	3900	2890	3900	2890	3740	2770	4110	3040	3950	2920	4330	3190	4170	3060	4770	3520	5240	3850	5720	4200
D-375		<b>4410</b>	<b>3140</b>	4210	2990	<b>4670</b>	<b>3320</b>	<b>4670</b>	<b>3320</b>	4810	3180	<b>4950</b>	<b>3510</b>	<b>4730</b>	<b>3360</b>	<b>5190</b>	<b>3680</b>	<b>4970</b>	<b>3530</b>	S	S	S	S	S	S

<sup>A</sup> Steel areas may be interpolated between those shown for variations in wall thickness. See 7.2 for provisions for special designs.

<sup>B</sup> The prescribed amounts of reinforcement do not provide any allowance for pressure surges (water hammer) in pipelines.

<sup>C</sup> Available in some areas.

**TABLE 2 Design Requirements for Reinforced Concrete Low-Head Pressure Pipe [300 to 3650 mm Diameter], Concrete Design Strength 34.5 MPa (except as noted) Steel Reinforcement Yield Strength 414 Mpa**

NOTE 1—See Appendix for specific installation conditions and design criteria conditions required in conjunction with the use of **Table 2**.

NOTE 2—Designations A, B, C, and D, for class of pipe, denote 1.5, 3.0, 4.5, and 6.0 m of earth cover over top of pipe. Figures 150, Figures 225, etc. for class of pipe, denote hydrostatic pressure heads in kilopascals measured to centerline of pipe.

NOTE 3—An “s” in place of a steel area indicates the pipe class is a special design requiring stirrup reinforcement. Stirrups may be eliminated by changing wall thickness, main reinforcement, concrete strength, or a combination thereof.

NOTE 4—The boldfaced value denotes 41.4 MPa concrete strength required.

Internal Designated Dia., mm	Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>																
	300		375		450		525		600		675						
	Type of Reinforcement	Circular	Circular	Circular	Elliptical	Circular	Elliptical	Circular	Elliptical	Circular	Elliptical	Circular	Elliptical				
Wall Thickness, mm	50	75	50	75	57	75	60	75	63	75	66	79	82	107	66	82	
Layers of Reinforcement	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Inner	Outer	Single	
Class	100	100	130	130	170	150	250	210	290	260	290	290	280	190	130	160	370
A-75	140	110	200	160	260	220	250	330	330	410	360	430	430	290	180	230	490
B-75	190	140	280	210	360	290	290	460	380	580	490	590	520	360	250	290	780
C-75	240	180	360	260	470	360	360	610	490	770	630	780	690	500	370	430	1050
D-75	220	220	270	270	320	320	520	380	610	430	490	490	490	280	210	280	780
A-150	220	220	270	270	320	320	520	380	610	430	490	490	490	280	210	280	780
B-150	230	220	330	270	420	350	520	400	610	490	440	520	520	360	250	290	780
C-150	280	220	410	310	530	420	520	530	610	660	570	690	690	460	300	360	800
D-150	340	340	430	430	520	520	520	680	610	850	720	870	870	570	360	430	780
A-225	340	340	430	430	520	520	520	600	690	690	690	770	770	430	350	430	370
B-225	340	340	430	430	520	520	520	600	690	690	690	770	770	430	350	430	370
C-225	340	340	430	430	520	520	520	600	690	690	690	770	770	430	350	430	370
D-225	340	340	470	430	590	520	520	750	630	930	800	960	960	630	420	490	370
A-300	490	490	610	610	730	730	860	860	860	980	980	1100	1100	590	500	590	480
B-300	490	490	610	610	730	730	860	860	860	980	980	1100	1100	590	500	590	480
C-300	490	490	610	610	730	730	860	860	860	980	980	1100	1100	590	500	590	480
D-300	490	490	610	610	730	730	860	860	860	1020	980	1230	1100	690	490	650	450
A-375	650	650	820	820	980	980	1140	1140	1140	1310	1310	1470	1470	790	680	780	690
B-375	650	650	820	820	980	980	1140	1140	1140	1310	1310	1470	1470	790	680	780	690
C-375	650	650	820	820	980	980	1140	1140	1140	1310	1310	1470	1470	790	680	780	690
D-375	650	650	820	820	980	980	1140	1140	1140	1310	1310	1470	1470	790	680	780	690

**TABLE 2 Continued**

Internal Designated Dia, mm	Circumferential reinforcement, mm <sup>2</sup> /linear m of pipe <sup>A, B</sup>													
	750						825							
	Circular						Circular							
Type of Reinforcement	Circular			Elliptical			Circular			Elliptical				
Wall Thickness, mm	82		88		119		82		94		119			
Layers of Reinforcement	Single	Inner	Outer	Inner	Outer	Single	Inner	Outer	Inner	Outer	Single	Inner	Outer	
Class	350	230	160	210	150	170	410	410	260	180	230	200	130	450
A-75	580	520	220	330	210	250	580	410	380	270	360	290	180	450
B-75	840	740	290	440	270	320	440	410	630	350	490	380	220	680
C-75	1160	980	360	560	330	400	840	560	900	450	620	480	270	1000
D-75							1160	1230	1230	450	620	480	270	1290
A-150	540	310	230	310	230	310	870	870	590	260	340	340	260	950
B-150	690	430	300	400	280	320	870	870	750	350	440	360	250	950
C-150	950	840	360	510	340	390	950	870	1020	430	560	450	290	1110
D-150	1270	1080	440	630	400	470	1270	870	1350	520	690	550	340	1410
A-225	860	470	390	470	390	470	...	...	950	420	520	520	430	...
B-225	860	500	370	490	370	490	...	...	950	430	540	540	400	...
C-225	1050	940	440	580	410	510	...	...	1220	510	640	560	390	...
D-225	1370	1190	510	700	470	530	...	...	1460	600	760	620	410	...
A-300	1220	660	560	660	560	660	...	...	1340	610	730	730	620	...
B-300	1220	690	530	690	530	690	...	...	1340	590	760	760	590	...
C-300	1220	710	520	700	520	710	...	...	1340	590	780	780	570	...
D-300	1470	820	580	770	540	720	...	...	1570	680	840	790	550	...
A-375	1630	870	760	870	760	870	...	...	1800	830	960	960	840	...
B-375	1630	910	730	900	730	900	...	...	1800	800	1000	1000	800	...
C-375	1630	930	700	930	710	930	...	...	1800	770	1020	1020	780	...
D-375	1690	950	690	950	690	950	...	...	1800	760	1040	1040	760	...