

Designation: E1377 - 99 (Reapproved 2022)

Standard Specification for Laboratory Glass Kjeldahl Flasks¹

This standard is issued under the fixed designation E1377; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification provides standard dimensional requirements for glass Kjeldahl flasks for nitrogen digestion analysis.
- 1.2 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

- 2.1 ASTM Standards:²
- E147 Specification for Apparatus for Microdetermination of Nitrogen by Kjeldahl Method
- E438 Specification for Glasses in Laboratory Apparatus
- E671 Specification for Maximum Permissible Thermal Residual Stress in Annealed Glass Laboratory Apparatus
- E694 Specification for Laboratory Glass Volumetric Apparatus
- E920 Specification for Commercially Packaged Laboratory
 Apparatus

 ASTM F137
- E921 Specification for Export Packaged Laboratory Apparatus
- E1133 Practice for Performance Testing of Packaged Laboratory Apparatus for United States Government Procurements
- E1157 Specification for Sampling and Testing of Reusable Laboratory Glassware

3. Classification

3.1 *Ungraduated Flasks*, *Type I*, shall be of the following capacities:

100 mL

300	mL
500	mL
650	mL
800	mL

- 3.1.1 Sizes 10 mL and 30 mL and the Soltys style 30 mL are covered under Specification E147 and are not included herein.
- 3.2 Graduated Flasks, Type II, shall be of the following capacity:

800 mL, graduated at 1000 mL

Note 1—The term millilitre (mL) is commonly used as a special name for the cubic centimetre (cm³) and similarly the litre (L) for 1000 cubic centimetres, in accordance with the International System of Units (SI).

4. Material and Annealing

- 4.1 Flasks shall be made of borosilicate glass conforming to the requirement of Type I, Class A of Specification E438.
- 4.2 Maximum residual thermal stress shall conform to Specification E671.

5. Appearance

9 (5.1) The general appearance of the flasks shall conform to Fig. 1. 2000-704fbf0a9161/astm-e1377-992022

6. Design

- 6.1 Necks on all flasks shall be circular in cross section, and shall be perpendicular to center of flask body.
- 6.2 Top finish of flask shall not be belled over 2 in. from the top. Top shall be tooled or beaded.
- 6.3 Interior neck finish of sizes 500 and 800 mL may be tooled to accept special rubber stopper especially made for Kjeldahl flasks.
- 6.4 Bottom of flask shall be hemispherical in shape, while top has a curved taper to point of junction with the flask neck. (See Fig. 1.)
- 6.5 Wall thickness of flasks shall be controlled in accordance with Table 1.


7. Volumetric Accuracy

7.1 Tolerance on volumetric accuracy of Type II flasks shall be in compliance with Specification E694 (1000 \pm 1.5 mL).

¹ This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of Subcommittee E41.01 on Laboratory Ware and Supplies.

Current edition approved Sept. 1, 2022. Published September 2022. Originally approved in 1990. Last previous edition approved in 2016 as E1377 - 99(2016). DOI: 10.1520/E1377-99R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.






FIG. 1 Glass Kjeldahl Flasks

8. Capacity and Dimensions

8.1 The nominal capacity of the ungraduated, Type I flasks shall not exceed the actual capacity to the base of the neck. The 1000 mL graduated flask capacity ring shall be within the neck of the flask. Dimensions shall conform to the requirements of Table 1.

TABLE 1 Capacity and Dimensions for Glass Kjeldahl Flasks

Nominal Capacity (mL)	Body OD max (mm)	Body Wall Thickness min (mm)	Neck OD max (mm)	Stopper Size	Overall Height max (mm)
100	60	0.8	23	1 or 2	214
300	82	0.8	28	5	310
500	103	0.8	34	6 or ^{<i>A</i>}	327
650	108	0.8	34	6	327
800	119	0.8	36	7 or ^{<i>A</i>}	369

A Stoppers specially made for Kjeldahl flasks.

9. Markings

- 9.1 Each flask shall be permanently marked with the name or known trademark of the manufacturer and the nominal capacity for Type I flasks and actual capacity for Type II flasks.
- 9.2 There shall be an area on one side of the flask neck for marking with a pencil.

10. Sampling

10.1 Refer to Specification E1157.

11. Sampling

11.1 Select from Specifications E920, E921, and E1133.

12. Keywords

12.1 flasks; glass; kjeldahl

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/