



Designation: A299/A299M – 17 (Reapproved 2022)

Standard Specification for Pressure Vessel Plates, Carbon Steel, Manganese-Silicon¹

This standard is issued under the fixed designation A299/A299M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers manganese-silicon carbon steel plates for use in welded boilers and other pressure vessels.

1.2 Plates under this specification are produced in two grades. The specified minimum yield strength decreases for thicknesses over 1 in. [25 mm].

1.3 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements.

1.4 For plates produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A20/A20M apply.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 1, 2022. Published September 2022. Originally approved in 1947. Last previous edition approved in 2017 as A299/A299M – 17. DOI: 10.1520/A0299_A0299M-17R22.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-299/SA-299M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels](#)

[A435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates](#)

[A577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates](#)

[A578/A578M Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications](#)

3. General Requirements and Ordering Information

3.1 Plates supplied to this product specification shall conform to Specification A20/A20M, which outlines the testing and retesting methods and procedures, permitted variations in dimensions and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available where additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A20/A20M.

3.3 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plates from coil are described in Specification A20/A20M.

3.4 If the requirements of this specification are in conflict with the requirements of Specification A20/A20M, the requirements of this specification shall prevail.

4. Materials and Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification A20/A20M.

TABLE 1 Chemical Requirements

Elements	Composition, %
Carbon, max: ^A	
1 in. [25 mm] and under	
Grade A	0.26
Grade B	0.28
Over 1 in. [25 mm]	
Grade A	0.28
Grade B	0.30
Manganese:	
1 in. [25 mm] and under	
Heat analysis	0.90 to 1.40
Product analysis	0.84 to 1.52
Over 1 in. [25 mm]	
Heat analysis	0.90 to 1.50
Product analysis	0.84 to 1.62
Phosphorus, max ^A	0.025
Sulfur, max ^A	0.025
Silicon:	
Heat analysis	0.15 to 0.40
Product analysis	0.13 to 0.45

^A Applies to both heat and product analyses.

5. Heat Treatment

5.1 Plates 2 in. [50 mm] and under in thickness are normally supplied in the as-rolled condition. Plates may be ordered normalized or stress relieved, or both.

5.2 Plates over 2 in. [50 mm] in thickness shall be normalized.

TABLE 2 Tensile Requirements

	Grade A	Grade B
Tensile strength, ksi [MPa]	75–95 [515–655]	80–100 [550–690]
Yield strength, min, ^A ksi [MPa]:		
1 in. [25 mm] and under	42 [290]	47 [325]
Over 1 in. [25 mm]	40 [275]	45 [310]
Elongation in 8 in. [200 mm], min, % ^B	16	16
Elongation in 2 in. [50 mm], min, % ^B	19	19

^A Determined by either the 0.2 % offset method or the 0.5 % extension-under-load method.

^B See the Elongation Requirement Adjustments subsection in the Tension Tests section of Specification **A20/A20M**.

6. Chemical Composition

6.1 The steel shall conform to the requirements given in **Table 1**.

7. Mechanical Properties

7.1 *Tension Test Requirements*—The plates, as represented by the tension test specimens, shall conform to the requirements given in **Table 2**.

8. Keywords

8.1 carbon steel plate; pressure containing parts; pressure vessel steels; steel plates; steel plates for pressure vessel applications

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order.

A list of standardized supplementary requirements for use at the option of the purchaser is included in Specification **A20/A20M**. Those that are considered suitable for use with this specification are listed below by title.

[ASTM A299/A299M-17\(2022\)](https://standards.iteh.ai/catalog/standards/sist/9488e771-b6b8-4bec-9ff0-22bbb73dc630/astm-a299-a299m-172022)

<https://standards.iteh.ai/catalog/standards/sist/9488e771-b6b8-4bec-9ff0-22bbb73dc630/astm-a299-a299m-172022>

- S1. Vacuum Treatment,
- S2. Product Analysis,
- S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons,
- S4. Additional Tension Test,
- S5. Charpy V-Notch Impact Test,
- S6. Drop Weight Test (for Material 0.625 in. [16 mm] and over in Thickness),

- S7. High-Temperature Tension Test,
- S8. Ultrasonic Examination in accordance with Specification **A435/A435M**,
- S9. Magnetic Particle Examination,
- S11. Ultrasonic Examination in accordance with Specification **A577/A577M**,
- S12. Ultrasonic Examination in accordance with Specification **A578/A578M**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/