



## Designation: A302/A302M – 17 (Reapproved 2022)

# Standard Specification for Pressure Vessel Plates, Alloy Steel, Manganese-Molybdenum and Manganese-Molybdenum-Nickel<sup>1</sup>

This standard is issued under the fixed designation A302/A302M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification<sup>2</sup> covers manganese-molybdenum and manganese-molybdenum-nickel alloy steel plates intended particularly for welded boilers and other pressure vessels.

1.2 Plates under this specification are available in four grades having different strength levels as follows:

Grade	Tensile Strength, ksi [MPa]	Type
A	75–95 [515–655]	manganese-molybdenum
B	80–100 [550–690]	manganese-molybdenum
C	80–100 [550–690]	manganese-molybdenum-nickel
D	80–100 [550–690]	manganese-molybdenum-nickel

1.3 The maximum thickness of plates is limited only by the capacity of the chemical composition to meet the specified mechanical property requirements.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 1, 2022. Published September 2022. Originally approved in 1947. Last previous edition approved in 2017 as A302/A302M – 17. DOI: 10.1520/A0302\_A0302M-17R22.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-302/SA-302M in Section II of that Code.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels

A435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates

A577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates

A578/A578M Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

## 3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A20/A20M. These requirements outline the testing and retesting methods and procedures, permitted variations in dimensions, and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A20/A20M.

3.3 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Chemical Requirements**

NOTE 1—Where “...” appears, there is no requirement.

Elements	Composition, %			
	Grade A	Grade B	Grade C	Grade D
Carbon, max: <sup>A</sup>				
Up to 1 in. [25 mm], incl, in thickness	0.20	0.20	0.20	0.20
Over 1 in. to 2 in. [50 mm], incl	0.23	0.23	0.23	0.23
Over 2 in. [50 mm] in thickness	0.25	0.25	0.25	0.25
Manganese:				
Heat analysis	0.95–1.30	1.15–1.50	1.15–1.50	1.15–1.50
Product analysis	0.87–1.41	1.07–1.62	1.07–1.62	1.07–1.62
Phosphorus, max <sup>A</sup>	0.025	0.025	0.025	0.025
Sulfur, max <sup>A</sup>	0.025	0.025	0.025	0.025
Silicon:				
Heat analysis	0.15–0.40	0.15–0.40	0.15–0.40	0.15–0.40
Product analysis	0.13–0.45	0.13–0.45	0.13–0.45	0.13–0.45
Molybdenum:				
Heat analysis	0.45–0.60	0.45–0.60	0.45–0.60	0.45–0.60
Product analysis	0.41–0.64	0.41–0.64	0.41–0.64	0.41–0.64
Nickel:				
Heat analysis	...	...	0.40–0.70	0.70–1.00
Product analysis	...	...	0.37–0.73	0.67–1.03

<sup>A</sup> Applies to both heat and product analyses.

**TABLE 2 Tensile Requirements**

	Grade A	Grade B	Grade C	Grade D
Tensile strength, ksi [MPa]	75–95 [515–655]	80–100 [550–690]	80–100 [550–690]	80–100 [550–690]
Yield strength, min, ksi [MPa]	45 [310]	50 [345]	50 [345]	50 [345]
Elongation in 8 in. [200 mm], min, % <sup>A</sup>	15	15	17	17
Elongation in 2 in. [50 mm], min, % <sup>A</sup>	19	18	20	20

<sup>A</sup> See Specification A20/A20M for elongation adjustment.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plates from coil are described in Specification A20/A20M.

3.4 If the requirements of this specification are in conflict with the requirements of Specification A20/A20M, the requirements of this specification shall prevail.

#### 4. Materials and Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine grain size requirement of Specification A20/A20M.

#### 5. Heat Treatment

5.1 Plates 2 in. [50 mm] and under in thickness are normally supplied in the as-rolled condition. Plates may be ordered normalized, normalized and tempered, or stress relieved.

5.2 Plates over 2 in. [50 mm] in thickness shall be normalized or normalized and tempered.

5.3 When normalizing plates 4 in. [100 mm] or over in thickness, the cooling rate may be accelerated by air blasting or liquid quenching followed by tempering in the temperature range from 1100 °F to 1300 °F [595 °C to 705 °C] to obtain mechanical properties comparable to those developed by normalizing plates in the lesser thicknesses.

5.4 If approved by the purchaser, for plates less than 4 in. [100 mm] in thickness, cooling rates faster than those obtained

by cooling in air are permissible for improvement of toughness, provided the plates are subsequently tempered in the temperature range from 1100 °F to 1300 °F [595 °C to 705 °C].

#### 6. Chemical Composition

6.1 The steel shall conform to the chemical requirements shown in Table 1 unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification A20/A20M.

#### 7. Mechanical Properties

7.1 *Tension Test Requirements*—The plates, as represented by the tension test specimens, shall conform to the requirements given in Table 2.

7.1.1 For accelerated cooled plates with a nominal thickness of ¾ in. [20 mm] or less, the 1½ in. [40 mm] wide rectangular specimen may be used for the tension test, and the elongation may be determined in a 2 in. [50 mm] gauge length that includes the fracture and that shows the greatest elongation.

#### 8. Keywords

8.1 alloy steel plate; pressure containing parts; pressure vessel steels; steel plates; steel plates for pressure vessel applications