



Designation: A338 – 84 (Reapproved 2022)

Standard Specification for Malleable Iron Flanges, Pipe Fittings, and Valve Parts for Railroad, Marine, and Other Heavy-Duty Service at Temperatures Up to 650 °F (345 °C)¹

This standard is issued under the fixed designation A338; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers malleable iron flanges, pipe fittings, and valve parts, including parts to be assembled for use in railroad, marine, and other heavy-duty service applications where fittings furnished in accordance with American National Standard for Malleable Iron Threaded Fittings, Classes 150 and 300 (ANSI B16.3) are not considered adequate.

1.2 Service shall include up to 650 °F (345 °C).²

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

[A47/A47M Specification for Ferritic Malleable Iron Castings](#)

[A153/A153M Specification for Zinc Coating \(Hot-Dip\) on Iron and Steel Hardware](#)

¹ This specification is under the jurisdiction of ASTM Committee A04 on Iron Castings and is the direct responsibility of Subcommittee A04.02 on Malleable and Ductile Iron Castings.

Current edition approved Oct. 1, 2022. Published October 2022. Originally approved in 1954. Last previous edition approved in 2018 as A338 – 84 (2018). DOI: 10.1520/A0338-84R22.

² Based on Marshall, L. C., and Sommer, G. F., "Stress Rupture Properties of Malleable Iron at Elevated Temperatures," *Proceedings*, ASTM International, Vol 58, 1958, p. 733.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *American National Standards:*⁴

[B2.1 Pipe Threads](#)

[B16.3 Malleable Iron Threaded Fittings, Classes 150 and 300](#)

2.3 *Other Standards:*

[Handbook H28, Section VI Screw-Thread Standards for Federal Services, 1944](#)⁵

[SP-25-1936 Standard Marking System for Valves, Fittings, Flanges, and Unions](#)⁶

3. Process

3.1 The castings shall be made in accordance with Specification [A47/A47M](#).

4. Materials and Manufacture

4.1 The sizes, shapes, and dimensions of the fittings covered by ANSI B16.3 shall conform to the requirements therein specified.

4.2 Screwed pipe fittings, unions, union fittings, and globe and angle valves that are covered by the various standards and recommended practices as issued by the Association of American Railroads shall conform to the requirements therein specified.

4.3 All pipe threads, unless otherwise specified, shall be in accordance with ANSI B2.1. (Standards for pipe threads are also available in Section VI of Screw-Thread Standards for Federal Services.)

4.4 Zinc coatings on fittings which are required to be galvanized by the hot-dip process shall conform to the requirements for Class A castings as prescribed in Specification

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

⁶ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.org>.

A153/A153M, except on surfaces where it is the practice to machine after galvanizing.

5. Manufacture Control and Records

5.1 The iron shall be produced under constant control of chemical composition and physical properties. Records of the chemical composition of the iron and of the physical properties of the test specimens shall be systematically made and maintained.

6. Tests

6.1 Tests shall be made when required by the specifications listed herein.

7. Certification

7.1 The manufacturer shall be prepared to certify, upon request of the purchaser, that his product conforms to the requirements of this specification.

8. Product Marking

8.1 The castings shall be marked with the manufacturer's name or trademark.

8.2 Malleable iron products conforming to the standards of the Manufacturers Standardization Society of the Valve and Fittings Industry shall be marked in accordance with SP-25-1936 of that society. Malleable iron products furnished in accordance with the standards issued by the American Standards Association or by the Association of American Railroads shall be marked as specified in the respective standards.

9. Keywords

9.1 flanges; heavy-duty service; malleable iron; marine service; pipe fittings; railroad service; valve parts

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

[ASTM A338-84\(2022\)](#)

<https://standards.iteh.ai/catalog/standards/sist/bffa032a-973d-4d8e-99b9-4bd62b8dcbd1/astm-a338-842022>