



## Designation: ~~B140/B140M – 12 (Reapproved 2022)~~ B140/B140M – 22

# Standard Specification for Copper-Zinc-Lead (Red Brass or Hardware Bronze) Rod, Bar, and Shapes<sup>1</sup>

This standard is issued under the fixed designation B140/B140M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification establishes the requirements for copper-zinc-lead (lead red brass or hardware bronze) rod, bar, and shapes of UNS Copper Alloy Nos. C31400, C31600, and C32000 available for general and screw machine applications.

1.2 *Units*—The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

- 2.1 *ASTM Standards:*<sup>2</sup>
- [B249/B249M Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings](#)
  - [B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast](#)
  - [B846 Terminology for Copper and Copper Alloys](#)
  - [E8/E8M Test Methods for Tension Testing of Metallic Materials](#)
  - [E62 Test Methods for Chemical Analysis of Copper and Copper Alloys \(Photometric Methods\) \(Withdrawn 2010\)](#)<sup>3</sup>
  - [E478 Test Methods for Chemical Analysis of Copper Alloys](#)

## 3. General Requirements

3.1 The following sections of Specification [B249/B249M](#) constitute a part of this specification:

3.1.1 Terminology ([B846](#)),

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee [B05](#) on Copper and Copper Alloys and is the direct responsibility of Subcommittee [B05.02](#) on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved ~~May 1, 2022~~ Oct. 1, 2022. Published ~~May 2022~~ October 2022. Originally approved in 1941. Last previous edition approved in ~~2017~~ 2022 as [B140/B140M – 12 \(2017\) \(2022\)](#). DOI: ~~10.1520/B0140\_B0140M-12R22~~ 10.1520/B0140\_B0140M-22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard



- 3.1.2 Materials and Manufacture,
- 3.1.3 Workmanship, Finish, and Appearance,
- 3.1.4 Sampling,
- 3.1.5 Number of Tests and Retests,
- 3.1.6 Specimen Preparation,
- 3.1.7 Test Methods,
- 3.1.8 Significance of Numerical Limits,
- 3.1.9 Inspection,
- 3.1.10 Rejection and Rehearing,
- 3.1.11 Certification,
- 3.1.12 Test Report,
- 3.1.13 Product Marking,
- 3.1.14 Packaging and Package Marking, and
- 3.1.15 Supplementary Requirements.

3.2 In addition, when a section with a title identical to one of those referenced in 3.1 appears in this specification, it contains additional requirements that supplement those appearing in Specification B249/B249M.

#### 4. Ordering Information

4.1 Include the following specified choices when placing orders for products under this specification, as applicable:

- 4.1.1 ASTM designation and year of issue;
- 4.1.2 Copper Alloy UNS No. designation (Scope);
- 4.1.3 Temper designation (Temper Section);
- 4.1.4 Dimensions—diameter, distance between parallel surfaces;
- 4.1.5 How furnished; length, specific or stock, with or without ends;
- 4.1.6 Quantity; total weight or length, or number of pieces of each temper, form, and alloy; and
- 4.1.7 Intended application, general use or automatic screw machine use (Straightness Tolerance).

4.2 The following options are available ~~but may not be included unless and, when required, shall be specified at the time of placing of the order when required:~~ the order:

- 4.2.1 Certification (Specification B249/B249M),
- 4.2.2 Mill Test Reports (Specification B249/B249M), and
- 4.2.3 If product is purchased for agencies of the U.S. government (Specification B249/B249M).

## 5. Material and Manufacture

### 5.1 Material:

5.1.1 The material of manufacture shall be a form (cast billets, logs, or rods) of Copper Alloy UNS Nos. C31400, C31600, or C32000 of such purity and soundness as to be suitable for processing into the products prescribed herein.

### 5.2 Manufacture:

5.2.1 The product shall be manufactured by such hot working, cold working, straightening, and annealing processes as to produce a uniform wrought structure in the finished product.

## 6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements in **Table 1** for the Copper Alloy UNS No. designation specified in the ordering information.

6.1.1 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and the purchaser, limits may be established and analysis required for unnamed elements.

6.2 For alloys in which zinc is listed as the “remainder,” either copper or zinc may be taken as the difference between the sum of results of all other elements determined and 100 %. When copper is so determined, that difference value shall conform to the requirements given in **Table 1**.

6.3 When all elements in **Table 1** are determined, the sum of the results shall be 99.6 % minimum.

## 7. Temper

7.1 The standard tempers, as defined in Classification **B601**, for products described in this specification are O60 (soft anneal), H02 (half-hard), and H04 (hard).

## 8. Mechanical Property Requirements

### 8.1 Tensile Strength Requirements:

8.1.1 Product furnished under this specification shall conform to the tensile requirements prescribed in **Table 2** (inch-pound units) or **Table 3** (SI units) when tested in accordance with Test Methods **E8/E8M**.

## 9. Dimensions, Mass and Permissible Variations

9.1 The dimensions and tolerances for product described by this specification shall be as specified in Specification **B249/B249M** with particular reference to the following tables and related paragraphs:

### 9.2 Diameter or Distance Between Parallel Surfaces:

9.2.1 *Rod*—Refer to Table 1 for round, hexagonal and octagonal rod.

**TABLE 1 Chemical Requirements**

| Element    | Composition, %       |              |              |
|------------|----------------------|--------------|--------------|
|            | Copper Alloy UNS No. |              |              |
|            | C31400               | C31600       | C32000       |
| Copper     | 87.5 to 90.5         | 87.5 to 90.5 | 83.5 to 86.5 |
| Lead       | 1.3 to 2.5           | 1.3 to 2.5   | 1.5 to 2.2   |
| Iron, max  | 0.10                 | 0.10         | 0.10         |
| Nickel     | 0.7 max              | 0.7 to 1.2   | 0.25 max     |
| Zinc       | remainder            | remainder    | remainder    |
| Phosphorus | ...                  | 0.04 to 0.10 | ...          |