



Standard Specification for Preformed Cranioplasty Plates¹

This standard is issued under the fixed designation F452; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers preformed cranioplasty plates which do not require further alteration for covering skull defects. This specification covers compositional and physical performance and packaging requirements, but does not cover toxicity nor biocompatibility of the materials.

1.2 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

F56 Specification for Stainless Steel Sheet and Strip for Surgical Implants (Withdrawn 1989)³

F75 Specification for Cobalt-28 Chromium-6 Molybdenum Alloy Castings and Casting Alloy for Surgical Implants (UNS R30075)

F86 Practice for Surface Preparation and Marking of Metallic Surgical Implants

F139 Specification for Wrought 18Chromium-14Nickel-2.5Molybdenum Stainless Steel Sheet and Strip for Surgical Implants (UNS S31673)

2.2 *American Society for Quality (ASQ) Standard:*⁴

ASQ C1 Specifications of General Requirements for a Quality Program

3. Materials

3.1 Cranioplasty plates conforming to this specification shall be fabricated from materials described in the latest issue

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.31 on Neurosurgical Standards.

Current edition approved Nov. 1, 2022. Published November 2022. Originally approved in 1976. Last previous edition approved in 2008 as F452 – 76 (2008). DOI: 10.1520/F0452-76R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, <http://www.asq.org>.

of Specification **F56**, Grade 2, **F75**, or **F139**, Grade 2. The condition of the material (such as annealed, cold finished, and so forth) should be specified in the purchase order.

4. Dimensions and Tolerances

4.1 Cranioplasty plates conforming to this specification shall be fabricated in a variety of dimensions to accommodate, without further alteration, various-sized skull defects.

4.2 Shape shall be contoured so as to re-establish the normal configuration and symmetry of the skull at various anticipated sites of defect such as the parietal bosses, theinion, the brow, the linea temporalis, and so forth.

4.3 Plates shall contain multiple perforations (see Fig. 1).

4.4 Thicknesses and individual shapes shall vary with need. Thickness tolerances shall be as follows:

Specified Thickness, in. (mm)	Thickness Tolerances, in. (mm)
0.005 (0.13) to 0.010 (0.25), incl	$\pm 10\%$
0.010 (0.25) to 0.020 (0.51), incl	± 0.0015 (0.04)
0.020 (0.51) to 0.035 (0.89), incl	± 0.002 (0.05)
0.035 (0.89) to 0.050 (1.27), incl	± 0.0025 (0.06)
0.050 (1.27) to 0.100 (2.54), incl	± 0.003 (0.08)

5. Finish and Identification

5.1 Cranioplasty plates conforming to this specification shall have their surfaces prepared in accordance with the latest issue of Practice **F86**. Specific requirements of surface finish (if any) shall be stated in the purchase order.

5.2 The method of marking the plates shall be one of those specified in Practice **F86**.

6. Precautions

6.1 Cranioplasty plates covered by this specification shall *not* be reshaped in any manner after manufacture.

6.2 Material used to fasten the cranioplasty plates covered by this specification shall be the same alloy as the material used to make the specific plate being installed.

7. Packaging and Labeling

7.1 Cranioplasty plates conforming to this specification shall be supplied packaged in accordance with the appropriate recommended practice being developed by ASTM Committee




FIG. 1 Preformed Cranioplasty Plate

7.1.1 An insert shall be included in the package for the plate showing the material from which it was fabricated and include a recommendation against using fasteners other than the same material or a recommended substitute to secure the plate when implanted.

7.1.2 Labeling shall include the nominal thickness of the plate.

8. Quality Program Requirements

8.1 The manufacturer of cranioplasty plates covered by this specification shall maintain a quality program such as, for example, defined in ASQ C1.

9. Keywords

9.1 bone plates; cranioplasty plates; neurosurgical medical devices/applications; orthopaedic medical devices

F04. Minimum packaging and labeling for cranioplasty plates shall include the following:

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

Document Preview

[ASTM F452-76\(2022\)](https://standards.iteh.ai/catalog/standards/sist/3da45a2a-b2aa-41d7-880e-70c5cf5b37ae/astm-f452-762022)

<https://standards.iteh.ai/catalog/standards/sist/3da45a2a-b2aa-41d7-880e-70c5cf5b37ae/astm-f452-762022>