



Designation: ~~D4154 – 14~~ D4154 – 22

Standard Performance Specification for Men's and Boys' Knitted and Woven Beachwear and Sports Shirt Fabrics¹

This standard is issued under the fixed designation D4154; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This performance specification covers knitted and woven fabrics comprised of any textile fiber or mixture of fibers used in men's and boy's beachwear and sports shirts.

1.2 This performance specification is not applicable to knitted and woven fabrics used for interlining and swimwear.

1.3 These requirements apply to both the length and width directions for those properties where fabric direction is pertinent.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

[ASTM D4154-22](https://standards.iteh.ai/catalog/standards/sist/78a80dbb-8c51-42d1-9a24-635505374a1a/astm-d4154-22)

<https://standards.iteh.ai/catalog/standards/sist/78a80dbb-8c51-42d1-9a24-635505374a1a/astm-d4154-22>

2.1 ASTM Standards:²

[D123 Terminology Relating to Textiles](#)

[D434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam \(Withdrawn 2003\)](#)³

[D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum \(Elmendorf-Type\) Apparatus](#)

[D2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue \(Single Rip\) Method \(Constant-Rate-of-Traversal Tensile Testing Machine\) \(Withdrawn 1995\)](#)³

[D2594 Test Method for Stretch Properties of Knitted Fabrics Having Low Power](#)

[D2724 Test Method for Bond Strength of Bonded, Fused, and Laminated Apparel Fabrics](#)

[D2905 Practice for Statements on Number of Specimens for Textiles \(Withdrawn 2008\)](#)³

[D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method](#)

[D3787 Test Method for Bursting Strength of Textiles—Constant-Rate-of-Traversal \(CRT\) Ball Burst Test](#)

[D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics \(Grab Test\)](#)

[D7022 Terminology Relating to Apparel \(Withdrawn 2022\)](#)³

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel. Current edition approved Feb. 1, 2014 (Nov. 1, 2022). Published March 2014 (November 2022). Originally approved in 1982. Last previous edition approved in 2008 (2014) as ~~D4154 – 04~~ D4154 – 14 (2008). DOI: ~~10.1520/D4154-14~~ 10.1520/D4154-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 AATCC Test Methods:⁴

~~8~~**TM8** Colorfastness to Crocking: Crockmeter Method
~~15~~**TM15** Colorfastness to Perspiration
~~16.3~~**TM16.3** Colorfastness to Light: Xenon-Arc
~~23~~**TM23** Colorfastness to Burnt Gas Fumes
~~61~~**TM61** Colorfastness to Laundering: Accelerated
~~96~~**TM96** Dimensional Changes in Laundering of Woven and Knitted Textiles Except Wool
~~116~~**TM116** Colorfastness to Crocking: Rotary Vertical Crockmeter Method
~~124~~**TM124** Smoothness Appearance of Fabrics After Repeated Home Launderings
~~132~~**TM132** Colorfastness to Drycleaning
~~135~~**TM135** Dimensional Changes of Fabrics after Home Laundering
~~172~~**TM172** Colorfastness to Powdered Non-chlorine Bleach in Home Laundering
~~188~~**TM188** Colorfastness to Sodium Hypochlorite Bleach in Home Laundering
~~Evaluation Procedure 1EP1~~ Gray Scale for Color Change
~~Evaluation Procedure 2EP2~~ Gray Scale for Staining
~~Evaluation Procedure 8EP8~~ AATCC 9-Step Chromatic Transference Scale
M11 A Glossary of AATCC Standard Terminology

2.3 Federal Standard:⁵

16 CFR, Chapter II—Consumer Product Safety Commission Subchapter D—Flammable Fabrics Act Regulations.

2.4 Military Standard:⁶

MIL-STD-105D Sampling Procedures and Tables for Inspection by Attributes

NOTE 1—Reference to test methods in this performance specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 For all terminology related to Apparel, see Terminology **D7022**.

3.1.1 The following terms are relevant to this standard: dimensional change; change; pressing and finishing.

3.2 For definition of all other textile terms see Terminology **D123.54-22**

<https://standards.iteh.ai/catalog/standards/sist/78a80dbb-8c51-42d1-9a24-635505374a1a/astm-d4154-22>

3.3 For terms relating to chemical or colorfastness testing, refer to specific AATCC test methods, or the Glossary of AATCC Standard Terminology, or both.

3.4 Definitions of terms used in a dictionary of common terms are suitable for terms used in this performance specification.

3.5 Definitions of Terms Specific to This Standard:

3.5.1 *pressing and finishing*—This term takes into account all of the industrial pressing and finishing treatments used in garment production.

NOTE 2—No standard method is available for reproducing on a laboratory level the results of industrial pressing or finishing treatments used in the manufacture of garments.

4. Specification Requirements

4.1 The properties of fabrics of woven and knitted fabrics for men's and boy's beachwear and sport shirts shall conform to the specification requirements in **Table 1**.

⁴ AATCC Technical Manual, available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, <http://www.aatcc.org>.

⁵ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

TABLE 1 Specification Requirements

NOTE 1—Grade for colorfastness and SA rating is based on a numerical scale of 5 for negligible or no color change, color transfer, or wrinkle to 1 for very severe color change, color transfer, or wrinkle. The numerical rating in **Table 1** or a higher numerical rating is acceptable.

Characteristic	Requirements		Section
	Knitted	Woven	
Breaking strength (load) (CRT)	...	111 N (25 lbf), min	7.1
Bursting strength (load) (ball burst)	222 N (50 lbf)	...	7.2
Yarn slippage, 6-mm (¼-in.) separation	...	89 N (20 lbf), min	7.3
Tongue tear strength	...	6.7 N (1.5 lbf), min	7.4
Dimensional Change:			
Pressing and finishing	2 % max	1 % max, pre-finished fabrics	7.5.1
After five launderings (see 7.5.2.2 if shrinkage exceeds 3 %)	3 % max	2 % max, post-finished fabrics	7.5.2
After three dry cleanings	3 % max	3 % max	7.5.3
Growth	3 % max	3 % max	7.5.4
Colorfastness:			
Burnt Gas Fumes—2 Cycles:			
Shade change, original fabric	Grade 4 ^A min	Grade 4 ^A min	7.6.1
Shade change after 1 laundering or 1 dry cleaning	Grade 4 ^A min	Grade 4 ^A min	
Laundering: ^E			
Shade change	Grade 4 ^A min	Grade 4 ^A min	7.6.2
Staining	Grade 3 ^B min	Grade 3 ^B min	
Dry cleaning:			
Shade change	Grade 4 ^A min	Grade 4 ^A min	7.6.3
Crocking: ^E			
Dry	Grade 4 ^C min	Grade 4 ^C min	7.6.4
Wet	Grade 3 ^C min	Grade 3 ^C min	
Perspiration: ^E			
Shade Change	Grade 4 ^A min	Grade 4 ^A min	7.6.5
Staining	Grade 3 ^B min	Grade 3 ^B min	
Light (40 AATCC Fading Units) (xenon-arc)	Grade 4 ^A min	Grade 4 ^A min	7.6.6
Light (40 AFU) (xenon-arc)	Grade 4 ^A min	Grade 4 ^A min	7.6.6
Sodium Hypochlorite Bleach	Grade 4 ^A , min	Grade 4 ^A , min	7.6.7
Powdered Non-chlorine Bleach	Grade 4 ^A , min	Grade 4 ^A , min	7.6.8
Fabric smoothness appearance (see 7.7.1)	SA 3.5 ^D min	SA 3.5 ^D min	7.7
Flammability	pass	pass	7.8
Flammability	Class 1	Class 1	7.8

^A AATCC Gray Scale for Color Change.

^B AATCC Gray Scale for Staining.

^C AATCC 9-Step Chromatic Transference Scale.

^D For durable-press fabrics only.

^E See **Note 4+10**.

ASTM D4154-22

5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the supplier, fabrics intended for this end use should meet all of the requirements listed in **Table 1** of this performance specification.

5.2 It is recognized that for purposes of fashion or aesthetics, the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in **Table 1**. Therefore, one or more of the requirements listed in **Table 1** may be modified by mutual agreement between the purchaser and the supplier.

5.2.1 In such cases, any references to the specification shall specify that: This fabric meets ASTM Specification D4154 except for the following characteristic(s).”

5.3 Where no prepurchase agreement has been reached between the purchaser and the supplier, and in case of controversy, the requirements listed in **Table 1** are intended to be used as a guide only. As noted in **5.2**, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The uses and significance of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable specification or other agreement between the purchaser and the supplier, such as an agreement to use MIL-STD-105D.

6.2 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric and at least 375 mm (15 in.) along the selvage.

7. Test Method (see Note 1)

7.1 *Breaking Force (Woven Fabric Only)*—Determine the dry breaking force, in the standard atmosphere for testing textiles, as directed in Test Method **D5034**, using a constant rate of traverse (CRT) tensile testing machine with the speed of the pulling clamp at ~~300~~300 mm ± 10 mm (~~±2~~±2(12 in. ± 0.5 in.)/min.

NOTE 2—If preferred, the use of a constant-rate-of-extension (CRE) tensile testing machine is permitted. The crosshead speed should be agreed upon between the purchaser and the supplier. There may be no overall correlation between the results obtained with the CRT machine and with the CRE machine. Consequently, these two breaking load testers should not be used interchangeably. In case of controversy the CRT method shall prevail.

7.2 *Bursting Strength (Knitted Fabric Only)*—Determine the bursting strength, in the standard atmosphere for testing textiles, as directed in Test Method **D3787** using an approved type of CRT machine equipped with a bursting attachment or Test Method **D3786** using an approved type of diaphragm bursting tester as agreed upon between the purchaser and the supplier.

NOTE 3—There is no overall correlation between the results obtained with the CRT machine equipped with a bursting attachment and the diaphragm bursting tester. Consequently, these two bursting testers cannot be used interchangeably. In case of controversy, Test Method **D3786** shall prevail.

NOTE 4—The precision of the ball burst method using the CRT machine equipped with a bursting attachment and the precision of the diaphragm bursting tester method are being established by Subcommittee D13.59. The test methods are accordingly not recommended for acceptance testing unless preceded by an interlaboratory test in the laboratory of the purchaser and the laboratory of the supplier using randomized replicate specimens of the material to be evaluated.

7.3 *Resistance to Yarn Slippage (Woven Fabric Only)*—Determine the resistance to yarn slippage as directed in Test Method **D434**.

NOTE 5—The precision of Test Method **D434** is being established, and it may not be suitable for fabrics with low yarn counts (see 5.2).

7.4 *Tear Strength (Woven Fabric Only)*—Determine the tear strength as directed in Test Method **D1424**.

NOTE 6—If preferred, use of Test Method **D2262** is permitted with existing requirements as given in this performance specification. There may be no overall correlation between the results obtained with the tongue tear machine and with the Elmendorf machine. Consequently, these two tear testers should not be used interchangeably. In case of controversy, Test Method **D1424** shall prevail.

7.5 Dimensional Change:

7.5.1 *Pressing and Curing During Manufacturing*—Mark specimen(s) as directed in 4.4 of AATCC ~~Test Method 135~~—TM 135. When appropriate press and cure specimen(s) as agreed upon between the purchaser and the supplier with respect to time cycles, temperature, steam, vacuum, and mechanical pressure of the press head. Measure the specimen(s) and calculate the dimensional change as directed in Section 6 and 7 of AATCC ~~Test Method 135~~—TM 135 (see Note 2).

7.5.1.1 If no agreement has been made between the purchaser and the supplier, press the specimen(s) using a flat-bed steam press according to the cycle in ~~40.1.4.1~~10.4.1 through ~~40.1.4.5~~10.4.5 of Test Methods **D2724**.

7.5.2 *Laundering*—Determine the maximum dimensional change after five launderings as directed in the applicable procedure in AATCC ~~Test Method 135~~—TM 135.

NOTE 7—Launderable fabrics are expected to be dry-cleanable except where all or part of the fabric is not dry-cleanable and is so labeled. For example, the fabric could contain a functional finish soluble in the solvent, or the fiber could be degraded by the solvent, which would be the case with poly(vinyl chloride) fiber. Goods labeled “dry-cleanable” are to be dry-cleaned only.

NOTE 8—Specimens prepared for 7.5.1 may be used for 7.5.2 and 7.5.3 as desired. When this is done, subtract the pressing and curing dimensional change from the total dimensional change to obtain that portion due to laundering or dry cleaning. The dimensional change to pressing and curing is determined on the fabric as it will reach the user. It is not to be added to the dimensional change due to laundering or dry cleaning of the fabric (see 6.1).

7.5.2.1 The wash conditions and drying procedure shall be as specified by the supplier.