



Designation: D2372 – 85 (Reapproved 2022)

Standard Practice for Separation of Vehicle From Solvent-Reducible Paints¹

This standard is issued under the fixed designation D2372; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This practice covers the procedure for the separation of the vehicle from the pigment in solvent-reducible paint.

1.2 In the development of the practice the following materials were tested: white soya and white fish oil isophthalic alkyd semi-gloss enamels, white linseed oil paint, white soya and white linseed *o*-phthalic alkyd enamels. It is considered to be applicable to similar materials.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D2371 Test Method for Pigment Content of Solvent-Reducible Paints

¹ This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Dec. 1, 2022. Published December 2022. Originally approved in 1965. Last previous edition approved in 2015 as D2372 – 85 (2015). DOI: 10.1520/D2372-85R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D2698 Test Method for Determination of the Pigment Content of Solvent-Reducible Paints by High-Speed Centrifuging

3. Significance and Use

3.1 Separation of the vehicle from the pigment in solvent-reducible paints is required in order to characterize paint vehicles by chemical, spectroscopic, or chromatographic techniques. Characterization of vehicles is important since they play a major role in the performance of coatings.

4. Apparatus

4.1 *Centrifuge*, high-speed, capable of developing in excess of 10 000 *g*.

NOTE 1—Calculate the gravity developed by the centrifuge as follows:

$$g = 1.118 \times 10^{-6} \times r \times n^2 \quad (1)$$

where:

r = rotating radius, mm, and

n = rotating speed, r/min.

5. Procedure

NOTE 2—If the percent of pigment is desired, see Test Method D2371 and Test Method D2698.

5.1 Mix the sample until it is homogeneous, preferably on a mechanical shaker.

5.2 Centrifuge about 20 mL of the whole paint on a high-speed centrifuge in excess of 10 000 *g* (Note 1) for 30 min or until separation is completed. If difficulty is encountered, add 10 mL of a suitable solvent (Note 3). Mix with the vehicle layer in the centrifuge tube and centrifuge as before. Pour off the supernatant liquid into a bottle and stopper under nitrogen for further use.

NOTE 3—If quantitative work must be done on the vehicle, the weight of the paint specimen and of the added solvent must be known.

6. Keywords

6.1 centrifuge; paint vehicle separation; solvent-reducible paint

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM D2372-85\(2022\)](#)

<https://standards.iteh.ai/catalog/standards/sist/def02412-b91c-4a3c-bc15-369a8a40d960/astm-d2372-852022>