

Designation: D1065 - 18 (Reapproved 2022)

Standard Test Method for Unsaponifiable Matter in Pine Chemicals, Including Rosin, Tall Oil, and Related Products¹

This standard is issued under the fixed designation D1065; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the percentage of material in pine chemicals products as defined in Terminology D804 including rosin, tall oil, and related products, other than insoluble dirt or similar visible foreign matter that does not yield a water-soluble soap when the sample is saponified with potassium hydroxide.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

Note 1—It has been reported that this method may not be applicable to gum rosin, especially any gum rosin containing volatile terpenes. Volatile terpenes are by definition unsaponifiable matter, and can be lost under the drying conditions described in 8.4. The method is applicable to tall oil rosin and wood rosin as these rosins do not contain volatile terpenes.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards:*² D509 Test Methods of Sampling and Grading Rosin

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.34 on Pine Chemicals and Hydrocarbon Resins.

Current edition approved Dec. 1, 2022. Published December 2022. Originally approved in 1949. Last previous edition approved in 2018 as D1065 – 18. DOI: 10.1520/D1065-18R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D803 Test Methods for Testing Tall Oil

- D804 Terminology Relating to Pine Chemicals, Including Tall Oil and Related Products
- E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods
- E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Significance and Use

3.1 This test method is designed to broaden the scope of the previous edition of the test method by the inclusion of tall oil and tall oil derived from products as test materials. Test Methods D803 currently includes a method for the determination of unsaponifiable matter.

3.2 The amount of unsaponifiable matter in tall oil and other related products is important in characterizing such products as it indicates the level of nonacidic material, both free and combined, present in the test material. The unsaponifiable in naval stores products is primarily composed of higher molecular weight alcohols, sterols, and hydrocarbons.

4. Apparatus 1d9677647608/astm-d1065-182022

4.1 *Erlenmeyer or Other Flat-Bottom Flask*, of 125 mL to 250 mL capacity, with standard-taper 24/40 joint.

4.2 *Erlenmeyer Flask*, of 250 mL to 300 mL capacity, with wide mouth.

4.3 *Separatory Funnels*, of 300 mL to 500 mL capacity, with glass or polytetrafluoroethylene (PFTE) stoppers.

4.4 *Graduated Cylinder*, one of 10 mL to 25 mL and one of 50 mL to 100 mL capacity.

4.5 Beaker, of up to 250 mL capacity.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled, or deionized water.

6. Preparation of Sample

6.1 Procurement and handling of samples will vary depending upon the physical state of the material. In all instances, the sampling should conform to accepted sampling techniques which ensure the sample is representative of the material being sampled.

6.2 Uniform liquid material should be mixed well and an aliquot removed for analysis. Titer in fatty acid samples should be resolubilized by gentle heating and agitation. Rosin crystallization in liquid samples, such as distilled tall oil (DTO), should be resolubilized by heating to 160 °C with periodic agitation. Homogeneous representative samples are imperative.

6.3 Solids that melt at relatively low temperature (that is, tall oil pitch) should be warmed to liquification to facilitate mixing and pouring. Homogeneous representative samples are imperative.

6.4 Solids that melt at relatively high temperatures (that is, rosin) should be fractured and chipped if possible, (see Test Methods D509). The sample taken for analysis shall consist of small pieces of rosin chipped from a freshly exposed part of a lump of lumps, and thereafter crushed to facilitate weighing and solution. The sample shall be prepared the same day on which the test is begun in order to avoid changes in properties due to surface oxidation that is very pronounced on ground rosin having a large surface area exposed to the air.

7. Reagents

7.1 Alkali (titrant), Standard Alcoholic Solution (0.1 N)— Dissolve 6.6 g KOH or 5.2 g NaOH, preferably in pellet form, in 1 L of methanol (99.5 %) or ethanol (95 %) denatured by Formula No. 3A or No. 30 of the U.S. Bureau of Internal Revenue. Standardize this solution to ± 0.001 N using potassium acid phthalate, or another accepted primary standard for alkaline titrant, according to accepted quantitative practice.

7.2 Ethyl Ether (diethyl ether).

7.3 *Isopropyl Alcohol (Isopropanol) (91 % to 99 %)*—If not neutral, make neutral to phenolphthalein by adding 0.1 *N* alkali solution dropwise.

7.4 *Phenolphthalein Solution*—Dissolve 1.0 g of phenolphthalein in 100 mL of alcohol conforming to 6.1. 7.5 Potassium Hydroxide, Ethanolic (Saponification) Solution (132 g KOH/L)—Dissolve 132 g of KOH (preferably pellets) in 150 mL of water and dilute to 1 L with ethanol (95%) denatured by Formula No. 3A or No. 30 of the U.S. Bureau of Internal Revenue.

7.6 *Thymol Blue Indicator Solution*—Dissolve 0.1 g of thymol blue in 100 mL methanol (99.5 %).

8. Procedure

8.1 Weigh 5.0 g \pm 0.1 g (to 0.01 g) of the sample into the 125-mL (250-mL) Erlenmeyer or other flat-bottom flask, using the 10-mL or 25-mL graduated cylinder add 15 mL of the *ethanolic* KOH solution (132 g KOH/L), attach to the condenser, and heat to reflux and maintain for 1.5 h. Remove the flask, add 30 mL water, transfer to a separatory funnel, and rinse the flask with an additional 20 mL of water that is added to the separatory funnel. Rinse the flask with 40 mL of ethyl ether, adding the ether rinse to the separatory funnel. Stopper and shake the separatory funnel, then allow to stand until the aqueous soap layer (lower layer) into a second separatory funnel, allowing a few drops of the aqueous layer to remain above the stopcock to prevent loss of ether extract by creepage through the stopcock joint.

8.2 To the aqueous soap layer in the second funnel, add 30 mL ether and extract as before. Drain the aqueous soap layer into the original saponification flask. Add the ether layer from the second separatory funnel to the first separatory funnel, thereby combining the extracts. Pour the aqueous soap layer from the original saponification flask into the second separatory funnel, add 30 mL ether and extract for the third time. Drain the aqueous soap layer from the second separatory funnel into the original saponification flask again, and add the ether layer to the first funnel as before, thereby combining it with the two previous extracts. Now drain off, and add to the soap solution already in the original saponification flask, all but a few drops of aqueous soap solution that has collected at the bottom of the *first* separatory funnel below the combined ether extract layers. Add 2 mL of water to the first separatory funnel and drain off all but a few drops, combining it in the saponification flask.

8.3 Again pour the combined aqueous soap layers from the original saponification flask into the second separatory funnel, add 30 mL ether, and extract for the fourth time. After separation of the layers, discard the aqueous soap layer (lower layer) from the second separatory funnel and add the ether layer to the combined ether extracts in the first separatory funnel. Carefully drain off any remaining aqueous soap layer that may have collected above the stopcock under the ether extracts in the first separatory funnel. Add 2 mL of water, swirl the separatory funnel gently, allow the water to settle, and then drain off and discard the water layer (lower). Repeat this washing once with 5 mL of water, followed by three washes with 30 mL of water. Drain a portion of the third 30-mL water wash into a beaker, add 2 drops of phenolphthalein solution, and examine for any pink color. If pink color is observed, wash once more with 30-mL water. The absence of pink color indicates the wash is neutral to phenolphthalein.

³ ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Analar Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.