



Designation: D3163 – 01 (Reapproved 2023)

# Standard Test Method for Determining Strength of Adhesively Bonded Rigid Plastic Lap-Shear Joints in Shear by Tension Loading<sup>1</sup>

This standard is issued under the fixed designation D3163; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method is intended to complement Test Method D1002 and extend its application to single-lap shear adhesive joints of rigid plastic adherends. The test method is useful for generating comparative shear strength data for joints made from a number of plastics. It can also provide a means by which several plastic surface treatments can be compared.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D907 Terminology of Adhesives

D1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal)

D2093 Practice for Preparation of Surfaces of Plastics Prior to Adhesive Bonding

D4896 Guide for Use of Adhesive-Bonded Single Lap-Joint Specimen Test Results

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.40 on Adhesives for Plastics.

Current edition approved Jan. 1, 2023. Published January 2023. Originally approved in 1973. Last previous edition approved in 2014 as D3163 – 01 (2014). DOI: 10.1520/D3163-01R23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 *Definitions*—Many of the terms used in this test method are defined in Terminology D907.

## 4. Significance and Use

4.1 Due to the increased use of adhesive-bonded plastics as a result of the inherent advantages afforded by bonded rather than mechanically fastened joints, particularly the alleviation of stress raisers and stress cracking, there is a need for standard tests by which joints of various plastic substrates and adhesives can be compared. This test method is intended to meet such a need.

4.2 This test method is limited to test temperatures below the softening point of the subject adherends, and is not intended for use on anisotropic adherends such as reinforced plastic laminates.

4.3 The misuse of strength values obtained from this test method as allowable design-stress values for structural joints could lead to product failure, property damage, and human injury. The apparent shear strength of an adhesive obtained from a given small single-lap specimen may differ from that obtained from a joint made with different adherends or by a different bonding process. The normal variation of temperature and moisture in the service environment causes the adherends and the adhesive to swell and shrink. The adherends and adhesive are likely to have different thermal and moisture coefficients of expansion. Even in small specimens, short-term environmental changes can induce internal stresses or chemical changes in the adhesive that permanently affect the apparent strength and other mechanical properties of the adhesive. The problem of predicting joint behavior in a changing environment is even more difficult if a different type of adherend is used in a larger structural joint than was used in the small specimen.

4.3.1 The apparent shear strength measured with a single-lap specimen is not suitable for determining allowable design stresses for designing structural joints that differ in any manner from the joints tested without thorough analysis and understanding of the joint and adhesive behaviors.

4.3.2 Single-lap tests may be used for comparing and selecting adhesives or bonding processes for susceptibility to fatigue and environmental changes, but such comparisons must

be made with great caution since different adhesives may respond differently in different joints. See Guide D4896 for further discussion of the concepts relative to interpretation of adhesive bonded single-lap joints.

**5. Apparatus**

5.1 *Testing Machine*, conforming to the requirements of and having the capabilities of the machine prescribed in Test Method D1002. The grips are self-aligning and capable of securely grasping the specimen throughout the test, without allowing the specimen to slip.

5.2 *Temperature-Controlling Equipment*, capable of maintaining the test temperature to  $\pm 3\text{ }^\circ\text{C}$  ( $\pm 5\text{ }^\circ\text{F}$ ). If ambient laboratory conditions are employed the same degree of control is required.

**6. Test Specimen**

6.1 Make specimens that conform to the form and dimensions set forth in Test Method D1002 where possible. However, due to the low yield points in plastics compared with those of metals, it may not always be feasible to limit test specimen geometry to that called for in Test Method D1002. Therefore adherend thicknesses and joint overlaps must be chosen so that failure occurs preferentially in the joint and not in the substrate. Thicker adherends allow the stress on the bonded area to be increased, before either tensile failure or yield occurs in the

adherend. Recognize, however, that depending on the surface treatment and adhesive used, the bond strength may often be greater than the tensile yield strength of the adherend. Use data collected by this test method only for comparative purposes when the investigator is certain that the specimen configurations and joint geometries of the specimens being compared are identical.

6.2 The surface preparation used on the adherend depends on the subject plastic adherend. Procedures such as those recommended in Practice D2093 serve as a useful guide.

6.3 Apply the adhesives in accordance with the manufacturer’s recommendations. Choose adhesives such that the cure temperature does not adversely affect the mechanical properties of the adherends.

6.4 Cut test specimens from the bonded panels pictured in Fig. 1. Cut the specimens without overheating or otherwise physically damaging the adherend or bonded interface. Individual specimens may also be prepared if desired.

**7. Procedure**

7.1 Place the specimens in the grips of the testing machine so that the applied load coincides with the long axis of the test specimen. Load the specimen to failure at a rate of 8.3 MPa to 9.7 MPa (1200 psi to 1400 psi) of shear area per minute (approximately 0.05 in./min cross head speed).




FIG. 1 Standard Test Panel and Specimen Configuration