



Designation: G110 – 92 (Reapproved 2022)<sup>ε2</sup>

# Standard Practice for Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminum Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution<sup>1</sup>

This standard is issued under the fixed designation G110; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Replaced Terminology G15 with Terminology G193, and other editorial changes made throughout in Dec. 2022.

<sup>ε2</sup> NOTE—Footnote 1 and the <sup>ε1</sup> NOTE were corrected editorially in January 2023.

## 1. Scope

1.1 This practice covers the procedures for immersion tests in sodium chloride + hydrogen peroxide solution. It is primarily for tests of wrought heat treatable aluminum alloys (2XXX and 7XXX) but may be used for other aluminum alloys, including castings. It sets forth the specimen preparation procedures and the environmental conditions of the test and the means for controlling them.

1.2 This practice is intended for evaluations during alloy development and for evaluating production where it may serve as a control test on the quality of successive lots of the same material (see MIL-H-6088 and U.S. Federal Test Method Std. 151b). Therefore strict test conditions are stipulated for maximum assurance that variations in results are attributable to lot-to-lot differences in the material being tested.

NOTE 1—This practice does not address sampling or interpretation or significance of results.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee G01 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.05 on Laboratory Corrosion Tests.

Current edition approved Dec. 1, 2022. Published January 2023. Originally approved in 1992. Last previous edition approved in 2015 as G110–92 (2015). DOI: 10.1520/G0110-92R22E02.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D1193 Specification for Reagent Water

E3 Guide for Preparation of Metallographic Specimens

E407 Practice for Microetching Metals and Alloys

G1 Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens

G67 Test Method for Determining the Susceptibility to Intergranular Corrosion of 5XXX Series Aluminum Alloys by Mass Loss After Exposure to Nitric Acid (NAMLT Test)

G69 Test Method for Measurement of Corrosion Potentials of Aluminum Alloys

G193 Terminology and Acronyms Relating to Corrosion

### 2.2 Other Documents:<sup>3</sup>

U.S. Military Specification MIL-H-6088 Heat Treatment of Aluminum Alloys

U.S. Federal Test Method, Std. No. 151b Method 822.1, Intergranular Corrosion Test for Aluminum Alloys

## 3. Summary of Practice

3.1 This practice consists of immersing etched test specimens in a sodium chloride + hydrogen peroxide solution for 6 or more hours. After immersion, metallographic sections are examined to determine the extent of intergranular corrosion (see Terminology G193).

## 4. Significance and Use

4.1 This practice is especially useful for evaluating the adequacy of quenching when performed on material in the as-quenched condition. The practice may also be used to study the effect of subsequent thermal processes (for example, paint

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, http://quicksearch.dla.mil.

or bonding cures) or of actual precipitation treatments on the inherent type of corrosion. Intergranular corrosion resistance of heat treatable aluminum alloys is often directly related to the quenching conditions applied after solution heat treatment and to the subsequent aging treatment.<sup>4</sup>

4.2 This practice is not well suited for non-heat treatable work hardening aluminum alloys, such as the 1XXX, 3XXX, and 5XXX series (see Test Method G67).

4.3 This practice does not deal with the interpretation of resulting intergranular corrosion. The significance of the extent and depth of any intergranular corrosion resulting from this test is to be agreed upon between producer and user.

## 5. Reagents

5.1 Reagent grade chemicals [sodium chloride (NaCl), 70 % nitric acid (HNO<sub>3</sub>), 48 % hydrofluoric acid (HF), 37 % hydrochloric acid (HCl), and 30 % hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>)] shall be used for preparation of all solutions.

5.2 The solutions shall be prepared using distilled or deionized water conforming to the purity requirements for Specification D1193, Type IV reagent water.

## 6. Solutions

6.1 Etching cleaner shall be prepared as follows: To 945 mL of reagent water add 50 mL of nitric acid (70 %) + 5 mL of hydrofluoric acid (48 %). (See 6.2).

6.2 Test solution shall be prepared as follows: 57 grams of sodium chloride + 10 mL of hydrogen peroxide (30 %—add just prior to initiation of exposure) diluted to 1.0 L with reagent water. (**Warning**—Care should be exercised in handling and mixing strong acids to avoid personal injury and damage to apparatus. Care should include use of personal protective equipment and use of appropriate apparatus and procedures for particular acids.)

NOTE 2—The concentration of the 30 % hydrogen peroxide may degrade; therefore, it should be verified before each use by the procedure stated in Test Method G69.

6.3 Metallographic etchant (Keller's etch) shall be prepared as follows: To 95 mL of reagent water add 2.5 mL of nitric acid (70 %) + 1.5 mL of hydrochloric acid (37 %) + 1.0 mL of hydrofluoric acid (48 %). A number of other etchants may be used, depending on the alloy and temper being examined (see Practice E407) (see 6.2).

## 7. Specimen Preparation

7.1 Place an identification mark on each specimen in an area that will not be subject to metallographic examination.

7.2 The entire surface of the specimen must be free of all foreign matter, including cladding, coatings, dirt, oils, and other residues.

7.3 Claddings (especially alcladding) shall be removed either mechanically or chemically to a depth of at least twice the nominal cladding thickness. Chemical removal can be accomplished by immersion in a 5 % sodium hydroxide solution at 140 °F followed by immersion for 1 min in concentrated nitric acid. Examine typical specimen cross sections to be certain that cladding has been removed.

7.4 Organic materials, such as coatings, soil, oils, and other residues, should be removed with organic solvents, for example, acetone (see Practice G1).

7.5 Prior to immersion in the test solution, immerse each specimen for 1 min in the etching cleaner (see 6.1) at 93 °C. Rinse in reagent water. Immerse in concentrated nitric acid (70 %) for 1 min. Rinse in reagent water and air dry.

## 8. Test Setup

8.1 The test vessel should be of nonmetallic material of sufficient size to hold at least 5 mL of test solution per square cm of specimen surface area.

8.2 More than one specimen may be placed in a test vessel, provided specimens do not contact each other and provided condition outlined in 8.1 is observed.

8.3 Specimens shall be prevented from contacting the bottom of the test vessel by placing the specimens on glass rods or rubber stoppers. (Rubber stoppers may be deteriorated by hydrogen peroxide.)

8.4 The exposure shall be conducted at a temperature of 30 °C ± 3 °C.

## 9. Procedure

9.1 Immerse the etched specimens in the test solution for a period of at least 6 h. Longer exposure periods of 24 h or more may be used by agreement, especially in the case of corrosion resistant alloys and tempers (for example, 6XXX alloys). Shorter exposure periods of less than 6 h may be appropriate for very thin sheet.

9.2 After exposure, rinse each specimen with reagent water and allow to dry.

9.3 Examination of specimens.

9.3.1 Examine each exposed specimen at a magnification of 10 times or less to locate areas of corrosion attack.

9.3.2 Prepare at least one metallographic cross section approximately 20 mm in length from each specimen, preferably through a corroded area identified in 9.3.1. Prepare each section by mounting and metallographically polishing (see Guide E3).

9.3.3 Examine the unetched polished surface with a metallograph at magnifications of 100 times to 500 times. If there is uncertainty as to the presence of intergranular corrosion, etch the polished surface to reveal the grain structure by immersion in the metallographic etchant solution for 6 s to 20 s, rinse, dry, and reexamine at 500 times.

9.4 Compare or document the type, extent, and depth of intergranular corrosion in accordance with criteria established between producer and purchaser.

<sup>4</sup> Lifka, B. W., and Sprowls, D. O., "Significance of Intergranular Corrosion of High Strength Aluminum Alloy Products," *Localized Corrosion Cause of Metal Failure*, ASTM STP 516, 1972, pp. 120–144.