



Designation: **D922—18** **D922 – 23**

Standard Specification for Nonrigid Vinyl Chloride Polymer Tubing¹

This standard is issued under the fixed designation D922; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers nonrigid tubing of vinyl chloride polymer or its copolymers with other materials for use in electrical insulation in three grades, as follows:

1.1.1 *Grade A*—General-purpose.

1.1.2 *Grade B*—Low-temperature.

1.1.3 *Grade C*—High-temperature.

1.2 This standard and IEC-60684-3-100 to -105 address the same subject matter but differ in technical content.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

~~1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.~~

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.5 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards*:²

[D876 Test Methods for Nonrigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation](#)

[D1711 Terminology Relating to Electrical Insulation](#)

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Electrical Insulating Materials.

Current edition approved May 1, 2018; Feb. 1, 2023. Published May 2018; February 2023. Originally approved in 1947. Last previous edition approved in 2014 as D922—14; D922 – 18. DOI: 10.1520/D0922-18-10.1520/D0922-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

D3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials
 E176 Terminology of Fire Standards

2.2 IEC Standards:

IEC-60684-3-100 to -105 Flexible insulating sleeving, Part 3, Sheets 100 to 105: Extruded PVC sleeving³

3. Terminology

3.1 Definitions:

3.1.1 For definitions pertaining to electrical insulation, refer to Terminology **D1711**.

3.1.2 For definitions pertaining to fire standards, refer to Terminology **E176**.

4. Ordering Information

4.1 Orders for material covered by this specification shall include the following:

4.1.1 Grade of tubing,

4.1.2 Size and color,

4.1.3 Total length in feet [or ~~metres~~;meters],

4.1.4 Length of cut pieces in inches [or ~~centimetres~~;centimeters], if any, and

4.1.5 Amount of tubing on each spool or in each coil, if not standard packaging with the supplier.

5. Color

5.1 Clear transparent, black, white, yellow, green, blue, and red shall be considered standard colors. Other colors shall be considered special. The color desired shall be specified in the purchase order.

5.2 Conditioning:

5.2.1 Unless otherwise specified, all testing for this standard shall be conducted at $23 \pm 5^\circ\text{C}$ ($73 \pm 9^\circ\text{F}$) $23 \pm 5^\circ\text{C}$ ($73 \pm 9^\circ\text{F}$) and a relative humidity of $50\% \pm 10\%$ RH. All samples shall be preconditioned at $23 \pm 5^\circ\text{C}$ ($73 \pm 9^\circ\text{F}$) $23 \pm 5^\circ\text{C}$ ($73 \pm 9^\circ\text{F}$) and a relative humidity of $50\% \pm 10\%$ RH for a minimum of 30 minutes prior to test.

6. Dimensional Requirements

6.1 *Inside Diameter*—The inside diameter of the tubing shall conform to the requirements prescribed in **Table 1** or **Table 2**.

6.2 *Wall Thickness*—The wall thickness of the tubing shall conform to the requirements prescribed in **Table 1** or **Table 2**.

6.3 *Commercial Lengths*—The tubing shall be supplied in continuous lengths.

7. Workmanship, Finish, and Appearance

7.1 The surface shall be smooth, free of blisters, cracks, or any other defects that have the potential to detrimentally affect its suitability for the service intended. It shall not be subject to peeling, scaling, or flaking.

8. Physical and Electrical Requirements

8.1 Tubing shall conform to the following requirements for physical and electrical properties, enumerated below, using the tests contained in Test Methods **D876**:

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

8.1.1 *Flammability*—The average duration of burning shall not exceed 15 s and the paper indicator shall show no evidence of being affected.

8.1.2 *Tensile Strength*—The average tensile strength shall be not less than 2000 psi [15 MPa] for Grades A and C, and not less than 1800 psi [13 MPa] for Grade B. The average ultimate elongation shall be not less than 200 % for Grades A and C and not less than 250 % for Grade B.

8.1.3 *Effect of Elevated Temperatures*—When Method A is used, the average loss of ultimate elongation after exposure to elevated temperatures shall be not greater than 35 % for Grades A, B, and C. When Method B is used, the loss of weight after exposure to elevated temperatures shall be not greater than 15 % of the original weight for Grades A and B, and not greater than 10 % for Grade C.

8.1.4 After immersion in oil, the average ultimate elongation shall be within the following limits based on the average test value for the un-immersed tubing:

Grades A and B	+ 5 % to – 20 %
Grade C	± 20 %

8.1.5 *Brittleness Temperature*—The brittleness temperature shall be not above -30°C [-22°F]- 30°C [-22°F] for Grade A, -55°C [-67°F]- 55°C [-67°F] for Grade B, and -10°C [$+14^{\circ}\text{F}$]- 10°C [$+14^{\circ}\text{F}$] for Grade C.

8.1.6 *Resistance to Penetration at Elevated Temperature*—The average temperature of failure shall be not less than those in [Table 3](#).

8.1.7 *Volume Resistivity*—The volume resistivity shall be not less than 10^{12} Ω·cm for Grades A and C and not less than 10^{11} Ω·cm for Grade B.

8.1.8 *Dielectric Breakdown*—The average dielectric breakdown shall be not less than that prescribed for the corresponding wall thickness in [Table 4](#).

8.1.9 *Dielectric Breakdown at High Humidity*—The average dielectric breakdown strength at 96 % relative humidity shall be not less than 90 % for Grade A, 75 % for Grade B, and 85 % for Grade C of the dry value, obtained on test.

TABLE 2 Metric Dimensional Tolerances of Tubing^a

Specified Size	Inside Diameter, mm		Thin Wall		Standard Wall		Thick Wall	
	max	min	Wall Thickness, mm	Tolerances, ± mm	Wall Thickness, mm	Tolerances, ± mm	Wall Thickness, mm	Tolerances, ± mm
0.3	0.4	0.2	0.3	0.1	0.4	0.1	0.5	0.1
0.5	0.6	0.4	0.3	0.1	0.4	0.1	0.5	0.1
0.8	0.9	0.7	0.3	0.1	0.4	0.1	0.5	0.1
1.0	1.15	0.85	0.3	0.1	0.4	0.1	0.5	0.1
1.5	1.65	1.35	0.3	0.1	0.4	0.1	0.5	0.1
2.0	2.15	1.85	0.3	0.1	0.4	0.1	0.5	0.1
2.5	2.65	2.35	0.3	0.1	0.4	0.1	0.5	0.1
3	3.15	2.85	0.3	0.1	0.4	0.1	0.5	0.1
4	4.25	3.75	0.3	0.1	0.5	0.1	0.6	0.1
5	5.25	4.75	0.3	0.1	0.5	0.1	0.6	0.1
6	6.25	5.75	0.3	0.1	0.5	0.1	0.6	0.1
8	8.25	7.75	0.5	0.1	0.7	0.1	0.8	0.15
10	10.5	9.5	0.5	0.1	0.7	0.1	0.8	0.15
12	12.5	11.5	0.5	0.1	0.7	0.1	0.8	0.15
16	16.5	15.5	0.5	0.1	0.85	0.15	1.2	0.2
20	20.5	19.5	0.5	0.1	0.85	0.15	1.2	0.2
25	25.5	24.5	0.5	0.1	0.85	0.15	1.2	0.2
30	30.5	29.5	0.5	0.1	0.85	0.15	1.2	0.2
40	41	39	0.5	0.1	0.85	0.15	1.35	0.15
50	51	49	0.5	0.1	0.85	0.15	1.55	0.25

^a For tubing sizes not listed in this table, the wall thickness of the nearest larger diameter shall apply.

TABLE 1 Dimensional Tolerances of Tubing^{A,B}

Specified Size	Inside Diameter, in.		Wall Thickness	
	max	min	Wall Thick-ness, in.	Tolerances, plus or minus, in.
No. 24 [0.022 in.]	0.027	0.020	0.012	0.002
No. 22 [0.027 in.]	0.032	0.025	0.012	0.002
No. 20 [0.034 in.]	0.039	0.032	0.016	0.003
No. 18 [0.042 in.]	0.049	0.040	0.016	0.003
No. 16 [0.053 in.]	0.061	0.051	0.016	0.003
No. 14 [0.066 in.]	0.074	0.064	0.016	0.003
No. 12 [0.085 in.]	0.091	0.081	0.016	0.003
No. 11 [0.095 in.]	0.101	0.091	0.016	0.003
No. 10 [0.106 in.]	0.112	0.102	0.016	0.003
No. 9 [0.118 in.]	0.124	0.114	0.020	0.003
No. 8 [0.133 in.]	0.141	0.129	0.020	0.003
No. 7 [0.148 in.]	0.158	0.144	0.020	0.003
No. 6 [0.166 in.]	0.178	0.162	0.020	0.003
No. 5 [0.186 in.]	0.198	0.182	0.020	0.003
No. 4 [0.208 in.]	0.224	0.204	0.020	0.003
No. 3 [0.234 in.]	0.249	0.229	0.020	0.003
No. 2 [0.263 in.]	0.278	0.258	0.020	0.003
No. 1 [0.294 in.]	0.311	0.289	0.020	0.003
No. 0 [0.330 in.]	0.347	0.325	0.020	0.003
5/16 in.	0.334	0.312	0.025	0.003
3/8 in.	0.399	0.375	0.025	0.003
7/16 in.	0.462	0.438	0.025	0.003
1/2 in.	0.524	0.500	0.025	0.003
5/8 in.	0.655	0.625	0.030	0.003
3/4 in.	0.786	0.750	0.035	0.005
7/8 in.	0.911	0.875	0.035	0.005
1 in.	1.036	1.000	0.035	0.005
1 1/4 in.	1.290	1.250	0.040	0.005
1 1/2 in.	1.550	1.500	0.045	0.006
1 3/4 in.	1.812	1.750	0.055	0.008
2 in.	2.070	2.000	0.060	0.010

^A Multiply inches by 25.4 to get millimetres—millimeters.

^B For tubing sizes not listed in this table, the wall thickness of the nearest larger diameter shall apply.

<https://standards.iteh.ai/catalog/standards/sist/42e1acc4-6550-4453-ab08-93d4396b1f84/astm-d922-23>

TABLE 3 Average Temperature of Failure

Grade	Nominal Wall Thickness, in. (mm)	Temperature, °C, min
A	all sizes	75
B	all sizes	80
C	0.016 and 0.020 (0.406 and 0.508)	70
	0.025, 0.030 and 0.035 (0.635, 0.762, and 0.889)	75
	0.040, 0.045, 0.055 and 0.060 (1.016, 1.143, 1.397, and 1.524)	85

8.1.10 *Strain Relief*—The change in length (shrinkage) shall not exceed 18 % for sizes AWG No. 24 to No. 20, inclusive; 14 % for sizes AWG No. 18 to 10, inclusive; and 9 % for sizes AWG No. 9 to 2 in. [50 mm], inclusive.

8.1.11 *Corrosive Effect*—The resistance of the copper wire shall increase by not more than 2 %.

9. Sampling

9.1 For dimensional and visual tests, lots shall be sampled in accordance with Inspection Level II of Practice **D3636**.