



Designation: F1613 – 95 (Reapproved 2023)

Standard Specification for Surgical Tissue/Dressing/Pick-Up Forceps (Thumb Type)¹

This standard is issued under the fixed designation F1613; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers general workmanship aspects of spring-action, tissue, dressing, or pick-up forceps (thumb-type) intended for the retraction, grasping, or dissection of tissue during surgical procedures.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E18 Test Methods for Rockwell Hardness of Metallic Materials

E92 Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials

E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

F899 Specification for Wrought Stainless Steels for Surgical Instruments

F921 Terminology Relating to Hemostatic Forceps

F1026 Specification for General Workmanship and Performance Measurements of Hemostatic Forceps

F1089 Test Method for Corrosion of Surgical Instruments

F1638 Terminology for Surgical Tissue/Dressing/Pick-Up Forceps (Thumb-Type)

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.33 on Medical/Surgical Instruments.

Current edition approved Feb. 1, 2023. Published February 2023. Originally approved in 1995. Last previous edition approved in 2016 as F1613 – 95 (2016). DOI: 10.1520/F1613-95R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *Definitions:*

3.1.1 Definitions shall be in accordance with Terminology F1638.

3.1.2 *modified working ends*—working surfaces possessing superior hardness characteristics that are the result of either depositing various materials on the base metal or securing an insert permanently (such as by brazing) to the base metal (see Note 3).

4. Material

4.1 All component parts of the instrument shall be fabricated from Class 4 martensitic stainless steel in accordance with Specification F899. The modified working ends may be of stellite, tungsten carbide, or other suitable material.

5. Requirements

5.1 *Heat Treatment and Hardness for Component Parts:*

5.1.1 The stainless steel component parts shall be heat treated under conditions recommended for the material used.

5.1.2 The Rockwell hardness (HRC) of the instrument with the working end not modified shall be 40 to 49 HRC (see Test Methods E18) after appropriate processing. Instruments in which the working end has been modified shall have an HRC of A77.

5.2 *Corrosion Resistance*—Instruments shall be subjected to corrosion tests as specified in Test Method F1089.

5.3 *Finish:*

5.3.1 *Surfaces*—Surfaces of the instruments shall be uniformly finished and free of burrs, sharp edges, cracks, coarse marks, and processing materials.

5.3.2 *Type*—The finish shall be one of the types specified in Terminology F921 or as specified by the purchaser.

5.4 *Workmanship:*

5.4.1 *Symmetry*—Excluding functional differences, both forceps halves shall be symmetrical.

5.4.2 *Teeth*—Teeth shall be well formed, uniform in depth and spacing, and mesh without binding, unless designed otherwise.

5.4.3 *Handle Serrations*—Handle serrations shall be uniform in depth and spacing.

5.5 *Guide Pin and Guide Pin Hole:*

5.5.1 The guide pin shall pass through the guide pin hole without binding.

5.5.2 The guide pin length shall not protrude past the outside surface of the guide pin hole when the forceps' tips come in contact.

NOTE 1—Guide pin/guide pin holes are generally used on forceps 7½ in. (191 mm) or longer.

6. Performance

6.1 *Alignment*—Scissoring shall be 0.015 in. (0.38 mm) or less upon closure.

7. Marking and Labeling

7.1 All marking and labeling shall be legible.

7.2 The instruments shall bear the following: (1) the manufacturer's (or contractor's) name or registered trademark; (2) the country of origin (when the instrument is not manufactured in the United States); and (3) other markings, as required, by the purchaser or the manufacturer (contractor).

7.3 The marking shall be located on a suitable surface of the instrument.

NOTE 2—This specification is not intended to cover delicate tissue forceps such as those used in microsurgery or neurosurgery.

NOTE 3—Typical methods of modifying the working end of the forceps is to use jaw inserts or to plasma deposit (flame plate) materials with improved wear characteristics such as tungsten carbide or stellite. For the jaw insert methods, the insert is brazed to the jaw face with a uniform deposit of silver solder that is free of crevices at all interfaces. For the flame plating method, a uniform layer of material that is 0.004 ± 0.001 in. (0.1 ± 0.03 mm) thick is deposited.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

[\(https://standards.iteh.ai/\)](https://standards.iteh.ai/)
Document Preview

[ASTM F1613-95\(2023\)](#)

<https://standards.iteh.ai/catalog/standards/sist/85813008-c5ff-4a0f-a9b-86e5d7a6bf60/astm-f1613-952023>