



Designation: D6491 – 09 (Reapproved 2023)

# Standard Practice for Evaluation of Aging Resistance of Prestressed Prepainted Metal In a Dry Heat Test<sup>1</sup>

This standard is issued under the fixed designation D6491; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice can be used to evaluate the resistance of a prestressed prepainted metal panel to cracking, or loss of adhesion, or both, after accelerated heat aging. Most coil coated products are formed and bent into specific shapes to produce a final product. These operations introduce stresses, which may be relieved by cracking of the coating after aging.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D4145 Test Method for Coating Flexibility of Prepainted Sheet**

## 3. Apparatus

3.1 *Gravity or Forced Air Laboratory Oven*, capable of maintaining a temperature of  $60\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$  ( $140\text{ }^{\circ}\text{F} \pm 5\text{ }^{\circ}\text{F}$ ).

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.53 on Coil Coated Metal.

Current edition approved March 1, 2023. Published March 2023. Originally approved in 1999. Last previous edition approved in 2016 as D6491 – 09 (2016). DOI: 10.1520/D6491-09R23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 *Bench Vise*, with smooth jaws or inserts, 130 mm (5 in.) permanently mounted on a work table or bench, or alternative equipment capable of making the appropriate bends.

3.3 *Bending Dies or Test Shims*, (optional).

3.4 *10X magnifier*, (optional).

3.5 *Adhesive Tape*.

## 4. Test Specimens

4.1 Cut samples 75 mm (3 in.) wide (across the bend direction) by whatever length is necessary to make the appropriate number of bends. The direction of the bend may be transverse or longitudinal to the “rolling direction” of the metal—or as agreed upon between customer and vendor.

## 5. Procedure

5.1 Perform the fabrication at room temperature,  $25\text{ }^{\circ}\text{C} \pm 1\text{ }^{\circ}\text{C}$  ( $77\text{ }^{\circ}\text{F} \pm 2\text{ }^{\circ}\text{F}$ ). All test specimens should be equilibrated to the same temperature before fabricating. Different fabrication temperatures may be used, when needed, to meet customer or vendor requirements, or both.

5.2 Prepare three “T-bend” test specimens in accordance with Test Method D4145. The T-bend used should be agreed upon between customer and vendor.

5.3 Examine the T-bend for cracking and tape pick-off in accordance with Test Method D4145 and record the results.

5.4 Place the formed test specimens in the  $60\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$  ( $140\text{ }^{\circ}\text{F} \pm 5\text{ }^{\circ}\text{F}$ ) oven for 16 h. Different times and temperatures may be used if agreed upon between the customer and vendor.

5.5 Remove the test specimens and allow them to cool to room temperature.

5.6 Repeat the tape adhesion test.

## 6. Report

6.1 Report the following information:

6.1.1 Reexamine the test specimens for cracking and tape pick-off.

6.2 The degree of cracking and tape pick-off allowed should be agreed upon between the customer and the vendor. Report

substrate, coating system, production or preparation date, the tape used, cracking and tape pick-off noted before heat aging, the heat aging time and temperature and cracking, and tape pick-off noted after heat aging.

## 7. Keywords

7.1 aging; coil; cracking; dry heat; fabrication; flexibility; heat aging; prepaint; pick-off; stresses; t-bend

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*

# iTeh Standards (<https://standards.itih.ai>) Document Preview

[ASTM D6491-09\(2023\)](#)

<https://standards.itih.ai/catalog/standards/sist/f0392963-5b70-420a-b7af-4ef00fea6d46/astm-d6491-092023>