



Designation: E6 – 23a

Standard Terminology Relating to Methods of Mechanical Testing¹

This standard is issued under the fixed designation E6; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This terminology covers the principal terms relating to methods of mechanical testing of solids. The general definitions are restricted and interpreted, when necessary, to make them particularly applicable and practicable for use in standards requiring or relating to mechanical tests. These definitions are published to encourage uniformity of terminology in product specifications.

1.2 Terms relating to fatigue and fracture testing are defined in Terminology [E1823](#).

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

[E74 Practices for Calibration and Verification for Force-Measuring Instruments](#)

[E796 Test Method for Ductility Testing of Metallic Foil \(Withdrawn 2009\)](#)³

[E1823 Terminology Relating to Fatigue and Fracture Testing](#)

¹ This terminology is under the jurisdiction of ASTM Committee [E28](#) on Mechanical Testing and is the direct responsibility of Subcommittee [E28.91](#) on Terminology except where designated otherwise. A subcommittee designation in parentheses following a definition indicates the subcommittee with responsibility for that definition.

Current edition approved Feb. 1, 2023. Published March 2023. Originally approved in 1923. Last previous edition approved in 2023 as E6 – 23. DOI: 10.1520/E0006-23A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 *BIPM Standard:*⁴

[JCGM 200 : International vocabulary of metrology — Basic and general concepts and associated terms \(VIM\)](#).

3. Index of Cross-References and Associated Definitions

3.1 The terms listed below are associated with terminology that is fundamental or commonly used. The definition for the term of interest is related to or is given below the definition for the fundamental term cited.

Term	
angular strain	indexed under strain
axial strain	indexed under strain
bending strain	indexed under strain
chord modulus	see modulus of elasticity
direct verification	indexed under verification
compressive stress	indexed under stress
elastic constants	see modulus of elasticity and Poisson's ratio
elastic modulus	use modulus of elasticity
elastic true strain	indexed under strain
engineering strain	indexed under strain
engineering stress	indexed under stress
fracture stress	indexed under stress
indirect verification	indexed under verification
initial tangent modulus	see modulus of elasticity
instantaneous strain	see initial strain
linear (tensile or compressive) strain	indexed under strain
load	use force
malleability	see ductility
modulus of rigidity	see shear modulus
movable Brinell hardness testing machine	indexed under Brinell hardness testing machine
movable Rockwell hardness testing machine	indexed under Rockwell hardness machine
nominal stress	indexed under stress
normal stress	indexed under stress
permanent set	see set
physical properties	see mechanical properties
plastic true strain	indexed under strain
portable Brinell hardness testing machine	indexed under Brinell hardness testing machine
portable Rockwell hardness testing machine	indexed under Rockwell hardness machine
principal stress (normal)	indexed under stress

⁴ Available from BIPM - Pavillon de Breteuil F-92312 Sèvres Cedex FRANCE. this document is available free-of-charge at <https://www.bipm.org/en/publications/guides/vim.html>

residual strain indexed under **strain**
 residual stress indexed under **stress**
 Rockwell hardness standardizing machine indexed under **Rockwell hardness machine**
 Rockwell hardness testing machine see **Rockwell hardness machine**

Rockwell superficial hardness number see also **Rockwell hardness number**
 secant modulus see **modulus of elasticity**
 shear strain indexed under **strain**
 shear stress indexed under **stress**
 static fatigue strength see **creep rupture strength**
 stress-rupture strength see **creep rupture strength**
 tangent modulus see **modulus of elasticity**
 tensile stress indexed under **stress**
 torsional modulus see **shear modulus**
 torsional stress indexed under **stress**
 transverse strain indexed under **strain**
 true strain indexed under **strain**
 true stress indexed under **stress**
 Type 1 extensometer system indexed under **extensometer**
 Type 2 extensometer system indexed under **extensometer**
 Type 3 extensometer system indexed under **extensometer**
 ultimate tensile strength (UTS) use **tensile strength**
 yield point use **upper yield strength**
 yield strength see also **upper yield strength** and **lower yield strength**

bend test, *n*—a test for ductility performed by bending or folding a specimen, usually by steadily applied forces but in some instances by blows.

DISCUSSION—The bending may be interrupted to examine the bent surface for cracks.

DISCUSSION—The ductility is usually judged by whether or not the specimen cracks under the specified conditions of the test.

DISCUSSION—There are four general types of bend tests according to the manner in which the forces are applied to the specimen to make the bend. These are as follows:

1. Free Bend
2. Guided Bend
3. Semi-Guided Bend
4. Wrap-Around Bend

DISCUSSION—The specimen has a substantially uniform cross-section and a length several times as great as the largest dimension of the cross-section. **(E28.02)**

biaxial stretching, *n*—a mode of sheet metal forming in which positive strains are observed in all directions at a given location. **(E28.02)**

breaking force [F], *n*—the force at which fracture occurs.

DISCUSSION—When used in connection with tension tests of thin materials or materials of small diameter for which it is often difficult to distinguish between the breaking force and the maximum force developed, the latter is considered to be the breaking force. **(E28.04)**

Brinell hardness number, *n*—a number, which is proportional to the quotient obtained by dividing the test force by the curved surface area of the indentation which is assumed to be spherical and of the diameter of the ball. **(E28.06)**

Brinell hardness scale, *n*—a designation that identifies the specific combination of ball diameter and applied force used to perform the Brinell hardness test. **(E28.06)**

Brinell hardness standardizing machine—a Brinell hardness machine used for the standardization of Brinell hardness test blocks. The standardizing machine differs from a regular Brinell hardness testing machine by having tighter tolerances on certain parameters. **(E28.06)**

Brinell hardness test, *n*—an indentation hardness test using a verified machine to force an indenter (tungsten carbide ball with diameter *D*), under specified conditions, into the surface of the material under test.

DISCUSSION—The diameter of the resulting indentation *d* is measured after removal of the force. **(E28.06)**

Brinell hardness testing machine—a Brinell hardness machine used for general testing purposes. **(E28.06)**

movable Brinell hardness testing machine—a Brinell hardness testing machine that is designed to be moved to different locations on a moveable frame, table or similar support that is integral to the testing machine (for example, securely fixed to a rolling table), or a Brinell hardness testing machine that is designed to move into the testing position prior to a test, (for example, securely fixed to a moving support arm), and has been previously verified to ensure that such moves will not affect the hardness result.

4. Terminology

4.1 Terms and Definitions:

absorbed energy [FL], *n*—work spent to fracture a specimen in a single pendulum swing, as measured by a compensated indicating device **(E28.07)**

accuracy, *n*—the permissible variation from the correct value. **(E28.01)**

adjusted length of the reduced section—the length of the reduced section plus an amount calculated to compensate for strain in the fillet region. **(E28.04)**

alignment, *n*—the condition of a testing machine that influences the introduction of bending moments into a specimen (or alignment transducer) during the application of tensile or compressive forces. **(E28.01)**

batch, *n*—for strain gages, a group of strain gages of the same type and lot, manufactured as a set (made at the same time and under the same conditions). **(E28.01)**

bearing area [L²], *n*—the product of the pin diameter and specimen thickness. **(E28.04)**

bearing force [F], *n*—a compressive force on an interface. **(E28.04)**

bearing strain, *n*—the ratio of the bearing deformation of the bearing hole, in the direction of the applied force, to the pin diameter. **(E28.04)**

bearing strength [FL⁻²], *n*—the maximum bearing stress which a material is capable of sustaining. **(E28.04)**

bearing stress [FL⁻²], *n*—the force per unit of bearing area. **(E28.04)**

bearing yield strength [FL⁻²], *n*—the bearing stress at which a material exhibits a specified limiting deviation from the proportionality of bearing stress to bearing strain. **(E28.04)**

portable Brinell hardness testing machine—a Brinell hardness testing machine that is designed to be transported, carried, set up, and operated by the users, and that measures Brinell hardness by the Brinell hardness test principle.

calibration, *n*—determination of the values of the significant parameters by comparison with values indicated by a reference instrument or by a set of reference standards. **(E28.06)**

calibration, *n*—operation that, under specified conditions, in a first step, establishes a relation between the quantity values with measurement uncertainties provided by measurement standards and corresponding indications with associated measurement uncertainties and, in a second step, uses this information to establish a relation for obtaining a measurement result from an indication.

DISCUSSION—A calibration may be expressed by a statement, calibration function, calibration diagram, calibration curve, or calibration table. In some cases, it may consist of an additive or multiplicative correction of the indication with associated measurement uncertainty.

DISCUSSION—Calibration should not be confused with adjustment of a measuring system, often mistakenly called “self-calibration”, nor with verification of calibration.

DISCUSSION—Often, the first step alone in the above definition is perceived as being calibration.

JCGM 200:2012⁵
(E28.01)

calibration factor, *n*—the factor by which a change in extensometer reading must be multiplied to obtain the equivalent strain.

DISCUSSION—For any extensometer, the calibration factor is equal to the ratio of change in length to the product of the gauge length and the change in extensometer reading. For direct-reading extensometers the calibration factor is unity.

(E28.01)

compressive strength [FL⁻²], *n*—the maximum compressive stress that a material is capable of sustaining.

DISCUSSION—Compressive strength is calculated by dividing the maximum force during a compression test by the original cross-sectional area of the specimen.

DISCUSSION—In the case of a material which fails in compression by a shattering fracture, the compressive strength has a very definite value. In the case of materials which do not fail in compression by a shattering fracture, the value obtained for compressive strength is an arbitrary value depending upon the degree of distortion which is regarded as indicating complete failure of the material.

(E28.04)

compressometer, *n*—a specialized extensometer used for sensing negative or compressive strain.

(E28.01)

constraint, *n*—any restriction to the deformation of a body.

(E28.91)

creep, *n*—the time-dependent strain that occurs after the application of a force which is thereafter maintained constant.

DISCUSSION—Creep tests are usually made at constant force and temperature. For tests on plastics, the initial strain – however defined–

is included; for tests on metals, the initial strain is not included.
(E28.04)

creep recovery, *n*—the time-dependent decrease in strain in a solid, following the removal of force.

DISCUSSION—Recovery is usually determined at constant temperature.

DISCUSSION—In tests of plastics, the initial recovery is generally included; for metals, it is not. Thermal expansion is excluded.
(E28.04)

creep rupture strength [FL⁻²], *n*—the stress causing fracture in a creep test at a given time, in a specified constant environment.

DISCUSSION—This is sometimes referred to as the *stress-rupture strength* or, in glass technology, the *static fatigue strength*. **(E28.04)**

creep strength [FL⁻²], *n*—the stress that causes a given creep in a creep test at a given time in a specified constant environment.

(E28.04)

deep drawing, *n*—a metal sheet forming operation in which strains on the sheet surface are positive in the direction of the punch travel and negative at 90° to that direction. **(E28.02)**

deflectometer, *n*—a specialized extensometer used for sensing of extension or motion, usually without reference to a specific gauge length.

(E28.01)

Demeri Split Ring Test—a test that measures the springback behavior of sheet metal by comparing the diameter of a ring extracted from the wall of a flat bottom cup and the diameter of the same ring split to release residual stresses. **(E28.02)**

differential indentation depth hardness test, *n*—an indentation hardness test using a verified hardness testing machine to force a truncated diamond cone indenter, diamond spheroconical indenter or tungsten carbide ball indenter, under specified conditions, into the surface of the material under test, and to measure the difference in depth of the indentation as the force on the indenter is increased from a specified preliminary test force to a specified total test force and then returned to the preliminary test force.

(E28.06)

differential indentation depth hardness number, *n*—a number derived from the net increase in the depth of indentation as the force on an indenter is increased from a specified preliminary test force to a specified total test force and then returned to the preliminary test force.

(E28.06)

differential indentation depth hardness testing machine, *n*—a machine capable of performing a Differential Indentation Depth hardness test and displaying the resulting hardness number.

(E28.06)

discontinuous yielding, *n*—in a uniaxial test, a hesitation or fluctuation of force observed at the onset of plastic deformation, due to localized yielding.

DISCUSSION—The stress-strain curve need not appear to be discontinuous.

(E28.04)

discontinuous yielding stress, σ_1 , *n*—the peak stress at the initiation of the first measurable serration on the curve of stress-versus-strain.

⁵ This definition is reproduced here from JCGM 200:2012 International vocabulary of metrology – Basic and general concepts and associated terms (VIM) with permission from the Director of BIPM. The text has been put in ASTM International’s form and style.

DISCUSSION—The parameter σ_1 is a function of test variables and is not a material constant. **(E28.04)**

ductility, n —the ability of a material to deform plastically before fracturing.

DISCUSSION—Ductility is usually evaluated by measuring (1) the elongation or reduction of area from a tension test, (2) the depth of cup from a cupping test, (3) the radius or angle of bend from the bend test, or (4) the fatigue ductility from the fatigue ductility test (see Test Method E796).

DISCUSSION—Malleability is the ability to deform plastically under repetitive compressive forces. **(E28.02)**

dynamic elastic modulus, E_d , n —the elastic modulus, either Young’s modulus or shear modulus, that is measured in a dynamic mechanical measurement. **(E28.04)**

dynamic mechanical measurement, n —a technique in which either the modulus or damping, or both, of a substance under oscillatory applied force or displacement is measured as a function of temperature, frequency, or time, or a combination thereof. **(E28.04)**

dynamic shear modulus, G_d [FL^{-2}], n —the value of the shear modulus determined using an oscillatory applied force or displacement and in conformance with this test method. **(E28.04)**

dynamic Young’s modulus, E_d [FL^{-2}], n —the value of the Young’s modulus determined using an oscillatory applied force or displacement and in conformance with this test method. **(E28.04)**

eccentricity [L], n —the distance between the line of action of the applied force and the axis of symmetry of the specimen in a plane perpendicular to the longitudinal axis of the specimen. **(E28.01)**

edge distance [L], n —the distance from the edge of a bearing specimen to the center of the hole in the direction of applied force. **(E28.04)**

edge distance ratio, n —the ratio of the edge distance to the pin diameter. **(E28.04)**

elastic force measurement standard, n —system consisting of an elastic member combined with an appropriate device for indicating the magnitude (or a quantity proportional to the magnitude) of deformation of the member under an applied force. **(E28.01)**

elastic limit [FL^{-2}], n —the greatest stress that a material is capable of sustaining without any permanent strain remaining upon complete release of the stress.

DISCUSSION—Due to practical considerations in determining the elastic limit, measurements of strain using a small force, rather than zero force, are usually taken as the initial and final reference. **(E28.04)**

elongation, El , n —the increase in gauge length of a body subjected to a tension force, referenced to a gauge length on the body.

DISCUSSION—Usually elongation is expressed as a percentage of the original gauge length.

DISCUSSION—The increase in gauge length may be determined either *at* or *after* fracture, as specified for the material under test.

DISCUSSION—The term elongation, when applied to metals, generally means measurement after fracture; when applied to plastics and elastomers, measurement at fracture. Such interpretation is usually applicable to values of elongation reported in the literature when no further qualification is given.

DISCUSSION—In reporting values of elongation, the gauge length shall be stated.

DISCUSSION—Elongation is affected by specimen geometry (area and shape of cross section, parallel length, parallelism, fillet radii, etc.), preparation (degree to which surfaces within the reduced section are smooth and free of cold work), and test procedure (alignment and test speed, for example). **(E28.04)**

elongation after fracture, n —the elongation measured by fitting the two halves of the broken specimen together. **(E28.04)**

elongation at fracture, n —the elongation measured just prior to the sudden decrease in force associated with fracture. **(E28.04)**

error, n —for a measurement or reading, the amount it deviates from a known or reference value represented by a measurement standard.

DISCUSSION—Mathematically, the error is calculated by subtracting the accepted value from the measurement or reading. (See also **percent error**.) **(E28.91)**

expanded uncertainty, n —a statistical measurement of the probable limits of error of a measurement.

DISCUSSION—NIST Technical Note 1297⁶ treats the statistical approach including the expanded uncertainty. **(E28.91)**

extensometer, n —a device for sensing strain. **(E28.01)**

extensometer system, n —a system for sensing and indicating strain.

DISCUSSION—The system will normally include an extensometer, conditioning electronics, and auxiliary device (recorder, digital readout, computer, etc.). However, completely self-contained mechanical devices are permitted. An extensometer system may be one of three types. **(E28.01)**

Type 1 extensometer system, n —an extensometer system which both defines gauge length, and senses extension, for example, a clip-on strain gauge type with conditioning electronics. **(E28.01)**

Type 2 extensometer system, n —an extensometer which senses extension and the gauge length is defined by specimen geometry or specimen features such as ridges or notches.

DISCUSSION—A Type 2 extensometer is used where the extensometer gauge length is determined by features on the specimen, for example, ridges, notches, or overall height (in case of compression test specimen). The precision associated with gauge length setting for a Type 2 extensometer should be specified in relevant test method or product standard. The position readout on a testing machine is not recommended for use in a Type 2 extensometer system. **(E28.01)**

⁶ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

Type 3 extensometer system, n—an extensometer system which intrinsically senses strain (ratiometric principle), for example, video camera system. (E28.01)

exercise, v—apply the maximum force to be used in the verification to either a force-measuring instrument or the force-sensing device of a testing machine or to both, to reestablish the hysteresis pattern that tends to disappear during periods of disuse, or with the change of mode of force application, as from compression to tension. (E28.01)

force [F], n—in mechanical testing, a vector quantity of fundamental nature characterized by a magnitude, a direction, a sense, and a discrete point of application, that acts externally upon a test object and creates stresses in it.

DISCUSSION—Force is a derived unit of the SI system. Units of force in the SI system are newtons (N).

DISCUSSION—Where applicable, the noun **force** is preferred to **load** in terminology for mechanical testing. (E28.91)

force indicator, n—of a testing machine, a component of a force-measuring system that presents, in force units, the force measured by the force-measuring system. (E28.01)

force measurement error, E, n—in the case of a testing machine, the difference obtained by subtracting the force indicated by the force measurement standard from the indicated force of the testing machine.

DISCUSSION—In a certificate and report of calibration and verification, “force measurement error” shall be used with numerical values, for example, “At a force of 300 kN [60 000 lbf], the force measurement error of the testing machine was + 67 N [+ 15 lbf].” (E28.01)

force measurement standard, n—a standard weight, an equal-arm balance and a standard weight, or an elastic force measurement standard used as a reference, with associated measurement uncertainty, in compliance Practices E74.

DISCUSSION—A force measurement standard is a specific type of “measurement standard” as defined in JCGM 200: International vocabulary of metrology — Basic and general concepts and associated terms (VIM). (E28.01)

force-measuring instrument—a system consisting of an elastic member combined with an appropriate instrument for indicating the magnitude (or a quantity proportional to the magnitude) of deformation of the member under an applied force. (E28.01)

force-measuring system, n—of a testing machine, a component of a testing machine that measures and indicates the force applied by the testing machine. (E28.01)

force-sensing device, n—of a testing machine, a component of the force-measuring system, that measures through deformation or other means the force applied by the testing machine.

DISCUSSION—Examples of a force-sensing device include a strain-gage force transducer (commonly called a load cell) and a pressure transducer. (E28.01)

forming limit curve, (FLC), n—an empirically derived curve showing the biaxial strain levels beyond which localized through-thickness thinning (necking) and subsequent failure occur during the forming of a metallic sheet. (E28.02)

forming limit diagram, (FLD), n—a graph on which the measured major and associated minor strain combinations are plotted to develop a forming limit curve. (E28.02)

gage factor, n—for strain gages, the ratio between the unit change of strain gage resistance due to strain and the causing strain.

DISCUSSION—The gage factor is dimensionless and is expressed as follows:

$$K = \frac{\frac{R - R_0}{R_0}}{\frac{L - L_0}{L_0}} = \frac{1}{\varepsilon} \frac{\Delta R}{R_0} \quad (1)$$

where:

K = gage factor,

R = strain gage resistance at test strain,

R_0 = strain gage resistance at zero or reference strain,

L = test structure length under the strain gage at test strain,

L_0 = test structure length under the strain gage at zero or reference strain,

ΔR = change in strain gage resistance when strain is changed from zero (or reference strain) to test strain, and

ε = the mechanical strain $\frac{L - L_0}{L_0}$ (E28.01)

gage length [L], n—the original length of that portion of the specimen over which strain or change of length is determined.

DISCUSSION—If the device is used for sensing extension or motion, and gage length is predetermined by the specimen geometry or specific test method, then only resolution and strain error for a specified gage length should determine the class of extensometer system. (E28.01)

gage length [L], n—the original length of that portion of the specimen over which strain, elongation, or change of length are determined.

DISCUSSION—Typically, this length is also the distance between gauge marks, if gauge marking is used to facilitate measurement of the elongation after fracture.

DISCUSSION—When sensing extension or motion with a gauge length that is predetermined by the specimen geometry or specific test method, then only resolution and strain error for the specified gauge length should determine the class of the extensometer system. (E28.04)

guided bend, n—the bend obtained by using a mandrel to guide and force the portion of the specimen being bent between two faces of a die. (E28.02)

hardness, n—the resistance of a material to deformation, particularly permanent deformation, indentation, or scratching.

DISCUSSION—Different methods of evaluating hardness give different ratings because they are measuring somewhat different quantities and characteristics of the material. There is no absolute scale for hardness; therefore, to express hardness quantitatively, each type of test has its own scale of arbitrarily defined hardness. (E28.06)

indentation hardness, n—the hardness as evaluated from measurements of area or depth of the indentation made by pressing a specified indenter into the surface of a material under specified static loading conditions. (E28.06)

indicated temperature [Θ], n —the temperature indicated by the temperature-measuring system that meets the requirements of this standard. (E28.04)

initial strain, n —the strain introduced into a specimen by the given loading conditions, before creep takes place.

DISCUSSION—This is sometimes referred to as instantaneous strain. (E28.04)

instrumented absorbed energy, W_t [FL], n —work spent to fracture a specimen in a single pendulum swing, as calculated by integrating the force-displacement curve. (E28.07)

Knoop hardness number, HK, n —the calculated result from a Knoop hardness test, which is proportional to the test force applied to the Knoop indenter divided by the projected area of the permanent indentation made by the indenter after removal of the test force.

DISCUSSION—The projected area of the permanent indentation made by the Knoop indenter is calculated based partly on the measured length of the long diagonal of the projected area of the indentation. (E28.06)

Knoop hardness test, n —an indentation test in which a Knoop rhombic-based pyramidal diamond indenter having specified edge angles, is forced under specified conditions into the surface of the test material, and, after removal of the test force, the length of the long diagonal of the projected area of the indentation is measured to calculate the Knoop hardness number. (E28.06)

lateral expansion [L], n —the maximum increase in thickness of the specimen as a result of the impact test, expressed in mm.

DISCUSSION—lateral expansion is used as a measure of ductility. (E28.07)

lead wire, n —for strain gages, an electrical conductor used to connect a sensor to its instrumentation. (E28.01)

least count, n —the smallest change in indication that can customarily be determined and reported.

DISCUSSION—In machines with close graduations the least count may be the value of a graduation interval; with open graduations or with magnifiers for reading, it may be an estimated fraction, rarely as fine as one tenth, of a graduated interval; and with verniers it is customarily the difference between the scale and vernier graduation measured in terms of scale units. If the indicating mechanism includes a stepped detent, the detent action may determine the least count.

length of the reduced section—the distance between the tangent points of the fillets that bound the reduced section. (E28.04)

limiting dome height (LDH) test, n —an evaluative test for metal sheet deformation capability employing a hemispherical punch and a circumferential clamping force sufficient to prevent metal in the surrounding flange from being pulled into the die cavity. (E28.02)

load [F], n —in mechanical testing, an external force or system of forces or pressures, acting upon the test specimen or sample.

DISCUSSION—**Load** is a deprecated term and, where practical, should be replaced by **force**, particularly when used as a noun. For reasons of editorial simplicity or traditional usage, replacement of **load** by **force**

may not always be desirable when used as a verb, adjective, or other part of speech. For example, it is appropriate to refer to **loading** a specimen, a **loading** rate, a **load** cell, or a **load**-line displacement. (E28.91)

lot, n —for strain gages, a group of strain gages with grid elements from a common melt, subjected to the same mechanical and thermal processes during manufacturing. (E28.01)

lower yield strength, LYS [FL⁻²], n —in a uniaxial test, the minimum stress recorded during discontinuous yielding, ignoring transient effects. (E28.04)

measurement accuracy, n —closeness of agreement between a measured quantity value and a true quantity value of a measurand

DISCUSSION—The concept ‘measurement accuracy’ is not a quantity and is not given a numerical quantity value. A measurement is said to be more accurate when it offers a smaller measurement error.

DISCUSSION—The term “measurement accuracy” should not be used for measurement trueness and the term “measurement precision” should not be used for ‘measurement accuracy’, which, however, is related to both these concepts.

DISCUSSION—‘Measurement accuracy’ is sometimes understood as closeness of agreement between measured quantity values that are being attributed to the measurand. JCGM 200:2012 (E28.01)

mechanical hysteresis, n —the energy absorbed in a complete cycle of loading and unloading.

DISCUSSION—A complete cycle of loading and unloading includes any stress cycle regardless of the mean stress or range of stress. (E28.91)

mechanical properties, n —those properties of a material that are associated with elastic and inelastic reaction when force is applied, or that involve the relationship between stress and strain.

DISCUSSION—These properties have often been referred to as “physical properties,” but the term “mechanical properties” is preferred. (E28.91)

mechanical testing, n —determination of the properties or the mechanical states of a material that are associated with elastic and inelastic reactions to force or that involve relationships between stress and strain. (E28.91)

metallic resistance bonded strain gage, n —a resistive element, with or without a matrix that is attached to a solid body by cementing, welding, or other suitable techniques so that the resistance of the element will vary as the surface to which it is attached is deformed.

DISCUSSION—These test methods apply to gages where the instantaneous gage resistance, R , is given by the equation:

$$R = R_o(1 + \epsilon K) \quad (2)$$

where:

R_o = element resistance at reference strain and temperature levels (frequently initial test or balanced circuit conditions),

ϵ = linear strain of the surface in the direction of the measurement axis of the strain gage produced either by a stress field (mechanical strain) or by a temperature change (thermal expansion), and

K = the gage factor.

(E28.01)

metrological traceability, n —property of a measurement result whereby the result can be related to a reference through a documented unbroken chain of calibrations, each contributing to the measurement uncertainty.

DISCUSSION—For this definition, a ‘reference’ can be a definition of a measurement unit through its practical realization, or a measurement procedure including the measurement unit for a non-ordinal quantity, or a measurement standard.

DISCUSSION—Metrological traceability requires an established calibration hierarchy.

DISCUSSION—Specification of the reference must include the time at which this reference was used in establishing the calibration hierarchy, along with any other relevant metrological information about the reference, such as when the first calibration in the calibration hierarchy was performed.

DISCUSSION—For measurements with more than one input quantity in the measurement model, each of the input quantity values should itself be metrologically traceable and the calibration hierarchy involved may form a branched structure or a network. The effort involved in establishing metrological traceability for each input quantity value should be commensurate with its relative contribution to the measurement result.

DISCUSSION—Metrological traceability of a measurement result does not ensure that the measurement uncertainty is adequate for a given purpose or that there is an absence of mistakes.

DISCUSSION—A comparison between two measurement standards may be viewed as a calibration if the comparison is used to check and, if necessary, correct the quantity value and measurement uncertainty attributed to one of the measurement standards. **JCGM 200:2012⁵**

(E28.01)

modulus of elasticity [FL⁻²], n —the ratio of stress to corresponding strain below the proportional limit.

DISCUSSION—The stress-strain relationships of many materials do not conform to Hooke’s law throughout the elastic range, but deviate therefrom even at stresses well below the elastic limit. For such materials, the slope of either the tangent to the stress-strain curve at the origin or at a low stress, the secant drawn from the origin to any specified point on the stress-strain curve, or the chord connecting any two specified points on the stress-strain curve is usually taken to be the “modulus of elasticity.” In these cases, the modulus should be designated as the “tangent modulus,” the “secant modulus,” or the “chord modulus,” and the point or points on the stress-strain curve described. Thus, for materials where the stress-strain relationship is curvilinear rather than linear, one of the four following terms may be used:

(a) *initial tangent modulus* [FL⁻²], n —the slope of the stress-strain curve at the origin.

(b) *tangent modulus* [FL⁻²], n —the slope of the stress-strain curve at any specified stress or strain.

(c) *secant modulus* [FL⁻²], n —the slope of the secant drawn from the origin to any specified point on the stress-strain curve.

(d) *chord modulus* [FL⁻²], n —the slope of the chord drawn between any two specified points on the stress-strain curve below the elastic limit of the material.

DISCUSSION—Modulus of elasticity, like stress, is expressed in force per unit of area (pounds per square inch, etc.). (E28.04)

necking, n —the onset of nonuniform or localized plastic deformation, resulting in a localized reduction of cross-sectional area. (E28.02)

percent error, n —the ratio, expressed as a percent, of an error to the known accepted value represented by a measurement standard. (See also, **error**.) (E28.91)

pile-up—a buildup of material around the edge of an indent that is the result of the indentation process. (E28.06)

Poisson’s ratio, μ , n —the negative of the ratio of transverse strain to the corresponding axial strain resulting from an axial stress below the proportional limit of the material.

DISCUSSION—Poisson’s ratio can be negative for some materials, for example, a tensile transverse strain will result from a tensile axial strain.

DISCUSSION—Poisson’s ratio will have more than one value if the material is not isotropic. (E28.04)

primary force standard, n —a deadweight force applied directly without intervening mechanisms such as levers, hydraulic multipliers, or the like, whose mass has been determined by comparison with reference standards traceable to the International System of Units (SI) of mass. (E28.01)

primary torque measurement standard, n —A deadweight force applied through a moment arm, all with metrological traceability to the International System of Units (SI). (E28.01)

proportional limit [FL⁻²], n —the greatest stress that a material is capable of sustaining without deviation from proportionality of stress to strain (Hooke’s law).

DISCUSSION—Many experiments have shown that values observed for the proportional limit vary greatly with the sensitivity and accuracy of the testing equipment, eccentricity of loading, the scale to which the stress-strain diagram is plotted, and other factors. When determination of proportional limit is required, the procedure and the sensitivity of the test equipment should be specified.

rapid indentation hardness test—an indentation hardness test using calibrated machines to force a tungsten carbide ball, under specified conditions, into the surface of the material under test and to measure the depth of the indentation.

DISCUSSION—The depth measured can be from the surface of the test specimen or from a reference position established by the application of a preliminary test force. The depth measurement is usually correlated to another scale or Brinell hardness number. (E28.06)

rate of creep, n —the slope of the creep-time curve at a given time. (E28.04)

reading, n —a quantity (typically a measurement or test result) indicated by a piece of equipment, such that it can be read by a user. (E28.91)

reduced parallel section, A , n —the central portion of the specimen that has a nominally uniform cross section, with an