



Designation: A288 – 18 (Reapproved 2023)

Standard Specification for Carbon and Alloy Steel Forgings for Magnetic Retaining Rings for Turbine Generators¹

This standard is issued under the fixed designation A288; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers quenched and tempered carbon and alloy steel forgings for magnetic retaining rings for turbine generators.

1.2 Supplementary requirements of an optional nature are provided. These shall apply only when specified by the purchaser.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A275/A275M Practice for Magnetic Particle Examination of Steel Forgings](#)

[A531/A531M Practice for Ultrasonic Examination of Turbine-Generator Steel Retaining Rings](#)

[A788/A788M Specification for Steel Forgings, General Requirements](#)

3. Ordering Information

3.1 In addition to the ordering information required by Specification [A788/A788M](#), the purchaser shall include with the inquiry and order a detailed drawing, sketch, or written

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved March 15, 2023. Published April 2023. Originally approved in 1946. Last previous edition approved in 2018 as A288 – 18. DOI: 10.1520/A0288-18R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

description of the forging, including the number and location of mechanical test specimens.

4. Manufacture

4.1 The melting processes of Specification [A788/A788M](#) shall be applicable except that the basic electric furnace process shall be used if separate refining or remelting is not employed.

4.2 *Vacuum Degassing*—Steel shall be vacuum degassed per any method listed in Specification [A788/A788M](#).

4.3 *Discard*—Sufficient discard shall be made from each ingot to secure freedom from piping and undue segregation.

4.4 *Heat Treatment:*

4.4.1 *Heat Treatment for Mechanical Properties*—Heat treatment for properties shall be by quenching and tempering. Forgings may be normalized prior to quenching and tempering.

4.4.2 *Tempering Temperature*—The final tempering temperature shall be not less than 1100 °F (595 °C).

4.5 *Machining:*

4.5.1 *Preliminary Machining*—Forgings shall be machined all over prior to quenching and tempering for mechanical properties.

4.5.2 *Machine to Purchaser's Requirements for Shipment*—If required, forgings shall be machined to the dimensions shown on the purchase order prior to shipment.

5. Chemical Composition

5.1 The steel shall conform to the chemical composition prescribed in [Table 1](#).

5.2 *Heat Analysis*—The heat analysis obtained from sampling in accordance with Specification [A788/A788M](#) shall comply with [Table 1](#).

5.3 *Product Analysis*—The purchaser may use the product analysis provision of [Table 1](#) of Specification [A788/A788M](#) to obtain a product analysis from a forging representing each heat or multiple heat.

6. Mechanical Properties

6.1 *Tensile Requirements*—The material shall conform to the requirements for tensile properties prescribed in [Table 2](#).

TABLE 1 Chemical Requirements

	Class 1, %	Classes 2 and 3, %	Classes 4, 5, 6, 7, and 8, %
Carbon, max	0.50 max	0.45 max	0.45
Manganese	0.60–1.00	0.60–1.00	1.00 max
Phosphorus, max	0.025	0.025	0.025
Sulfur, max	0.025	0.020	0.020
Silicon	0.15–0.30	0.15–0.35	0.15–0.35
Nickel	...	^A	1.65–3.50
Chromium	...	0.70–1.25	0.70–1.25
Molybdenum	...	0.15 min	0.20 min
Vanadium	...	optional	0.07–0.12

^A For Class 3 rings with wall thickness over 2½ in. (63.5 mm) drawing size, the nickel content shall be 0.85–2.0 %.

TABLE 2 Tensile and Notch Toughness Requirements

Class	Tensile Strength min, psi (MPa)	Yield Strength (0.02 % offset), min, psi (MPa)	Elongation in 2 in. or 50 mm, %	Reduction of Area, min, %	Charpy V-notch Impact Strength, Room Temperature min, ft-lbf (J)
1	70 000 (485)	45 000 (310)	18	40	15 (20)
2	90 000 (620)	65 000 (450)	20	50	25 (34)
3	110 000 (760)	80 000 (550)	18	50	20 (27)
4	120 000 (825)	95 000 (655)	18	45	35 (47)
5	130 000 (895)	110 000 (760)	16	40	30 (41)
6	140 000 (965)	125 000 (860)	14	40	30 (41)
7	150 000 (1035)	135 000 (930)	13	35	25 (34)
8	165 000 (1140)	150 000 (1035)	12	35	25 (34)

6.2 *Notch Toughness Requirements*—The material shall conform to the requirements for notch toughness as prescribed in [Table 2](#).

7. General Requirements

7.1 Material supplied to this specification shall conform to the requirements of Specification [A788/A788M](#) which outlines additional ordering information, manufacturing, requirements, testing and retesting methods, and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

7.2 If the requirements of this specification are in conflict with the requirements of Specification [A788/A788M](#), the requirements of this specification shall prevail.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

8. Sampling

8.1 *Test Location*—Tension and notch toughness test specimens shall be taken tangentially from prolongations on one or both ends of the forging. The direction of the notch of the Charpy bars shall be radial. All test specimens shall be located at midwall and at a distance at least equal to one-half the wall thickness from the end face of the prolongation.

8.2 *Removal*—All tension and notch toughness test specimens shall be removed after final heat treatment.

9. Number of Tests and Retests

9.1 *Number of Tests*—The number of tension and notch toughness test specimens shall be as prescribed by the purchaser, but in no case shall there be less than one tension and one notch toughness test specimen for each ring.

9.2 If any test specimen fails to meet the requirements specified, two adjacent test specimens may be selected for retest without reheat-treatment if the failure was not caused by ruptures, cracks, or flakes in the steel. Both of these must meet the requirements of this specification.

9.3 If the results of the mechanical tests of any forging do not conform to the requirements specified, the manufacturer may re-austenitize the forging, but not more than once without approval of the purchaser. Forgings may be retempered without obtaining approval of the purchaser.

10. Test Methods

10.1 *Nondestructive Tests:*

10.1.1 *General Requirements*—The ring shall be free from cracks, seams, laps, shrinkage, and other injurious imperfections.

10.1.2 *Magnetic Particle Test*—Magnetic particle tests of all surfaces shall be made at the manufacturer's plant. The procedure for tests shall be in accordance with Practice [A275/A275M](#). The standards of acceptance shall be by agreement between purchasers and manufacturers.

10.1.3 *Ultrasonic Inspection*—An ultrasonic inspection shall be made at the manufacturer's plant on the machined ring in accordance with Practice [A531/A531M](#). The standards of acceptance shall be by agreement between purchaser and manufacturer.