



Designation: B677 – 23

Standard Specification for Nickel-Iron-Chromium-Molybdenum, Iron-Nickel-Chromium-Molybdenum-Copper, and Nickel-Iron-Chromium-Molybdenum-Nitrogen Seamless Pipe and Tube¹

This standard is issued under the fixed designation B677; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers UNS N08925, UNS N08354, UNS N08926², and UNS N08935 seamless, cold-worked or hot-finished pipe and tube intended for general corrosive service.

1.2 ASTM International has adopted definitions whereby some grades, such as UNS N08904 previously in this specification, were recognized as stainless steels, because those grades have iron as the largest element by mass percent. Such grades are under the oversight of ASTM Committee A01 and its subcommittees. The products of N08904 previously covered in this specification are now covered by Specifications A269 and A312/A312M.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved April 1, 2023. Published April 2023. Originally approved in 1980. Last previous edition approved in 2021 as B677–21. DOI: 10.1520/B0677-23.

² New designation established in accordance with ASTM E527 and SAE J1086, Recommended Practice for Numbering Metals and Alloys (UNS).

2. Referenced Documents

- 2.1 *ASTM Standards*:³
- A269 Specification for Seamless and Welded Austenitic Stainless Steel Tubing for General Service
 - A312/A312M Specification for Seamless, Welded, and Heavily Cold Worked Austenitic Stainless Steel Pipes
 - B829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube
 - B899 Terminology Relating to Non-ferrous Metals and Alloys
 - E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology B899.

4. General Requirements

4.1 Material furnished under this specification shall conform to the requirements of Specification B829 unless otherwise provided herein. In the case of conflict, the requirements of this specification shall take precedence.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

- 5.1.1 Alloy name or UNS number.
- 5.1.2 ASTM designation and year of issue.
- 5.1.3 Finish.
- 5.1.4 *Dimensions*:
 - 5.1.4.1 *Tube*—Outside diameter and the average or minimum wall thickness.
 - 5.1.4.2 *Pipe*—Standard pipe size and schedule.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements^A

| Element | UNS N08925 | UNS N08926 | UNS N08935 | UNS N08354 |
|------------|--------------|----------------|--------------|--------------|
| Carbon | 0.020 | 0.020 | 0.030 | 0.030 |
| Manganese | 1.0 | 2.00 | 1.2 | 1.00 |
| Phosphorus | 0.045 | 0.03 | 0.030 | 0.030 |
| Sulfur | 0.030 | 0.01 | 0.020 | 0.010 |
| Silicon | 0.50 | 0.5 | 0.5 | 1.00 |
| Nickel | 24.0 to 26.0 | 24.00 to 26.00 | 34.0 to 36.0 | 22.0 to 24.0 |
| Chromium | 19.0 to 21.0 | 19.00 to 21.00 | 26.0 to 28.0 | 34.0 to 36.0 |
| Molybdenum | 6.0 to 7.0 | 6.0 to 7.0 | 6.1 to 7.1 | 7.0 to 8.0 |
| Copper | 0.8 to 1.5 | 0.5 to 1.5 | 0.4 | ... |
| Nitrogen | 0.1 to 0.2 | 0.15 to 0.25 | 0.25 to 0.36 | 0.17 to 0.24 |
| Iron | balance | balance | balance | balance |

^A Maximum unless range is given. Where ellipses (...) appear in this table, there is no requirement and analysis for the element need not be determined or reported.

TABLE 2 Mechanical Properties of Pipe and Tube

| Alloy | Temper | Tensile Strength, min, ksi (MPa) | Yield Strength, 0.2 % offset, min, ksi (MPa) | Elongation in 2 in. or 50 mm (or 4D), min, % |
|------------|-------------------|----------------------------------|--|--|
| UNS N08925 | solution annealed | 87 (600) | 43 (300) | 40 |
| UNS N08354 | solution annealed | 93 (640) | 43 (295) | 40 |
| UNS N08926 | solution annealed | 94 (650) | 43 (295) | 35 |
| UNS N08935 | solution annealed | 109 (750) | 58 (400) | 35 |

5.1.4.3 *Length* (cut to length or random).

5.1.5 *Quantity* (feet or number of pieces).

5.1.6 *Nondestructive Testing* (see 8.2):

5.1.6.1 *Pressure Requirements*—Test pressure if other than required by 8.2.1.

5.1.6.2 Specify if an electric test is to be performed.

5.1.7 *Ends*—Plain ends cut and deburred will be furnished. If threaded ends or ends beveled for welding are desired, give details.

5.1.8 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished (see 7.2).

5.1.9 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state, indicating which tests or inspections are to be witnessed.

6. Materials and Manufacture

6.1 The material shall be supplied in the solution-treated condition.

NOTE 1—The recommended heat treatment shall consist of heating to a temperature of 2010 °F to 2100 °F (1100 °C to 1150 °C) for UNS N08925 and UNS N08926, followed by quenching in water or rapid cooling by other means. The recommended heat treatment shall consist of heating to a temperature of 1975 °F (1080 °C) minimum for UNS N08935, followed by water quenching or rapid cooling by other means.

7. Chemical Composition

7.1 The material shall conform to the requirements as to chemical composition prescribed in Table 1. One test is required for each lot as defined in Specification B829.

7.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations per Specification B829.

8. Mechanical Properties and Other Requirements

8.1 *Mechanical Properties*—The material shall conform to the mechanical properties prescribed in Table 2. One test is required for each lot as defined in Specification B829.

8.2 *Nondestructive Tests*—Each pipe and tube shall be subjected to either a hydrostatic test or a nondestructive electric test as described in Specification B829. The purchaser may specify which test is to be used.

8.2.1 *Hydrostatic Test*—The fiber stress for the purpose of calculating the hydrostatic test pressure shall be 20 000 psi (138 MPa).

9. Dimensions and Permissible Variations

9.1 The permissible variations in dimensions set forth in Specification B829 shall apply.

10. Certification

10.1 A manufacturer's certification shall be furnished to the purchaser stating that material has been manufactured, tested, and inspected in accordance with this specification, and that the test results on representative samples meet specification requirements. A report of the test results shall be furnished.

11. Keywords

11.1 N08354; N08925; N08926; N08935; seamless pipe; seamless tube