



Designation: ~~B399/B399M—04 (Reapproved 2021)~~ B399/B399M – 23

## Standard Specification for Concentric-Lay-Stranded Aluminum-Alloy 6201-T81 and 6201-T83 Conductors<sup>1</sup>

This standard is issued under the fixed designation B399/B399M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers concentric-lay-stranded conductors, made from round aluminum-alloy 6201-T81 (hard: solution heat-treated, cold worked, and then artificially aged) wires or 6201-T83 (hard: higher conductivity, solution heat-treated, cold worked, and then artificially aged) wires, for use for electrical purposes. These conductors shall be constructed with a central core surrounded by one or more layers of helically laid wires (Explanatory Notes 1 and 2).

NOTE 1—The aluminum alloy and temper designations conform to ANSI H35.1/H35.1[M]. Aluminum-alloy 6201 corresponds to Unified Numbering System alloy A96201 in accordance with Practice E527.

1.2 The values stated in inch-pound units or SI units are to be regarded separately as standard. The values in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.2.1 For density, resistivity and temperature, the values stated in SI units are to be regarded as standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

#### 2.2 ASTM Standards:<sup>2</sup>

- B193 Test Method for Resistivity of Electrical Conductor Materials
- B263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors
- B354 Terminology Relating to Uninsulated Metallic Electrical Conductors
- B398/B398M Specification for Aluminum-Alloy 6201-T81 and 6201-T83 Wire for Electrical Purposes
- B682 Specification for Standard Metric Sizes of Electrical Conductors
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.07 on Conductors of Light Metals.

Current edition approved Feb. 1, 2021/April 1, 2023. Published February 2021/April 2023. Originally approved in 1963. Last previous edition approved in 2015/2021 as B399/B399M – 04 (2015)-(2021). DOI: 10.1520/B0399-B0399M-04R21.10.1520/B0399\_B0399M-23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.



E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.3 ANSI Standards:<sup>3</sup>

ANSI H35.1 American National Standard for Alloy and Temper Designation Systems for Aluminum

ANSI H35.1[M] American National Standard Alloy and Temper Designation Systems for Aluminum [Metric]

2.4 NIST Standards:<sup>4</sup>

NBS Handbook 100 Copper Wire Tables of the National Bureau of Standards

2.5 Aluminum Association Publication:<sup>5</sup>

Publication 50 Code Words for Overhead Aluminum Electrical Conductors

### 3. Classification

3.1 For the purpose of this specification, conductors are classified as follows (Explanatory Notes 1 and 2):

3.1.1 Class AA—For bare conductors usually used in overhead lines.

3.1.2 Class A—For conductors to be covered with weather-resistant materials.

### 4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity of each size, stranding, and class,

4.1.2 Conductor size, area, and aluminum 1350 equivalent size (if required) (Section 8 and Table 1, Table 2, or Table 3),

4.1.3 Number of wires (Table 1, Table 2 or Table 3),

4.1.4 Direction of lay of outer layer of aluminum wires if other than right-hand (see 7.4),

4.1.5 Compressed stranding, if required (see 8.2),

4.1.6 Special tension test, if required (see 9.2 and 14.2),

4.1.7 Place of inspection (see 15.2),

4.1.8 Special package marking, if required (Section 16),

4.1.9 Package size and type (see 16.1), and

4.1.10 Heavy wood lagging, if required (see 16.4).

### 5. Requirements of Wires

5.1 The aluminum-alloy wire used shall conform to the requirements of Specification B398/B398M; before stranding.

### 6. Joints

6.1 In conductors composed of seven wires, only cold-pressure joints or electric-butt, cold-upset joints are permitted in the six outer finished wires; no joints are permitted in the center wire. In other conductors, cold-pressure welds, electric-butt, cold-upset welds, or electric-butt welds may be made in the finished wires composing conductors, but such joints shall be not closer than prescribed in Table 4. Following welding, electric-butt welds shall be annealed for a distance of at least ~~6 in.~~ 6 in. [150 mm] on each side of the weld.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>4</sup> Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

<sup>5</sup> Available from Aluminum Association, Inc., 1525 Wilson Blvd., Suite 600, Arlington, VA 22209, <http://www.aluminum.org>.



TABLE 1 Construction Requirements of Concentric-Lay-Stranded Aluminum-Alloy 6201 Conductors Sized to Have Diameter Equal to ACSR, Class AA and Class A

NOTE 1—Metric values listed below represent a soft conversion and as such they may not be the same as those metric masses which are calculated from the basic metric density.

Table with columns: Conductor Size (cmil, mm²), Code Words, Approximate Aluminum Size, Size and Stranding of ACSR, Required Construction (Number of Wires, Diameter of Wires, Class), Mass (lb per 1000 ft, kg per km), Rated Strength (kips, kN), and Nominal dc Resistance (ohm per 1000 ft, ohm per km).

A Code words shown in this column are obtained from, "Publication 50, Code Words for Overhead Aluminum Electrical Conductors," by the Aluminum Association. They are provided here for information only.

B Conversion factors: 1 mil = 2.54 E-02 mm; 1 cmil = 5.067 E-04 mm²; 1 in. = 25.4 mm; 1 lb/1000 ft = 1.488 E + 00 kg/km; 1 ft = 3.048 E-01 m; 1 lb = 4.536 E-01 kg; 1 lbf = 4.448 E-03 kN

7. Lay

7.1 For Class AA conductors, the preferred length of lay of a layer of wires is 13.5 shall not be less than 10 nor more than 16 times the outside diameter of that layer, but the lay shall be not less than 10 nor more than 16 times this diameter layer. The length of lay of any aluminum-alloy layer shall not be less than the length of lay of the aluminum-alloy layer immediately beneath it.

7.2 For Class A conductors, the length of lay of a layer of wires shall be not be less than 8 nor more than 16 times the outside diameter of that layer, except that for conductors composed of 37 wires or more, this requirement shall apply only to the two outer layers. The length of lay of the layers other than the two outer layers shall be at the option of the manufacturer, unless otherwise agreed upon.

7.3 Other lays for special purposes shall be furnished by agreement between the manufacturer and the purchaser.

7.4 The direction of lay of the outer layer shall be right-hand unless specified otherwise by the purchaser.

7.5 The direction of lay shall be reversed in successive layers, unless otherwise specified by the purchaser.

**TABLE 2 Construction Requirements of Concentric-Lay-Stranded Aluminum-Alloy 6201 Conductors Sized by Standard Areas, Class AA and Class A**

NOTE 1—Metric values listed below represent a soft conversion and as such they may not be the same as those metric masses which are calculated from the basic metric density.

Conductor Size			Required Construction				Mass		Rated Strength		Nominal dc Resistance @ 20°C at 20 °C	
cmil	AWG	mm <sup>2</sup>	Number of Wires	Diameter of Wires		Class	lb per 1000 ft	kg per 1000 m	kips	kN	ohm per 1000 ft	ohm per 1000 m
				in.	mm							
1 750 000	...	886	61	0.1694	4.30	AA	1632	2431	56.9	251	0.01151	0.03781
1 500 000	...	759	61	0.1568	3.98	AA	1399	2082	48.8	215	0.01344	0.04414
1 250 000	...	631	61	0.1431	3.63	AA	1165	1732	40.6	179	0.01613	0.05306
1 000 000	...	508	37	0.1644	4.18	AA	932.5	1393	32.9	146	0.02015	0.06597
900 000	...	456	37	0.1560	3.96	AA	839.7	1250	29.6	131	0.02238	0.07351
800 000	...	404	37	0.1470	3.73	AA	745.6	1109	26.3	116	0.02520	0.08285
750 000	...	381	37	0.1424	3.62	AA	699.6	1045	24.7	109	0.02686	0.08796
700 000	...	354	37	0.1375	3.49	AA	652.3	971.2	23.0	101	0.02881	0.09464
650 000	...	330	37	0.1325	3.37	AA	605.7	905.5	21.4	94.9	0.03102	0.10150
600 000	...	303	37	0.1273	3.23	AA, A	559.1	831.9	20.6	91.0	0.03361	0.11049
550 000	...	279	37	0.1219	3.10	AA, A	512.7	766.2	18.9	83.9	0.03665	0.11995
500 000	...	253	19	0.1622	4.12	AA	466.1	695.0	16.8	74.2	0.04031	0.13224
450 000	...	228	19	0.1539	3.91	AA	419.6	626.0	15.1	66.8	0.04478	0.14683
400 000	...	203	19	0.1451	3.69	AA, A	373.0	557.5	13.4	59.5	0.05037	0.16486
350 000	...	178	19	0.1357	3.45	A	326.3	487.3	11.8	52.0	0.05759	0.18860
300 000	...	152	19	0.1257	3.19	A	280.0	416.7	10.5	46.6	0.06712	0.22059
250 000	...	126	19	0.1147	2.91	A	233.1	346.7	8.76	38.8	0.08061	0.26509
211 600	0000	107	7	0.1739	4.42	AA, A	197.4	294.7	7.34	32.5	0.09519	0.31188
167 800	000	84.9	7	0.1548	3.93	AA, A	156.4	233.0	5.82	25.7	0.12013	0.39450
133 100	00	67.3	7	0.1379	3.50	AA, A	124.1	184.8	4.62	20.4	0.15137	0.49738
105 600	0	53.5	7	0.1228	3.12	AA, A	98.43	146.8	3.82	17.0	0.19089	0.62592
66 360	2	33.5	7	0.0974	2.47	AA, A	61.92	92.00	2.40	10.6	0.30343	0.99870
41 740	4	21.1	7	0.0772	1.96	A	38.90	57.90	1.51	6.69	0.48300	1.5860
26 240	6	13.2	7	0.0612	1.55	A	24.49	36.20	0.949	4.18	0.76856	2.5361

## ASTM B399/B399M-23

**8. Construction**

8.1 The cross-sectional areas and the numbers and diameters of wires in the concentric-lay-stranded conductors shall conform to the requirements prescribed in [Table 1](#), [Table 2](#), or [Table 3](#) as applicable ([Explanatory Notes 2 and 6](#)).

8.2 Where compressed stranding is required in order that the conductor may be properly insulated, one or more layers of any stranded conductor consisting of 7 wires or more may be slightly compressed, thereby reducing the outside diameter of the conductor by not more than 3 %, provided that the area of cross section after compressing is in accordance with [Section 12](#).

NOTE 2—The user’s attention is called to the claim that certain compressed strand constructions may be subject to patent rights, for example: Patents 3,383,704 and 3,444,684.

8.3 The nominal wire diameter shall be as specified in [Table 1](#) and [Table 2](#) and this diameter shall be referred to as the “mean diameter”. The nominal outside diameter of the conductor shall be calculated by summing the mean diameter of the core wire and twice the mean diameter of each layer. The minimum and maximum outside diameter shall be based on calculations made using the method described above and the mean diameter tolerances as specified by Specification [B398/B398M](#) for the corresponding mean diameter of each layer.

**9. Rated Strength of Conductor**

9.1 The rated strength of a conductor shall be taken as that percentage, indicated in [Table 5](#) of the sum of the strengths of the 6201 wires, calculated on the basis of the nominal wire diameter and the specified minimum average tensile strength given in Specification [B398/B398M](#).



**TABLE 3 Construction Requirements and Rated Strengths of Concentric-Lay-Stranded Aluminum-Alloy 6201-T81 Conductors Sized by Standard Areas, Class AA and Class A**

NOTE 1—Sizes were selected from Specification B682.

Conductor Size, mm <sup>2</sup>	Required Construction			Mass, kg per 1000 m	Rated Strength 6201-T81, kN	Nominal dc Resistance @ 20°C, ohm per 1000 m
	Number of Wires	Diameter of Wires, mm	Class			
630	37	4.66	AA	1731	181	0.05308
560	37	4.39	AA	1537	161	0.05981
500	37	4.15	AA	1373	143	0.06693
450	37	3.94	AA	1238	129	0.07426
400	37	3.71	AA	1097	115	0.08375
355	37	3.50	AA	976.7	102	0.09410
315	37	3.29	AA	863.0	90.2	0.10650
280	37	3.10	AA	766.2	83.9	0.11995
250	19	4.09	AA	684.9	73.1	0.13419
224	19	3.87	AA	613.2	65.5	0.14988
200	19	3.66	AA, A	548.5	58.6	0.16758
180	19	3.47	AA, A	493.0	52.6	0.18643
160	19	3.27	AA, A	437.8	46.7	0.20993
140	19	3.06	AA, A	383.4	42.9	0.23973
125	19	2.89	AA, A	342.0	38.3	0.26877
112	7	4.51	AA	306.8	33.8	0.29955
100	7	4.26	AA, A	273.8	30.2	0.33574
80.0	7	3.81	AA, A	219.0	24.1	0.41974
63.0	7	3.39	AA, A	173.4	19.1	0.53019
50.0	7	3.02	AA, A	137.6	15.9	0.66806
40.0	7	2.70	AA, A	110.0	12.7	0.83580
31.5	7	2.39	A	86.2	9.95	1.0667
25.0	7	2.13	A	68.4	7.90	1.3430
20.0	7	1.91	A	55.0	6.35	1.6702
16.0	7	1.71	A	44.1	5.09	2.0837

**TABLE 4 Minimum Distance Between Joints in the Completed Conductor**

Number of Wires in Conductor	Distance Between Joints, min. ft (m)
7	50 (15) <sup>A</sup>
19	50 (15)
37	25 (7.5)
61	25 (7.5)

<sup>A</sup> Only cold-pressure welds and electric-butt, cold-upset welds are permitted in the six outer wires of conductors composed of seven wires; no welds are permitted in the center or core wire.

**TABLE 5 Rating Factors**

Stranding		
Number of Wires in Conductor	Number of Layers	Rating Factor, %
7	1	96
19	2	93
37	3	91
61	4	90

9.2 Tests for determining the breaking strength of a conductor are not required by this specification but may be made if agreed upon between the manufacturer and the purchaser at the time of placing an order. When tested, the breaking strength of a conductor shall be not less than the rated strength if failure occurs in the free length at least 1 in. [25 mm] beyond the end of either gripping device, or shall be not less than 95 % of the rated strength if failure occurs inside, or within 1 in. [25 mm] of the end of, either gripping device (Explanatory Note 3).

9.3 Rated strength and breaking strength values shall be rounded to three significant figures, in the final value only, in accordance with the rounding method in Practice E29.