



Designation: C467 – 14 (Reapproved 2023)

Standard Classification of Mullite Refractories¹

This standard is issued under the fixed designation C467; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers refractory products consisting predominantly of mullite ($3\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$) crystals that are formed by either converting any of the sillimanite group of minerals, or synthesizing from appropriate materials in a melt or sinter process.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C16 Test Method for Load Testing Refractory Shapes at High Temperatures](#)

[C832 Test Method for Measuring Thermal Expansion and Creep of Refractories Under Load](#)

NOTE 1—Chemical analysis of refractory products is determined by a combination of X-ray fluorescence (XRF) and inductively coupled plasma (ICP) using standard reference materials (SRM), including various types of minerals and refractory materials which are available from the National Institute of Standards and Technology and other appropriate sources.

3. Significance and Use

3.1 The mullite content of an alumina-silica refractory material has an important influence on volume stability, load-

¹ This classification is under the jurisdiction of the ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.92 on The Joseph E. Kopanda Subcommittee for Editorial, Terminology and Classification.

Current edition approved April 1, 2023. Published April 2023. Originally approved in 1961. Last previous edition approved in 2018 as C467 – 14 (2018). DOI: 10.1520/C0467-14R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

bearing properties, and its satisfactory use in refractory applications. This classification is considered useful for purchase specifications and quality control.

4. Basis of Classification

4.1 The refractory products falling within the scope of this classification are classified by chemical and physical tests to meet the following requirements:

Alumina content, %	56 to 79
Impurities, ^A max, %	5
Deformation, ^B max, %	5

^A Impurities refer to metal oxides other than those of aluminum and silicon.

^B When tested in accordance with 6.1.2.

5. Test Specimens

5.1 Testing for compliance with this classification shall be performed on 9 by 4½ by 2½-in. (228 by 114 by 64-mm) rectangular brick as made, or on specimens of this size cut from larger shapes, utilizing existing plane surfaces as much as possible.

6. Test Methods

6.1 The properties enumerated in this classification shall be determined in accordance with the following ASTM methods:

6.1.1 *Alumina Content*—XRF and ICP.

6.1.2 *Load Test*—Schedule 6 of Table 1 in Test Method C16.

6.1.3 *Thermal Expansion and Creep*—Test Method C832.

7. Retests

7.1 Because of possible variables that may result from sampling or an unsatisfactory reproducibility of tests by different laboratories, the material may be resampled and retested at the request of either the manufacturer or the purchaser. This could apply where the first test results may not conform to the requirements prescribed in this classification. Therefore, the final results to be used shall be the average of at least two series of tests, each of which has been obtained by following the specified testing procedures in detail.

8. Keywords

8.1 alumino-silicate; classification; mullite; refractories

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTM C467-14\(2023\)](#)

<https://standards.itih.ai/catalog/standards/sist/7740a46a-b6af-47ad-9dc7-b862e324b3fa/astm-c467-142023>