



SLOVENSKI STANDARD
SIST ISO 5451:2000
01-april-2000

Ferovanadij - Specifikacija in dobavni pogoji

Ferrovandium -- Specification and conditions of delivery

Ferro-vanadium -- Spécifications et conditions de livraison

Ta slovenski standard je istoveten z: ISO 5451:1980

[SIST ISO 5451:2000](https://standards.iteh.ai/catalog/standards/sist/13935bf2-16f9-494a-b0f3-02c51a3907a4/sist-iso-5451-2000)

<https://standards.iteh.ai/catalog/standards/sist/13935bf2-16f9-494a-b0f3-02c51a3907a4/sist-iso-5451-2000>

ICS:

77.100 Železove zlitine Ferroalloys

SIST ISO 5451:2000 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 5451:2000

<https://standards.iteh.ai/catalog/standards/sist/13935bf2-16f9-494a-b0f3-02c51a3907a4/sist-iso-5451-2000>

International Standard



5451

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Ferrovandium — Specification and conditions of delivery

Ferro-vandium — Spécifications et conditions de livraison

First edition — 1980-12-01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 5451:2000](https://standards.iteh.ai/catalog/standards/sist/13935bf2-16f9-494a-b0f3-02c51a3907a4/sist-iso-5451-2000)

<https://standards.iteh.ai/catalog/standards/sist/13935bf2-16f9-494a-b0f3-02c51a3907a4/sist-iso-5451-2000>

UDC 669.15'292-198

Ref. No. ISO 5451-1980 (E)

Descriptors : ferroalloys, ferrovandium, specifications, delivery conditions, chemical composition.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 5451 was developed by Technical Committee ISO/TC 132, *Ferroalloys*, and was circulated to the member bodies in November 1979.

It has been approved by the member bodies of the following countries :

Australia	Germany, F.R.	Romania
Austria	India	South Africa, Rep. of
Brazil	Italy	Sweden
Canada	Japan	United Kingdom
China	Norway	USA
Czechoslovakia	Poland	USSR
France	Portugal	Yugoslavia

No member body expressed disapproval of the document.

Ferrovandium — Specification and conditions of delivery

1 Scope and field of application

This International Standard specifies requirements and conditions of delivery for ferrovandium usually supplied for steelmaking and foundry use.

2 References

ISO 565, *Test sieves — Woven metal wire cloth and perforated plate — Nominal sizes of apertures.*

ISO 3713, *Ferroalloys — Sampling and preparation of samples — General rules.*¹⁾

ISO 6467, *Ferrovandium — Determination of vanadium content — Potentiometric method.*¹⁾

3 Definition

3.1 ferrovandium : A master alloy of iron and vanadium with a minimum vanadium content of 35,0 % by mass, and a maximum vanadium content of 85,0 % by mass, obtained by reduction.

4 Information for ordering

Orders for ferrovandium shall include the following information.

- a) Quantity.
- b) Constitution of consignment.
- c) Chemical composition in accordance with the designations given in table 1.
- d) Particle size ranges in accordance with the classes given in table 2.
- e) Necessary requirements for analysis reports, packing, etc., as appropriate.

5 Requirements

5.1 Constitution of consignment

Ferrovandium shall be delivered in consignments constituted by one of the following methods.

5.1.1 Tapped lot method

A consignment constituted by the tapped lot method consists of a ferrovandium mass of one melt (or one part of a continuous tap).

5.1.2 Graded lot method

A consignment constituted by the graded lot method consists of a number of melts (or parts of continuous taps) of one ferrovandium designation.

The vanadium content of the melts (or parts of continuous taps) constituting the consignment shall not differ from each other by more than 3 % absolute.

5.1.3 Blended lot method

A consignment constituted by the blended lot method consists of a number of melts (or parts of continuous taps) of one ferrovandium designation, which have been crushed to a particle size less than 50 mm and thoroughly mixed.

The content of the main constituent of the melts (or parts of continuous taps) constituting the consignment may vary between the minimum and maximum limits specified for the appropriate ferrovandium designation.

5.2 Chemical composition

5.2.1 The chemical composition of ferrovandium shall be as specified in table 1. The limits stated correspond to particle size ranges in classes 1 to 5 in accordance with table 2.

¹⁾ At present at the stage of draft.

ISO 5451-1980 (E)

5.2.2 The chemical compositions given in table 1 show only the main constituent elements and usual impurities. If the purchaser requires closer ranges for the main element contents and/or different limits for specified elements and/or limits for non-specified elements, this shall be agreed upon between supplier and purchaser.

5.2.3 The chemical compositions given in table 1 are subject to the precision of the methods of sampling and analysis for ferrovanadium (see clause 6).

5.3 Particle size ranges

5.3.1 Ferrovanadium is supplied in lumps or as crushed and screened particles. The particle size ranges and tolerances shall be in accordance with table 2. The undersize values shall be valid at the point of delivery to the purchaser.¹⁾

The particle sizes specified refer to screening on a steel sieve with square openings; see ISO 565.

5.3.2 If the purchaser requires particle size ranges and/or tolerances other than those given in table 2, these shall be agreed upon between supplier and purchaser.

5.4 Extraneous contamination

The material shall be as free as possible from extraneous contamination.

6 Testing

6.1 Sampling for chemical analysis and sieve analysis

6.1.1 Sampling for chemical analysis and sieve analysis²⁾ shall preferably be carried out by the method specified in ISO 3713, but other methods of sampling having similar precision may also be used.

6.1.2 Sampling is usually carried out at the supplier's stockyard, unless otherwise agreed. Wherever sampling is carried out, representatives of both supplier and purchaser may be present.

6.1.3 If required, arbitration sampling shall be carried out by an arbitrator chosen by mutual agreement between supplier and purchaser. Sampling shall be carried out by the method specified in ISO 3713, but other methods of sampling having similar precision may be agreed upon between supplier, purchaser and arbitrator.

The sample obtained by arbitration shall be accepted by both parties.

6.2 Analysis

6.2.1 The chemical analysis of ferrovanadium shall preferably be carried out by the method specified in ISO 6467, but other methods of chemical analysis having similar precision may also be used.

6.2.2 Ferrovanadium shall be furnished with an analysis certificate, established by the supplier, for the vanadium content and, if agreed, the contents of other elements either specified in table 1 or additionally agreed and, upon request of the purchaser, with a sample representative of the consignment.

6.2.3 In case of dispute, one of the following two procedures may be used.

6.2.3.1 Contradictory analysis

The chemical analysis shall be carried out on the same sample and preferably by the method specified in ISO 6467. Other methods of chemical analysis having similar precision may be used, but shall be agreed upon between supplier and purchaser.

If the difference between the results of the two analyses is within x %³⁾, the mean value shall apply. If the difference exceeds x %, then, provided that no other agreement is reached, arbitration analysis shall be carried out by an arbitrator chosen by mutual agreement between supplier and purchaser.

1) The point of delivery is defined as that point where the responsibility for the consignment passes from supplier to purchaser. If neither the supplier nor the purchaser is responsible for the transportation, then the point at which the values become valid shall be agreed upon.

2) Sieve analysis of ferroalloys will form the subject of ISO 4551.

3) The value of x will be specified later. In the meantime, the value should be agreed upon between purchaser and supplier.

6.2.3.2 Arbitration analysis

Arbitration analysis shall preferably be carried out by the method specified in ISO 6467. Other methods of chemical analysis having similar precision may be used, but shall be agreed upon between supplier, purchaser and arbitrator.

The arbitrator's result is final, provided it is within the two

disputed values or not more than $y\%$ ¹⁾ outside one of these values.

7 Despatch and storage

Ferrovandium shall be packed, stored and transported according to international regulations.²⁾

Table 1 – Chemical composition

Designation	Chemical composition, %									
	V	Si max.	Al max.	C max.	P max.	S max.	As max.	Cu max.	Mn max.	Ni max.
FeV40	35,0 to 50,0	2,0	4,0	0,30	0,10	0,10				
FeV60	50,0 to 65,0	2,0	2,5	0,30	0,06	0,05	0,06	0,10		
FeV80	75,0 to 85,0	2,0	1,5	0,30	0,06	0,05	0,06	0,10	0,50	0,15
FeV80Al2	75,0 to 85,0	1,5	2,0	0,20	0,06	0,05	0,06	0,10	0,50	0,15
FeV80Al4	70,0 to 80,0	2,0	4,0	0,20	0,10	0,10	0,10	0,10	0,50	0,15

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Table 2 – Particle size

SIST ISO 5451:2000

Class	Particle size range mm	Undersize, max. % by mass	Oversize, max. % by mass
1	2 to 100	3	10
2	2 to 50	3	
3	2 to 25	5	
4	2 to 10	5	
5	up to 2	—	No piece to exceed 1,15 × the maximum limit of the size range specified in two or three directions.

1) This value, as an overall precision, will be specified as β_{SDM} .

2) Examples of appropriate international regulations are :

- RID : Règlement International concernant le transport des marchandises dangereuses par chemin de fer, Annexe C.
- International maritime dangerous goods code.