

Designation: E342 - 11 (Reapproved 2016) E342 - 23

Standard Test Method for Determination of Chromium Oxide in Chrome Ores by Permanganate Titrimetry ¹

This standard is issued under the fixed designation E342; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of chromium oxide (Cr_2O_3) in chrome ores in the compositional range from 25 % to 60 %.

Note 1—As used in this test method, "%" refers to a mass fraction (wt/wt %) (g/100g).

- 1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.
- 1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

https://standards.iteh.ai/catalog/standards/sist/1d8b6df3-ebbd-4a12-be4e-0dcdb411d4e0/astm-e342-23

2.1 ASTM Standards:²

D1193 Specification for Reagent Water

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

E276 Test Method for Particle Size or Screen Analysis at 4.75 mm (No. 4) Sieve and Finer for Metal-Bearing Ores and Related Materials

E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory

3. Terminology

3.1 Definitions—For definitions of terms used in this test method, refer to Terminology E135.

¹ This test method is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.02 on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved Nov. 15, 2016April 1, 2023. Published December 2016April 2023. Originally approved in 1967. Last previous edition approved in $\frac{20112016}{2016}$ as $\frac{E342-11}{E342-11}$ (2016). DOI: $\frac{10.1520/E0342-11R16}{2016}$ 10.1520/E0342-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



4. Summary of Test Method

4.1 The sample is decomposed by fusion with sodium peroxide. After leaching in water and boiling to decompose peroxides, the solution is acidified with HNO_3 and H_2SO_4 . Residual chromium is oxidized to chromate with silver nitrate, potassium permanganate, and peroxydisulfate. The excess of permanganate is destroyed by the addition of NaCl. After cooling, the chromate is reduced by the addition of a measured excess of a ferrous ammonium sulfate, and the excess is titrated with a permanganate solution.

5. Significance and Use

5.1 This test method is intended to be used for compliance with compositional specifications for chromium oxide content in chromium-bearing ores. It is assumed that all who use these procedures will be trained analysts capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly equipped laboratory and that proper waste disposal procedures will be followed. Appropriate quality control practices must be followed such as those described in Guide E882.

6. Interferences

6.1 None of the elements normally found in chrome ores interfere with this test method.

7. Reagents and Materials

- 7.1 Purity of Reagents—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available³. Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.
- 7.2 Purity of Water—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type I or II of Specification D1193. Type III or IV may be used if they effect no measurable change in the blank or sample.
- 7.3 Ammonium Peroxydisulfate Solution (250 g/L)—Dissolve 25 g of ammonium persulfate (ammonium peroxydisulfate) $((NH_4)_2S_2O_8)$ in water, and dilute to 100 mL. Prepare fresh as needed.
- 7.4 Ferrous Ammonium Sulfate Solution $(0.2\ N)$ —Dissolve 78.4 g of ferrous ammonium sulfate (FeSO₄(NH₄)₂SO₄·6H₂O) in 1 L of cool H₂SO₄ (5 + 95). Because the ferrous ammonium sulfate solution gradually weakens in reducing power, it is necessary to standardize the ferrous ammonium sulfate solution daily or at the same time that the chrome ore is analyzed. To standardize, transfer 100 mL of FeSO₄(NH₄)₂SO₄·6H₂O to a 600-mL beaker, dilute to 300 mL with cold H₂SO₄ (5 + 95), add 2 mL of H₃PO₄ and 2 drops of ortho-phenanthroline ferrous sulfate (ferroin). Titrate immediately with 0.2 N KMnO₄ solution (7.8) to a faint, permanent pink color.
- 7.5 Ferrous Sulfate Solution (0.025 M)—Dissolve 6.95 g of ferrous sulfate (FeSO₄·7H₂O) in 500 mL of water and dilute to 1 L.
- 7.6 Ortho-Phenanthroline Ferrous Sulfate Indicator Solution—(0.025 M)—Dissolve 1.485 g of 1,10-phenanthroline monohydrate in 100 mL of ferrous sulfate solution (FeSO₄·7H₂O) prepared in 7.5.
- 7.7 Potassium Permanganate Solution (20 g/L)—Dissolve 20 g of potassium permanganate (KMnO₄) in water and dilute to 1 L.
- 7.8 Potassium Permanganate Solution (0.2 N)—Dissolve 6.4 g of KMnO₄ in 1 L of water. Standardize against a National Institute of Standards and Technology Reference Material for sodium oxalate ($Na_2C_2O_4$) or equivalent.
- 7.9 Silver Nitrate Solution (8 g/L)—Dissolve 8 g of silver nitrate (AgNO₃) in water and dilute to 1 L.

³ Reagent Chemicals, American Chemical Society SpecificationsACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials, -American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Analar Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmaceutical Pharmacopeial Convention, Inc. (USPC), Rockville, MD.



- 7.10 Sodium Chloride Solution (100 g/L)—Dissolve 10 g of NaCl in water and dilute to 100 mL.
- 7.11 Sodium Peroxide (Na₂O₂).

8. Hazards

8.1 For precautions to be observed in this method, refer to Practices E50.

9. Sampling, Test Specimens, and Test Units

10. Procedure

- 10.1 Transfer 0.50 g of the previously dried sample, weighed to the nearest 0.1 mg to a 30-mL iron crucible (Note 2) and add 8 g of dry Na₂O₂ (Note 3). Thoroughly mix the contents of the crucible and cover the mixture with an additional 1 g to 2 g of Na₂O₂.
- 10.2 Cover the crucible with an iron or nickel cover and carefully fuse the contents at 600 °C to 700 °C, preferably in an electric muffle furnace. After the mix has melted, fuse for several minutes at a low red heat while giving a slight rotary motion to the crucible to ensure complete decomposition.
- Note 2—Ordinary iron crucibles that may contain significant amounts of chromium should be avoided. Crucibles made of ingot iron are satisfactory.
- Note 3—Only about 5 g of Na_2O_2 is required if about 0.2 g of very fine pulverized sugar charcoal is mixed with the Na_2O_2 . After heating for about 30 s, ignition of the charcoal takes place, and the crucible will suddenly become a dull red on the outside. The total time required to complete the fusion is about 2 min. By shortening the time for fusion and contact with the flux, the life of the crucible is extended.
- 10.3 Place the cool crucible and its cover into a 600-mL covered beaker, leach the melt with 150 mL of water, remove the crucible and cover, and rinse the crucible and cover into the beaker. Boil 10 min to destroy the residual peroxide.
- 10.4 Add to the cooled solution 60 mL of H_2SO_4 (1 + 1) and 5 mL of HNO_3 and boil for several minutes until any iron scale from the crucible is dissolved.
- 10.5 Add 15 mL of AgNO₃ solution, 2 drops of KMnO₄ solution (7.7), and 10 mL of (NH₄)₂S₂O₈ solution and boil for 5 min.
- 10.6 Add 10 mL of NaCl solution and boil for 5 min to 10 min after the KMnO₄ or any MnO₂ has completely disappeared.
- 10.7 Cool, and if necessary, dilute with cold water to 350 mL, 350 mL, then add 3 mL to 5 mL 3 mL to 5 mL of H₃PO₄.
- 10.8 Add a measured excess of $FeSO_4(NH_4)_2SO_4\cdot 6H_2O$. The point at which reduction is complete can be detected by the development of deep green color. The $FeSO_4(NH_4)_2SO_4\cdot 6H_2O$ may be added either as the 0.2 N prepared solution (7.4) or a weighed amount of the salt (Note 4). Add 2 drops of orthophenanthroline ferrous sulfate (ferroin) as an indicator.
- 10.9 Titrate the excess $FeSO_4(NH_4)_2SO_4\cdot 6H_2O$ with 0.2 N KMnO₄ solution (7.8). The end point is reached whenever the solution becomes clear green in color.
- Note 4—Approximately 70 mL of $0.2 N \text{ FeSO}_4(\text{NH}_4)_2 \text{SO}_4 \cdot 6\text{H}_2 \text{O}$ solution (7.4) containing 5.5 g of the salt is required for a chrome ore containing 65 % $\text{Cr}_2 \text{O}_3$ (Note 1).

11. Calculation

11.1 Rounding of test results obtained using this test method shall be performed as directed in Practice E29, Rounding Method, unless an alternative rounding method is specified by the customer or applicable material specification.