



Designation: B 523/B 523M – 01

Standard Specification for Seamless and Welded Zirconium and Zirconium Alloy Tubes¹

This standard is issued under the fixed designation B 523/B 523M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers three grades of zirconium and zirconium alloy seamless and welded tubes.

1.2 Unless a single unit is used, for example corrosion mass gain in mg/dm^2 , the values stated in either inch-pound or SI units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. SI values cannot be mixed with inch-pound values.

1.3 The following precautionary caveat pertains only to the test methods portion of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products³

B 551 Specification for Zirconium and Zirconium Alloy Strip, Sheet, and Plate⁴

E 8 Test Methods for Tension Testing of Metallic Materials⁵

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁶

E 213 Practice for Ultrasonic Examination of Metal Pipe and Tubing⁷

E 426 Practice for Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys⁷

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *annealed*—for purposes of this specification “annealed” denotes material that exhibits a recrystallized grain structure.

3.2 Lot Definitions:

3.2.1 *castings*—a lot shall consist of all castings produced from the same pour.

3.2.2 *ingot*—no definition required.

3.2.3 *rounds, flats, tubes, and wrought powder metallurgical products (single definition, common to nuclear and non-nuclear standards)*—a lot shall consist of a material of the same size, shape, condition, and finish produced from the same ingot or powder blend by the same reduction schedule and the same heat treatment parameters. Unless otherwise agreed between manufacturer and purchaser, a lot shall be limited to the product of an 8 h period for final continuous anneal, or to a single furnace load for final batch anneal.

3.2.4 *sponge*—a lot shall consist of a single blend produced at one time.

3.2.5 *weld fittings*—definition is to be mutually agreed upon between manufacturer and the purchaser.

4. Classification

4.1 The tubes are furnished in three grades as follows:

4.1.1 *Grade R60702*—Unalloyed zirconium.

4.1.2 *Grade R60704*—Zirconium-tin alloy.

4.1.3 *Grade R60705*—Zirconium-niobium alloy.

5. Ordering Information

5.1 Orders for material under this specification should include the following information:

5.1.1 Quantity (weight or number of pieces, or both),

5.1.2 Name of material (zirconium seamless or welded tube),

5.1.3 Dimensions (diameter, wall thickness, lengths),

5.1.4 ASTM designation and year of issue,

5.1.5 Grade number (see 4.1), and

5.1.6 Additions to the specification and supplementary requirements, if required.

NOTE 1—A typical ordering description is as follows: 1000 pieces of

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.02 on Zirconium and Hafnium.

Current edition approved Nov. 10, 2001. Published January 2002. Originally published as B 523 – 70. Last previous edition B 523 – 97.

² For ASME Boiler and Pressure Vessel Code Applications, see related Specification SB-523 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 01.03.

⁴ *Annual Book of ASTM Standards*, Vol 02.04.

⁵ *Annual Book of ASTM Standards*, Vol 03.01.

⁶ *Annual Book of ASTM Standards*, Vol 14.02.

⁷ *Annual Book of ASTM Standards*, Vol 03.03.



seamless zirconium tubes, 2 in. (50 mm) in outside diameter by 0.06 in. (1.5 mm) in wall thickness by 10 ft (3 m) in length, ASTM B 523, dated ____, Grade R60702.

6. Materials and Manufacture

6.1 Seamless tube shall be made by any seamless method that will yield a product meeting the requirements of this specification.

6.2 Welded tube shall be made from sheet or strip meeting the requirements of Specification B 551 by an automatic arc-welding process or other method of welding that will yield a product meeting the requirements of this specification. Filler metal shall not be used. Welded tubing shall be supplied as follows:

- 6.2.1 As welded, and
- 6.2.2 As welded and further reduced.
- 6.3 The tube shall be furnished annealed.

7. Chemical Composition

7.1 The material shall conform to the requirements as to chemical composition prescribed in Table 1.

7.2 The manufacturer's ingot analysis shall be considered the chemical analysis for tubing, except for hydrogen and nitrogen, which shall be determined on the finished product.

7.3 When requested by the purchaser and stated in the purchase order, a product analysis for any elements listed in Table 1 shall be made on the finished product.

7.3.1 The manufacturer's analysis shall be considered as verified if the check analysis confirms the manufacturer's reported values within the tolerances prescribed in Table 2.

8. Tensile Requirements

8.1 The material, as represented by the test specimens, shall conform to the tensile properties prescribed in Table 3.

9. Permissible Variation in Dimensions

9.1 *Diameter*—Variations in outside diameter shall not exceed those prescribed in Table 4.

9.2 *Length*—When tubes are ordered cut to length, the length shall be not less than that specified, but a variation of 1/8 in. (3.2 mm) will be permitted on tube up to 10 ft (3 m), inclusive. For lengths over 10 ft, an additional over-tolerance

TABLE 1 Chemical Requirements^A

Element	Composition, %		
	UNS Grade Designation		
	R60702	R60704	R60705
Zirconium + hafnium, min ^B	99.2	97.5	95.5
Hafnium, max	4.5	4.5	4.5
Iron + chromium	0.2 max	0.2 to 0.4	0.2 max
Tin	...	1.0 to 2.0	...
Hydrogen, max	0.005	0.005	0.005
Nitrogen, max	0.025	0.025	0.025
Carbon, max	0.05	0.05	0.05
Niobium	2.0 to 3.0
Oxygen, max	0.16	0.18	0.18

^ABy agreement between the purchaser and the manufacturer, analysis may be required and limits established for elements and compounds not specified in the table of chemical composition.

^BThe value for zirconium + hafnium, min, is a warranted but not a measured value.

TABLE 2 Permissible Variation in Product Analysis Between Different Laboratories

Element	Permissible Variation in Product Analysis, %
Hydrogen	0.002
Nitrogen	0.01
Carbon	0.01
Hafnium	0.1
Iron + chromium	0.025
Tin	0.05
Niobium	0.05
Oxygen	0.02

TABLE 3 Tensile Requirements

	UNS Grade Designation		
	R60702	R60704	R60705
Tensile strength, min, ksi (MPa)	55 (380)	60 (415)	80 (550)
Yield strength, min, ksi (MPa)	30 (205)	35 (240)	55 (380)
Elongation in 2 in. or 50 mm, min, %	16	14	16

of 1/8 in. (3.2 mm) for each 10 ft (3 m) or fraction thereof shall be permissible up to 1/2 in. (13 mm), maximum.

9.3 *Straightness*—The tube shall be free of bends or kinks and the maximum uniform bow shall not exceed the values shown in Table 5.

9.4 *Squareness of Cut*—The angle of cut of the end of any tube up to 1 1/2 in. (40 mm) in outside diameter may depart from square not more than 0.016 in./in. (mm/mm).

10. Workmanship and Quality Level Requirements

10.1 The finished tube shall be clean and free of foreign material, shall have smooth ends, free of burrs, and shall be free of injurious external and internal imperfections in accordance with standards of acceptability agreed upon between the manufacturer and the purchaser. Minor defects may be removed provided the dimensional tolerances of Table 4 are not exceeded.

11. Significance of Numerical Limits

11.1 For the purpose of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value or a calculated value shall be rounded as indicated in accordance with the rounding methods of Practice E 29.

Property	Rounded Unit for Observed or Calculated Value
Chemical composition, and tolerances (when expressed as decimals)	nearest unit in the last right-hand place of figures of the specified limit
Tensile strength and yield strength	nearest 1000 psi (10 MPa)
Elongation	nearest 1 %

12. Number of Tests and Retests

12.1 One longitudinal tension test, see 13.1, shall be made from each lot.

12.2 One chemistry test, see 7.2 and 13.7, for hydrogen and nitrogen shall be made from each lot of finished product.

12.3 One flare test, see 13.5, shall be made from each lot.