



Designation: D4258 – 23

Standard Practice for Surface Cleaning Concrete for Coating¹

This standard is issued under the fixed designation D4258; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice includes surface cleaning of concrete to remove grease, dirt, and loose material prior to the application of coatings. Procedures include broom cleaning, vacuum cleaning, air blast cleaning, water cleaning, detergent water cleaning, and steam cleaning.

1.2 This practice is not intended to alter the surface profile of the concrete but to clean the surface.

1.3 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D4259 Practice for Preparation of Concrete by Abrasion Prior to Coating Application

D4260 Practice for Liquid and Gelled Acid Etching of Concrete

D4262 Test Method for pH of Chemically Cleaned or Etched Concrete Surfaces

D4263 Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method

¹ This practice is under the jurisdiction of ASTM Committee D33 on Protective Coating and Lining Work for Power Generation Facilities and is the direct responsibility of Subcommittee D33.05 on Application and Surface Preparation.

Current edition approved April 1, 2023. Published April 2023. Originally approved in 1983. Last previous edition approved in 2017 as D4258 – 05 (2017). DOI: 10.1520/D4258-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D4285 Test Method for Indicating Oil or Water in Compressed Air

2.2 *Other Standard:*

ACI-308 Guide to Curing Concrete³

3. Summary of Practice

3.1 Surface cleaning is intended to provide a clean, contamination-free surface without removing concrete from intact, sound surfaces.

3.2 Acceptable surfaces shall be free of oil, grease, loosely adhering concrete, and other contamination. Fins and projections shall be corrected prior to surface cleaning.

3.3 Air, water cleaning, scrubbing, sweeping, or vacuuming are acceptable cleaning methods. Cleaning agents may also be used to remove oil and grease spots followed by a fresh water rinse.

3.4 Any one or a combination of the listed cleaning procedures may be used to achieve acceptably cleaned surfaces.

4. Significance and Use

4.1 Surface cleaning is used to prepare concrete surfaces for applying coatings intended for light-duty service.

4.2 Use of this practice alone is not intended where protective systems will be used for continuous or intermittent immersion, mechanical loading, or for protective systems needing optimum bond for satisfactory performance (see Practices D4259 and D4260).

5. Hazards and General Considerations

5.1 New concrete shall be cured according to ACI-308 and sufficient additional time allowed for drying.

5.2 Moisture in the concrete may be detrimental to coating adhesion. Moisture content shall be in compliance with coating manufacturer's recommendation (see Test Method D4263).

5.3 Concrete cure compounds, form release materials, or concrete hardeners not compatible with the coating may require removal by other surface preparation methods as in Practices D4259 and D4260.

³ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

5.4 Use and disposal of materials should conform to established federal, state, local, and project requirements.

6. Procedures

6.1 *Broom Cleaning:*

6.1.1 This procedure is intended to remove most surface dust and other loosely adherent solid contaminants.

6.1.2 Broom cleaning shall consist of sweeping the surface with a clean industrial stiff-bristled broom or similar device. Sweepings shall be removed from the immediate work area.

6.1.3 Broom-cleaned surfaces require additional cleaning using one or more of the surface preparation procedures specified in 6.2 – 6.6.

6.2 *Vacuum Cleaning:*

6.2.1 This cleaning procedure is intended to remove surface dust and other debris.

6.2.2 Vacuum cleaning shall consist of vacuuming the surface with a heavy-duty type industrial vacuum to provide an essentially dust-free surface.

6.3 *Air Blast Cleaning:*

6.3.1 This procedure is intended to remove debris, dust, dirt, loosely adherent laitance, and concrete from walls and ceilings and to provide an essentially sound dust-free surface.

6.3.2 Air blast cleaning shall consist of cleaning the surface with a compressed air stream at 80 to 100 psi through a blasting nozzle held approximately 2 ft from the surface.

6.3.3 The air stream shall be free of oil. This may be verified using Test Method D4285.

6.3.4 Surface cleanliness is dependent upon carrying off airborne dust before it is redeposited. Vacuum cleaning may be required to remove redeposited dust.

6.4 *Water Cleaning:*

6.4.1 This procedure is intended to remove dust, dirt, and water-soluble surface contaminants.

6.4.2 Water cleaning shall consist of cleaning the surface with a stream of clean potable water having sufficient pressure to remove dust, dirt, and loose material. When necessary, hand scrub with a stiff-bristled brush.

6.4.3 Prior to water cleaning, provisions shall be made for the removal of wash water and contaminants generated by this cleaning method.

6.4.4 The cleaned surface may be tested for moisture content in accordance with Test Method D4263 prior to applying coatings.

6.5 *Detergent Water Cleaning:*

6.5.1 This procedure is intended to remove water-soluble surface contaminants and oils, grease, and other emulsifiable materials on the surface.

6.5.2 Detergent water cleaning shall consist of scraping off heavy deposits of grease or oil and cleaning the surface with a stiff-bristled brush using an aqueous solution of detergent or nonsolvent emulsifier. Immediately after treatment, before the surface dries, residues of the cleaning agent shall be removed

by thoroughly flushing the surface with clean potable water. Repeat flushing until the pH of the surface water meets the acceptance criteria of Test Method D4262.

6.5.3 Trisodium phosphate at not less than 4 oz/gal, or proprietary products intended for cleaning concrete, may be used following manufacturers instructions. The effectiveness of trisodium phosphate may be improved with the use of hot water.

6.5.4 Repeat 6.5.2 until water does not bead on the surfaces.

6.5.5 Prior to detergent water washing, provisions shall be made for the removal of wash water and contaminants generated by this cleaning method.

6.5.6 The cleaned surface may be tested for moisture content in accordance with Test Method D4263.

6.6 *Steam Cleaning:*

6.6.1 This cleaning procedure is similar to detergent water washing, but is more effective for the removal of heavy deposits of grease and oil.

6.6.2 Steam cleaning shall consist of cleaning the surface with a jet of high-pressure steam sufficient to remove contaminants.

6.6.3 Detergents or nonsolvent emulsifying agents intended for use with steam cleaning equipment may be added where required for removal of oil and grease.

6.6.4 When detergents or other emulsifying agents are used, after cleaning and before the surface dries, the surface shall be thoroughly flushed with potable water. Repeat flushing may be necessary to remove cleaning residues.

6.6.5 The surfaces cleaned with detergent or nonsolvent emulsifying agents shall be tested for pH in accordance with Test Method D4262 and may be tested for moisture content in accordance with Test Method D4263 prior to applying coatings.

6.6.6 Prior to steam cleaning, provisions shall be made for the removal of water and contaminants generated by this cleaning method.

7. Inspection

7.1 Visually examine the prepared surface for the presence of debris, dust, dirt, oil, grease, loosely adherent concrete, and other contaminants.

7.2 Test surfaces cleaned with detergent or nonsolvent emulsifying agents for pH following Test Method D4262.

7.3 Moisture content may be determined following Test Method D4263.

8. Acceptance

8.1 Acceptable surfaces shall be free of oil, grease, loosely adhering concrete, and other contamination.

9. Keywords

9.1 concrete; liquid/gelled acid; surface cleaning; surface profile