



Designation: A815/A815M – 23

Standard Specification for Wrought Ferritic, Ferritic/Austenitic, and Martensitic Stainless Steel Piping Fittings¹

This standard is issued under the fixed designation A815/A815M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers two general classes, WP and CR, of wrought ferritic, ferritic/austenitic, and martensitic stainless steel fittings of seamless and welded construction covered by the latest revision of Specification A960/A960M. Fittings differing from these standards may be furnished in accordance with Supplementary Requirement S58 of Specification A960/A960M.

1.1.1 Class WP fittings are subdivided into four subclasses: Classes WP-S, WP-W, WP-WX, and WP-WU. They are manufactured to the requirements of Specification A960/A960M, and they shall have pressure ratings compatible with 13.2. Class WP-S fittings are those manufactured from seamless product by a seamless method of manufacture (marked with class symbol WP-S); Class WP-W fittings are those which contain welds where the fitting fabrication or construction welds have been radiographed (marked with class symbol WP-W); and Class WP-WX fittings are those which contain welds where all welds have been radiographed (marked with class symbol WP-WX); and Class WP-WU fittings are those which contain welds where all welds have been ultrasonically tested (marked with class symbol WP-WU).

1.1.2 Class CR fittings are those manufactured to the requirements of MSS SP-43, and they shall have pressure ratings compatible with 13.3.

1.2 This specification does not apply to cast fittings.

1.3 Optional supplementary requirements are provided. When desired, one or more of these may be specified in the order.

1.4 This specification is expressed in both inch-pound units and in SI units. However, unless the order specifies the applicable “M” specification designation [SI units], the material shall be furnished to inch-pound units.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

A388/A388M Practice for Ultrasonic Examination of Steel Forgings

A751 Test Methods and Practices for Chemical Analysis of Steel Products

A763 Practices for Detecting Susceptibility to Intergranular Attack in Ferritic Stainless Steels

A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels

A960/A960M Specification for Common Requirements for Wrought Steel Piping Fittings

E165/E165M Practice for Liquid Penetrant Testing for General Industry

2.2 *ASME Standards:*³

B16.9 Factory-Made Wrought Butt-Welding Fittings

B16.11 Forged Fittings, Socket-Welding and Threaded

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved May 1, 2023. Published May 2023. Originally approved in 1983. Last previous edition approved in 2022 as A815/A815M – 22. DOI: 10.1520/A0815_A0815M-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

*A Summary of Changes section appears at the end of this standard

2.3 MSS Standards:⁴

MSS SP-43 Standard Practice for Light Weight Stainless Steel Butt-Welding Fittings

MSS SP-79 Socket-Welding Reducer Inserts

MSS SP-83 Steel Pipe Unions, Socket-Welding and Threaded

MSS SP-95 Swage(d) Nipples and Bull Plugs

MSS SP-97 Integrally Reinforced Forged Branch Outlet Fittings—Socket Welding, Threaded and Buttwelding Ends

2.4 ASME Boiler and Pressure Vessel Codes:³

Section VIII Division I

Section IX

2.5 ASNT Standard:⁵

SNT-TC-1A Recommended Practice for Nondestructive Testing Personnel Qualification and Certification

5.2 All classes of fittings shall be heat treated in accordance with Section 6.

5.3 Fittings ordered as Class WP-S shall be of seamless construction and shall meet all requirements of Specification A960/A960M.

5.4 Fittings ordered as Class WP-W shall meet the requirements of Specification A960/A960M and (1) shall have all welds made by the fitting manufacturer and all pipe welds made with the addition of filler metal radiographically examined throughout the entire length in accordance with Paragraph UW-51 of Section VIII, Division 1, of the ASME Boiler and Pressure Vessel Code; and (2) shall not require radiography of the starting pipe weld if the pipe was welded without the addition of filler metal. In place of radiographic examination, welds made by the fitting manufacturer may be ultrasonically examined in accordance with the code requirements stated in 5.6.

5.5 Fittings ordered as Class WP-WX shall meet the requirements of Specification A960/A960M and shall have all welds, whether made by the fitting manufacturer or the starting material manufacturer, radiographically examined throughout their entire length in accordance with Paragraph UW-51 of Section VIII, Division I of the ASME Boiler and Pressure Vessel Code. The radiography of welds for this class of fittings can be done either prior to or after forming at the option of the manufacturer.

5.6 Fittings ordered as Class WP-WU shall meet the requirements of Specification A960/A960M and shall have all welds, whether made by the fitting manufacturer or the starting material manufacturer, ultrasonically examined throughout their entire length in accordance with Appendix 12 of Section VIII, Division 1 of ASME Boiler and Pressure Vessel Code.

5.7 The radiography or ultrasonic examination for this class of fittings may be done at the option of the manufacturer, either prior to or after forming.

5.8 Personnel performing NDE examinations shall be qualified in accordance with SNT-TC-1A.

5.9 Fittings covered in Specification A960/A960M and ordered as CR shall meet the requirements of Specification A960/A960M and do not require nondestructive examination.

5.10 All classes of fittings shall have the welders, welding operators, and welding procedures qualified under the provisions of Section IX of the ASME Boiler and Pressure Vessel Code except that starting pipe welds made without the addition of filler metal do not require such qualification.

5.11 All joints welded with filler metal shall be finished in accordance with the requirements of Paragraph UW-35 (a) of Section VIII, Division 1, of the ASME Boiler and Pressure Vessel Code.

5.12 Fittings machined from bar shall be restricted to NPS 4 or smaller.

5.12.1 All caps machined from bar shall be examined by liquid penetrant in accordance with Practice E165/E165M.

3. Common Requirements and Ordering Information

3.1 Material furnished to this specification shall conform to the requirements of Specification A960/A960M including any supplementary requirements that are indicated in the purchase order. Failure to comply with the common requirements of Specification A960/A960M constitutes nonconformance with this specification. In case of conflict between this specification and Specification A960/A960M, this specification shall prevail.

3.2 Specification A960/A960M identifies the ordering information that should be complied with when purchasing material to this specification.

4. Materials

4.1 The material for fittings shall consist of forgings, bars, plates, or seamless or welded tubular products that conform to the chemical requirements in Table 1.

4.2 The steel shall be melted by one of the following processes:

4.2.1 Electric furnace (with separate degassing and refining optional),

4.2.2 Vacuum furnace, or

4.2.3 Electric furnace followed by vacuum or electroslag-consumable remelting.

4.3 If secondary melting is employed, the heat shall be defined as all ingots remelted from a primary heat.

5. Manufacture

5.1 *Forming*—Forging or shaping operations may be performed by hammering, pressing, piercing, extruding, upsetting, rolling, bending, fusion welding, machining or by combination of two or more of these operations. The forming procedure shall be so applied that it will not produce surface discontinuities deeper than 5 % of the specified nominal thickness of the fitting.

⁴ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

⁵ Available from American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

TABLE 1 Chemical Requirements

NOTE 1—Where an ellipsis (...) appears in this table, there is no requirement.

| Composition, % | | | | | | | | | | | | | | |
|----------------------------|-----------|--------|-------------|------------------------|-----------------|-------------|--------------|---------------------|------------------------|------------------------|---------------------|------------------------|----------------------------|------------------------------|
| Grade ^A | | | | | | | | | | | | | | |
| Grade WP | Grade CR | UNS | Carbon, max | Manganese ^B | Phosphorus, max | Sulfur, max | Silicon, max | Nickel ^B | Chromium | Molybdenum | Copper ^B | Nitrogen ^B | Titanium | Other |
| Ferritic Steels | | | | | | | | | | | | | | |
| WP27 | CR27 | S44627 | 0.010 | 0.75 | 0.020 | 0.020 | 0.40 | 0.50 | 25.0–27.5 | 0.75–1.50 | 0.20 | 0.015 | ... | Nb ^D 0.05–0.20 |
| WP33 | CR33 | S44626 | 0.06 | 0.75 | 0.040 | 0.020 | 0.75 | 0.50 | 25.0–27.0 | 0.75–1.50 | 0.20 | 0.040 | 0.20–1.00 (7×(C+N)) min | ... |
| WP429 | CR429 | S42900 | 0.12 | 1.0 | 0.040 | 0.030 | 0.75 | 0.50 | 14.0–16.0 | ... | ... | ... | ... | ... |
| WP430 | CR430 | S43000 | 0.12 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 | 16.0–18.0 | ... | ... | ... | ... | ... |
| WP430Ti | CR430Ti | S43036 | 0.10 | 1.00 | 0.040 | 0.030 | 1.00 | 0.75 | 16.0–19.5 | ... | ... | ... | (5×C) min 0.75 max | ... |
| WP446 | CR446 | S44600 | 0.20 | 1.50 | 0.040 | 0.030 | 0.75 | 0.50 | 23.0–27.0 | ... | ... | 0.25 | ... | ... |
| Ferritic/Austenitic Steels | | | | | | | | | | | | | | |
| WPS31803 | CRS31803 | S31803 | 0.030 | 2.00 | 0.030 | 0.020 | 1.0 | 4.5–6.5 | 21.0–23.0 | 2.5–3.5 | ... | 0.08–0.20 | ... | ... |
| WPS32101 | CRS32101 | S32101 | 0.040 | 4.0–6.0 | 0.040 | 0.030 | 1.00 | 1.35–1.70 | 21.0–22.0 | 0.10–0.80 | 0.10–0.80 | 0.20–0.25 | ... | ... |
| WPS32202 | CRS32202 | S32202 | 0.030 | 2.00 | 0.040 | 0.010 | 1.00 | 1.00–2.80 | 21.5–24.0 | 0.45 | ... | 0.18–0.26 | ... | ... |
| WPS32750 | CRS32750 | S32750 | 0.030 | 1.20 | 0.035 | 0.020 | 0.8 | 6.0–8.0 | 24.0–26.0 | 3.0–5.0 | 0.5 | 0.24–0.32 | ... | ... |
| WPS32950 | CRS32950 | S32950 | 0.030 | 2.00 | 0.035 | 0.010 | 0.60 | 3.5–5.2 | 26.0–29.0 | 1.00–2.50 | ... | 0.15–0.35 | ... | ... |
| WPS32760 | CRS32760 | S32760 | 0.030 | 1.00 | 0.030 | 0.010 | 1.00 | 6.0–8.0 | 24.0–26.0 ^C | 3.0–4.0 ^C | 0.50–1.00 | 0.20–0.30 ^C | ... | W 0.50–1.00 |
| WPS39274 | CRS39274† | S39274 | 0.030 | 1.00 | 0.030 | 0.020 | 0.80 | 6.0–8.0 | 24.0–26.0 | 2.50–3.50 ^C | 0.20–0.80 | 0.24–0.32 | ... | W 1.50–2.50 |
| WPS32550 | CRS32550 | S32550 | 0.04 | 1.50 | 0.040 | 0.030 | 1.00 | 4.5–6.5 | 24.0–27.0 | 2.9–3.9 | 1.50–2.50 | 0.10–0.25 | ... | ... |
| WPS32205 | CRS32205 | S32205 | 0.030 | 2.00 | 0.030 | 0.020 | 1.00 | 4.5–6.5 | 22.0–23.0 | 3.0–3.5 | ... | 0.14–0.20 | ... | ... |
| Martensitic Steels | | | | | | | | | | | | | | |
| WP410 | CR410 | S41000 | 0.15 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 max | 11.5–13.5 | ... | ... | ... | ... | ... |
| WPS41008 | CRS41008 | S41008 | 0.08 | 1.00 | 0.040 | 0.030 | 1.00 | 0.60 | 11.5–13.5 | ... | ... | ... | ... | ... |
| WPS41500 | CRS41500 | S41500 | 0.05 | 0.50–1.00 | 0.030 | 0.030 | 0.60 | 3.5–5.5 | 11.5–14.0 | 0.50–1.00 | ... | ... | ... | W 0.50–1.00 |

^A Naming system developed and applied by ASTM International.

^B Maximum unless otherwise indicated.

^C % Cr + 3.3 × % Mo + 16 × % N = 40 min.

^D Niobium and columbium are interchangeable names for the same element and both names are acceptable for use in A01.22 specifications.

5.13 Weld buildup is permitted to dimensionally correct unfilled areas produced during forming of stub ends. Radiographic examination of the weld buildup shall not be required provided that all of the following steps are adhered to:

5.13.1 The weld procedure and welders or welding operators meet the requirements of 5.10,

5.13.2 Heat-treatment is performed after welding and prior to machining,

5.13.3 All weld surfaces are liquid penetrant examined in accordance with Appendix 8 of Section VIII, Division 1 of the ASME Boiler and Pressure Vessel Code, and

5.13.4 Repair of areas in the weld is permitted, but 5.13.1, 5.13.2, and 5.13.3 must be repeated.

5.14 Stub ends may be produced with the entire lap added as weld metal to a straight pipe section provided the welding satisfies the requirements of 5.10 for qualifications and Section 6 for post weld heat treatment.

5.14.1 *Class WP-W*—Radiographic inspection of the weld is required (see 5.4).

5.14.2 *Class WP-WX*—Radiographic inspection of all welds is required (see 5.5).

5.14.3 *Class WP-WU*—Ultrasonic inspection of all welds is required (see 5.6).

5.14.4 *Class CR*—Nondestructive examination is not required (see 5.9).

5.15 Stub ends may be produced with the entire lap added by the welding of a ring, made from plate or bar of the same alloy grade and composition, to the outside of a straight section of pipe, provided the weld is double welded, is a full penetration joint, satisfies the requirements of 5.10 for qualifications and Section 6 for post weld heat treatment.

5.15.1 *Class WP-W*—Radiographic inspection of all welds, made with the addition of filler metal is required (see 5.4).

5.15.2 *Class WP-WX*—Radiographic inspection of all welds, made with or without the addition of filler metal, is required (see 5.5).

5.15.3 *Class WP-WU*—Ultrasonic inspection of all welds, made with or without the addition of filler metal, is required (see 5.6).

5.15.4 *Class CR*—Nondestructive examination is not required (see 5.9).

6. Heat Treatment

6.1 Unless otherwise stated herein, heat treatment shall be performed after welding and in accordance with the requirements of Table 2.

6.1.1 No final heat treatment of welded fittings (HT-O) fabricated from ferritic/austenitic plate that has been heat

treated as required by Table 2 for the particular grade, is required, provided material representative of the fittings, including base metal, weld metal, and heat affected zone, passes a Test Methods A923 Method B or C (See Note 1) corrosion evaluation per heat. Each fitting supplied under this requirement shall be stenciled with the suffix HT-O.

6.1.2 For materials not listed in Table 3 of Test Methods A923, the HT-O provision does not apply.

NOTE 1—The Test Methods A923 test method (B or C) is at the manufacturer’s option, unless otherwise specified by the purchaser.

6.2 All fittings machined directly from forgings or bars (see 5.12), previously heat treated in accordance with the requirements specified in Table 2, need not be reheat treated.

7. Chemical Composition

7.1 The chemical composition of each cast or heat shall be determined and shall conform to the requirements of the chemical composition for the respective grades of materials listed in Table 1. Methods and practices relating to chemical analyses required by this specification shall be in accordance with Methods, Practices, and Definitions A751. Product analysis tolerances in accordance with Specification A960/A960M are applicable.

7.2 Except as listed below, in fittings of welded construction, the composition of the deposited weld shall conform to the same requirements as the base metal.

TABLE 2 Heat Treatment

| Stainless Steel | All WP and CR Grades | Temperature | Cooling | Tempering Temperature |
|---------------------|----------------------|--|---|---------------------------|
| Ferritic | All | ≥ 1200 °F [650 °C] | As appropriate for grade | Not specified |
| Ferritic/Austenitic | S31803 | 1870–2010 °F [1020–1100 °C] | Water quench or rapidly cooled by other means | Not required |
| | S32101 | 1870 °F [1020 °C] min | Water quench or rapidly cooled by other means | Not required |
| | S32202 | 1870–1975 °F [1020–1080 °C] | Water quench or rapidly cooled by other means | Not required |
| | S32205 | 1870–2010 °F [1020–1100 °C] | Water quench | Not required |
| | S32750 | 1880–2060 °F [1025–1125 °C] | Water quench or rapidly cooled by other means | Not required |
| | S32760 | 2010–2085 °F [1100–1140 °C] | Water quench or rapidly cooled by other means | Not required |
| | S39274 | 1920–2060 °F [1050–1125 °C] | Water quench or rapidly cooled by other means | Not required |
| | S32550 | 1950–2060 °F ^A [1065–1125 °C] ^A | Water quench | Not required |
| | S32950 | Not specified | Not specified | Not required |
| Martensitic | S41000 | ≥ 1200 °F [650 °C] | Not specified | Not specified |
| | S41008 | > 1200 °F [650 °C] | In still air as appropriate for grade | Not specified |
| | S41500 | ≥ 1750 °F [955 °C] | Air cool to ≤ 200 °F [95 °C] prior to any optional intermediate temper and prior to final temper. | 1050–1150 °F [565–620 °C] |

^AThe higher temperature (2000 to 2060 °F [1095 to 1125 °C]) PWHT is best used on welded product—the lower temperature PWHT (1950 to 2010 °F [1065 to 1100 °C]) is best used on wrought or seamless products only.

7.2.1 Welds on S32950 base metal shall be made with nominal 26 % Cr, 8 % Ni, 2 % Mo weld metal.

7.2.2 Welds on S31803 and S32205 base metals shall conform to the same requirements as the base metal or shall be made with nominal 22 % Cr, 9 % Ni, 3 % Mo or 25 % Cr, 9 % Ni, 4 % Mo weld metal.

7.2.3 Welds on S32202 base metal shall be made with nominal 22 % Cr, 9 % Ni, 3 % Mo weld metal.

7.2.4 Welds on S32750 and S32760 base metals may be made with nominal 25 % Cr, 9 % Ni, 4 % Mo weld metal.

8. Tensile Requirements

8.1 The tensile properties of the fitting material shall conform to the requirements of **Table 3**. The testing and reporting shall be performed in accordance with Specification **A960/A960M**.

8.2 The fittings manufacturer shall perform a tensile test on material representative of the finished fitting. Records of the tensile test made on the starting material may be certification that the material of hot-finished fittings meets the tensile requirements of this specification provided the heat treatments are the same. For purposes of tensile, yield and elongation requirements listed in **Table 3**, the tensile specimen shall consist of base metal only. If the purchaser requires results, involving the weld, in addition to the base metal only results, then the S2 supplemental requirement of this specification shall be specified on the purchase order. When S2 is specified, the weld metal must meet only the minimum ultimate tensile strength of **Table 3**.

TABLE 3 Tensile and Hardness Requirements

| All WP and CR Grades | Yield Strength, min, ksi [MPa] | Tensile Strength, ⁴ ksi [MPa] | Elongation in 2 in. [50 mm] or 4D, min, % | HBW max |
|------------------------------------|--------------------------------|--|---|---------|
| <i>Ferritic Steels:</i> | | | | |
| S44627 | 40 [275] | 65 [450]–90 [620] | 20.0 | 190 |
| S44626 | 45 [310] | 68 [470]–93 [640] | 20.0 | 241 |
| S42900 | 35 [240] | 60 [415]–85 [585] | 20.0 | 190 |
| S43000 | 35 [240] | 65 [450]–90 [620] | 20.0 | 190 |
| S43036 | 35 [240] | 60 [415]–85 [585] | 20.0 | 190 |
| S44600 | 40 [275] | 70 [485]–95 [655] | 18.0 | 207 |
| <i>Ferritic/Austenitic Steels:</i> | | | | |
| S31803 | 65 [450] | 90 [620] | 20.0 | 290 |
| S32101 | 65 [450] | 94 [650] | 30.0 | 290 |
| S32202 | 65 [450] | 94 [650] | 30.0 | 290 |
| S32205 | 65 [450] | 95 [655] | 20.0 | 290 |
| S32750 | 80 [550] | 116 [800] | 15.0 | 310 |
| S32760 | 80 [550] | 109 [750] | 25.0 | 270 |
| S32950 | 70 [485] | 100 [690] | 15.0 | 290 |
| S39274 | 80 [550] | 116 [800] | 15.0 | 310 |
| S32550 | 80 [550] | 110 [760] | 15.0 | 302 |
| <i>Martensitic Steels:</i> | | | | |
| S41000 | 30 [205] | 70 [485]–95 [655] | 20.0 | 207 |
| S41008 | 30 [205] | 60 [415] | 22.0 | 183 |
| S41500 | 90 [620] | 110 [760]–135 [930] | 15.0 | 295 |

⁴Minimum unless otherwise indicated.

9. Hardness Requirements

9.1 Fittings shall not exceed the maximum hardness shown in **Table 3**.

10. Dimensions

10.1 The sizes, shapes, and dimensions of the fittings covered by ASME B16.9, ASME B16.11, MSS SP-43, MSS SP-79, MSS SP-83, MSS SP-95, or MSS SP-97 shall be as specified in those standards.

10.2 Fittings of size or shape differing from these standards, but meeting all other requirements of this specification, may be furnished in accordance with Supplementary Requirement S58 of Specification **A960/A960M**.

11. Surface Finish, Appearance, and Corrosion Protection

11.1 In addition to the requirements of this section, the requirements of Specification **A960/A960M** apply.

11.2 Fittings supplied under this specification shall be examined visually. Selected typical surface discontinuities shall be explored for depth. The fittings shall be free from surface discontinuities that penetrate more than 5 % of the specified nominal wall thickness, except as defined in **11.4** and **11.5**, and shall have a workmanlike finish.

11.3 Surface discontinuities deeper than 5 % of the specified nominal wall thickness, except as defined in **11.4** and **11.5**, shall be removed by the manufacturer by machining or grinding to sound metal, and the repaired areas shall be well faired. The wall thickness at all points shall be at least 87½ % of the specified nominal wall thickness, and the diameters at all points shall be within the specified limits.

11.4 Surface checks (fish scale) deeper than ¼ in. [0.4 mm] shall be removed.

11.5 Mechanical marks deeper than ¼ in. [1.6 mm] shall be removed.

11.6 When the removal of a surface discontinuity reduces the wall thickness below 87½ % of the specified nominal wall thickness at any point, the fitting shall be subject to rejection or to repair as provided in **12.1**.

12. Repair by Welding

12.1 Repair by Welding:

12.1.1 Repair welding, of the base metal by the manufacturer, is permissible for fittings made to the dimensional standards listed in **10.1** or for other standard fittings made for stock. Prior approval of the purchaser is required to repair special fittings made to the purchaser's requirements. Repair by welding shall neither exceed 10 % of the outside surface area of the fitting nor 33⅓ % of the nominal wall thickness.

12.1.2 The welding procedure and welders shall be qualified in accordance with Specification **A960/A960M**.

12.1.3 The alloy content (carbon, chromium, nickel, molybdenum, niobium, and titanium) of the deposited weld metal shall be within the same percentage range as permitted for the base metal. (**Warning**—When selecting the filler metal