



Designation: F724 – 23

# Standard Test Method for Outdoor Evaluation of Tire Sidewall Component Cracking Resistance<sup>1</sup>

This standard is issued under the fixed designation F724; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers procedures for evaluating passenger car tires for sidewall component integrity and cracking resistance, using an outdoor roadwheel.

1.2 This test method evaluates the resistance of tire sidewalls to dynamic weathering, atmospheric ozone cracking, fatigue cracking, or openings of splices within, or of junctures between, sidewall components and cracking at molded sidewall elements.

1.3 This test method is useful for evaluating tire black sidewalls, white, or other colored, sidewalls, and coverstrips.

1.4 This test method is limited to comparative performance testing between a “control” sidewall component or assembly and one or more experimental alternatives that are built onto the same tire (“multisection”) or onto tires that are identical in all respects other than the sidewall variation.

1.5 This test method is not applicable to evaluation of sidewall resistance to abrasion, as may be experienced in severe cornering or curb scuffing.

1.6 The values stated in SI units are to be regarded as the standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For specific precaution statements, see 5.2.

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F09 on Tires and is the direct responsibility of Subcommittee F09.30 on Laboratory (Non-Vehicular) Testing.

Current edition approved May 1, 2023. Published May 2023. Originally approved in 1981. Last previous edition approved in 2016 as F724 – 94a (2016). DOI: 10.1520/F0724-23.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D1149 Test Methods for Rubber Deterioration—Cracking in an Ozone Controlled Environment

D1171 Test Method for Rubber Deterioration—Surface Ozone Cracking Outdoors (Triangular Specimens)

F538 Terminology Relating to Characteristics and Performance of Tires

## 3. Terminology

3.1 *Definitions*:

3.1.1 *black sidewall, n*—a sidewall on which only black compounds comprise the outer visible surface of a tire. **F538**

3.1.2 *clinch strip, n*—high-modulus or high-hardness compound applied between the carcass and the sidewall in the bead area to reinforce the bead. **F538**

3.1.3 *coverstrip, n*—a thin layer of black compound that covers the unexposed white sidewall portion of a finished tire. **F538**

3.1.4 *crazing, n*—minute, closely grouped, generally superficial cracks that usually result from light-activated oxidation. **F538**

3.1.5 *flex cracking, v*—cracking primarily caused by application of mechanical stress-strain cycling. **F538**

3.1.6 *junction, n*—the interface between two different tire components or different compounds within the same component. **F538**

3.1.7 *junction cracking, n*—a crack with opening originating at a junction between two components. **F538**

3.1.8 *junction opening, n*—a separation developing in a junction. **F538**

3.1.9 *rim strip, n*—a layer of compound, with or without fabric reinforcement, that is applied at the bead to protect the carcass plies against damage from mounting tools and from rim chafing during service. **F538**

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

3.1.10 *sidewall*, *n*—of a tire, that portion of a tire between the tread and the bead. **F538**

3.1.11 *sidewall component*, *n*—an individual part of the sidewall construction, either a separate compound or a separately assembled piece. **F538**

3.1.12 *sidewall rubber*, *n*—the exterior rubber layer of a tire that extends over the sidewall part of the carcass. **F538**

3.1.13 *splice*, *n*—the joint formed either by overlapping or butting the ends of a given tire component in the course of assembling the tire. **F538**

3.1.14 *splice crack*, *n*—a crack originating at a splice. **F538**

3.1.15 *splice opening*, *n*—a parting of a splice along the interface of the assembled ends of a given component. **F538**

3.1.16 *veneer*, *n*—a thin layer of rubber covering the surface of the tire sidewall. **F538**

3.1.17 *weather cracking*, *n*—distinct surface cracks induced by action of ozone in those areas of sidewall that are under tension; the cracks usually form perpendicularly to the direction of stress.

3.1.18 *white sidewall*, *n*—a sidewall that contains a white (or light-colored) compound as a part of the total sidewall. **F538**

#### 4. Significance and Use

4.1 Test Methods **D1149** and **D1171** can be used to evaluate different aspects of fatigue and weather cracking resistance of sidewall component materials in the form of test specimens. The present method applies to complete tires that are subjected to actual weather exposure conditions. The present method is satisfactory for research and development purposes but is not applicable to regulatory statutes or purchase specifications until standard classifications of state of cracking, similar to those in Test Method **D1171**, can be established.

#### 5. Apparatus

5.1 *Outdoor Roadwheel*—An apparatus situated outdoors and consisting of:

5.1.1 One or more smooth steel road wheels of specified diameter. The road wheel(s) shall be wide enough to extend beyond the test tire foot print width. The road wheel diameter shall be no less than 610 mm (24 in.). Smaller diameter wheels may produce excessive flexing and premature extraneous tire failure.

5.1.2 Satellite stations for loading several test tires against the road wheel with known constant force.

5.1.2.1 Each satellite station can individually unload and withdraw the tire from contact with the road wheel in the event of an inflation pressure loss or other potentially catastrophic occurrence.

5.1.2.2 The tire-loading system may be done by any system that provides a constant force to maintain the desired tire deflection throughout the test.

5.1.3 A drive motor that can drive the road wheel(s), within  $\pm 1\%$  of a set test speed for extended periods of time. A commonly used speed is 48 km/h (30 mph).

5.1.4 System for determining accumulated cycles of rotation of each test tire.

#### 5.2 Safety Precautions:

5.2.1 The apparatus shall be surrounded by a suitable enclosure to trap tire fragments in the event of a catastrophic failure during the test.

5.2.2 The controls for the apparatus shall be situated outside the enclosure.

#### 6. Sampling

6.1 A sampling plan is not applicable since this test method is intended for research and development testing only. Test specimens (see Section 7) shall be tested simultaneously with a control specimen for direct comparison of relative performance.

#### 7. Test Specimens

7.1 A test specimen shall be a given assembly of sidewall components, specific as to component formulations, assembly cross-section geometry, and preparation procedure. The test specimen may cover the entire sidewall circumference of the test tire and be compared with a control tire or it may cover a section of the sidewall and be compared with a control section and other test specimen sections built onto the same (multi-section) tire.

7.2 A test specimen section shall cover  $\frac{1}{4}$  of the circumference of the tire sidewall.

7.3 In multisection tire tests, only specimens on the same side of the tire shall be compared directly.

#### 8. Selection and Preparation of Test Tires

8.1 For tire-to-tire comparative tests, all test tires shall have been manufactured within a 4 week period based on the date code and subjected to the same pretest conditions, particularly as related to heat and ultraviolet exposure.

8.2 Multisection test tires shall have been prepared with the test components (for example, varied compounds) having the same cross-sectional profile and dimensions, so as to avoid extraneous mechanical stress variability between the components, unless the profile variation is a test variable.

8.3 The test component surfaces of tires shall be washed with water to remove any temporary protective coating but shall not be subjected to solvent or other surface treatment (in the process of mounting, etc.) that may affect performance unless this is a part of the experimental study.

#### 9. Procedure

9.1 Mount a test tire on a rim contour as described by the TRA Yearbook<sup>3</sup> for its particular size. For tire-to-tire comparative tests, rims shall be of the same width.

9.2 Mount the tire with the valve at a convenient reference point for describing the locations of cracks or other degradation as they occur.

9.3 The tire shall be inflated to 138 kPa (20 psi) at  $38 \pm 3$  °C. This pressure facilitates the desired deflection of the tire

<sup>3</sup> Available from the Tire and Rim Association, Inc., 4000 Embassy Parkway, Suite 390, Akron, OH 44333.

(see 9.4.2) with moderate axle loading. Any alternative pressures shall be agreed upon between the test facility and the test requestor.

9.4 Install the tire on the test machine. Run the tire at 45 kph at full (test) load for 60 to 90 s to ensure that the beads have fully seated. Unload the tire and allow it to return to  $38 \pm 3$  °C. Adjust inflation pressure to the selected test pressure. Reload the tire and adjust the load to achieve the specified deflection, while the tire is stationary and in equilibrium with ambient temperature.

9.4.1 Measure sidewall deflection using a device and a method accurate to  $\pm 1$  %. An analog measuring device and method are described in **Annex A1**. Digital devices are also permitted.

9.4.2 Select the deflection to yield a relatively severe sidewall flexing without early durability failure of the tire. Use 30 % deflection for radial tires, 20 % for bias tires. Use lower deflection if the above levels produce early durability failure of tires.

9.5 Run the test tire against the road wheel continuously at the set axle loading associated with the initial inflation, the selected deflection, and selected speed, except for periodic inspection shutdowns.

9.6 Inspections of test tires are made commonly at two-day intervals.

9.6.1 Inspection includes:

9.6.1.1 Close visual (unmagnified) examination of the test component areas for crack initiation and propagation or other degradation development. In a multisection test tire, component performance should not be evaluated within 50 mm (2 in.) of segment junctures.

9.6.1.2 Examination of the tire for extraneous durability problems.

9.6.1.3 Inflation pressure and loaded deflection checks after the tire has cooled to ambient temperature. Air pressure is adjusted if necessary to return to the original cold starting pressure level.

**NOTE 1**—Cold tire deflections are used. Use of warm (from running) tire deflection is not feasible due to cool down errors when a number of tires are run simultaneously, and they must be measured for deflection sequentially during inspection shutdowns.

9.6.1.4 In the final inspection, measure the inflation pressure for comparison with the original value.

9.7 Test duration is discretionary but generally need not exceed 64 000 km (40 000 miles), which requires 56 to 60 days.

9.8 Data sheet formats for recording test conditions, periodic inspection data, and observations appear in **Figs. 1 and 2**.

## 10. Report

10.1 Full description of the tire, including brand, serial number, size, basic construction, and test variable construction features, etc.

10.2 Rim diameter, width and contour.

10.3 Description of test machine and operation conditions:

10.3.1 Road wheel diameter,

10.3.2 Road wheel speed,

10.3.3 Axle load,

10.3.4 Tire inflation pressure, cold starting at ambient temperature,

10.3.5 Loaded tire deflection, cold starting,

10.3.6 Total tire test time and cycles of rotation or equivalent travel distance,

10.3.7 Inclusive dates between which the test was run, and

10.3.8 Specific data characterizing atmospheric conditions, such as ozone concentration, solar radiation, rain, chemical agents, and ambient temperature shall be recorded if available, but are not necessary since the test always involves a control tire or tire multisection(s) running concurrently with the test tires or multisection(s), as the base line for assessing relative performance.

10.4 *Test Results:*

10.4.1 Notations describing the types of flaws initiated (that is, cracks, openings, etc.), their number, and approximate dimensions (length and depth) or qualitative comments if measurements are not feasible.

10.4.2 Elapsed test time and tire cycles of rotation, at which flaws initiated or progressed significantly.

10.4.3 Only major differences in flaw development are significant in comparing relative performance of test specimens. For example, general occurrence of or deep penetration of flaws of a given type in white sidewall A versus essentially no occurrence in white sidewall B.

10.5 Notations of inflation pressure adjustments required during the test.

10.6 Inflated, unloaded tire section width and height before and after test measured at ambient temperature and the original inflation pressure.

## 11. Precision and Bias

11.1 No statement is made about either the precision or bias of this test method since the result merely states whether there is conformance to the criteria for success specified in this procedure.

## 12. Keywords

12.1 component; cracking; evaluation; outdoor; resistance; road wheel; sidewall; tire

PROGRAM	
TIRE BRAND	
MANUFACTURER NAME	
EXPERIMENT NUMBER	
TIRE TEST NUMBER	
TIRE SERIAL NUMBER	

TEST INFORMATION	
MACHINE TEST POSITION	
TIRE SIZE	
RIM SIZE/CONTOUR	
GENERAL CONSTRUCTION	
TREAD WING CONSTRUCTION (TOS/SOT)	
OTHER (MULTISECTION CONSTRUCTION DETAILS)	
ROADWHEEL DIAMETER (M)	

TEST CONDITIONS	
INFLATION PRESSURE (138 KPA/OTHER)	
TARGET DEFLECTION (20%, 25%, 30%, OTHER)	
ROADWHEEL SPEED (KPH)	
AXLE LOAD (KG)	
UNLOADED SECTION HEIGHT (MM)	
LOADED SECTION HEIGHT (MM)	
ACTUAL DEFLECTION (%)	

<https://standards.iteh.ai/catalog/standards/sist/3d06e744-9818-49c9-b791-295d27b0bfd8/astm-f724-23>

TEST DATA						
DATE	TEST TIME (HOURS)	TIRE DURATION / KC OF TIRE ROTATION		AMBIENT TEMPERATURE (°C)	INFLATION PRESSURE (KPA)*	REMARKS
		PERIOD	CUMULATIVE			

TIRE INFLATION TAKEN ON NON-RUNNING TIRE AT 21 - 25 °C

FIG. 1 Data Recording Format