



Designation: B689 – 97 (Reapproved 2023)

# Standard Specification for Electroplated Engineering Nickel Coatings<sup>1</sup>

This standard is issued under the fixed designation B689; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification covers the requirements for electroplated nickel coatings applied to metal products for engineering applications, for example, for use as a buildup for mismatched or worn parts, for electronic applications, including as underplates in contacts or interconnections, and in certain joining applications.

1.2 Electroplating of nickel for engineering applications (Note 1) requires technical considerations significantly different from decorative applications because the following functional properties are important:

- 1.2.1 Hardness, strength, and ductility,
- 1.2.2 Wear resistance,
- 1.2.3 Load bearing characteristics,
- 1.2.4 Corrosion resistance,
- 1.2.5 Heat scaling resistance,
- 1.2.6 Fretting resistance, and
- 1.2.7 Fatigue resistance.

NOTE 1—Functional electroplated nickel coatings usually contain about 99 % nickel, and are most frequently electrodeposited from a Watts nickel bath or a nickel sulfamate bath. Typical mechanical properties of nickel electroplated from these baths, and the combined effect of bath operation and solution composition variables on the mechanical properties of the electrodeposit are given in Guide B832. When electroplated nickel is required to have higher hardnesses, greater wear resistance, certain residual stress values and certain leveling characteristics, sulfur and other substances are incorporated in the nickel deposit through the use of certain addition agents in the electroplating solution. For the effect of such additives, see Section 4 and Annex A3. Cobalt salts are sometimes added to the plating solution to produce harder nickel alloy deposits.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standard-*

*ization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

- B183 Practice for Preparation of Low-Carbon Steel for Electroplating
- B242 Guide for Preparation of High-Carbon Steel for Electroplating
- B252 Guide for Preparation of Zinc Alloy Die Castings for Electroplating and Conversion Coatings
- B253 Guide for Preparation of Aluminum Alloys for Electroplating
- B254 Practice for Preparation of and Electroplating on Stainless Steel
- B281 Practice for Preparation of Copper and Copper-Base Alloys for Electroplating and Conversion Coatings
- B320 Practice for Preparation of Iron Castings for Electroplating
- B322 Guide for Cleaning Metals Prior to Electroplating
- B343 Practice for Preparation of Nickel for Electroplating with Nickel
- B374 Terminology Relating to Electroplating
- B480 Guide for Preparation of Magnesium and Magnesium Alloys for Electroplating
- B487 Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section
- B499 Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals
- B507 Practice for Design of Articles to Be Electroplated on Racks
- B530 Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Electrodeposited Nickel Coatings on Magnetic and Nonmagnetic Substrates

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.03 on Engineering Coatings.

Current edition approved May 1, 2023. Published June 2023. Originally approved in 1981. Last previous edition approved in 2018 as B689 – 97 (2018) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/B0689-97R23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- B558** Practice for Preparation of Nickel Alloys for Electroplating
- B568** Test Method for Measurement of Coating Thickness by X-Ray Spectrometry
- B571** Practice for Qualitative Adhesion Testing of Metallic Coatings
- B602** Guide for Attribute Sampling of Metallic and Inorganic Coatings
- B697** Guide for Selection of Sampling Plans for Inspection of Electrodeposited Metallic and Inorganic Coatings
- B765** Guide for Selection of Porosity and Gross Defect Tests for Electrodeposits and Related Metallic Coatings
- B809** Test Method for Porosity in Metallic Coatings by Humid Sulfur Vapor (“Flowers-of-Sulfur”)
- B832** Guide for Electroforming with Nickel and Copper
- B849** Specification for Pre-Treatments of Iron or Steel for Reducing Risk of Hydrogen Embrittlement
- B850** Guide for Post-Coating Treatments of Steel for Reducing the Risk of Hydrogen Embrittlement
- B851** Specification for Automated Controlled Shot Peening of Metallic Articles Prior to Nickel, Autocatalytic Nickel, or Chromium Plating, or as Final Finish
- D762** Method of Test for Hot Extraction of Asphaltic Materials and Recovery of Bitumen by the Modified Abson Procedure (Withdrawn 1965)<sup>3</sup>
- D1193** Specification for Reagent Water
- D3951** Practice for Commercial Packaging
- F519** Test Method for Mechanical Hydrogen Embrittlement Evaluation of Plating/Coating Processes and Service Environments
- 2.2 *Military Standards:*
- MIL-R-81841** Rotary Flap Peening of Metal Parts<sup>4</sup>
- MIL-S-13165** Shot Peening of Metal Parts<sup>4</sup>
- MIL-W-81840** Rotary Flap Peening Wheels<sup>4</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *significant surfaces*—those surfaces normally visible (directly or by reflection) that are essential to the appearance or serviceability of the article when assembled in normal position; or that can be the source of corrosion products that deface visible surfaces on the assembled article. When necessary, the significant surfaces shall be indicated on the drawing for the article, or by the provision of suitably marked samples.

3.1.1.1 *Discussion*—The thickness of the electrodeposit in holes, corners, recesses, and other areas where thickness cannot be controlled under normal electroplating conditions shall be specified by the buyer (see **Note 3**).

3.1.1.2 *Discussion*—When a deposit of controlled thickness is required in holes, corners, recesses, and similar areas, special racking, auxiliary anodes or shielding will be necessary.

3.2 Terminology **B374** contains most of the terms used in this specification.

### 4. Classification

4.1 Electroplated nickel shall be provided in any one of the following three types (**Note 2**):

4.1.1 *Type 1*—Nickel electroplated from solutions not containing hardeners, brighteners, or stress control additives.

4.1.2 *Type 2*—Nickel electrodeposits used at moderate temperatures and containing sulfur or other codeposited elements or compounds that are present to increase the hardness, to refine the grain structure, or to control the internal stress of the electrodeposited nickel.

4.1.3 *Type 3*—Electrodeposited nickel containing dispersed submicron particles, such as silicon carbide, tungsten carbide, and aluminum oxide that are present to increase hardness and wear resistance at temperatures above 325 °C (618 °F).

**NOTE 2**—Good adhesion of electroplated nickel to stainless steels and high alloy steels usually requires a preliminary strike of electrodeposited nickel. The recommended practices for the preparation of and electroplating on stainless steels and nickel alloys are given in Practices **B254** and **B558**, respectively.

4.2 *Thickness Classification*—The electroplated nickel thickness, in view of the wide variety for industrial uses, shall be specified according to the following classes (**Note 3**):

Class	Minimum Nickel Thickness, μm
5	5
25	25
50	50
100	100
200	200
X	thickness as specified

**NOTE 3**—There is no technical limit to the nickel thickness that can be electroplated. There are practical limits to nickel thickness and uniformity of thickness distribution caused by the size and geometric configuration of the parts. (See **3.1**.)

### 5. Ordering Information

5.1 The buyer shall supply the following information to the seller in either the purchase order or engineering drawings, marked samples, or other governing documents.

5.1.1 Title, ASTM designation number, and year of the standard.

5.1.2 Classification type and thickness classification of electroplated nickel to be applied (see **4.1** and **4.2**).

5.1.3 Significant surfaces (see **3.1**).

5.1.4 Sampling plan (see **Section 8**).

5.1.5 Number of test specimens for destructive testing (see **7.1**). Identify the substrate material by alloy identification, such as by ASTM, AISI, or SAE numbers, or by equivalent composition information.

5.1.6 The thickness, adhesion, porosity, and hydrogen embrittlement tests required. See **6.3 – 6.7**.

5.1.7 The required grinding or polishing operations of the basis metal as are necessary to yield deposit with the desired properties.

5.1.8 Where required, the basis metal finish shall be specified in terms of centerline average (CLA), or arithmetical average (AA).

5.1.9 Appearance: whether superficial staining from final rinsing or discoloration after baking is acceptable.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

5.1.10 Where required, post-treatment grinding or machining shall be specified for parts which are to be electroplated and subsequently ground or machined to size.

5.1.11 Where required dimensional tolerances allowed for the specified electroplated nickel thickness or class shall be specified.

5.1.12 Where required, microhardness ranges shall be specified for the nickel deposit.

5.1.13 The buyer of the parts to be electroplated shall provide the electroplater with the following information as required:

5.1.13.1 Ultimate tensile strength of the parts.

5.1.13.2 Rockwell C hardness of the parts.

5.1.13.3 Heat treatment for stress relief, whether it has been performed or is required (see 6.2).

5.1.13.4 Heat treatment for hydrogen embrittlement relief (see 6.3 and Test Method F519).

5.1.13.5 Tensile loads required for the embrittlement relief test, if applicable.

5.1.13.6 Procedures and requirements for peening to induce residual compressive stress in specified surfaces (see Note 4 and 6.4).

NOTE 4—Electroplating on hardened (high alloy and high carbon) steels can reduce the fatigue strength of the metal parts. This must be considered if the parts will be subjected to repeated applications of complex load patterns in service. Shot peening of significant surfaces before electroplating can reduce the loss of fatigue strength.<sup>5</sup> Rotary flap peening, a manual method, can also be used in the repair of components in the field where conventional shot peening equipment is not available. If rotary flap peening is used, extreme care should be taken to ensure that the entire surface to be treated has been peened. Also, reduction in the fatigue life of nickel-electroplated steels can be reduced by considering the relations among the variables that influence fatigue life of nickel-electroplated, hardened steels.<sup>6</sup>

5.1.13.7 What, if any, mechanical treatment was applied by the manufacturer to the significant surface; that is, particulate blasting, grinding, polishing, or peening.

5.1.14 The manufacturer of the parts to be electroplated shall provide the electroplating facility with test specimens (see Section 7) to be electroplated for conformance tests as requested for preparation, control, inspection, and lot acceptance.

## 6. Coating Requirements

### 6.1 Appearance:

6.1.1 The coating on the significant surfaces of the product shall be smooth and free of visual defects such as blisters, pits, roughness, cracks, flaking, burned deposits, and uncoated areas. Visual defects are defined as those visible, unmagnified, to the unaided eye, 20/20 vision, or vision corrected to 20/20. The boundaries of electroplating that cover only a portion of the surface shall, after finishing as indicated in the drawing, be free of beads, nodules, jagged edges, and other detrimental irregularities. Imperfections and variations in appearance in the coating that arise from surface conditions of the basis metal

<sup>5</sup> Hammond, R. A. F., "Technical Proceedings," *TPAEA*, American Electroplaters' Society, 1964, pp. 9–20.

<sup>6</sup> Sanborn, C. B., and Carlin, F. S., "Influence of Nickel Plating on the Fatigue Life of Hardened Steel," *Electrodeposited Metals for Selected Applications*. Battelle Memorial Institute, Columbus, OH, November 1973.

(scratches, pores, roll marks, inclusions, etc.) and that persist in the finish despite the observance of good metal finishing practices shall not be cause for rejection (Note 5).

6.1.2 For parts that are electroplated and subsequently ground to size, the grinding shall be done with a sulfur-free liquid coolant, never dry, and with a sufficiently light cut to prevent cracking.

NOTE 5—Applied finishes generally perform better in service when the substrate over which they are applied is smooth and free of torn metal, inclusions, pores, and other defects. It is recommended that the specifications covering the unfinished product provide limits for these defects. A metal finisher can often remove defects through special treatments, such as grinding, polishing, abrasive blasting, chemical treatments, and electropolishing. However, these are not normal in the treatment steps preceding the application of the finish. When they are desired they must be stated in the purchase order (see 5.1.7).

6.2 *Pretreatment of Iron and Steel for Reducing the Risk of Hydrogen Embrittlement*—Parts for critical applications that are made of steels with ultimate tensile strengths of 1000 MPa, hardness of 31 HRC or greater, that have been machined, ground, cold formed, or cold straightened subsequent to heat treatment, shall require stress relief heat treatment when specified by the purchaser, the tensile strength to be supplied by the purchaser. Specification B849 may be consulted for a list of pretreatments that are used widely.

6.3 *Post-Coating Treatments of Iron and Steel for Reducing the Risk of Hydrogen Embrittlement*—Parts for critical applications that are made of steels with ultimate tensile strengths of 1000 MPa, hardness of 31 HRC or greater, as well as surface hardened parts, shall require post coating hydrogen embrittlement relief baking when specified by the purchaser, the tensile strength to be supplied by the purchaser. Specification B850 may be consulted for a list of post treatments that are used widely.

6.4 *Peening of Metal Parts*—If peening is required before electroplating to induce residual compressive stress to increase fatigue strength and resistance to stress corrosion cracking of the metal parts, refer to Specification B851 and to MIL-S-13165, MIL-R-81841, and MIL-W-81840.

6.5 *Thickness*—The thickness of the coating everywhere on the significant surface shall conform to the requirements of the specified class as defined in 4.2 (see Note 6 and 7.2).

NOTE 6—The coating thickness requirements of this specification are minimum requirements; that is, the coating thickness is required to equal or exceed the specified thickness everywhere on any significant surface (see 3.1.1). Variation in the coating thickness from point to point on a coated article is an inherent characteristic of the electroplating process. Therefore, the coating thickness will have to exceed the specified value at some points on the significant surfaces to ensure that the thickness equals or exceeds the minimum specified value at all points. Hence, in most cases, the average coating thickness on an article will be greater than the specified value; how much greater is largely determined by the shape of the article (see Practice B507) and the characteristics of the electroplating process. In addition, the average coating thickness on articles will vary from article to article within a production lot. Therefore, if all of the articles in a production lot are to meet the thickness requirement, the average coating thickness for the production lot as a whole will be greater than the average necessary to assure that a single article meets the requirement.

6.6 *Adhesion*—The coating shall be sufficiently adherent to the basis metal to pass the adhesion test specified (see 7.3).

6.7 *Porosity*—The coating shall be sufficiently free of pores to pass the porosity test specified (see 7.4).

6.8 *Workmanship*—Adding to (spotting-in) or double electroplating, unless evidence of a satisfactory bond is established, shall be cause for rejection (see 7.3). Parts having a hardness greater than 35 HRC (equivalent to a tensile strength of 1200 MPa or greater) that have been acid-stripped for recoating shall be rebaked for embrittlement relief (see 6.2) before electroplating. Stress relieving after stripping is not necessary if the stripping is done anodically in an alkaline solution. Within the areas designated as significant surfaces there shall be no uncoated (or bare) areas (see 4.1). Contact marks shall be minimized in size and frequency. When contacts must be located on significant areas, they shall be placed in areas of minimum exposure to service or environmental conditions as designated by the purchaser. Superficial staining resulting from rinsing, or slight discoloration resulting from baking operations to relieve embrittlement shall not be cause for rejection unless specified to the contrary by the purchaser. (See 5.1.9.) Electrodeposited nickel that is to be finished by machining may have slight surface blemishes in the as-electroplated condition provided that these can be eliminated by the machining operation.

#### 6.9 *Supplementary Requirements:*

6.9.1 *Packaging*—If packaging requirements are to be met under this Specification, they shall be in accordance with Practice D3951, or as specified in the contract or order.

NOTE 7—Some contemporary packaging materials may emit fumes that are deleterious to the surface of the coating.

## 7. Test Methods

### 7.1 *Special Test Specimens:*

7.1.1 The permission or the requirement to use special test specimens, the number to be used, the material from which they are to be made, and their shape and size shall be stated by the purchaser.

NOTE 8—Test specimens often are used to represent the coated articles in a test if the articles are of a size, shape, or material that is not suitable for the test, or if it is preferred not to submit articles to a destructive test because, for example, the articles are expensive or few in number. The specimen should duplicate the characteristics of the article that influence the property being tested.

7.1.2 Special test specimens used to represent articles in an adhesion, solderability, porosity, corrosion resistance, or appearance test shall be made of the same material, shall be in the same metallurgical condition, and shall have the same surface condition as the articles they represent, and they shall be placed in the production lot of and be processed along with the articles they represent.

7.1.3 Special test specimens used to represent articles in a coating thickness test may be made of a material that is suitable for the test method even if the represented article is not of the same material. For example, a low-carbon steel specimen may represent a brass article when the magnetic thickness test is used (Test Method B499). The thickness specimen need not be carried through the complete process with the represented article. If not, it shall be introduced into the process at the point where the coating is applied and it shall be carried through all

steps that have a bearing on the coating thickness. In rack plating, the specimen shall be racked in the same way with the same distance from and orientation with the anodes and other items in the process as the article it represents.

NOTE 9—When special test specimens are used to represent coated articles in a thickness test, the specimens will not necessarily have the same thickness and thickness distribution as the articles unless the specimens and the articles are of the same general size and shape. Therefore, before finished articles can be accepted on the basis of a thickness test performed on special test specimens, the relationship between the thickness on the specimen and the thickness on the part needs to be established. The criterion of acceptance is that thickness on the specimen that corresponds to the required thickness on the article.

7.2 *Thickness*—The thickness of the electroplated nickel shall be measured by one of the following methods.

#### *Destructive Methods:*

Microscopical method	B487
Coulometric method	B504

#### *Nondestructive Methods:*

Magnetic method	B530
X-Ray method	B568

If the accuracy of the thickness measurement is to be 10 % or less, then Test Method B487 (Microscopical) should not be used for thicknesses less than 10 µm. Test Method B530 (Magnetic) should not be used for thicknesses less than 10 µm. Test Method B568 (X-ray) is instrument-dependent with regard to accuracy with increasing nickel thicknesses.

NOTE 10—Since many factors influence the accuracy of each thickness test method, the buyer is advised to review the test method being selected. Type 2 nickel coatings produced with certain organic additives can exhibit significant leveling properties on rough surfaces where less nickel is deposited on sharper points and more in depressions of a microprofile. Thickness measurements with the microscopical method can show large differences on these rough profiles.

### 7.3 *Adhesion:*

7.3.1 The coated article or designated test specimen shall pass one of the following tests, or any special test particular to the function of the part as specified by the purchaser:

- 7.3.1.1 Bend test,
- 7.3.1.2 File test,
- 7.3.1.3 Heat and quench test, or
- 7.3.1.4 Push test.

7.3.2 These and other adhesion tests are described in Test Methods B571. The test selected should take into consideration the size, shape, or thickness of the part. Adhesion tests may at times fail to detect adhesion failure; subsequent fabrication may reveal poor or inadequate adhesion, which shall be cause for rejection.

NOTE 11—Adhesion is influenced by the method of pretreating the basis metal and the type of basis metal used. Helpful information is given in Practices B183, B242, B252, B253, B254, B281, B320, B322, and B343, and Guide B480.

7.4 *Porosity*—The coating shall pass one of the following tests as specified by the purchaser; aid in the selection is contained in Guide B765.

7.4.1 *Hot Water Porosity Test*—Conduct according to the procedure described in Annex A1; observe the results after 60 min. The part fails if more than the number of pores specified by the purchaser per part or per unit area is found.

7.4.2 *Ferroxyl Test*—Conduct in accordance with the procedure described in **Annex A2**; observe the results after 10 min. The part fails if more than the number of pores specified by the purchaser per part or per unit area is found.

7.4.3 *Flowers of Sulfur Test*—The tests described in 7.4.1 – 7.4.3 are used for ferrous bases. Test Method **B809**, the Flowers-of-Sulfur (or Humid Sulfur Vapor) test, can be used for nickel on copper and copper alloy substrates. Also refer to Guide **B765** for more information.

7.5 *Hydrogen Embrittlement Relief*—Parts shall be examined for cracks indicating embrittlement failure, or the effectiveness of the hydrogen embrittlement relief shall be determined by a procedure specified by the purchaser.

NOTE 12—When both destructive and non-destructive tests exist for the measurement of a characteristic, the purchaser needs to state which is to be used so that the proper sampling plan is selected. A test may destroy the coating but in a non-critical area; or, although it may destroy the coating, a tested part can be reclaimed by stripping and recoating. The purchaser needs to state whether the test is to be considered destructive or non-destructive.

## 8. Sampling Requirements

8.1 The sampling plan used for the inspection of a quantity of the coated articles shall be as agreed upon between the purchaser and the supplier.

NOTE 13—Usually, when a collection of coated articles, the inspection lot (8.2), is examined for compliance with the requirements placed on the articles, a relatively small number of the articles, the sample, is selected at random and is inspected. The inspection lot is then classified as complying or not complying with the requirements based on the results of the inspection of the sample. The size of the sample and the criteria of compliance are determined by the application of statistics. The procedure is known as sampling inspection. Three standards, Test Method **B602**, Guide **B697**, and Methods **D762** contain sampling plans that are designed for the sampling inspection of coatings.

Test Method **B602** contains four sampling plans, three for use with tests that are non-destructive and one when they are destructive. The buyer and

seller may agree on the plan or plans to be used. If they do not, Test Method **B602** identifies the plan to be used.

Guide **B697** provides a large number of plans and also gives guidance in the selection of a plan. When Guide **B697** is specified, the buyer and seller need to agree on the plan to be used.

Methods **D762** can be used only for coating requirements that have numerical limit, such as coating thickness. The test must yield a numerical value and certain statistical requirements must be met. Methods **D762** contains several plans and also gives instructions for calculating plans to meet special needs. The buyer and the seller may agree on the plan or plans to be used. If they do not, Methods **D762** identifies the plan to be used.

8.2 An inspection lot shall be defined as a collection of coated articles that are of the same kind, that have been produced to the same specifications, that have been coated by a single supplier at one time, or at approximately the same time, under essentially identical conditions, and that are submitted for acceptance or rejection as a group.

8.3 If special test specimens are used to represent the coated articles in a test, the number used shall be that required in 7.1.1.

## 9. Rejection and Rehearing

9.1 Articles that fail to conform to the requirements of this standard shall be rejected. Rejection shall be reported to the producer or supplier promptly, and in writing. In case of dissatisfaction with the results of a test, the producer or supplier may make a claim for a rehearing. Finishes that show imperfections during subsequent manufacturing operations may be rejected.

## 10. Certification

10.1 The purchaser may require in the purchase order or contract, that the producer or supplier give to the purchaser, certification that the finish was produced and tested in accordance with this standard and met the requirements. The purchaser may similarly require that a report of the test results be furnished.

# ANNEXES

## (Mandatory Information)

### A1. HOT WATER POROSITY TEST

#### A1.1 General

A1.1.1 This method reveals discontinuities, such as pores, in electroplated nickel on iron or steel. It is noncorrosive to nickel.

#### A1.2 Materials

A1.2.1 A stainless steel (Type 304 or 316) or rubber-lined or glass vessel equipped to suspend the part that should be insulated from contact with metal vessels. The significant electroplated areas should be totally immersed in clean water that meets Specification **D1193**, Type IV water standard or another type of water approved by the purchaser. The pH of the water shall be maintained between 6.0 and 7.5. Additives

required for pH control shall be noncorrosive to nickel and shall be approved by the purchaser, for example, pH can be adjusted by introducing CO<sub>2</sub> or by additions of H<sub>2</sub>SO<sub>4</sub> or acetic acid, or NaOH. A source of oil-free air shall be available to aerate the water with agitation vigorous enough to prevent air bubbles from clinging to significant surfaces of the part.

NOTE A1.1—Ordinarily, common factory air supply does not meet the oil-free requirement.

#### A1.3 Procedure

A1.3.1 Clean and degrease the electroplated surface to be tested to provide a water break free surface. Totally immerse the electroplated areas of the part in the water which has been heated to 85 °C. The 60 min test period starts when the water