



Designation: E956 – 83 (Reapproved 2023)

Standard Classification for Municipal Mixed Nonferrous Metals (MNM)¹

This standard is issued under the fixed designation E956; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers municipal mixed nonferrous metals (MNM), not source-separated, that are recovered from municipal waste destined for disposal.

1.2 The mixed nonferrous metals (MNM) have been subdivided according to processing history, nonferrous metal content, size, and moisture content.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D2013/D2013M Practice for Preparing Coal Samples for Analysis

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process

E276 Test Method for Particle Size or Screen Analysis at

4.75 mm (No. 4) Sieve and Finer for Metal-Bearing Ores and Related Materials

E753 Specification for Municipal Aluminum Scrap (MAS) (Discontinued 2001) (Withdrawn 2001)³

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *loose combustible material (organic)*—loose combustible organics (LCO) that consist of, but are not limited to, nonmetallic materials such as paper, rags, plastic, rubber, wood, food wastes, and yard or lawn wastes, etc., which are not permanently attached to noncombustible objects. The LCOs are defined as material larger than No. 12 Mesh (U.S. Standard Sieve) as stated in Specification E11. A determination of LCOs is best done by sampling the material and handpicking, hand cleaning, and visually identifying the materials described previously.

3.1.2 *mixed nonferrous metal content*—mixed nonferrous metals remaining after removal of magnetics, combustibles, and other nonmetals (for example, glass, rock, etc.). Further methods of separation and identification may be agreed upon between purchaser and seller and can include picking or dense-media separation.

3.1.3 *moisture percent—liquid content*, as determined by weight loss when sample material is dried to a constant weight at 110 ± 5 °C.

3.1.4 *total combustibles*—materials that include paints, lacquers, coatings, plastics, etc., associated with the original nonferrous products, as well as combustible materials (paper, plastic, textile, etc.) which become associated with the nonferrous product after it is manufactured.

4. Significance and Use

4.1 This classification is intended for use in the marketing of mixed nonferrous metals.

4.2 Mixed nonferrous metals covered by this classification are suitable for use by one or more of the following industries:

4.2.1 Secondary aluminum smelters,

4.2.2 Primary aluminum producers,

¹ This classification is under the jurisdiction of ASTM Committee D34 on Waste Management and is the direct responsibility of Subcommittee D34.03 on Treatment, Recovery and Reuse.

Current edition approved June 1, 2023. Published June 2023. Originally approved in 1983. Last previous edition approved in 2015 as E956 – 83 (2015). DOI: 10.1520/E0956-83R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- 4.2.3 Scrap dealers and processors,
- 4.2.4 Zinc refiners, and
- 4.2.5 Copper refiners.

5. Basis of Classification (refer to **Table 1**)

5.1 This classification covers material either processed to recover aluminum or not processed to recover aluminum.

5.2 This classification consists of four types of MNM, based on nonferrous metal content. The four types of MNM are further subdivided into three grades, based on size. The three grades of MNM are further subdivided into two classes, based on moisture content.

6. Ordering Information

6.1 Mixed nonferrous metals may be identified using the criteria in **Table 1**. This is an unusual material, and the table is included for information purposes rather than to establish limits. The unit operations used to recover MNM may aid the purchaser and seller in establishing a classification. Some of the more common unit operations used to recover MNM include the following:

6.1.1 *Wet Processing*—Water elutriators, dense media, and mineral jig.

6.1.2 *Dry Processing*—Air classifier, air knife, gravity or concentrating table, Humphrey spiral, eddy-current separator, electrostatic separator, and handpicking.

6.2 It is recognized that variations in the MNM may occur due to the heterogeneous nature of the solid waste stream. The criteria indicated are intended as a means for the purchaser and the seller to establish the value and quality of the MNM.

6.3 Mixed nonferrous metals shall be considered to be of a particular classification if the value for each component specified, as obtained by the test method agreed upon between the purchaser and seller, shall not exceed any of the limits for that grade.

7. Physical Requirements

7.1 In addition to **Table 1**, the MNM physical requirements include the following:

7.1.1 *Bulk Density*—The density for MNM is not specified and shall be agreed upon between the purchaser and the seller.

7.1.2 *Fineness*—Acceptability of contained fines shall be determined by the purchaser and seller.

7.1.3 *Loose Combustibles*—As agreed upon between purchaser and seller.

7.1.4 *Magnetics*—The presence of free magnetic material is not specified and shall be as agreed upon between the purchaser and seller as part of the purchase contract.

8. Sampling

8.1 Sampling shall be in accordance with the procedures described in **Annex A1** or **Annex A2**. Either procedure may be used, as determined by agreement between the purchaser and the seller.

8.1.1 **Annex A1** covers sampling at the point of origin.

8.1.2 **Annex A2** covers sampling at the point of receipt.

9. Test Methods

9.1 Determine the properties of fineness, moisture, and metal recovery in accordance with the procedures described in **Annex A3**.

10. Rejection and Rehearing

10.1 Material that fails to conform to the requirements of this classification may be rejected. Rejection should be reported to the seller promptly and in writing. In case of dissatisfaction with the results of the test, the seller may make claim for a rehearing.

11. Shipping

11.1 Mixed nonferrous metals shall be shipped in rail cars, trailers, or other containers as agreed upon between the purchaser and the seller. The shipping equipment shall be sufficiently watertight to prevent the MNM from becoming wet during shipment.

TABLE 1 Classification of Municipal Mixed Nonferrous Metals (MNM)^A

Classification	Type I Over 90 % MNM	Type II 50 to 90 % MNM	Type III 30 to 50 % MNM	Type IV Less Than 30 % MNM
Grades	1	2	3	
	over 6 in. (150 mm)	2 to 6 in. (50 to 150 mm) incl	under 2 in. (50 mm)	
Class	A		B	
	high (5 % moisture and over)		low (under 5 % moisture)	

^A It is important for both purchaser and seller to note whether material *had been* processed to recover aluminum or whether it *had not been* processed to recover aluminum and what, if any, procedures were used.

ANNEXES
(Mandatory Information)
A1. TEST METHOD FOR COLLECTION OF A SAMPLE OF MNM SCRAP RECOVERED FROM MUNICIPAL SOLID WASTE AND ITS PREPARATION FOR ANALYSIS
A1.1 Scope

A1.1.1 This test method describes procedures for collection of a sample of MNM scrap recovered from municipal refuse, and the preparation and secondary sampling of the metal for analysis.

A1.2 Summary of Test Method

A1.2.1 A selected size, gross sample of MNM scrap is taken from the metal recovery system conveyor in increments. Sample increments are taken at timed intervals from a full cross section of the conveyor while it is stopped, or by briefly taking the total flow at the discharge of the conveyor while it is moving.

A1.2.2 The quantity of gross sample may be further reduced by mixing, cone-and-quarter sampling, and riffling.

A1.3 General Precautions

A1.3.1 In solids sampling, each step must be designed to eliminate accidental classification by size or gravity. Different sizes usually have different analyses.

A1.3.2 The increments obtained during the sampling period shall be protected from changes in composition due to exposure to the weather.

A1.3.3 Plan the sampling arrangement to avoid contamination of the increments with foreign material.

A1.3.4 A satisfactory sampling arrangement is one that takes an unbiased sample at the desired degree of precision of the constituent for which the sample is to be analyzed. The weight or volume of the collected sample is compared with that of the total lot to ensure a constant sampling ratio.

A1.3.5 It is preferable that the MNM scrap be weighed and sampled at about the same time. If there is a long lapse in time between these two events, both the purchaser and seller should give consideration to changes in moisture during this interval and the consequent shift in relationship of moisture to the true content at the instant when ownership of the nonferrous metal scrap transfers from one to the other.

A1.3.6 Samples and subsamples shall be collected in such a manner that there is no unmeasured loss of moisture of significant amount. The samples shall be weighed before and after drying or other operations to measure all significant weight loss. The material balances shall be adjusted accordingly.

A1.4 Selection of Gross Sample Size

A1.4.1 Choose the gross sample size by methods given in Practice E122, whenever practicable. The chief difficulty for implementing this practice can be that insufficient information concerning possible variation is available. This information

should be gathered with practice. Due to the heterogeneity in size and type of material comprising municipal solid waste, the choice of a large sample is desirable.

A1.4.2 Shredding is recommended for metals larger than 4 to 6 in. (100 to 150 mm) for ease in sampling and handling.

A1.5 Taking a Gross Sample

A1.5.1 In order to obtain complete representation of materials in a gross sample, it is desirable that the sample increments be withdrawn from the full cross section of the stream. The best possible increment is either a full cross section removed from a stopped conveyor belt or the total flow at the discharge of the moving conveyor taken during a suitable interval of time.

A1.5.2 The choice of sample size can be estimated using Practice E122. It is imperative for a given degree of precision that not less than the minimum size and number of sample increments be collected from a lot (see Table A1.1).

A1.5.3 *Number of Gross Samples*—For quantities up to approximately 20 tons, it is recommended that one gross sample represent the lot. Take this sample in accordance with the requirements prescribed in Table A1.1.

A1.5.4 *Distribution of Increments*—It is essential that the increments be distributed throughout the lot to be sampled. The taking of increments shall be at regularly spaced intervals.

A1.6 Sample Preparation

A1.6.1 Cone and quarter the sample until approximately 2 ft³ (0.06 m³) remains. Pile the material to be sampled into a conical heap and then spread out into a circular cake. Divide the cake into quarters, take two of the diagonally opposite quarters as the sample, and reject the two remaining quarters. Collect the two quarters taken as the sample and repeat the procedure of coning and quartering until the desired size is obtained.

A1.6.2 Divide the sample into approximately equal parts. Take one half 1 ft³ (0.03 m³) for use in the melt test (see Annex A3). Divide the sample by riffling until the analytical sample is obtained. (Typical rifflers can be found in the apparatus section of Practice D2013/D2013M.)

A1.6.3 Store the prepared analytical sample in a covered, labeled, corrosion-resistant metal can or plastic container until needed for chemical analysis.

TABLE A1.1 Number and Weight of Increments for Sampling

Top Size, in. (mm)	5/8 (15)	2 (50)	6 (150)	12 (300)
Minimum number of increments	15	15	15	15
Minimum weight of increments, lb (kg)	2 (1)	6 (3)	18 (9)	36 (18)