



Designation: D4122 – 17 (Reapproved 2023)

Standard Practice for Carbon Black—Evaluation of an Industry Reference Black¹

This standard is issued under the fixed designation D4122; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers guidelines for the production and testing for uniformity of a lot of carbon black to be used as an Industry Reference Black (IRB).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D1506 Test Methods for Carbon Black—Ash Content
- D1508 Test Method for Carbon Black, Pelleted Fines and Attrition
- D1509 Test Methods for Carbon Black—Heating Loss
- D1510 Test Method for Carbon Black—Iodine Adsorption Number
- D1513 Test Method for Carbon Black, Pelleted—Pour Density
- D1514 Test Method for Carbon Black—Sieve Residue
- D1618 Test Method for Carbon Black Extractables—

¹ This practice is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.61 on Carbon Black Sampling and Statistical Analysis.

Current edition approved May 1, 2023. Published June 2023. Originally approved in 1982. Last previous edition approved in 2017 as D4122 – 17^{e1}. DOI: 10.1520/D4122-17R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- Transmittance of Toluene Extract
- D2414 Test Method for Carbon Black—Oil Absorption Number (OAN)
- D3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets
- D3191 Test Methods for Carbon Black in SBR (Styrene-Butadiene Rubber)—Recipe and Evaluation Procedures
- D3192 Test Methods for Carbon Black Evaluation in NR (Natural Rubber)
- D3265 Test Method for Carbon Black—Tint Strength
- D3493 Test Method for Carbon Black—Oil Absorption Number of Compressed Sample (COAN)
- D5230 Test Method for Carbon Black—Automated Individual Pellet Hardness
- D6556 Test Method for Carbon Black—Total and External Surface Area by Nitrogen Adsorption

3. Significance and Use

3.1 These guidelines are intended to ensure that IRBs are evaluated by a standard procedure.

3.2 These guidelines are to be used to establish the average physicochemical and physical rubber properties of a lot of carbon black to be used as an IRB.

4. Production, Quality Control, and Quality Assurance

4.1 It is assumed that the manufacturer of the IRB will use state-of-the-art techniques to ensure maximum uniformity throughout the entire production run. The production should be made in one continuous production lot run. The testing called for in this practice is not intended to be a substitute for in-process quality control. This interlaboratory study is only adequate to verify the quality of a homogeneous lot.

4.2 The size of the lot is determined by historical records on the rate of use. The lot should have an expected life of eight to ten years at the most recent rate of use.

4.3 The black should be bagged in 50 lb polyethylene bags to reduce moisture incursion. Each pallet of bagged black should be wrapped in plastic to reduce environmental exposure. Depending on the size of the lot, the bagged black will be segregated into equal sized sublots, typically ten to twenty, representing some logical subdivision, such as a truck load.

5. Sampling

5.1 To avoid having to break down stacked and wrapped bags on a pallet, the bags to be used as samples for uniformity and property determination testing are typically removed at appropriate times from the bagging stream. At least one sample per subplot will be collected for uniformity testing. If more than one sample point is identified for each subplot, they should be spaced to represent approximately equal quantities. Typically, two bags are taken at each sampling point. One is retained by the producer for in-house uniformity testing and one is used for samples to be distributed to participants in the rubber testing and uniformity ITP. The bags selected will be numbered from one through *n*, where *n* is the total number of sublots, in order to represent the corresponding production lot or labeled to identify the subplot and its position relative to the whole of the corresponding production lot.

5.2 *n* 4-dm³ (1 gal) samples, numbered from one through *n*, or marked with the labels from 5.1 as taken from the corresponding bags, will be sent to each participant in the interlaboratory study to evaluate the new IRB.

5.3 Additionally, a 4-dm³ (1 gal) sample of the *previous* IRB taken from a common blended source will also be sent to each participant.

6. Procedure

6.1 It is preferred that all of the samples be tested on the same day for any of the test methods described in 6.2 and 6.3. If the testing cannot be completed in the same day, it should be completed in consecutive days.

6.2 Rubber Physical Tests:

6.2.1 Perform the following physical tests in rubber on both the new and previous IRB. Test samples mixed in accordance with Test Methods **D3191**, Test Method A, Test Method B, or Test Method C and cure for 50 min at 145 °C as well as samples mixed in accordance with Test Methods **D3192**, Test Method A, Test Method B, or Test Method C and cure for 30 min at 145 °C. It is preferred that participating laboratories be found so that data from all test methods can be included for evaluation.

6.2.1.1 In accordance with Test Methods **D412**, Test Method A, test five dumbbells from each cured sheet and determine the mean values of tensile stress at 300 % elongation, tensile strength, and ultimate elongation.

6.2.1.2 Record data in absolute numbers (not as differences from IRB) on **Table 1**, reporting tensile stress and tensile strength to the nearest 0.1 MPa and ultimate elongation to the nearest 5 %.

6.3 Informational Physicochemical Tests:

6.3.1 Perform the following physicochemical tests on the new IRB:

6.3.1.1 *Iodine Adsorption Number (Test Method D1510)*— Report the result obtained from an individual determination in grams of iodine per kilogram to the nearest 0.1 unit.

6.3.1.2 *Oil Absorption Number (Test Method D2414)*— Report the result obtained from an individual determination in 10⁻⁵ m³kg (cm³/100 g) to the nearest 0.1 unit.

6.3.2 Record data on **Table 2** (or in a form that captures the same information as in **Table 2**).

TABLE 1 Industry Reference Black Test Data

Laboratory Number _____ Test Method _____		Tensile Strength, MPa D3191		Tensile Stress at 300 %, MPa D3191	Elongation, % D3191	Tensile Strength, MPa D3192		300 % Modulus, MPa D3192	Elongation, % D3192
Day of Mixing and Date	Sample No.								
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			
Day No. ___		50'				30'			
Date ___	Prev. IRB	50'				30'			

average may be rejected by Committee D24 as being a nonhomogeneous portion of the production lot.

7.3 If any laboratory average test result (column average) falls outside the upper and lower control limits shown in **Table 3**, then that laboratory's data for that test should be deleted and **Table 3** should be recalculated excluding that laboratory. Such data indicates that the laboratory has a significant reproducibility problem, which needs corrective action.

7.4 After deleting data, the remaining data for each test can be used to provide average differences between the new IRB and the previous one.

7.5 For each test in **Table 2**, enter the results from each laboratory for each sample in the form shown in **Table 3**. Then calculate the statistics defined in **Table 3**. The results are for information only and not to determine the uniformity of the lot.

8. Acceptance

8.1 All sublots tested as homogeneous by this practice will be considered acceptable by Committee D24 for use as the new IRB.

9. Shelf Life

9.1 The shelf life of the Industry Reference Black (IRB) carbon blacks is indefinite when properly stored in a manner that protects it from exposure to sources of moisture, such as precipitation, other sources of liquid water, or high humidity environments. Iodine number is the only property known to change over an extended period (years). This is due to a slow increase in the oxygen content and is primarily observed with tread blacks and other high surface area carbon blacks. Steps are being taken within ASTM Committee D24 to develop standards that are more stable over a long period.

10. Keywords

10.1 blending; industry reference blacks (IRBs); lot size; physical properties; physicochemical properties; shelf life; statistical analysis form; table for IRB test data; uniformity guidelines for production and testing

ANNEX

(Mandatory Information)

A1. LISTING OF THE PROPERTIES OF INDUSTRY REFERENCE BLACKS

A1.1 The listing of properties for Industry Reference Blacks (IRBs) is given in **Table A1.1**. The absolute values for I_2 number, OAN, COAN, and tint strength are listed. Values for tensile stress at 300 % elongation or "modulus" and tensile strength are given in relation to the previous IRB as a "difference." Since the purpose of an IRB is the elimination of the major part of laboratory-to-laboratory variation, it is used as a reference material within each laboratory to correct actual measured property values in that laboratory.

A1.1.1 The rubber properties of carbon black are typically reported as the difference between the values obtained for the test and those obtained for the current IRB.

NOTE A1.1—IRB No. 8³ is an N330 type carbon black prepared at one location, then evaluated by ASTM Committee D24 to ensure uniformity. A large volume (115 910 kg (255 000 lb)) of this carbon black was prepared since it is used daily as a standard reference material by carbon black producers. The carbon black has an iodine number of 81.8 g/kg and OAN of $103.0 \times 10^{-5} \text{ m}^3/\text{kg}$.

NOTE A1.2—IRB No. 9³ is an N330 type carbon black prepared at one location, then evaluated by ASTM Committee D24 to ensure uniformity. A large volume (181 818 kg (400 000 lb)) of this carbon black was prepared since it is used daily as a standard reference material by carbon black producers. The carbon black has an iodine number of 82.1 g/kg and OAN value of $98.9 \times 10^{-5} \text{ m}^3/\text{kg}$.

NOTE A1.3—Prior to the introduction of IRB8, all rubber testing was done following Method A of Test Methods **D3191** and Test Methods

D3192. No laboratory in the ITP to validate IRB8 provided data for Method A for either Test Methods **D3191** or Test Methods **D3192**. Therefore, data from Methods B and C were included in the table. In the ITP to validate IRB9, data was provided for all three methods of Test Methods **D3191** and Test Methods **D3192**. The difference from IRB8 to IRB9 data for all three methods has been included in **Table A1.1**.³

NOTE A1.4—All the reported "difference from IRB8 to IRB9" values for all three test methods of Test Methods **D3191** and Test Methods **D3192** are less than the within laboratory test error reported in the applicable precision statement sections of those two Test Methods. This means that in a given laboratory using these test methods for testing both IRB8 and IRB9, they would not be able to distinguish which sample was which material based on their test results. Therefore, it can be concluded that, within testing error, IRB9 is a virtual drop-in replacement for IRB8, negating the need to revise industry specifications.

A1.2 The user of this table is cautioned against attempting to add the differences listed in the modulus and tensile strength columns to determine the relationship of two carbon blacks not adjacent in time. Such an addition is likely to produce spurious results due to additive errors.

A1.3 The listing of the properties of IRB No. 8 is given in **Table A1.2**. These values are the average from the producer from their data to evaluate the uniformity of IRB No. 8.

A1.4 The listing of the properties of IRB9 is given in **Table A1.3**. These values are the average of the test results obtained during the testing of IRB9 in the D24 LPRS program in March 2016 except where noted that the data is from the producer.

³ Available from Laboratory Standards, 227 Somerset, Borger, TX 79007, www.carbonstandard.com.