



Designation: ~~D8066/D8066M—17~~ D8066/D8066M – 23

Standard Practice Unnotched Compression Testing of Polymer Matrix Composite Laminates¹

This standard is issued under the fixed designation D8066/D8066M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice provides instructions for using the Test Method ~~D6484~~ D6484/D6484M open hole compression test fixture to determine unnotched compressive strength of multi-directional laminates. The composite material forms are limited to continuous-fiber reinforced polymer matrix composites in which the laminate is both symmetric and balanced with respect to the test direction. The range of acceptable test laminates and thicknesses are described in 8.2.1.

1.2 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system ~~may not be~~ are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other. ~~Combining other, and values from the two systems may result in non-conformance with the standard. shall not be combined.~~

1.2.1 Within the text the inch-pound units are shown in brackets.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:

[D695 Test Method for Compressive Properties of Rigid Plastics](#)

[D792 Test Methods for Density and Specific Gravity \(Relative Density\) of Plastics by Displacement](#)

[D883 Terminology Relating to Plastics](#)

[D3410/D3410M Test Method for Compressive Properties of Polymer Matrix Composite Materials with Unsupported Gage Section by Shear Loading](#)

[D3171 Test Methods for Constituent Content of Composite Materials](#)

[D3878 Terminology for Composite Materials](#)

[D5229/D5229M Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials](#)

¹ This test method is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.05 on Structural Test Methods.

Current edition approved Aug. 1, 2017; May 1, 2023. Published September 2017; June 2023. Originally approved in 2017. Last previous edition approved in 2017 as D8066/D8066M – 17. DOI: ~~10.1520/D8066–D8066M-17~~ 10.1520/D8066_D8066M-23.

- [D5467/D5467M Test Method for Compressive Properties of Unidirectional Polymer Matrix Composite Materials Using a Sandwich Beam](#)
- [D6484/D6484M Test Method for Open-Hole Compressive Strength of Polymer Matrix Composite Laminates](#)
- [D6507 Practice for Fiber Reinforcement Orientation Codes for Composite Materials](#)
- [D6641/D6641M Test Method for Compressive Properties of Polymer Matrix Composite Materials Using a Combined Loading Compression \(CLC\) Test Fixture](#)
- [D7249/D7249M Test Method for Facesheet Properties of Sandwich Constructions by Long Beam Flexure](#)
- [E6 Terminology Relating to Methods of Mechanical Testing](#)
- [E132 Test Method for Poisson's Ratio at Room Temperature](#)
- [E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)
- [E456 Terminology Relating to Quality and Statistics](#)

3. Terminology

3.1 *Definitions*—Terminology [D3878](#) defines terms relating to high-modulus fibers and their composites, as well as terms relating to structural sandwich constructions. Terminology [D883](#) defines terms relating to plastics. Terminology [E6](#) defines terms relating to mechanical testing. Terminology [E456](#) and Practice [E177](#) define terms relating to statistics. In the event of a conflict between terms, Terminology [D3878](#) shall have precedence over the other standards.

3.2 *Definitions of Terms Specific to This Standard*—

NOTE 1—If the term represents a physical quantity, its analytical dimensions are stated immediately following the term (or letter symbol) in fundamental dimension form, using the following ASTM International standard symbology for fundamental dimensions, shown within square brackets: [M] for mass, [L] for length, [T] for time, [θ] for thermodynamic temperature, and [nd] for non-dimensional quantities. Use of these symbols is restricted to analytical dimensions when used with square brackets, as the symbols may have other definitions when used without the brackets.

3.2.1 *nominal value, n*—a value, existing in name only, assigned to a measurable property for the purpose of convenient designation. Tolerances may be applied to a nominal value to define an acceptable range for the property.

3.3 *Symbols:*

- A —cross-sectional area of a specimen
- B_y —face-to-face percent bending in specimen
- CV —sample coefficient of variation, in percent
- E^c —laminare compressive modulus
- F_x^{unc} —ultimate unnotched compressive strength in the test direction
- h —specimen thickness
- P^{max} —maximum force carried by test specimen prior to failure
- P_1 —load at ϵ_{x1}
- P_2 —load at ϵ_{x2}
- w —specimen width
- ϵ_{x1} —actual measured axial strain value nearest lower end of strain range used
- ϵ_{x2} —actual measured axial strain value nearest upper end of strain range used
- ϵ_{y1} —actual measured transverse strain value nearest lower end of strain range used
- ϵ_{y2} —actual measured transverse strain value nearest upper end of strain range used
- ϵ_{xg1} —indicated axial strain from Gage 1 (used in % bending equation)
- ϵ_{xg2} —indicated axial strain from Gage 2 (used in % bending equation)
- ν_{xy}^c —Compressive Poisson's ratio

4. Summary of Practice

4.1 In accordance with Test Method [D6484/D6484M](#), perform a uniaxial compression test of a balanced, symmetric laminate without a hole.

5. Significance and Use

5.1 This practice provides supplemental instructions for the use of Test Method [D6484/D6484M](#) to determine unnotched compressive strength data for material specifications, research and development, material design allowables, and quality assurance.

Factors that influence compressive strengths and shall therefore be reported include the following: material, methods of material fabrication, accuracy of lay-up, laminate stacking sequence and overall thickness, specimen preparation, specimen conditioning, environment of testing, specimen alignment and gripping, speed of testing, time at temperature, void content, and volume percent reinforcement. Composite properties in the test direction that may be obtained from this test method include:

- 5.1.1 Unnotched compressive (UNC) strength, F_x^{unc} ,
- 5.1.2 Ultimate compressive strain,
- 5.1.3 Compressive (linear or chord) modulus of elasticity, E^c , and
- 5.1.4 Poisson's ratio in compression.

5.2 This practice provides a compression test method for laminates containing fibers in multiple fiber directions, particularly those combining axial (0 degree) fibers and off-axis ($\pm \theta$ degree) fibers. Other compression strength test methods include SACMA SRM-1 (also known as the modified **D695**), **D3410/D3410M**, **D5467/D5467M**, **D6641/D6641M**, and **D7249/D7249M**. The SRM-1 test uses 12.6 mm [0.50 in.] wide specimens, which is only appropriate for unidirectional tape, cross-ply [0/90]ns tape, or small unit-cell-size fabrics (e.g. 3K-70-P). Larger cell-size fabrics (e.g., (for example, spread-tow 12K fabrics) should be tested with wider specimens. The standard **D3410/D3410M** and **D6641/D6641M** test fixtures do permit the use of wider specimens, e.g., for example, 25.4 mm [1.0 in.] wide, and thus can be used to test laminates containing both axial and off-axis fibers; however their gage lengths are relatively short. Test Method **D5467/D5467M** is intended to obtain the compressive strength of unidirectional laminates, but is expensive due to the sandwich beam configuration. Test Method **D7249/D7249M** is intended to obtain the compressive strength of sandwich facesheets.

5.2.1 Advantages of this practice include:

5.2.1.1 Avoiding the use of tabs, which are typically required with the end-loaded SRM-1 specimen, which are often required with the shear loaded Test Method **D3410/D3410M** specimen, and sometimes required with the Test Method **D6641/D6641M** test specimen, in order to obtain valid failure modes, and

5.2.1.2 Longer and wider gage section imposing less constraint on in-plane transverse displacement.

5.2.2 Disadvantages of this practice include:

5.2.2.1 Longer and wider specimen, thus consuming more material than other standards noted above

6. Interferences

6.1 *Environment*—Results are affected by the environmental conditions under which the tests are conducted. Laminates tested in various environments can exhibit significant differences in both failure force and failure mode. Experience has demonstrated that elevated temperature, humid environments are generally critical for compressive strength. However, critical environments must be assessed independently for each material system and stacking sequence tested.

6.2 *Material Orthotropy*—The degree of laminate orthotropy strongly affects the failure mode and measured strengths. Valid strength results should only be reported when appropriate failure modes are observed, according to Section 12.

6.3 *Thickness Scaling*—Thick composite structures do not necessarily fail at the same strengths as thin structures with the same laminate orientation (that is, strength does not always scale linearly with thickness). Thus, data gathered using the test method described in this practice may not translate directly into equivalent thick-structure properties.

6.4 *Support Fixture*—Results are affected by the amount of lateral pressure applied to the test specimen by the support fixture. Sources of variation in this lateral pressure include fixture grip surface, fixture bolt torque, hydraulic gripping pressure, and fixture shimming choices, and should be controlled and reported as required in Section 11, Procedure, and Section 14, Report. Testing unnotched specimens in the Test Method **D6484/D6484M** support fixture is very sensitive to fixture gaps, tolerances, and alignment; the fixture can become bent due to high unnotched compressive failure forces, therefore the fixture dimensions should be periodically checked. The support fixture can inhibit the growth of delamination damage by inhibiting out-of-plane deformation, and by relieving force from the specimen via friction effects.

NOTE 2—It has been found for at least one carbon tape material that the thermal-spray gripping surface on the Test Method **D6484/D6484M** test fixture (see Flagnote 2 in Test Method **D6484/D6484M** Figures 5 to 8) can lead to premature failures at the ends of the gripped areas, and that smooth grip surfaces (no thermal spray) yield superior strength results **(1)**.²

6.5 *Type of Loading*—Differences in force versus crosshead displacement and force versus extensometer strain response may be observed when comparing hydraulic grip-loaded specimens with end-loaded specimens. Hydraulic grip-loaded data typically exhibit linear behavior at the onset of loading. At high force levels, some nonlinear behavior may be observed due to grip slippage. End-loaded data typically display some initial nonlinear behavior at low force levels, due to seating of the specimen/fixture assembly underneath the load platens, but then exhibit linear behavior to failure. The use of specimen end loading is not allowed by this standard for unnotched specimen testing, as it often leads to end brooming/crushing failures in unnotched compression specimens.

7. Apparatus

7.1 *General Apparatus*—General apparatus shall be in accordance with Test Method **D6484/D6484M**.

7.2 *Strain-Indicating Device*—When required by the test requestor, longitudinal strain shall be either *a*) simultaneously measured using strain gages on opposite faces in the center of the specimen (so as to be within the support fixture opening) to allow for a correction as a result of any bending of the specimen, *b*) measured by use of edge mounted extensometers, or *c*) suitable non-contact strain measurement devices. When Poisson's ratio is to be determined, the specimen shall be strain gaged instrumented to measure strain in the lateral direction using the same type of transducer. The same type of strain transducer shall be used for all strain measurements on any single coupon. Attachment of the strain-indicating device to the coupon shall not cause damage to the specimen surface. Refer to Test Method **D3410/D3410M** for additional requirements for strain measurement on compression specimens.

7.3 *Data Acquisition Equipment*—Equipment capable of recording force and strain data is required.

8. Sampling and Test Specimens

8.1 *Sampling*—shall be in accordance with Test Method **D6484/D6484M**.

8.2 *Geometry*: [ds.iteh.ai/catalog/standards/sist/42dc6a72-cfd6-4675-9ce5-c173d30cd6c0/astm-d8066-d8066m-23](https://dx.doi.org/10.1520/D8066-23)

8.2.1 *Stacking Sequence*—The standard laminates shall have multidirectional fiber orientations (fibers shall be oriented in a minimum of two directions) and balanced and symmetric stacking sequences. Nominal thickness shall be 4 mm [0.160 in.], with a permissible range of 3 to 5 mm [0.125 to 0.200 in.], 3 mm to 5 mm [0.125 in. to 0.200 in.], inclusive. Fabric laminates containing satin-type weaves shall have symmetric warp surfaces, unless otherwise specified and noted in the report.

NOTE 3—Typically, a [45_i/−45_j/0_k/90_l]_{ns} tape or [45_i/0_j]_{ns} fabric laminate should be selected such that a minimum of 5 % of the fibers lay in each of the four principal orientations. This laminate design has been found to yield the highest likelihood of acceptable failure modes. Note that testing [0_i/90_j]_{ns} tape or fabric laminates can result in acceptable failure modes (see also Section 5). Consult Practice **D6507** for information on fiber orientation codes.

8.2.2 *Specimen Configuration*—The test specimen configuration shall be in accordance with Test Method **D6484/D6484M**. No hole, notch or damage shall be introduced into the specimen.

8.3 *Specimen Preparation*—Specimens shall be prepared in general accordance with Test Method **D6484/D6484M**, with the omission of the hole.

9. Calibration

9.1 The accuracy of all measuring equipment shall have certified calibrations that are current at the time of use of the equipment.

² The boldface numbers in parentheses refer to a list of references at the end of this standard.



10. Conditioning

10.1 The recommended pre-test condition is effective moisture equilibrium at a specific relative humidity as established by Test Method [D5229/D5229M](#); however, if the test requestor does not explicitly specify a pre-test conditioning environment, no conditioning is required and the test specimens may be tested as prepared.

10.2 The pre-test specimen conditioning process, to include specified environmental exposure levels and resulting moisture content, shall be reported with the test data.

NOTE 4—The term moisture, as used in Test Method [D5229/D5229M](#), includes not only the vapor of a liquid and its condensate, but the liquid itself in large quantities, as for immersion.

10.3 If no explicit conditioning process is performed the specimen conditioning process shall be reported as “unconditioned” and the moisture content as “unknown.”

11. Procedure

11.1 *Parameters to Be Specified Before Test:*

11.1.1 The specimen sampling method, specimen type and geometry, and conditioning travelers (if required).

11.1.2 All other parameters documented in Test Method [D6484/D6484M](#).

11.2 *General Instruction:*

11.2.1 Any deviations from these procedures, whether intentional or inadvertent, shall be reported.

11.2.2 If specific gravity, density, reinforcement volume, or void volume are to be reported, then obtain these samples from the same panels being tested. Specific gravity and density may be evaluated by means of Test Method [D792](#). Volume percent of the constituents may be evaluated by one of the matrix digestion procedures of Test Method [D3171](#), or, for certain reinforcement materials such as glass and ceramics, by the matrix burn-off technique of Test Method [D3171](#).

11.2.3 Condition the specimens as required. Specimens shall be stored in the conditioned environment until test time, if the test environment is different than the conditioning environment.

11.2.4 Following final specimen ~~preparation and any conditioning~~, machining but before conditioning and testing, measure the specimen width, w , and the specimen thickness, h , recording the average of three measurements. The width and thickness measurements shall be made in the gage section of the specimen, taking care not to measure directly over a strain gage or gage adhesive. The precision of all measurements shall be within 1 % of the dimension, unless otherwise specified in this practice. Dimensions shall be recorded to three significant figures in units of millimeters [inches].

NOTE 5—The test requester may request that additional measurements be performed after the machined specimens have gone through any conditioning or environmental exposure.

11.3 *Test Procedure*—The compression test of the laminate specimen shall be performed in accordance with Test Method [D6484/D6484M](#). Specimen grip loading shall be used. End loading is not allowed as it often leads to end brooming/crushing failures.

NOTE 6—When testing a conditioned specimen at elevated temperature with no fluid exposure control, the percentage moisture loss of the specimen prior to test completion may be estimated by placing a conditioned traveler coupon of known weight within the test chamber at the same time the specimen is placed in the chamber. Upon completion of the test, the traveler coupon is removed from the chamber, weighed, and the percentage weight loss calculated and reported.

11.4 *Data Recording*—Record force versus crosshead displacement (and force versus strain, if extensometers or gages are used) continuously, or at frequent regular intervals; for this test method, a sampling rate of 2 to 3 data recordings per second, and a target minimum of 100 data points per test are recommended. If any initial failures are noted, record the force, displacement, and mode