



Designation: D3970 – 05 (Reapproved 2023)

Standard Test Method for Cerium in Paint Driers by Oxidimetric Determination¹

This standard is issued under the fixed designation D3970; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the titrimetric determination of cerium in liquid cerium and rare earth paint driers and utilizes ferrous ammonium sulfate.

1.2 This test method is not applicable to dryer blends.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For a specific hazard statement, see Section 7.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
- D444 Test Methods for Chemical Analysis of Zinc Yellow Pigment (Zinc Chromate Yellow)
 - D600 Specification for Liquid Paint Driers (Withdrawn 2021)³
 - D1193 Specification for Reagent Water
 - E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³
 - E300 Practice for Sampling Industrial Chemicals

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved June 1, 2023. Published June 2023. Originally approved in 1980. Last previous edition approved in 2017 as D3970 – 05 (2017). DOI: 10.1520/D3970-05R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3. Summary of Test Method

3.1 The organic constituents of the liquid drier specimen are eliminated by treatment with nitric, sulfuric, and hydrochloric acids, and the cerium is converted to cerous sulfate. The cerous sulfate is oxidized to ceric sulfate with sodium bismuthate and titrated with standard ferrous ammonium sulfate.

4. Significance and Use

4.1 This test method may be used to confirm in the presence of rare earths the stated cerium content of liquid pure cerium or rare earth driers manufactured for use in the coatings industry.

5. Interferences

5.1 This test method is specific for cerium in the presence of rare earth metals. Other drier metals with more than one valence may interfere and should be absent.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents purchased or prepared shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type II of Specification D1193.

⁴ *ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

6.3 *Ceric Sulfate Solution, Standard (0.1 N)*—Standardized 0.1 *N* solutions of ceric sulfate ($\text{Ce}(\text{SO}_4)_2$) in 1 *N* sulfuric acid may be purchased or prepared.⁵

6.4 *Ferroin Indicator (0.025 M)*—Orthophenanthroline ferrous complex indicator.⁶

6.5 *Ferrous Ammonium Sulfate Solution, Standard (0.1 M)*—Standardized ferrous ammonium sulfate ($\text{FeSO}_4 \cdot (\text{NH}_4)_2\text{SO}_4$), 0.1 *M*, may be purchased or prepared in the following manner. Dissolve 39.2 g of ferrous ammonium sulfate in 250 mL of distilled water and add 20 mL of concentrated sulfuric acid with stirring. Dilute to 1 L in a volumetric flask and standardize as follows:

6.5.1 Pipet duplicate 20.0 mL portions of standard 0.1 *N* ceric sulfate solution into 400 mL beakers and add 200 mL of 1.5 *N* sulfuric acid. Titrate with 0.1 *N* ferrous ammonium sulfate solution as described in 6.6. Calculate the molarity, *M*, of this approximately 0.1 *M* solution as follows:

$$M = V_2N/V_1 \quad (1)$$

where:

V_2 = ceric sulfate solution, mL,

N = normality of ceric sulfate solution, and

V_1 = ferrous ammonium sulfate solution, mL.

6.6 *Ferrous Ammonium Sulfate Solution, Standard (0.01 M)*—Transfer 100 mL of the standardized 0.1 *M* ferrous ammonium sulfate solution from a volumetric flask to a 1 L volumetric flask and dilute with distilled water. This 0.01 *M* ferrous ammonium sulfate solution is designated as M_2 . Alternatively, 0.2 *N* ferrous ammonium sulfate solution (see Test Methods D444) may be used and diluted to 0.01 *M* in accordance with 6.5.

6.7 *Hydrochloric Acid (sp gr 1.19)*—Concentrated hydrochloric acid (HCl).

6.8 *Nitric Acid (sp gr 1.42)*—Concentrated nitric acid (HNO_3).

6.9 *Sodium Bismuthate (NaBiO_3)*⁷—The grade required is a yellow powdery solid. If it is any other color it has decomposed and fresh material should be obtained.

6.10 *Sulfuric Acid (sp gr 1.84)*—Concentrated sulfuric acid (H_2SO_4).

6.11 *Sulfuric Acid (1 + 49, 2 %)*—Dilute 10 mL of the concentrated sulfuric acid (H_2SO_4) to 500 mL with water.

⁵ The sole source of supply of reagent grade 0.1 *N* solution of ceric sulfate in 1 *N* sulfuric acid, known to the committee at this time is G. Frederick Smith Co. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁶ The sole source of supply of 0.025 *M* ferroin indicator, known to the committee at this time is G. Frederick Smith Co. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁷ The sole source of supply of reagent grade sodium bismuthate, known to the committee at this time is Mallinckrodt Co. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

6.12 *Sulfuric Acid (1.5 N)*—Dilute 16.7 mL of concentrated sulfuric acid (H_2SO_4) to 400 mL with water.

7. Precautions

7.1 Use only a rubber bulb aspirator for pipetting liquids.

8. Sampling

8.1 Take a small sample of liquid drier from bulk using the procedures in Practice E300 appropriate for the size of container: Bottle Sampling section for tanks and tank cars or Tube Sampling section for drums and cans.

NOTE 1—Liquid driers are normally homogeneous so that only simple physical tests, such as specific gravity or solids content, on top and bottom samples from tanks are required to confirm that separation has not occurred. Agitate drums in accordance with the Tube Sampling section of Practice E300.

8.2 Examine the sample of drier for sediment or suspended matter which, if present, is evidence of noncompliance with the Physical Appearance requirements section of Specification D600.

8.3 If the sample is homogeneous keep it in a stoppered vessel to prevent solvent evaporation prior to analysis.

9. Procedure

9.1 For the analysis use 1.0 g for 6 % of cerium and 2.0 g or more for materials containing proportionally less cerium. Rare earth driers are generally 45 % to 50 % cerium. Thus in the analysis of 6 % rare earth driers, containing cerium, use 2.0 g. Weigh the specimen from a weighing bottle or syringe by difference, to 0.5 mg, transferring the specimen to a 250 mL Erlenmeyer flask.

9.2 Place the flask on a hot plate and warm to volatilize solvent (Note 2). Cool the flask.

NOTE 2—It is easier to volatilize the solvent than to destroy it with acid.

9.3 Under a hood, add 10 mL of HNO_3 and 10 mL of HCl to the specimen in the flask. Add boiling aids, heat strongly on a hot plate, and boil down to 2 mL to 3 mL. Repeat the acid addition and boiling down.

NOTE 3—Sulfuric acid is not added at the beginning of the digestion because it carbonizes the material making it more difficult to digest.

9.4 Add 10 mL of concentrated H_2SO_4 (Note 3), and 10 mL of HNO_3 , and heat strongly on the hot plate until the evolution of brown fumes ceases and white fumes appear. At this point salt precipitation causes a tendency to bump which may be avoided by mixing while heating until the salt dissolves. Cool. All HCl must be removed before proceeding to 9.5. If thick fumes appear the HCl has been removed.

9.5 Add 100 mL of 2 % H_2SO_4 , and 1.0 g of NaBiO_3 , and bring to a boil. Cool.

9.6 Vacuum filter through a medium fritted-glass filter, rinse flask and filter with 2 % H_2SO_4 , and wash the filter with an additional 150 mL of 2 % H_2SO_4 . The filter may be used for several determinations without cleaning. When it plugs, it can be cleaned easily with HCl.

9.7 Dilute the solution to approximately 400 mL with water and titrate with 0.01 *M* ferrous ammonium sulfate until the