



Designation: E2152 – 12 (Reapproved 2023)

Standard Practice for Computing the Colors of Fluorescent Objects from Bispectral Photometric Data¹

This standard is issued under the fixed designation E2152; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The fundamental procedure for evaluating the color of a fluorescent specimen is to obtain bispectral photometric data for specified irradiating and viewing geometries, and from these data to compute tristimulus values based on a CIE (International Commission on Illumination) standard observer and a CIE standard illuminant. Procedures for such computation are contained in this practice. This practice also contains procedures for computing illuminant-specific spectral radiance factor values from illuminant-independent bispectral photometric data.

1. Scope

1.1 This practice provides the values and practical computation procedures needed to obtain tristimulus values, designated X, Y, Z and X₁₀, Y₁₀, Z₁₀ for the CIE 1931 and 1964 observers, respectively, from bispectral photometric data for the specimen. Procedures for obtaining such bispectral photometric data are contained in Practice E2153.

1.2 Procedures for conversion of results to color spaces that are part of the CIE system, such as CIELAB and CIELUV are contained in Practice E308.

1.3 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This practice is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.05 on Fluorescence.

Current edition approved June 1, 2023. Published July 2023. Originally approved in 2001. Last previous edition approved in 2017 as E2152 – 12 (2017). DOI: 10.1520/E2152-12R23.

2. Referenced Documents

2.1 *ASTM Standards*:²

E284 Terminology of Appearance

E308 Practice for Computing the Colors of Objects by Using the CIE System

E2153 Practice for Obtaining Bispectral Photometric Data for Evaluation of Fluorescent Color

2.2 *CIE Standards*:

CIE 15 Colorimetry³

2.3 *ISO Standards*:

ISO 11476 Paper and Board—Determination of CIE-Whiteness, C/2 Degrees⁴

3. Terminology

3.1 *Definitions*—The definitions contained in Terminology E284 are applicable to this practice.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *bispectrometer, n*—an optical instrument equipped with a source of irradiation, two monochromators, and a detection system, such that a specimen can be measured at independently-controlled irradiation and viewing wavelengths. The bispectrometer is designed to allow for calibration to

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from CIE (International Commission on Illumination) at www.cie.co.at or www.techstreet.com.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

provide quantitative determination of the bispectral radiation-transfer properties of the specimen (1).⁵

NOTE 1—Typically, a reference detection system monitors the radiation incident on the specimen. This reference detection system serves to compensate for both temporal and spectral variations in the flux incident upon the specimen, by normalization of readings from the instrument's emission detection system.

3.2.2 *diagonal elements, n*—elements of a bispectral matrix for which irradiation and viewing wavelengths are equal.

3.2.3 *fluorescence, n*—this standard uses the term “fluorescence” as a general term, including both true fluorescence (with a luminescent decay time of less than 10^{-8} s) and phosphorescence with a delay time short enough to be indistinguishable from fluorescence for the purpose of colorimetry.

3.2.4 *off-diagonal element, n*—any element of a bispectral matrix for which irradiation and viewing wavelengths are not equal.

4. Summary of Practice

4.1 *Procedures*—Procedures are given for computing from bispectral photometric measurements the CIE tristimulus values X, Y, Z for the CIE 1931 standard observer and the CIE 1964 supplementary standard observer. While recognizing the CIE recommendation of numerical integration at 1 nm intervals (in CIE 15) as the basic definition, this practice is limited in scope to measurements and calculations using spectral intervals greater than or equal to 5 nm.

4.2 *Calculations*—CIE tristimulus values X, Y, Z or X₁₀, Y₁₀, Z₁₀ are calculated by numerical summation of the products of weighting factors for selected illuminants and observers with the bispectral Donaldson radiance factor of the specimen. The tristimulus values so calculated may be converted to coordinates in a more nearly uniform color space such as CIELAB or CIELUV.

5. Significance and Use

5.1 The bispectral or two-monochromator method is the definitive method for the determination of the general radiation-transfer properties of fluorescent specimens (2). In this method, the measuring instrument is equipped with two separate monochromators. The first, the irradiation monochromator, irradiates the specimen with monochromatic light. The second, the viewing monochromator, analyzes the radiation leaving the specimen. A two-dimensional array of bispectral photometric values is obtained by setting the irradiation monochromator at a series of fixed wavelengths (μ) in the ultraviolet and visible range, and for each μ , using the viewing monochromator to record readings for each wavelength (λ) in the visible range. The resulting array, once properly corrected, is known as the Donaldson matrix, and the value of each element (μ, λ) of this array is here described as the Donaldson radiance factor ($D(\mu, \lambda)$). The Donaldson radiance factor is an instrument- and illuminant-independent photometric property of the specimen, and can be used to calculate its

⁵ The boldface numbers in parentheses refer to a list of references at the end of this standard.

color for any desired illuminant and observer. The advantage of this method is that it provides a comprehensive characterization of the specimen's radiation-transfer properties, without the inaccuracies associated with source simulation and various methods of approximation.

6. Procedure

6.1 *Selecting Standard Observer*—Select standard observer according to the guidelines of Practice E308.

6.2 *Selecting Illuminants*—Select illuminants that are similar to the light under which the objects will be viewed or for which their colors will be specified or evaluated. In general, follow the recommendations of Practice E308. For fluorescent samples, however, special attention must be given to the relative UV content of the selected illuminants and the light under which the objects will be viewed.

6.2.1 When object will be viewed indoors, by daylight filtered through a glass window, use values for the extended version of Illuminant C defined in ISO 11476.

6.2.2 When object will be viewed outdoors, by unfiltered daylight, use values for CIE Illuminant D65, or other daylight illuminants, as defined by the formulas developed by Judd, and presented in CIE 15.

6.2.3 When object will be viewed under well-defined special conditions of irradiation which are not similar to any standard illuminant, a provisional illuminant may be defined. Such a provisional illuminant must represent the relative spectral irradiance upon the object surface under these special conditions.

7. Calculation

7.1 *Calculation of Colorimetric Quantities*—Use the method of calculating tristimulus values at 5 nm intervals over the viewing wavelength range 380 nm to 780 nm, and irradiation wavelength range 300 nm to 780 nm. 152-122023

7.2 *Calculation of Tristimulus Values*—The calculation procedures described below involve numerical summation of the products of the Donaldson radiance factor of the specimen and a bispectral factor derived from the tabulated standard illuminant and observer functions. After normalization, the sums are the CIE tristimulus values X, Y, Z (3, 2, 1).

7.2.1 *Application of Illuminant Weights*—Select the desired CIE standard illuminant from Tables given in Practice E308. Multiply each element $D(\mu, \lambda)$ of the specimen's Donaldson matrix by the tabulated value of the relative spectral power of the illuminant Φ at the element's irradiation wavelength (μ).

7.2.2 *Calculation of Stimulus Function*—Obtain the sum over μ of these products at 5 nm intervals over the wavelength range 300 nm to 780 nm. The sum obtained at each viewing wavelength λ is the value of the specimen's stimulus function (relative spectral radiance) $F(\lambda)$, under the specified conditions of irradiation. From these values, either tristimulus values or spectral radiance factor values may be derived.

$$F(\lambda) = \sum_{\mu=300}^{780} \Phi(\mu)D(\mu, \lambda) \quad (1)$$

7.2.3 *Derivation of Tristimulus Values*—Use the color-matching functions selected in 6.1. Multiply the specimen's

stimulus function at each viewing wavelength (λ) by the corresponding tabulated values of the observer color-matching functions. Obtain the sum of these spectral products at 5 nm intervals over the wavelength range 380 nm to 780 nm:

$$X = k \sum_{\lambda=380}^{780} \bar{x}(\lambda)F(\lambda) \quad (2)$$

$$Y = k \sum_{\lambda=380}^{780} \bar{y}(\lambda)F(\lambda)$$

$$Z = k \sum_{\lambda=380}^{780} \bar{z}(\lambda)F(\lambda)$$

where:

k = the normalization constant:

$$k = \frac{100}{\sum_{\lambda=380}^{780} \Phi(\lambda)\bar{y}(\lambda)} \quad (3)$$

7.3 Derivation of Other Colorimetric Quantities—Other colorimetric values, such as chromaticity coordinates, CIELAB and CIELUV values, may be calculated from tristimulus values as described in Practice E308.

NOTE 2—The validity of CIELAB and CIELUV values for describing the color of fluorescent materials is subject to question, for two reasons. First, because the appearance of a fluorescent material may be influenced by irradiation at wavelengths outside the visible range, the appropriate definition of the “white point” (incorporated in the CIELAB and CIELUV calculations) is not clear. Second, the perceptual uniformity of these color spaces has not been evaluated in regions where L^* exceeds 100, as it may for fluorescent materials. It is the responsibility of the user to determine the appropriateness of such metrics for any particular specimen and application.

7.4 Derivation of Spectral Radiance Factors—Calculate the specimen’s stimulus function (relative spectral radiance) $F(\lambda)$ for the selected illuminant as described in section 7.2.2. Divide F at each viewing wavelength (λ) by the corresponding tabulated value of the relative spectral power Φ_l of the selected illuminant. Note that for a fluorescent specimen, the spectral radiance factor ($\beta_f(\lambda)$) is illuminant-specific (3).

$$\beta_f(\lambda) = \frac{F_f(\lambda)}{\Phi_l(\lambda)} = \sum_{\mu=300}^{780} \frac{\Phi_l(\mu)}{\Phi_l(\lambda)} D(\mu, \lambda) \quad (4)$$

7.5 Separation of Fluorescence and Reflection Components—Fluorescence and reflection components of tristimulus and spectral radiance factor values can be calculated by substituting the fluorescent or reflection components of Donaldson radiance factor (D_F or D_R) for Donaldson radiance factor (D) in the calculations described in sections 7.2 and 7.3. This separation of components is valid for D , β , and tristimulus values; it may not be valid for other colorimetric values.

7.5.1 Estimation of Components—To a first approximation, the contribution of fluorescence and reflectance to the appearance of the specimen can be separated by treating diagonal values of the Donaldson matrix as representing reflectance only, and off-diagonal values as representing fluorescence.

7.5.2 Calculation of Components—While more rigorous and accurate methods for the separation of reflection and

fluorescence components may be employed, description of such calculations lies outside the scope of this standard.

7.6 Abridged Calculation Procedures:

7.6.1 Wavelength Intervals of Greater than 5 nm—When data for $D(\mu, \lambda)$ are not available at 5 nm intervals, estimated values at 5 nm intervals should be derived by appropriate interpolation, as described in Annex A1.

7.6.2 Viewing Wavelength Range Less Than 380 nm to 780 nm—When data for $D(\mu, \lambda)$ are not available for the full viewing wavelength range, add the illuminant or observer weights, or both, at the wavelengths for which data are not available to the weights at the shortest and longest wavelength for which spectral data are available. Note that such use of spectrally-truncated data is not recommended when significant fluorescent emission occurs in the region of truncation.

7.6.3 Irradiation Wavelength Range Less Than 300 nm to 780 nm—When the bispectral region of fluorescence is known for a particular specimen, it is acceptable to limit the collection of fluorescence data (off-diagonal values) to this region. Complete the standard Donaldson matrix by setting off-diagonal values outside this region to zero.

8. Report

8.1 The report of the measurement of colorimetric for fluorescent samples data shall include the following:

8.2 Specimen Description—Including the following:

8.2.1 Type and identification,

8.2.2 Date of preparation or manufacture, if required,

8.2.3 Method of cleaning and date, if cleaned,

8.2.4 Orientation of the specimen during measurement, and

8.2.5 Any changes in the specimen during measurement.

8.3 Source of Date—Give instrument identification, irradiating and viewing geometry, spectral bandpass, and date of measurement.

8.4 Observer—Indicate whether the reported data were computed for the CIE 1931 standard observer (2°) or the 1964 supplementary standard observer (10°).

8.5 Illuminants—Indicate which illuminants were used.

8.6 Method of Calculation—Indicate whether the procedure using a 5 nm wavelength interval, or a specified abridged procedure was used, and what wavelength range of spectral data was available.

8.7 Colorimetric Data—Report according to the guidelines of Practice E308.

8.8 Spectral Radiance Factor (Optional)—When reporting spectral radiance factor values for fluorescent samples, indicate for which illuminant the reported spectral radiance factor is defined.

9. Keywords

9.1 bispectral; bispectrometer; color; colorimetry; Donaldson matrix; Donaldson radiance factor; fluorescence; luminescence; radiance factor; tristimulus